Effect of Pb doping on the electrical properties of textured Bi-2212 superconductors

A. Sotelo¹, Sh. Rasekh¹, G. Constantinescu¹, H. Amaveda¹, M. A. Torres², M. A. Madre¹, J. C. Diez¹

¹Instituto de Ciencia de Materiales de Aragón (ICMA) (CSIC-Universidad de Zaragoza), C/M^a de Luna, 3 50018 Zaragoza. Spain

²Departamento de Ingeniería de Diseño y Fabricación, Universidad de Zaragoza, M^a de Luna, 3. 50018 Zaragoza, Spain.

Abstract

Bi_{2-x}Pb_xSr₂CaCu₂O_y textured materials (x=0.0, 0.2, 0.4, and 0.6) have been successfully prepared by the laser floating zone technique. Microstructure and electrical properties (J_C and T_C) have been clearly affected by Pb addition. From the $E-I$ curves, slope of the transition between the superconducting and the normal state (n) at 77 K reaches a maximum of about 16 for the 0.4 Pb doped samples. This value is much higher than the typical ones for the Bi-2212 materials. Moreover, when the electrical properties of the 0.4 Pb doped samples are measured at lower temperatures (between 65 and 77 K), n values increase when the temperature is decreased. A maximum n value of 32 has been reached at 65 K which makes this material very attractive for its use as resistive fault current limiters.

Keywords: Grain growth; Bi-2212; Doping; Platelets; Electrical properties

Corresponding author: A. Sotelo, asotelo@unizar.es; Tel: +34 976762617; Fax:
+34 976761957

1. INTRODUCTION

The fabrication of bulk high- T_c superconducting ceramics with well oriented microstructure and being able of carrying high currents below 77 K, is of great interest for the development of practical devices [1]. As a consequence, great efforts have been devoted to develop techniques leading to the production of highly oriented superconducting grains [2-5]. Among all the High- T_c superconductors, $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ (Bi-2212) materials have demonstrated that they are suitable for many applications when they are properly processed in order to obtain a good grain alignment [6,7]. A very useful technique for rapidly growing from the melt well textured BSCCO rods from the melt is the Laser Floating Zone (LFZ) method, as reported in previous works [8-10]. The microstructure of the superconducting materials is characterized by a good alignment of the grains, with their a - b planes quasi-parallel to the growth direction [11]. This high degree of texture leads to a very important increase of the transport properties, as J_c , due to the reduction of the number of low-angle junctions [12].

On the other hand, the low slope of the superconducting to normal transition on the electrical current curve, E - I , for the Bi-2212 phase, imposes severe limitations for its application as fault current limiters. The usual solution to overcome this problem is based on the use of samples with long lengths.

Another possible way is the cationic substitution, which could introduce effective flux pinning centers and increase the slope of the E - I curves [13]. The partial substitution of Bi by Pb has shown to be useful to increase the intragranular pinning properties in single crystals, leading to the enhancement of both irreversibility field and critical current density [14,15]. Furthermore, this type of

substitution has been found to decrease the anisotropy at high temperatures [16]. In these Pb-doped crystals the existence of two alternating Bi(Pb)-2212 phases is well established [17]. One, the so-called α phase, exhibits a modulated structure with a nominal Pb content of ~ 0.4 [17]. The other one, the β phase, is a modulation-free structure and has higher Pb content, around 0.6 [17]. The α phase exhibits a one-dimensionally modulated structure along the b-axis in which atomic positions are displaced in a wavy manner. The interfaces between the two phases are extended planar defects, which act as strong flux pinning centers [17]. More recently, it has been found that the β phase (modulated-free one) enhances pinning due to its lower anisotropy. In fact, the best pinning properties are exhibited by the combination of a dominant β phase strengthened by α/β interfaces [15]. This optimal phase combination has been obtained for 0.33 effective Pb substitution [15]. Contrarily to the results obtained for single crystals, limited success is obtained in bulk and tape systems with this cationic doping [18-21].

The aim of this work is to study the influence of Pb doping on the sharpness of the superconducting to normal transition of the $E-I$ curves in LFZ textured Bi-2212 thin rods. For this purpose, the well-known power law, $E \sim I^n$, has been selected to describe the $E-I$ curves. The fitting parameter n reflects the sharpness of the superconducting to normal transition and it is correlated with the quality of the superconducting material.

2. EXPERIMENTAL

The initial $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_y$ materials ($x=0.0, 0.2, 0.4$, and 0.6), used in this work, were prepared by a polymer matrix method developed in our laboratory

which has shown a high reproducibility and high quality of the precursor powders [22,23]. $\text{Bi}(\text{CH}_3\text{CO}_2)_3$ (≥ 99.99 %, Aldrich), $\text{Pb}(\text{CH}_3\text{CO}_2)_2 \cdot 3\text{H}_2\text{O}$ (≥ 99 %, Aldrich), $\text{Sr}(\text{CH}_3\text{CO}_2)_2 \cdot 0.5\text{H}_2\text{O}$ (99 %, Panreac), $\text{Ca}(\text{CH}_3\text{CO}_2)_2 \cdot 2\text{H}_2\text{O}$ (98 %, Alfa Aesar), and $\text{Cu}(\text{CH}_3\text{CO}_2)_2 \cdot \text{H}_2\text{O}$ (98 %, Panreac) initial powders were suspended in distilled H_2O . Glacial acetic acid (ACS Reagent, Panreac) was added dropwise until a light blue clear solution was formed. Polyethylenimine (PEI) (50% aqueous, Aldrich) was then added to the above solution, which turned darker immediately due to the nitrogen-metal coordination. After partial evaporation (~ 80 vol. %) of water and acetic acid in a rotary evaporator, the concentrated solution was placed on a hot plate at 50°C until a very dark blue thermoplastic paste appeared. Further heating produced a slow combustion with the release of brown fumes (nitrogen oxides). The resulting powder was manually milled and calcined at 750 and 800°C for ca. 12 h, with an intermediate milling. This thermal treatment has been designed and checked in previous works [24] to decompose the alkaline earth carbonates, otherwise they would produce CO_2 bubbles in the molten zone which would disturb the solidification front. After the thermal treatment, the powders were cold isostatically pressed at 200 MPa in form of cylindrical bars which were subsequently used as feed in a directional solidification process performed in an LFZ installation [25]. The textured bars were obtained using a continuous power Nd:YAG laser ($\lambda = 1064$ nm), under air, at a growth rate of 30 mm/h and a relative rotation of 18 rpm between seed and feed. Using these growth conditions and adjusting the laser power input to obtain a melted zone of 1-1.5 times the rod diameter, it is possible to obtain a stable solidification front, which allows the fabrication of homogeneous textured bars.

Bi-2212 ceramic presents incongruent melting and, in consequence, after the directional solidification process, it is necessary to perform a thermal treatment in order to form the Bi-2212 superconducting phase [26,27]. This annealing process was performed under air, and consisted in two steps: 60 h at 835 °C to produce the Bi-2212 phase, followed by 12 h at 800 °C to adjust the oxygen content and, finally, quenched in air to room temperature. Before the thermal treatment, silver contacts were painted on the as-grown samples for the electrical measurements. After annealing, the silver contacts have typical resistance values below $1\ \mu\Omega$. The annealing temperature has been determined using DTA analysis, on as-grown fibers, performed in a SDT Q600 (TA Instruments) between room temperature and 900 °C.

Structural identification of all ceramic samples was performed by powder XRD utilizing a Rigaku D/max-B X-ray powder diffractometer ($\text{CuK}\alpha$ radiation) with 2θ ranging between 10 and 60 degrees. Microstructural characterization was performed on polished longitudinal cross-sections of the samples, in a scanning electron microscope (JEOL JSM 6400) equipped with an energy dispersive spectroscopy (EDX) system.

Annealed samples used for electrical characterization were, approximately, 4 cm long and were measured using the standard four-probe configuration.

Transport critical current density (J_C) values were determined at 77 K using the $1\ \mu\text{V}/\text{cm}$ criterion and the slope of the E - I curve was also calculated by the power law $E \sim I^n$. Resistivity as a function of temperature, from 77 to 300 K, was measured using a dc current of 1 mA, in order to determine the transport T_C values. Moreover, the E - I characteristics of the 0.4 Pb annealed rods have been determined between 65 and 77 K by pumping liquid nitrogen in an

experimental setup described elsewhere [24]. From these results, the variation of the slope of the $E-I$ curves as a function of the temperature was determined using the power law $E \sim I^n$. From these $E-I$ curves, transport J_C was calculated as a function of temperature using the standard 1 $\mu\text{V}/\text{cm}$ criterion.

3. RESULTS AND DISCUSSION

After the directional growth of $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_y$ materials, DTA analysis has been performed in the as-grown materials in order to determine their melting point and establish the annealing temperature for all the samples. In Fig. 1, the DTA graph, as a function of temperature, in the melting temperatures region (between 800 and 950 $^{\circ}\text{C}$, for clarity) is shown for all the samples. In the plot, it can be easily seen that Pb decreases melting point from around 870 $^{\circ}\text{C}$ for the undoped samples, to about 845 $^{\circ}\text{C}$ for the 0.6 Pb-containing ones. As a consequence, the annealing temperature has been determined to be 835 $^{\circ}\text{C}$ for all samples in order to avoid their melting.

Powder XRD patterns of all samples are presented in Fig. 2 between 10 and 60 degrees. The peaks corresponding to the Bi-2212 phase have been indicated by a * in Fig. 2d. In the figure, it is clear that most of the peaks correspond to the Bi-2212 phase, independently of the Pb-content, indicating that the annealing conditions have been adequate to produce this phase as the majority one. Minor peaks are due to the presence of small amounts of Bi-2201 (identified by +), $(\text{Sr},\text{Ca})\text{CuO}_2$ (marked with x), and the $(\text{Bi},\text{Pb})\text{:Sr:Ca:Cu}$ oxide with 3:2:2:1 cation relationship (indicated by #). In these patterns, the main differences in the peaks intensity are reflecting the different preferential grain orientation in the powder preparation of these plate-like grains for the XRD

characterization. On the other hand, in the 0.6Pb-doped samples, a new peak corresponding to a plumbate-like phase, (Bi,Pb):Sr:Ca:Cu oxide, has been identified [28].

The typical microstructure obtained in all the samples after annealing is represented in Fig. 3 where representative longitudinal polished sections are shown. From the figure, it can be observed that undoped samples are composed by nearly pure Bi-2212 phase (grey contrast, Fig. 3a) with well aligned grains. On the other hand, Pb addition increases the amount of secondary phases, identified by EDX as Bi(Pb)-2201 (light grey contrast, #1 in Fig. 3b), (Sr,Ca)CuO₂ (black contrast, #2 in Fig. 3c), and (Sr,Ca)₁₄Cu₂₄O₄₁ (14:24, dark grey contrast, #3 in Fig.3c). This last phase has only been identified in Pb-doped samples and can be due to the modification of the equilibrium between the melt and the solidification front induced by Pb addition. Moreover, in the figure it can be seen that Pb is also responsible of an increased grain misorientation when the amount of Pb is raised. This effect is more pronounced for Pb contents of 0.6 which produces the destruction of the grain alignment (see Fig. 3d).

When analysing the Bi(Pb)-2212 phase, different Pb contents are found, depending on the nominal Pb addition. The amount of Pb in the Bi-2212 is always lower than the nominal amount. EDX analysis has shown a mean Pb content of 0.13, 0.34, and 0.20 in the Bi-2212 phase for the 0.2, 0.4, and 0.6 Pb doped samples. In all cases, the variation of Pb content between the different grains and regions has been determined to be around 15 %. From these data, it is evident that for small amounts of Pb addition (until 0.4), the amount of Pb incorporated in the Bi-2212 structure increases when the nominal content is

raised. On the contrary, 0.6 Pb possess very low Pb in the Bi-2212 structure due to the formation of a plumbate-like phase, (Bi,Pb):Sr:Ca:Cu oxide, with a high Pb and Bi proportion (cation proportion around 3:2:2:1). The contrast shown by this phase is very similar to the observed for the Bi-2212 one, and can only be distinguished by its shape. This phase is presented in Fig. 4 (surrounded by a black line, for easy identification), where a representative longitudinal polished section of the 0.6 Pb-doped samples is shown. The presence of this phase is detrimental by two main reasons: firstly, it is a Pb- and Bi-very rich one and will limit, in a very important manner, the amount of superconducting phase, and secondly, as it is an insulating phase, it will cut the superconducting paths weakening the electrical connectivity between grains. The different microstructures and phase contents observed previously are reflected in the electrical properties, as it is illustrated by Fig. 5, where resistivity vs temperature from 77 to 300 K is represented. In the plot it can be seen that room temperature resistivity slightly increases with 0.2 and 0.4 Pb doping, compared with the undoped samples, while it raises in an important manner for the 0.6 Pb doped samples. This behaviour clearly reflects the microstructural features of these samples, discussed previously. Moreover, the T_C values decrease with Pb addition compared with the values obtained for the undoped samples, as illustrated in Table I. From these data, it is evident that the best T_C results for the Pb doped samples are obtained for the 0.4 Pb containing ones. On the other hand, the relatively low T_C values obtained for the undoped samples are due to the low annealing temperature used (835 °C) for all samples, which is lower than the optimal one determined in previous works (860 °C) [29,30].

The same evolution of T_C is found in the transport J_C values calculated from the E-I curves. J_C decreases with the amount of Pb (see Table I) due to their microstructural evolution when raising Pb content discussed previously. As discussed for the T_C values, J_C in the pure samples is much lower than the typical ones obtained when the samples are annealed at the optimal temperatures [19]. On the other hand, when calculating the slope of the transition curves between the superconducting and the normal state (n), the general evolution shown in Table I reflects a decrease of n values when Pb content is raised. Surprisingly, 0.4 Pb doped samples break this tendency and displays a very high value, more than twice the obtained in the undoped samples which can be associated to the high amount of Pb in the Bi-2212 phase discussed in the microstructural paragraphs. This is a very high value when taking into account that n typical values in Bi-2212 materials are lower than 10, and it is closer to the values for the Bi-2223 which can reach about 20. This impressive n value obtained in the 0.4 Pb doped samples opens the possibility of their use as resistive fault current limiters if the J_C values could be raised. In order to explore this possibility, the transport J_C and n values were determined at temperatures between 77 and 65 K. As it can be easily seen in Fig. 6, transport J_C values are increased, in an important manner, when temperature is decreased to 65 K. The maximum value of 3300 A/cm² obtained at 65 K is high enough for the practical application of these samples as resistive fault current limiters at temperatures easily reached by using cryocoolers. On the other hand, it is necessary to know the behaviour of the n values with temperature in order to confirm the applicability of these materials as current limiters. In Fig. 7 the calculated n values for the 0.4 Pb doped samples, as a

function of temperature, is displayed. In the figure, it can be easily seen that n values increase when the temperature is decreased, reaching about 32 at 65 K. Both transport J_C and n values obtained at 65 K clearly show the applicability of LFZ textured $\text{Bi}_{1.6}\text{Pb}_{0.4}\text{Sr}_2\text{CaCu}_2\text{O}_y$ rods as elements for resistive fault current limiters working at $T \leq 65$ K.

4. CONCLUSIONS

$\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_y$ ($x=0.0, 0.2, 0.4$, and 0.6) textured materials have successfully been fabricated by the LFZ technique. The results indicate that the microstructure is clearly affected by Pb, leading to an increased grain misalignment. The highest Pb substitution (0.6) produces a new plumbate-like phase in the samples, reducing the amount of Pb in the Bi-2212 phase. The microstructural evolution is reflected in the electrical properties (T_C and J_C) which are diminished when Pb is added. The only exception to this evolution is found in the n values which are spectacularly raised for the 0.4 Pb doped samples, reaching values of around 16 at 77 K, much higher than the typical ones obtained in Bi-2212 and comparable to the ones determined in Bi-2223. The transport J_C and n values determined on 0.4 Pb doped samples between 77 and 65 K have demonstrated that this material is suitable for application as resistive fault current limiter at 65 K, an easily reached temperature using cryocoolers, where J_C and n of around 3300 A/cm^2 and 32, respectively, have been obtained.

Acknowledgements

The authors wish to thank the Gobierno de Aragón (Research Groups T12 and T87) for financial support. M. A. Madre and H. Amaveda acknowledge the Spanish MINECO-FEDER (Project MAT2011-22719) for funding. The technical contributions of C. Estepa and C. Gallego are also acknowledged. Sh. Rasekh acknowledges a JAE-PreDoc2010 grant from CSIC.

References

1. Chen M, Donzel L, Lakner M, Paul W. High temperature superconductors for power applications. *J Eur Ceram Soc* 2004;**24**:1815–22
2. Garnier V, Caillard R, Sotelo A, Desgardin G. Relationship among synthesis, microstructure and properties in sinter-forged Bi-2212 ceramics. *Physica C* 1999;**319**:197–208
3. Marinel S, Bourgault D, Belmont O, Sotelo A, Desgardin G. Microstructure and transport properties of YBCO zone melted samples processed in a microwave cavity and infra-red furnace. *Physica C* 1999;**315**:205–14
4. Hensel B, Grasso G, Flukiger R. Aspects of the current understanding of the supercurrent transport in $(\text{Bi,Pb})_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$ silver-sheathed tapes - the railway-switch model. *J Electron Mater* 1995;**24**:1877–81
5. Vieira JM, Silva RA, Silva RF, Costa FM. Enhancement of superconductivity in LFZ-grown BSCCO fibres by steeper axial temperature gradients. *Appl Surface Sci* 2012;**258**:9175–80
6. Hermann PF. Handbook of Applied Superconductivity. Bristol: IOP Publishing; 1998).
7. Noe M, Juengst KP, Werfel FN, Elschner S, Bock J, Breuer F, Kreutz R. Testing bulk HTS modules for resistive superconducting fault current limiters. *IEEE Trans Appl Supercond* 2003;**13**:1976–79
8. Feigelson RS, Gazit D, Fork DK, Geballe TH. Superconducting Bi-Ca-Sr-Cu-O fibers grown by the laser-heated pedestal growth method. *Science* 1988;**240**:1642–5

9. Mora M, Sotelo A, Amaveda H, Madre MA, Diez JC, Angurel LA, de la Fuente GF. Ag addition effect on laser textured Bi-2212 samples. *Bol Soc Esp Ceram V* 2005;**44**:199–203
10. Mora M, Sotelo A, Amaveda H, Madre MA, Diez JC, Capel F, López-Cepero JM. Properties variation of Bi-2212 directionally solidified induced by 0.4Pb substitution. *J Eur Ceram Soc* 2007;**27**:3959–62
11. De la Fuente GF, Ruiz MT, Sotelo A, Larrea A, Navarro R. Microstructure of laser floating-zone (LFZ) textured (Bi,Pb)-Sr-Ca-Cu-O superconductor composites. *Mater Sci Eng A* 1993;**173**:201–4
12. Shi D. High temperature superconducting materials science and engineering. Oxford: Pergamon Press; 1995
13. Sotelo A, Mora M, Madre MA, Amaveda H, Diez JC, Angurel LA, Mayoral MC. Study of the variation of the E-I curves in the superconducting to normal transition of Bi-2212 textured ceramics by Pb addition. *Bol Soc Esp Ceram V* 2006;**45**:228–32
14. Chong I, Hiroi Z, Izumi M, Shimoyama J, Nakayama Y, Kishio K, Terashima T, Bando Y, Takano M. High Critical-Current Density in the Heavily Pb-Doped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ Superconductor: Generation of Efficient Pinning Centers. *Science* 1997;**276**:770–3
15. Musolino N, Bals S, van Tendeloo C, Clayton N, Walker E, Flukiger R. Modulation-free phase in heavily Pb-doped (Bi,Pb)2212 crystals. *Physica C* 2003;**399**:1–7
16. Motohashi T, Nakayama Y, Fujita T, Kitazawa K, Shimoyama J, Kishio K. Systematic decrease of resistivity anisotropy in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_y$ by Pb doping. *Phys Rev B* 1999;**59**:14080–6

17. Hiroi Z, Chong I, Takano M. Two-Phase Microstructures Generating Efficient Pinning Centers in the Heavily Pb-Substituted $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ Single Crystals. *J Solid State Chem* 1998;**138**:98–110
18. Miao H, Kitaguchi H, Kumakura H, Togano K. Microstructure and superconducting properties of Pb-substituted $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x/\text{Ag}$ dip-coated tapes. *Physica C* 1998;**298**:312–20
19. Sotelo A, Madre MA, Diez JC, Rasekh Sh, Angurel LA, Martinez E. The influence of Pb and Ag doping on the $J_c(H,T)$ dependence and the mechanical properties of Bi-2212 textured rods. *Supercond Sci Technol* 2009;**22**:034012
20. Crossley A, Caplin AD, Berenov AV, MacManus-Driscoll JL. The effect of high Pb doping on phase stability of $\text{Bi}_{1.6}\text{Pb}_{0.6}\text{Sr}_{1.8}\text{CaCu}_2\text{O}_{8+\delta}$ and on microstructure and pinning $\text{Bi}_{1.6}\text{Pb}_{0.6}\text{Sr}_{1.8}\text{CaCu}_2\text{O}_{8+\delta}/\text{Ag}$ tapes. *Supercond Sci Technol* 2000;**13**:551–7
21. Funahashi R, Matsubara I, Ueno K, Mizuno K. Isotropic pinning in heavily Pb-doped Bi-2212/Ag tapes. *Physica C* 1999;**315**:247–53
22. Sotelo A, de la Fuente GF, Lera F, Beltran D, Sapina F, Ibanez R, Beltran A, Bermejo MR. Novel Polymer Solution Synthesis of the 110 K Superconducting Phase in the Bismuth System. *Chem Mater* 1993;**5**:851–6
23. Sotelo A, Peña JI, Angurel LA, Diez JC, Ruiz MT, de la Fuente GF, Navarro R. Synthesis of the $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ superconductor following a polymer matrix route. *J Mater Sci* 1997;**32**:5679–85
24. Madre MA, Amaveda H, Mora M, Sotelo A, Angurel LA, Diez JC. Ag doped $(\text{Bi}_{1.6}\text{Pb}_{0.4})\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ textured rods. *Bol Soc Esp Ceram V* 2008;**47**:148–52

25. Carrasco MF, Costa FM, Silva RF, Gimeno F, Sotelo A, Mora M, Diez JC, Angurel LA. Textured Bi–Sr–Ca–Cu–O rods processed by laser floating zone from solid state or melted precursors. *Physica C* 2004;**415**:163–71
26. Funahashi R, Matsubara I, Ueno K, Ishikawa H. Mechanism of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$ crystallization and superconducting properties for $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x/\text{Ag}$ tapes prepared using isothermal partial melting method. *Physica C* 1999;**311**:107–21
27. Sotelo A, Rasekh Sh, Madre MA, Diez JC. Precursor Influence on the Electrical Properties of Textured Bi-2212 Superconductors. *J Supercond Nov Magn* 2011;**24**:19–25
28. Sotelo A, Majewski P, Park H-S, Aldinger F. Synthesis of highly pure Bi-2223 ceramics using defined precursors. *Physica C* 1996;**272**:115–24
29. Ozkurt B, Madre MA, Sotelo A, Yakinci ME, Ozcelik B. Relationship Between Growth Speed, Microstructure, Mechanical and Electrical Properties in Bi-2212/Ag Textured Composites. *J Supercond Nov Magn* 2012;**25**:799–804
30. Natividad E, Diez JC, Angurel LA, Andres JM. Successful Application of Simplex Methods to the Optimization of Textured Superconducting Ceramics. *J Am Ceram Soc* 2004;**87**:1216–21

Figure captions

Figure 1. DTA graph for the different $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_x$ samples between 800 and 950 °C, for $x =$ a) 0.0; b) 0.2; c) 0.4; and d) 0.6.

Figure 2. Powder XRD patterns for the different $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_x$ samples after annealing, for $x =$ a) 0.0; b) 0.2; c) 0.4; and d) 0.6.

Figure 3. SEM micrographs of representative longitudinal polished sections of the different $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{CaCu}_2\text{O}_x$ samples after annealing, for $x =$ a) 0.0; b) 0.2; c) 0.4; and d) 0.6.

Figure 4. SEM micrograph of a representative longitudinal polished section of $\text{Bi}_{1.4}\text{Pb}_{0.6}\text{Sr}_2\text{CaCu}_2\text{O}_x$ sample after annealing showing a plumbate-like, $(\text{Bi,Pb})(\text{Sr,Ca})\text{O}_x$, grain surrounded by a black line for easy identification.

Figure 5. Resistivity measurements vs. temperature, for textured $\text{Bi}_{1.4}\text{Pb}_{0.6}\text{Sr}_2\text{CaCu}_2\text{O}_x$ samples after annealing, for $x=$ 0.0 ■; 0.2 ▲; 0.4 ●; and 0.6 ▼.

Figure 6. Evolution of transport J_C values with temperature, for the 0.4 Pb doped samples, determined between 77 and 65 K.

Figure 7. Evolution of n values with temperature, for the 0.4 Pb doped samples, determined between 77 and 65 K.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7