Promoting Deoxygenation of Bio-Oil by Metal-Loaded Hierarchical ZSM-5 Zeolites.

Alberto Veses,[†] Begoña Puértolas,[‡] José Manuel López,[†] María Soledad Callén,[†]

Benjamín Solsona,[‡] and Tomás García,[†]*

[†]Instituto de Carboquímica (ICB-CSIC), C/ Miguel Luesma Castán, 50018 Zaragoza,
Spain.

[‡]Department of Chemical Engineering, Universitat de Valencia, 46100 Burjassot, Spain.

*E-mail: tomas@icb.csic.es;

The supporting information consists of 9 pages, 1 table and 4 figures.

Table S1. Individual compounds quantified by GC/MS for the upgraded bio-oil.

		Meso- HZ40	Meso- SnHZ40	Meso- CuHZ40	Meso- NiHZ40	Meso- MgHZ40
time	Compound Name	Area	Area	Area	Area	Area
(min)		(%)	(%)	(%)	(%)	(%)
7.82	Methoxyacetic acid, pentyl ester	2.1	1.8	1.7	2.0	1.5
7.95	5,9-Dodecadien-2-one,6,10-dimethyl- (E,E)-	1.3	1.2	1.1	1.5	1.6
8.04	Furan,-2-methyl-	0.8	0.7	0.8	0.9	0.9
8.99	1,3-cyclohexadiene	0.2	0.1	0.2	0.2	0.2
9.11	1,4-cyclohexadiene	0.1	0.2	0.1	0.2	0.2
9.44	2-Butenal, (E)-	0.0	0.0	0.0	0.0	0.0
9.64	Benzene	1.1	0.8	0.6	0.8	0.5
9.67	2-Hydroxyacetaldehyde	0.2	0.2	0.4	0.2	0.2
9.94	3-Penten-2-one	0.1	0.1	0.1	0.2	0.2
10.99	Furan,2,5-dimethyl-	0.2	0.2	0.2	0.2	0.2
11.74	Ethane ,1,2-diethoxy	0.2	0.0	1.1	0.2	1.1
12.36	1,4-cyclohexadiene, 1-methyl-	0.1	0.1	0.1	0.2	0.2
12.66	1-methylcyclohexa-2,4-diene	0.1	0.1	0.1	0.1	0.2
13.00	1,3,5- Heptatriene, (E,E)-	0.1	0.1	0.1	0.1	0.1
13.47	Toluene	5.5	5.7	4.2	5.7	3.6
14.53	Cyclopentanone	0.4	0.4	0.4	0.4	0.4
16.31	Pyrazole,1,4-dimethyl	1.2	1.6	1.4	1.4	1.3
16.75	2,4-Hexandien-1-ol	0.1	0.1	0.1	0.1	0.1
17.11	(R)-(+)-3-Methylcyclopentanone	0.1	0.1	0.1	0.1	0.1
17.60	Ethylbenzene	1.3	1.3	1.3	1.4	1.3
17.98	p-xylene	7.3	6.4	5.2	5.7	4.8
19.01	Xylene (isomers mixture)	2.1	2.1	1.5	1.9	1.4
19.55	2-cyclopenten-1-one, 2-methyl-	1.0	1.0	1.1	1.1	1.2
19.75	Ethanone, 1-(2-furanyl)-	0.2	0.2	0.2	0.1	0.1
20.02	1,3-Cyclohexadiene, 1,3,5,5-tetramethyl-	0.1	0.2	0.1	0.2	0.1
20.96	2-cyclopenten-1-one,3,4-dimethyl-	0.3	0.3	0.4	0.4	0.4
21.63	1,3-cyclopentadiene,5,5-dimethyl-2-propyl-	0.1	0.2	0.1	0.2	0.1

21.82	1,3-cyclopentadiene,5-(1,1-dimethylethyl)-	0.1	0.1	0.1	0.1	0.1
22.03	Benzene,1-ethyl-3-methyl-	1.3	1.2	0.9	1.1	1.0
22.07	2-Furancarboxaldehyde , 5-methyl-	0.1	0.2	0.2	0.2	0.1
22.22	Benzene,1,2,3-trimethyl	0.9	0.8	0.6	0.8	0.8
22.66	Phenol	2.8	2.4	2.4	2.7	2.5
23.02	1,3-Cyclohexadiene, 1,3,5,5-tetramethyl-	0.3	0.3	0.3	0.3	0.3
23.56	Benzene,1-ethyl-3-methyl-	3.1	2.7	2.0	2.4	2.1
23.79	Benzocyclobuten-1(2H)-one	0.4	0.3	0.3	0.3	0.3
24.50	Cyclohexene, 1-methyl-4-(1-methylethylindene)	0.1	0.1	0.1	0.1	0.1
24.58	o-cymene	0.3	0.2	0.3	0.3	0.3
24.77	2-cyclopenten-1-one, 2-hydroxy-3-methyl-	0.4	0.4	0.5	0.5	0.5
25.02	D-Limonene	0.2	0.2	0.2	0.2	0.2
25.29	2-cyclopenten-1-one, 2,3-dimethyl-	0.8	0.7	0.8	0.9	0.9
25.45	Indane	0.9	0.7	0.7	0.5	0.6
25.65	Methacrylic anhydride	0.1	0.1	0.1	0.1	0.1
25.87	Phenol, 2-methyl-	1.9	1.8	1.8	1.9	1.9
26.14	Benzene,1,4-diethyl	0.2	0.2	0.2	0.3	0.3
26.29	2-cyclopenten-1-one,3,4,4-trimethyl	0.3	0.3	0.3	0.3	0.3
26.70	p-cresol	3.4	3.2	3.1	3.3	3.3
27.47	Phenol, 2-methoxy- or guaiacol	3.6	3.3	3.7	3.8	3.4
28.29	Phenol,2,6-dimethyl-	0.3	0.3	0.3	0.3	0.3
28.50	Benzofuran, 2-methyl-	0.8	0.7	0.7	0.7	0.6
29.73	Phenol, 2,5-dimethyl-	1.6	1.6	1.6	1.7	1.8
29.79	Phenol, 2,3-dimethyl-	1.6	1.6	1.3	1.5	1.5
30.20	Napthalene,1,2-dihydro	0.5	0.4	0.3	0.4	0.3
30.43	Phenol, 3-ethyl-	1.4	1.3	1.4	1.4	1.5
30.52	Phenol, 2,5-dimethyl-	0.3	0.3	0.3	0.3	0.3
31.01	2-methoxy,5-methylphenol	0.3	0.2	0.2	0.3	0.2
31.38	Catechol	1.9	2.2	3.3	1.7	3.2
31.48	Creosol	3.4	3.3	3.3	3.7	3.4
31.77	Napthalene	1.4	0.9	0.6	1.2	0.4
32.07	Phenol,2,4,6-trimethyl-	0.4	0.4	0.4	0.4	0.4
32.68	Benzofuran,4,7-dimethyl-	0.4	0.3	0.3	0.4	0.4

33.09	Phenol, 2-ethyl, 5-methyl-	1.5	1.6	1.7	1.6	1.8
33.84	1,2-Benzenediol, 3- methyl-	1.1	1.3	1.5	1.1	1.8
34.60	Phenol, 4-ethyl,2-methoxy-	4.3	4.3	4.2	4.7	4.3
34.84	1,2-Benzenediol, 4- methyl-	1.8	2.2	3.0	1.9	3.0
35.23	1H-Indene-1-one,2,3-dihydro-	0.1	0.2	0.2	0.1	0.2
35.84	1H-Indene-1-ethylidene	1.6	1.3	1.0	1.4	0.7
35.97	2-Methoxy-4-vinylphenol	0.8	0.8	0.9	0.8	0.7
36.86	Phenol, 4-(2-propenyl)-	0.0	0.1	0.1	0.1	0.1
37.18	1,4-Benzenediol, 2,6-dimethyl-	0.5	0.5	0.7	0.5	0.7
37.36	Eugenol	0.4	0.5	0.4	0.4	0.4
37.70	Phenol, 2-methoxy-4-propyl-	2.5	2.3	2.1	2.4	2.3
38.12	4-ethylcatechol	2.0	2.3	3.2	2.2	2.6
39.01	Vanillin	0.4	0.5	0.5	0.4	0.4
39.12	Phenol, 2-methoxy-4-(1-propenyl)-	0.5	0.6	0.6	0.6	0.5
40.19	Napthalene,1,8-dimethyl-	0.6	0.6	0.5	0.6	0.3
40.57	trans-Isoeugenol	1.8	2.3	2.1	2.0	1.9
41.77	Apocynin	0.5	0.7	0.6	0.6	0.5
42.01	Levoglucosan	0.0	0.0	0.0	0.0	0.0
42.24	.alpha-Murolene	0.2	0.2	0.2	0.2	0.3
42.68	Benzoic acid, 4-hydroxy-3-methoxy-,methyl ester	0.1	0.2	0.2	0.1	0.1
43.00	2-Propanone, 1-(4-hydroxy-3-methoxyphenyl)-	1.1	1.4	1.3	1.2	1.1
43.14	2-Naphtalenol	0.5	0.5	0.4	0.4	0.2
44.70	alpha-Amino-3'-hydroxy-4'-methoxyacetophenone	0.2	0.3	0.3	0.3	0.2
45.00	Naphtalene,1-methyl-7-(1-methylethyl)-	0.3	0.3	0.3	0.3	0.3
46.58	Homovanillic acid	0.2	0.3	0.3	0.2	0.2
49.14	2- Propenal, 3-(4-hydroxy-3 methoxyphenyl)-	0.0	0.0	0.0	0.0	0.0
53.46	Hexadecanoic acid, methyl ester	0.0	0.0	0.0	0.0	0.0
54.84	Phenanthrene,1-methyl	0.7	0.6	0.5	0.5	0.5
55.68	1-Phenanthrenecarboxaldehyde, 1,2,3,4,4a,9,10,10a-octahydro-1,4a-dimethyl-7-(1- methylethyl)	0.4	0.4	0.4	0.4	0.4
56.65	4b,8-Dimethyl-2- isopropylphenanthrene,4b,5,6,7,8,8a,9,10- octahydro	0.2	0.2	0.3	0.2	0.3
57.70	Phenanthrene ,4,5-dimethyl-	0.2	0.5	0.6	0.5	0.6

57.99	1,7,7-Trimethyl-3-phenethylidenebicyclo[2.2.1]heptan-2-one	0.0	0.1	0.1	0.0	0.0
58.53	10,18-Bisnorabieta-5,7,9(10),11,13-pentaene	0.5	0.5	0.5	0.5	0.6
59.29	4,4'-Diisopropylbiphenyl	0.1	0.2	0.2	0.2	0.2
60.04	Phenanthrene,2,3,5-trimethyl	0.6	0.6	0.7	0.6	0.7
60.32	Anthracene,9-butyl,1,2,3,4-tetrahydro-	0.1	0.1	0.2	0.1	0.2
60.57	1-[4-(2-p-Tolylvinyl)phenyl]ethanone	0.1	0.3	0.2	0.2	0.2
60.68	Primaric acid	0.1	0.1	0.1	0.1	0.1
61.35	Retene	7.6	7.7	8.3	7.5	9.1
63.33	8-Isopropyl-1,3-dimethylphenanthrene	0.2	0.3	0.4	0.3	0.3
63.42	Homovanilyl alcohol	0.5	0.3	0.9	0.7	0.9
63.58	Methyl dehydroabietate	3.4	4.5	4.7	4.0	5.5
64.68	Methyl abietate	0.0	0.0	0.0	0.0	0.0
66.79	Diisooctyl phthalate	0.2	0.3	0.0	0.2	0.2

Table S1 shows the different compounds identified in the organic liquid fraction by GC/MS.

Figure S1. Scheme of the lab-scale experimental setup used for the upgrading of bio-oil.

Description of the experimental setup. The experimental setup consists of two main inlets, one for the carrier gas (7 mL/min N₂) and another one for the raw bio-oil (5 mL/h), which are joined before the reactor. The solid zeolite (0.5 g) was placed in a tubular stainless steel fixed-bed reactor supported by two quartz wool plugs (0.5 g each) and 4 g of quartz beads located above the catalyst bed. The temperature of the catalytic reaction (450 °C) was controlled by a thermocouple located at the top of the catalyst bed. The resulting volatile fraction passes through an ice trap and non-condensable gases are collected for further characterization. The duration of the experiments was divided in two stages: 120 min of feeding the raw bio-oil and inert N₂ gas and 30 min of sweeping with merely N₂.

Figure S2. XRD results of the acid and cation-loaded hierarchical zeolites.

XRD patterns only display the sharp reflections corresponding to the MFI structure.

Figure S3. Nitrogen isotherms of the acid and cation-loaded hierarchical zeolites.

All the samples exhibit a type I-V isotherm, characteristic of mesoporous materials

Figure S4. Transmission electron microscopy applied to catalyst. (A) Meso-SnHZ40, (B) Meso-NiHZ40, (C) Meso-CuHZ40 (D) Meso-MgHZ40.

TEM images of the hierarchical zeolites clearly highlight the uniform distribution of intracrystalline mesopores and only indicate the presence of metallic nanoparticles at the external surface in the case of Meso-SnHZ40 and Meso-NiHZ40 catalysts.