Localized magnetic moments in metallic SrB_6 single crystals

Jolanta Stankiewicz¹, Pedro Schlottmann², Ana Arauzo³,
María José Martínez Pérez⁴, Priscila F. S. Rosa⁵, Leonardo
Civale⁵ and Zachary Fisk⁶

¹ Instituto de Ciencia de Materiales de Aragón and Departamento de Física de la Materia Condensada, CSIC–Universidad de Zaragoza, 50009-Zaragoza, Spain

² Department of Physics, Florida State University, Tallahassee, FL 32306, USA

³ Servicio de Medidas Físicas, Universidad de Zaragoza, Zaragoza 50009, Spain

⁴ Instituto de Ciencia de Materiales de Aragón and Departamento de Física de la Materia Condensada, CSIC–Universidad de Zaragoza, 50009-Zaragoza, Spain, and Fundación ARAID, 50004-Zaragoza, Spain

⁵ Condensed Matter and Magnet Science, Los Alamos National Laboratory, Los Alamos, New Mexico 87545, U.S.A.

⁶ Department of Physics and Astronomy, University of California, Irvine, CA 92697, USA

E-mail: jolanta@unizar.es

Abstract. The specific heat C_p of metallic SrB_6 single crystals shows an anomalous behavior for $T \lesssim 5\text{K}$ which varies strongly with an applied magnetic field. This is consistent with a two-level Schottky system. We ascribe the excess of C_p in this temperature range to localized magnetic moments. In addition, features that are attributable to a partial ferromagnetic polarization of a conduction electron gas are observed. These results are supported by magnetization measurements and are compatible with the transport properties reported previously (DOI: 10.1103/PhysRevB.94.125141).

Keywords: specific heat, alkaline–earth hexaborides, localized moments

Submitted to: *J. Phys.: Condens. Matter*

1. Introduction

The discovery of an unusual type of ferromagnetism in alkaline-earth hexaborides like CaB₆ [1] and SrB₆ [2] triggered extensive theoretical and experimental research of these materials for last two decades. The long-range ordering to a Curie temperature of 600 K was unexpected because these compounds do not have partially occupied 3d or 4f orbitals. Ferromagnetic polarization of the low-density electron gas has been first suggested to explain this phenomenon [1, 2, 3] but even most favorable numerical estimates for the temperature at which ordering occurs are far below room temperature [3]. Another early attempt assumed doping of an excitonic insulator [4, 5], a model whose theoretical foundation has been published long ago [6]. However, it has been shown that the excitonic state is unlikely to be stable [7]. Later on, ferromagnetic Fe-B phases and other impurities have been found to contribute to ferromagnetic behavior [8, 9, 10, 11, 12]. In particular, impurities in 3N boron seemed to be responsible for ferromagnetic signal as no magnetism was found in single crystals of CaB₆ grown using boron of 99.9999% purity (6N) [13]. The idea of an intrinsic magnetism brought about by defects was invoked as well [2, 14, 15, 16]. This was studied closely by Edwards and Katsnelson [17], who showed that electrons in a narrow impurity band near the Fermi level could be responsible for high-temperature Stoner ferromagnetism in CaB₆. Metal [2, 18] or boron vacancies [13, 19, 20] are good candidates for impurity bands, as hexaborides have a tendency to self-doping. More recent experiments [21, 22, 23, 24, 25] are not conclusive, leaving the origin of the ferromagnetism in alkaline-earth hexaborides unexplained. We address this issue here by means of heat capacity experiments.

Divalent hexaborides AEB₆ (AE=Ca, Sr, Ba) crystallize in a cubic CsCl-type structure, and the physical properties are alike for all alkaline earth members. SrB₆ is a semiconductor with a sizable gap of about 1 eV at the X-point in the Brillouin zone, as shown by angle-resolved photoemission spectroscopy (ARPES) [26]. Band structure calculations often underestimate gaps and the results depend sensitively on the value of lattice parameters and doping, showing sometimes a small band overlap at the X-point [27, 28]. Despite of a rather simple cubic crystal structure, almost all hexaborides, including rare-earth compounds, show unexpected physical behavior at low temperatures. It follows from the presence of native defects, mainly boron or cation vacancies, which seem to be inherent to this class of materials [29, 14, 30, 18, 31, 32]. These defects give rise to a self-doping. As a consequence, divalent hexaborides, which are expected to be semiconductors, show often metallic-like conductivity. Frequently, it is not straightforward to disentangle the contribution of intrinsic defects from that of unintended impurities or contamination.

In addition, the structure of hexaborides favors disorder in the metal sublattice upon introducing boron vacancies [26]. The cation, which is at the center of an oversized "cage" consisting of 48 boron atoms, is weakly bound and can move largely away from its equilibrium position. The boron framework, on the other hand, is rigid leading to high melting points and low coefficients of thermal expansion. Boron vacancies may

Localized magnetic moments in metallic SrB₆ single crystals

displace some cations and thus bring disorder which increases as the temperature is lowered. All this makes for extraordinary behavior observed in hexaborides.

In order to understand mechanisms behind some puzzling physical properties of the alkaline-earth hexaborides, we study low-temperature specific heat of SrB₆ single crystals with different carrier concentration. Additional measurements on a BaB₆ single crystal have been carried out for comparison purposes. The electrical transport properties of these samples have been previously carefully characterized and accounted for by a variable-charge defect model [33, 34]. We discuss results of experimental specific heat measurements in the context of localized magnetic moments and electronic correlations in the low-density electron gas. Additional support for such scenario comes from low-temperature magnetization measurements performed on the very same crystals used in heat capacity studies.

2. Experiment

The single crystals of AEB₆ were grown from an Al flux with no intentional doping. The SrB₆ samples studied are from different batches but were prepared under the same conditions. The as-grown nominally stoichiometric crystals have carrier densities of approximately 10^{19} – 10^{20} cm⁻³. This can only be explained by off-stoichiometry that also gives rise to considerable variation of the chemical potential position from sample to sample. Energy Dispersive X-ray Spectra (EDS) yield a value of 0.17 ± 0.005 for the atomic ratio Sr:B in all samples, very close to the nominal value of 0.167. No presence of Al was found in the EDS spectra. Therefore, we estimate the content of Al in the samples at less than 0.1 wt% which is the approximate sensitivity of our SEM-EDS measurements. Prior to measurements, crystals were etched in concentrated HCl acid.

Our heat capacity measurements were performed on small single crystals, cleaved from the as-grown crystals, with an approximate mass and volume of 1 mg and 5×10^{-4} cm⁻³, respectively. Some of these samples were used in transport studies reported previously [34]. All measurements were performed in a Quantum Design physical properties measurement system (PPMS), with a He-3 insert, which enables access to temperatures as low as 0.3 K. A small amount of Apiezon N grease was used to hold the crystal in place on a sapphire platform and to assure good thermal contact between the crystal and the platform. The PPMS measures the heat capacity at high vacuum using the relaxation method.

Magnetization measurements were performed at 300 K and 2 K using a commercial superconducting quantum interference device (SQUID) magnetometer and from 10 K down to 300 mK with a high-sensitivity (10^{-9} emu) Hall magnetometer. For the latter, the Hall signal is sensitive to the magnetization of a small area (50×400) μm^2 of the sample that lies on top of the cross formed by contacts of the Hall device [36]. Thus, the very same samples used in the heat capacity experiments could be measured by this method. In the SQUID measurements, more than five or six pieces were used because of the very small volume of single crystals. Consequently, we obtain values of magnetization

Localized magnetic moments in metallic SrB_6 single crystals

Figure 1. (Color online) Variation of the heat capacity with temperature for BaB_6 and SrB_6 single crystals. The upper inset shows the electron concentration *vs* temperature for the same samples. A zoomed plot for SrB_6 -2 and SrB_6 -3 crystals is exhibited in the lower inset.

averaged over several samples from these measurements. On the other hand, only a qualitative behavior of magnetization can be judged from micro-Hall results.

3. Results and Discussion

The low-temperature heat capacity C_p as a function of temperature for BaB_6 and SrB_6 single crystals is displayed in Fig. 1. All three SrB_6 samples we studied have much lower resistivity and larger (by almost two orders of magnitude) carrier concentration than the BaB_6 sample at low temperatures. The electron concentration n , obtained from Hall effect measurements [34, 35], is shown in the inset of Fig. 1 as a function of temperature T . (Here, we use the one-band approximation as the hole-like bands affect negligibly transport properties of our self-doped samples.) Overall, C_p is much larger for SrB_6 than for BaB_6 below approximately 4 K. Clearly, this is brought about by a much larger electronic contribution in the strontium compound.

A feature indicative of some kind of anomaly is evident at 1 K for the SrB_6 -1 sample, and at 0.6 K for the BaB_6 sample, respectively. Below this temperature, C_p drops linearly towards zero down to 0.3 K (the lowest temperature of measurement) with a slope of $1.4 \times 10^{-3} \text{ J/K}^2(\text{mol Sr})$ and $2.5 \times 10^{-4} \text{ J/K}^2(\text{mol Ba})$ in these samples. A much broader anomaly is observed in the SrB_6 -2 and SrB_6 -3 specimens. The decrease of C_p occurs below 0.5 K and the corresponding slope is about $3 \times 10^{-3} \text{ J/K}^2(\text{mol Sr})$. We note that the similar value has been obtained in Ref. [29] for the slope of $C(T)$

Localized magnetic moments in metallic SrB_6 single crystals

Figure 2. (Color online) Specific heat C_p divided by temperature T vs T^2 for BaB_6 and SrB_6 single crystals. The inset shows the excess specific heat ΔC vs temperature for the same samples. Note a break in the y axis and change of scale.

below 0.2 K, albeit for a more resistive SrB_6 sample. At higher temperatures ($4 \text{ K} \lesssim T \lesssim 10 \text{ K}$), we obtain smaller values for the linear in T contribution to the specific heat. Identifying this term as the electronic heat capacity parameter γ , we obtain a value of approximately $0.6 m_o$ for the effective mass m^* in the parabolic band approximation, close to the effective mass of conduction electrons in SrB_6 [28]. Here, m_o is the free electron mass.

The zero-field specific heat, in addition to the electronic linear in T term, has a T^3 phonon contribution: $C_p(T) = \gamma T + \beta T^3$. In Fig. 2 we plot C_p/T as a function of T^2 for the BaB_6 and SrB_6 single crystals we have studied. In this plot, the data points above 3 K follow straight lines with a slope β yielding a Debye temperature Θ_D of $400 \pm 20 \text{ K}$ for SrB_6 (we apply a low-temperature approximation: $\Theta_D \approx (1945/\beta)^{1/3}$). Below approximately 5 K, an excess specific heat is observed, in addition to the linear and cubic contributions. The inset of Fig. 2 shows this excess specific heat, $\Delta C = C_p - (\gamma T + \beta T^3)$, versus temperature. We use for γ and β values obtained from fits in the (4-10) K temperature range; *i.e.* $\gamma = 1.8 \times 10^{-4} \text{ J/K}^2 \text{ mol}$ for the BaB_6 and SrB_6 -1 samples, and $5 \times 10^{-4} \text{ J/K}^2 \text{ mol}$ ($4.5 \times 10^{-4} \text{ J/K}^2 \text{ mol}$) for the SrB_6 -2 (SrB_6 -3) sample; $\beta \approx 1.4 \times 10^{-4} \text{ J/K}^4 \text{ mol}$ for all the Sr-samples and $\beta = 3.3 \times 10^{-5} \text{ J/K}^4 \text{ mol}$ for BaB_6 .

The excess specific heat for SrB_6 samples increases with decreasing temperature reaching a broad maximum below 1 K with a value of the order of 1 mJ/K mol. Weak

Localized magnetic moments in metallic SrB_6 single crystals

Figure 3. (Color online) Excess entropy ΔS vs T for the BaB_6 and SrB_6 single crystals. The inset shows the square of the Schottky splitting vs B^2 .

anomalous features seen approximately at 3 K (SrB_6 -1) and 1.2 K (SrB_6 -3) are, in our opinion, spurious because of uncertainty in C_p values coming from experimental noise in this temperature range. The maximum of ΔC is higher for samples with larger carrier concentration. No perceptible excess specific heat, with exception of a small peak at 0.6 K, is found for the BaB_6 crystal, in line with the low carrier density in this sample. Thus, the excess specific heat in SrB_6 crystals appears to be related to electronic degrees of freedom. More puzzling is a weak anomaly in the SrB_6 -1 sample, consisting of a maximum of ΔC at about 1 K. A similar feature has been observed earlier for a more resistive SrB_6 sample [29] and for YbBiPt [37] in the same temperature range. It is unlikely that the anomaly in SrB_6 would be brought about by the same mechanism as in YbBiPt which is a putative heavy fermion semimetal whereas SrB_6 is a semiconductor with intrinsic defects that control its electronic properties. On the other hand, thorough studies of the specific heat at very low temperature down to 0.05 K on a high quality single crystal of SrB_6 , reported by Ott *et al.*, show very similar behavior to that of the SrB_6 -2 and SrB_6 -3: a steep decrease of C_p down to about 2 K followed by a decrease with a very small slope down to the lowest temperatures. The weak anomaly of ΔC with an onset at 0.4 K and the subsequent drop below 0.2 K has been tentatively related by these authors to strong correlations in the electronic system of SrB_6 . We will refer to these results later.

The excess entropy, ΔS , related to the ΔC , saturates at 5 K with values lower than 10^{-3} of $R \ln 2$, where R is the gas constant (see Fig. 3). Since $\Delta C/T$ increases for $T \rightarrow 0$, the entropy below our lowest measuring temperature cannot be estimated reliably. As a rough guess we have assumed a linear drop of ΔC towards zero for $T \rightarrow 0$ which likely undervalues ΔS . The number of spins contributing to the excess entropy

Localized magnetic moments in metallic SrB_6 single crystals

Figure 4. (Color online) Specific heat *vs* *T* at various magnetic fields for the BaB_6 and SrB_6 -1 single crystals. The density of spins, contributing to the excess entropy, and the density of the Schottky sites for all SrB_6 single crystals are shown in the inset.

can be estimated from the relation: $N_S = \Delta S / (k_B \ln 2)$ (k_B is the Boltzmann constant). We obtain $N_S \approx 5 \times 10^{18}$ spins per cm^3 for SrB_6 -1 and $N_S \approx 8 \times 10^{18}$ (7×10^{18}) spins per cm^3 for SrB_6 -2 (SrB_6 -3).

We now turn to the magnetic-field dependence of the specific heat. Figure 4 shows the magnetic field dependence of $C_p(B)$ for SrB_6 -1 and BaB_6 . The temperature variation of the excess specific heat ΔC in various magnetic fields is shown in Fig. 5 for all SrB_6 samples studied. The ΔC was obtained for high fields by subtracting the zero-field βT^3 term (the phonon contribution is not expected to be field dependent) and the zero-field electronic term γT . The remaining specific heat for $T \lesssim 5$ K is well described by a two-level Schottky anomaly: $\Delta C = \alpha R (\Delta/T)^2 \exp(\Delta/T) / (1 + \exp(\Delta/T))^2$, where α is the concentration of the Schottky sites. This implies the presence of localized magnetic moments. The solid lines in Fig. 5 are fits to the experimental data. The values obtained for α are in the range $(0.5-1) \times 10^{-4}$. As seen in the inset of Fig. 3, there is a straight line dependence in Δ^2 *vs* B^2 whose slope yields a value of approximately 2 for the effective g -factor [38], as in Zeeman splitting for a two-level system with an electron spin $S = 1/2$. There is a small zero-field splitting, indicating the presence of a weak internal field of about 1.4 T. The effective fields B_{eff} , estimated from the maximum of the Schottky anomalies T_m ($B_{\text{eff}} \cong 1.2 k_B T_m / \mu_B$, where μ_B is the Bohr magneton), are larger than the applied magnetic field, indicating ferromagnetic interactions between local moments.

From our fits of a two-level Schottky anomaly to the data for various magnetic

Localized magnetic moments in metallic SrB_6 single crystals

Figure 5. (Color online) Excess specific heat ΔC vs T at various magnetic fields for SrB_6 single crystals. The solid lines are fits to the two-level Schottky anomaly. The data for SrB_6 -3 sample in the applied field of 5 T have been exceptionally noisy at low temperatures.

fields, we can estimate the density of localized moments N_{Sch} and compare it to the concentration of spins contributing to the excess entropy at $B = 0$. This is shown in the inset of Fig. 4. We find that N_{Sch} is systematically 20% below N_S . Both quantities increase with increasing electron concentration in the SrB_6 samples. In addition, the values of N_{Sch} match the concentration of one-electron localized states in the model of variable-valence defects as obtained from transport measurements on the same samples [33, 34].

In the variable-valence defects model, the intrinsic defects form an impurity band which merges with the conduction band. In the extended states, the defects are positively charged. These centers may bind electrons and give rise to resonant levels with one or two electrons. In the model, only neutral (one-electron) localized centers have unpaired electrons, which can contribute to the ferromagnetism. The Fermi energy

Localized magnetic moments in metallic SrB_6 single crystals

Figure 6. (Color online) Magnetization *vs* B for SrB_6 and BaB_6 single crystals, measured using a SQUID magnetometer. The inset shows the same plot after final etching with acid.

is effectively pinned to such levels at low temperatures. In particular, fits of the above model to the temperature variations of the electron concentration yield a value of $4 \times 10^{18} \text{cm}^{-3}$ ($6 \times 10^{18} \text{cm}^{-3}$) for the density of the one-electron defects in SrB_6 -1 (SrB_6 -2). This agrees very well with the value of N_{Sch} obtained from ΔC . All above results imply that the weak ferromagnetism in electron-doped SrB_6 could be brought about by intrinsic defects, and not by extrinsic contamination with ferromagnetic elements.

We observe a clear correlation between resistivity, carrier concentration and defect density in our data for SrB_6 , in agreement with findings for other alkaline-earth hexaborides [33, 34]. Samples with larger carrier concentration (lower resistivity) have more native defects. This, in turn, gives rise to higher density of the one-electron localized states (localized magnetic moments) observed in the excess entropy and Schottky anomaly. All the above points to a crucial role of native defects, mainly brought about by off-stoichiometry, in the physical behavior of alkaline-earth hexaborides.

We examine next the magnetic behavior of the samples at low temperatures. All of the samples we studied seemed to be ferromagnetic, with highly nonlinear magnetization curves and small coercive fields of less than 10^{-2} T. Figure 6 shows SQUID magnetization curves $M(B)$ for SrB_6 and BaB_6 single crystals before and after final etching with acid. We observe that the saturation moment of the samples is reduced by about 40% with the repeated etching process. Therefore, some of the weak ferromagnetic moment is most likely related to extrinsic impurities, which are generally found within $10 \mu\text{m}$ of the sample surface, and can be removed with the surface by etching. However, the

Localized magnetic moments in metallic SrB_6 single crystals

10

magnetization is not entirely suppressed after final etching. The SQUID measurements show an approximate density of $6.5 \times 10^{18} \mu_B/\text{cm}^3$ and $3.8 \times 10^{18} \mu_B/\text{cm}^3$ of magnetic moment at this stage for SrB_6 and BaB_6 , respectively.

Low-temperature magnetization curves, obtained with micro-Hall devices, are plotted in Fig. 7. The single crystals measured are the same ones used in the heat capacity measurements. These plots suggest that at least part of the magnetic moment is associated with the crystal bulk, as the values of the saturation moment and the low-field $M(B)$ slope vary with temperature. This is plotted in the upper inset of Fig. 7. Therefore, we see two overlapping effects in the magnetization curves: (1) – an extrinsic ferromagnetism coming from ferromagnetic impurities which saturates rapidly at small fields of ≈ 0.02 T, and (2) – an intrinsic ferromagnetism, seen in the specific heat measurements, which requires a higher field of about 1 T to polarize. Extrinsic ferromagnetic impurities or defects are presumably segregated at the step or facet edges as the etch process is more effective at removing metallic contaminants on the surface than from these sites [12]. This could explain why they do not polarize intrinsic moments contributing to the specific heat excess. All these observations lead us to conclude that one-electron localized centers of intrinsic defects, which may give rise to a narrow impurity band close to the Fermi level, are responsible for the specific heat excess and weak ferromagnetism at low temperatures in SrB_6 .

The question arises why the more resistive SrB_6 sample studied by Ott *et al.* shows a similar entropy excess as the SrB_6 -1 sample though it seems to contain much less defects. The resistivity of this sample varies with temperature very much as of one of CaB_6 samples reported in Ref. [34] whose defects' concentration is approximately $1 \times 10^{18} \text{cm}^{-3}$. This is compatible with the entropy excess found in Ref. [29] and it is one order of magnitude less than the concentrations of defects in our samples. Therefore, the model we propose can account for the entropy excess reported by Ott and his collaborators. In addition, Ott *et al.* observe an excitation at about 40 cm^{-1} in their optical conductivity measurements which seems to define some sort of a characteristic energy scale. We believe that it could be attributed to the intrinsic-defect excitation between resonant levels with one and two electrons as the match in energy is quite good.

Finally, we discuss the anomalous features found in the excess specific heat of AEB_6 . We speculate that these anomalies can be accounted for by a ferromagnetic polarization of the conduction electron gas which has originally been proposed to explain the unusual ferromagnetism in these compounds [1]. The ferromagnetic ground state of a dilute electron gas has not yet been reported experimentally. The results of computational studies of electronic correlations in this case somewhat depend on the method employed [3, 39, 40]. In Ref. [40] it is concluded that a partially spin-polarized state is stable for $15 \leq r_s \leq 40$, where r_s is related to the average electron density ρ by: $\rho^{-1} = 4\pi r_s^3/3$. A single band interpretation of the Hall coefficient for the SrB_6 samples indicates electron-like carriers, with densities of the order of 10^{19}cm^{-3} (see inset of Fig. 1). This gives $r_s \approx 43a_B$ for SrB_6 -1 and $r_s \approx 35a_B$ for SrB_6 -2 (a_B is the Bohr radius for the free electron) placing these samples as good candidates for such a scenario. The specific

Localized magnetic moments in metallic SrB_6 single crystals

11

Figure 7. (Color online) Magnetization *vs* B for SrB_6 -1 (main panel) and SrB_6 -3 (lower inset) single crystals, measured using a micro-Hall device. The upper inset shows the low-field susceptibility as a function of temperature for the same crystals.

heat anomalies observed at 1 K in SrB_6 -1 and, at a lower temperature in BaB_6 , could therefore be attributed to a spontaneous partial magnetization. The initial susceptibility of the SrB_6 -1 sample also shows a peak at 1 K (see the inset of Fig. 7). Inhomogeneities in the more conductive SrB_6 -2 and SrB_6 -3 samples may well give rise to a distribution of critical temperatures T_c and lead to a broad maximum at low temperatures instead of a well defined peak. These inhomogeneities are related to stoichiometric and structural defects whose density in SrB_6 -2 and SrB_6 -3 crystals is more than twice as large as in the less conductive SrB_6 -1 specimen. We also note that the deviations from the calculated Schottky curves are larger below T_c , where the ferromagnetic correlations are stronger (see Fig. 5). All the above consistently fits in with a ferromagnetic polarization of a diluted electron gas. The systematic difference between the density of localized moments N_{Sch} and the concentration of spins obtained from the excess entropy at $B = 0$ in SrB_6 suggests a spin polarization of nearly 10% of all conduction electrons, which agrees well with the stochastic calculations of Ref. [40].

4. Conclusions

Results of experimental specific heat and magnetization studies on several SrB_6 single crystals with different carrier concentration are presented and discussed in the context of localized magnetic moments and electronic correlations in the low-density electron gas. In the absence of a magnetic field, the specific heat for $T \lesssim 5$ K shows, apart

Localized magnetic moments in metallic SrB_6 single crystals 12

from phonon and electronic contributions, an excess specific heat which evolves into a Schottky anomaly at larger fields. We estimate the number of spins contributing to the excess entropy and the density of the Schottky sites. These numbers agree well with the density of one-electron localized states obtained from transport properties of the same samples using a variable-charge defect model. This suggests ordered defect moments as a source of intrinsic ferromagnetism in SrB_6 . An additional support for it comes from the magnetization measurements. Although an extrinsic ferromagnetism which saturates rapidly at small fields masks the intrinsic contribution, this is clearly seen as the measured saturation moment and low-field susceptibility vary with temperature. The intrinsic magnetization requires a higher field of about 1 T to polarize, in agreement with the heat capacity results.

Additionally, we observe some anomalous features in the low-temperature heat capacity of AEB_6 single crystals like a maximum at about 1 K for the SrB_6 -1 sample and, at 0.6 K, for BaB_6 sample. The initial susceptibility of the SrB_6 -1 sample shows a peak at 1 K as well. These anomalies can be ascribed to the magnetic polarization emerging from electronic correlations in the low-density electron gas. However, its contribution to the intrinsic ferromagnetism is much weaker than that of the native defects.

Acknowledgments

We acknowledge support from grant MAT2015-73914-JIN, from the Ministerio de Economía y Competitividad of Spain. Work at Los Alamos National Laboratory was performed under the auspices of the U.S. DOE through the Los Alamos LDRD program.

References

- [1] Young D P *et al* 1999 *Nature* **397** 412
- [2] Ott H R *et al* 2000 *Physica B* **281-282** 423
- [3] Ceperley D 1999 *Nature* **397** 386
- [4] Zhitomirskiy M E, Rice T M and Anisimov V I 1999 *Nature* **402** 251
- [5] Murakami S, Shindou R, Nagaosa N and Mishchenko A S 2002 *Phys. Rev. Lett.* **88** 126404
- [6] Keldysh L V and Kopaev Yu V 1965 *Soviet Physics Solid State* **6** 2219; des Cloizeaux J 1965 *J. Phys. Chem. of Solids* **26** 259
- [7] Hotta C, Fukuyama H and Ogata M 2002 *Phys. Rev. B* **65** 184421
- [8] Matsubayashi K, Maki M, Tsuzuki T, Nishioka T and Sato N K 2002 *Nature* **420** 143
- [9] Taniguchi K, Katsufuji T, Sakai F, Ueda H, Kitazawa K and Takagi H 2002 *Phys. Rev. B* **66** 064407
- [10] Meegoda C, Trenary M, Mori T and Otani S 2003 *Phys. Rev. B* **67** 172410
- [11] Jarlborg T 2003 *J. Phys.: Condens. Matter* **15** L249
- [12] Bennett M C *et al* 2004 *Phys. Rev. B* **69** 132407
- [13] Cho B K *et al* 2004 *Phys. Rev. B* **69** 113202
- [14] Monnier R and Delley B 2001 *Phys. Rev. Lett.* **87** 157204
- [15] Lofland S E, Seaman B, Ramanujachary K V, Hur N and Cheong S W 2003 *Phys. Rev. B* **67** 020410(R)
- [16] Maiti K, Medicherla V R R, Patil S and Singh R S 2007 *Phys. Rev. Lett.* **99** 266401
- [17] Edwards D M and Katsnelson M I 2006 *J. Phys.: Condens. Matter* **18** 7209

Localized magnetic moments in metallic SrB_6 single crystals 13

[18] Vonlanthen P, Felder E, Degiorgi L, Ott H R, Young D P, Bianchi A D and Fisk Z 2000 *Phys. Rev. B* **62** 10076

[19] Cao J X, Zhu Y, Yang Z Q and Wu R Q 2009 *Phys. Rev. B* **79** 132404

[20] Maiti K 2008 *Eur. Phys. Lett.* **82** 67006

[21] Li M, Wang H, Snoussi K, Li L, Yang W and Gao Ch 2010 *J. Appl. Phys.* **108** 103710

[22] Li Y, Yang J, Cui X, Hu T, Liu C, Tian Y, Liu H, Han Y and Gao Ch 2011 *Phys. Stat. Sol. B* **248** 1162

[23] Kolmogorov A N, Shah S, Margine E R, Kleppe A K and Jephcoat A P 2012 *Phys. Rev. Lett.* **109** 075501

[24] Ackland K, Venkatesan M and Coey J M D 2013 *Eur. Phys. J. B* **86** 104

[25] Zhao G, Zhang L, Hu L, Yu H, Min G and Yu H 2014 *J. Alloys and Compounds* **599** 175

[26] Denlinger J D, Clack J A, Allen J W, Gweon G -H, Poirier D M, Olson C G, Sarrao J L, Bianchi A D and Fisk Z 2002 *Phys. Rev. Lett.* **89** 157601

[27] Massidda S, Continenza A, Pascale T M and Monnier R 1997 *Z. Phys. B* **102** 83

[28] Rodriguez C O, Weht R and Pickett W E 2000 *Phys. Rev. Lett.* **84** 3903

[29] Ott H R, Chernikov M, Felder E, Degiorgi L, Moshopoulou E G, Sarrao J L and Fisk Z 1997 *Z. Phys. B* **102** 337

[30] Paschen S, Pushin D, Schlatter M, Vonlanthen P, Ott H R, Young D P and Fisk Z 2000 *Phys. Rev. B* **61** 4174

[31] Giannó K, Sologubenko A V, Ott H R, Bianchi A D and Fisk Z 2002 *J. Phys.: Condens. Matter* **14** 1035

[32] Fisk Z, Ott H R, Barzykina V and Gor'kov L P 2002 *Physica B* **312–313** 808

[33] Stankiewicz J, Sesé J, Balakrishnan G and Fisk Z 2014 *Phys. Rev. B* **90** 155128

[34] Stankiewicz J, Rosa P F S, Schlottmann P and Fisk Z 2016 *Phys. Rev. B* **94** 125141

[35] The labels for the SrB_6 samples in this report do not necessarily correspond to the labels of samples in Ref. [34].

[36] Kent A, von Molnar S, Gider S and Awschalom D D 1994 *J. Appl. Phys.* **76** 6656

[37] Fisk Z *et al* 1991 *Phys. Rev. Lett.* **67** 3310

[38] Rosenberg H M 1963 *Low Temperature Solid State Physics. Some selected topics.* (Oxford University Press, New York)

[39] Ceperley D M and Alder B J 1980 *Phys. Rev. Lett.* **45** 566; Alder B J, Ceperley D M and Pollock E L 1982 *Int. J. Quant. Chem.* **22** S16 49

[40] Ortiz G, Harris M and Ballone P 1999 *Phys. Rev. Lett.* **82** 5317