Complete Ca/Cu Cycle for H₂ production via CH₄ sorption enhanced reforming in a Lab-Scale Fixed Bed Reactor.

Díez-Martín, L.¹; López, J.M.¹; Fernández, J.R.² Martínez, I.¹; Grasa, G.^{1}; Murillo, R.¹*

¹Instituto de Carboquímica, CSIC, Miguel Luesma Castán 4, 50018-Zaragoza, Spain

² Instituto Nacional del Carbón, INCAR-CSIC, Francisco Pintado Fe, 26, 33011, Oviedo, Spain

Keywords: pressurized H₂ production, CO₂ capture, Ca/Cu cycle, fixed bed reactor, CH₄ sorption enhanced reforming

*Corresponding author email address: gga@icb.csic.es

Abstract

The three main reaction stages of a H₂ production process based on the combination of the CaO/CaCO₃ and Cu/CuO loops have been experimentally studied in a lab scale fixed bed reactor. The solid bed contained the three functional materials required to run the process, namely a commercial Ni-based catalyst, a CaO-Ca₁₂Al₁₄O₃₃ CO₂ sorbent and a CuO-Al₂O₃ material in a proportion that resulted in a bed with 43.3 % wt. CuO, 25.6 % wt. CaO and 1.7 % wt. Ni. The system was able to convert 13.5 kg CH₄ h⁻¹ kg Ni⁻¹, at 675 °C producing a gas stream with a 93.5 % vol. H₂ at 10 bar. The Cu-based material presented high oxidation kinetics, being totally converted in a narrow reaction front with a highly diluted air stream at 10 bar. The Cu-based material presented also fast reduction kinetics and it was completely converted with a fuel gas with typical composition of a SMR stage at high temperature. A Cu/Ca molar ratio of 2 allowed for calcination efficiencies over 85 % molar basis at the CO and H₂ break-through, and 95 % of the CO₂ from CaCO₃ exited the reactor at CH₄ break-through. The experimental results have been validated with a pseudo homogeneous reactor model for the three reaction stages that

was able to predict product gas compositions, bed breakthrough, and temperature profiles along
bed.

1. Introduction

In the Paris Agreement that aimed at stabilizing the CO₂ concentration in the atmosphere at a level which could limit the increase in global temperature at around 1.5 °C, Carbon capture and storage (CCS) remained as a promising alternative for drastically reducing CO₂ emissions from industries powered by fossil fuels or biomass. Pre-combustion CO₂ capture systems have a crucial role in achieving large CO₂ emission reduction in energy intensive industries since around 90% of the hydrogen produced worldwide is used as a raw material in the ammonia, methanol and oil refining industries [1]. Moreover, it is expected that the worldwide hydrogen production will progressively increase in the coming decades as a result of the growing demand from petroleum refineries and chemical industries, but also due to the role of hydrogen as a clean source of energy in a near future [2].

The dominant technology for hydrogen production at large scale is the steam methane reforming (SMR) [1]. This technology is based on the endothermic steam methane reforming reaction (Eq.(1)) that typically occurs in the presence of a Ni-based catalyst inside the tubes of a fired tubular reformer (FTR). Such reaction occurs at a very high temperature (i.e. 800-920°C) and very high pressures (i.e. 20-35 bar) to overcome the thermodynamic limits of such process, and the energy needed for carrying out such reaction is typically supplied by burning additional natural gas with air, which leads to CO₂ emissions with the flue gas produced [3]. The syngas produced in the FTR contains CO₂, CO, H₂ and unconverted CH₄ and it is further processed into a two-stage catalytic water gas shift (WGS) process in order to reduce the CO content down to 3%vol. according to reaction (2). A last purification stage is required in order to remove the impurities contained in the syngas (i.e. CO₂ and CO) and so produce the final H₂ product. Despite being the most efficient and economic process for hydrogen

production at large scale from natural gas and light hydrocarbons, this technology shows important drawbacks linked to the stringent conditions needed in the FTR, the need of a large number of catalytic steps and the large amount of energy required for driving the endothermic reforming process. Therefore, there is an intense research and development effort in developing new chemical processes for large scale H₂ production from fossil fuels joined with CO₂ capture systems in order to reduce the cost and the energy penalty associated to the commercial technology.

(1)

(2)

In this context, the Ca/Cu looping process was proposed as a novel intensified process capable of producing a highly concentrated pressurized H₂ stream with inherent CO₂ capture via sorption enhanced steam methane reforming (SER) based on the CaO/CaCO₃ loop [4, 5] In this process, a second Cu/CuO chemical loop is coupled so that the exothermic reduction of CuO with H₂, CO or CH₄ provides the energy required for the calcination of CaCO₃ [4]. In this way, the coupling of both endothermic and exothermic reactions in one single stage allows for a tighter integration as the heat is directly transferred within the solid bed without the need for intermediate heat exchange devices. The basic Ca/Cu looping process consists of a sequence of three main reaction steps, which are adiabatically carried out in fixed-bed reactors operating in parallel. In the first stage, an enriched stream of H₂ is produced by the SER of CH₄ in the presence of a reforming catalyst, a CaO-based sorbent and a Cu-based solid. This process stage has been designed to take place at 600-750°C, steam-to-carbon molar ratios (S/C) between 2.5 and 5, and pressures between 10 and 35 bar in order to achieve high H₂ production yields with high CO₂ capture efficiencies [5-7]. In the next step, the Cu-

1 based material is oxidized with diluted air at a high pressure. Low oxygen content in the
2 feed moderates the maximum bed temperature reached during the oxidation of Cu to
3 CuO, thereby avoiding the prompt decomposition of CaCO_3 by partial calcination [8].
4
5 In the following reaction stage, the calcination of the CaCO_3 formed during the SER is
6
7 accomplished by means of the simultaneous reduction of CuO with a gaseous fuel at
8
9 atmospheric pressure. A suitable CuO/ CaCO_3 molar ratio in bed composition has to be
10
11 selected to ensure that the heat released during CuO reduction is sufficient to
12
13 completely decompose the CaCO_3 without any external energy supply [9].
14
15
16
17
18
19

20 Due to the inherent characteristics of the Ca/Cu looping process, it can be fully
21
22 integrated as a standalone hydrogen production plant [10, 11] and/or as a CO_2 capture
23
24 route in power production process [12-14]. Hydrogen production efficiencies as high as
25
26 77 % (accounting also for electric consumption) with CO_2 capture efficiencies of about
27
28 95% have been demonstrated in the literature for hydrogen production standalone plants
29
30 based on the Ca/Cu looping process [10, 15], which are noticeably better than the
31
32 performance of the well-established SMR technology. Moreover, promising
33
34 applications of such Ca/Cu looping process into different industrial sectors have been
35
36 recently assessed in the literature. Martinez et al. [16] demonstrated that the application
37
38 of the Ca/Cu looping process into a state-of-the-art ammonia production plant allows
39
40 reducing the specific primary energy consumption by 14 % with respect to the
41
42 commercial process and simplifies noticeably the ammonia synthesis loop.
43
44 Alternatively, the Ca/Cu looping process can be also considered as possible
45
46 decarbonisation route of the flue gas coming from a blast furnace in a steel mill, which
47
48 will allow reducing the CO_2 emissions in the steelworks as well as producing electricity
49
50 to partly fulfill the electric consumption of the steel mill processes [17] Regarding the
51
52 operation and reactor's design, dynamic reactor models have been developed to study
53
54
55
56
57
58
59
60
61
62
63
64
65

1 the transient behavior of the different stages of this process in a fixed bed reactor [9, 15,
2 18, 19], which have been useful to identify those process design and operation strategies
3 that maximize the efficiency of the Ca/Cu looping process [15, 20]. In a recent FP7
4 project, ASCENT [21], the viability of the critical reduction/calcination stage of the
5 Ca/Cu process has been demonstrated at a laboratory scale under pseudo-adiabatic
6 conditions [19]. In a subsequent study, the effect of using different reducing gases in
7 such reduction/calcination stage was also successfully demonstrated [22]. Moreover, the
8 joint performance of a CaO-sorbent and a Ni-based catalyst under relevant conditions
9 for the H₂ production stage of the Ca/Cu looping process [23] has been also studied in
10 the framework of the aforementioned EU project, which has served to define the
11 operation limits of such materials in this process stage.
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26

27 Concerning the three functional materials required in the Ca/Cu looping process (i.e. the
28 Ca-based CO₂ sorbent, the Cu-based material and the reforming catalyst), noticeably
29 progress has been made in the development of high-performance materials with direct
30 application to the Ca/Cu looping process in the recent years. Regarding the Ca-based
31 sorbent, high CO₂ uptake and high mechanical and chemical stability along numerous
32 carbonation/calcination cycles are the desirable properties of this material for this
33 process. Synthetic CaO-based sorbents with stable CO₂ sorption capacity of around 30
34 % wt. along up to 50 cycles have been obtained through different synthesis routes based
35 on mechanical mixing and co-precipitation among others [24-28]. Cu-based oxygen
36 carriers with sufficient active content (Cu loads over 60 % wt.) have been also
37 synthesized [29, 30], which have demonstrated to be resistant to agglomeration and
38 deactivation in the long term. Some recent works are oriented to the development of
39 composite materials containing CaO and CuO [31-35] and/or CaO and Ni acting as
40 reforming catalyst [36, 37] that have been tested in TGA and fixed bed reactors. In
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1 general, these materials have shown reasonable solid conversions for the operating
2 conditions of the Ca/Cu looping process. However, their stability along multiple cycles
3
4 needs still to be further demonstrated to be suitable and advantageous with respect to
5
6 individual pellets for the Ca/Cu looping process.
7
8
9

10 In the present work, the performance of consecutive cycles of the three main reaction
11 Ca/Cu looping stages (i.e. SER, Cu oxidation and calcination/reduction) has been
12
13 experimentally demonstrated in a lab-scale fixed bed reactor under relevant conditions
14
15 for this process at a larger scale. As reviewed in the previous paragraphs, the H₂
16
17 production, Cu oxidation and reduction/calcination stages of the Ca/Cu looping process
18
19 have been individually demonstrated in lab-scale fixed bed reactors in the presence of
20
21 the functional material involved in each particular case (i.e. the CO₂ sorbent and
22
23 reforming catalyst for the H₂ production stage or the CaO- and CuO based materials for
24
25 the reduction/calcination one). However, to the authors' knowledge, consecutive cycles
26
27 of the different Ca/Cu looping process stages have not been carried out in a fixed bed
28
29 reactor at conditions relevant to the process. Moreover, in the experiments carried out in
30
31 this work, the three functional materials needed for this process are present in the solid
32
33 bed, which will allow assessing any interaction between them through each reacting
34
35 stage under realistic conditions. Operation conditions chosen for the process stages are
36
37 representative for the scaling up of the process in terms of pressure, gas spatial
38
39 velocities and gas composition. Moreover, the evolution of product gas composition
40
41 with time, as well as the temperature profiles within bed along each reaction stage will
42
43 be registered, which will be useful for validating the profiles predicted by a pseudo
44
45 homogeneous reactor model developed by some authors of this work [8, 9, 38].
46
47
48
49
50
51
52
53
54
55
56
57

58 **2. Experimental section**

59 Fixed bed reactor

60
61
62
63
64
65

1 The core of the experimental rig consists of a tubular stainless steel fixed bed reactor
2 with an internal diameter of 18.0 mm, which is externally heated by an electric heating
3 wire wrapping the reactor (the power of the heating wire is 1.25 kW, and it has a total
4 length of 5m). Aiming to operate the reactor close to adiabatic conditions, an external
5 layer of insulation (quartz wool) covers the reactor and heating wire. A series of 15
6 thermocouples are placed along the reactor to allow measuring and recording the
7 temperature profiles throughout the reactor's length in any of the reaction stages
8 occurring. The bed temperature control is performed setting as a control thermocouple
9 that placed in the bottom part of the bed (i.e. this is the last portion of bed facing the
10 reaction). The control system is also able to record the power input that receives the
11 reactor through the electric wire at any time. Up to 90 g. of bed material have been
12 introduced in the reactor during the experimental tests, which turns into a bed length of
13 approximately 0.2 m.

14 The flow rate of CH₄, N₂, CO₂, H₂, CO and O₂ in the feed gas is controlled by means of
15 the corresponding gas mass flow controllers and it is preheated up to 400°C before
16 being introduced into the fixed bed. When needed depending on the process stage, water
17 is fed from a pressurized vessel through a mass flow controller, being mixed with the
18 rest of the gases before passing through the evaporator at 400 °C. Feed gas flows
19 downstream in the reactor and the product gas passes through a condenser to remove
20 moisture before the gas analyser. The reactor's system has an end valve that regulates
21 and controls the pressure in the system, allowing operating pressures in the reactor up to
22 10 bars. Finally, the dry gas composition is on line analysed with an extractive analyser
23 SICK GMS810 (IR-analysis and heat conductivity analysis) that takes aliquots of the
24 gas production stream. In this way, the concentration of H₂, CH₄, CO, CO₂ and O₂ are
25 determined and N₂ is used as an internal standard to quantify the total gas production

(i.e. a flow rate of 5 lN/h of N₂ is introduced with the feed gas during the experiments to calculate the product gas flow rate). Figure 1 shows a scheme of the experimental rig used in this work.

Figure 1. Scheme of the experimental fixed bed reactor used

In order to consider the heat losses to the environment of the experimental rig in the reactor model, the overall heat transfer coefficient has been evaluated. The solid bed has been heated up to 800 °C passing a flow of N₂. Once the solid bed is at that temperature, the set point of the bed was lowered to avoid any heating by the electrical wire. The evolution of temperature profile with time and the bed length served to determine the overall heat transfer coefficient as 9.5 W/m²K, considering a constant ambient temperature of 25 °C.

Materials description:

Three functional materials have been selected to carry out this study. A CaO-Ca₁₂Al₁₄O₃₃ sorbent prepared by mechanical mixing of CaO (from calcined natural

limestone) and calcium aluminate cement, followed by an agglomeration process and a later calcination stage at 900 °C has been chosen [23]. The aim of this final calcination stage is that the CaO reacts with the Al₂O₃ contained in the aluminate cement to form Ca₁₂Al₁₄O₃₃, which brings chemical and mechanical stability to the sorbent material [26, 39]. The material was prepared by mixing in a shear agglomerator a 10 % wt. calcium aluminate cement with CaO from calcined natural limestone, while drop wise addition of a 10 % wt. poly-ethylene glycol aqueous solution addition. The particle size cut of the agglomerates used in the experiments was 600-1000 µm. This material has been widely characterized in TGA [23], and a long term CO₂ carrying capacity of 0.2 g. CO₂/g. calcined sorbent has been determined under representative conditions for the Ca/Cu looping process. The evolution of its CO₂ carrying capacity with the number of carbonation/calcination cycles can be estimated from Eq.(3), with material deactivation constant k=0.5 and the residual carrying capacity at infinite number of cycles X_r=0.17. The reactivity of the material towards carbonation reaction has been assessed according to Eq. (4) where k_{carb} resulted to be 2160 h⁻¹ and the effect of operation pressure was accounted by the parameter q (equal to 0.4) [23]:

$$\frac{X_t - X_r}{X_r} = \frac{X_0 - X_r}{X_r} e^{-k t} \quad (3)$$

$$X_t = X_r + (X_0 - X_r) e^{-k t} \quad (4)$$

The catalyst is a commercial reforming catalyst supplied by the Johnson Matthey Company (HiFUEL® R110) in the framework of the ASCENT project [21]. It is a Ni-based catalyst supported on CaAl₂O₄ suitable for steam reforming of natural gas. This material was available in pellet form and it was crushed and sieved to produce a particle size cut of 600-1000 µm for the experimental tests. The Ni content in the material

1 ranged from 15.9 to 20 % wt., as determined by ICP elemental analysis within this
 2 study. According to a recent study carried out with this material [40], the HiFUEL
 3 catalyst has proved to maintain sufficient catalytic activity after multiple redox cycles.
 4
 5

6
 7 The Cu-based material used for the experiments has been synthesized by Johnson
 8 Matthey with an adequate proportion of Cu (i.e. 72 % wt. CuO on Al₂O₃) to sustain the
 9 energy balance required in the reduction/calcination stage of the Ca/Cu process [6, 10,
 10 15]. The material has been prepared by co-precipitation and it presents an stable oxygen
 11 transport capacity (OTC) of 0.149 mg. O/mg. oxidized material, as determined through
 12 more than 100 oxidation/reduction cycles in a TGA apparatus [30]. The material was
 13 pelletized and the final particle size was in a range 0.6-2 mm to form a homogeneous
 14 bed with the sorbent and catalyst. A detailed kinetic study has been also performed
 15 elsewhere to determine oxidation and reduction kinetics of the Cu-based material under
 16 suitable conditions for the process[41, 42]. It was determined that the evolution of
 17 material conversion with time can be successfully predicted by a shrinking core model
 18 under chemical reaction control and cylindrical geometry. The equation that governs the
 19 evolution of the particle conversion for this model is:
 20
 21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42

$$- \quad (5)$$

43 where $X_{\text{red, ox}}$ represents either the reduction or oxidation Cu or CuO conversion
 44 respectively, t the time and τ_i the time required to achieve complete conversion of the
 45 material when using the reacting gas i . This time depends on the reacting gas ($i=\text{O}_2, \text{H}_2,$
 46 CO, CH_4), and it can be determined as:
 47
 48
 49
 50
 51
 52

$$\text{---} \quad (6)$$

53 where L represents the particle or pellet radius (in m), ρ_b the molar density of CuO in
 54 the particle (in mol m⁻³), b the stoichiometric coefficient of the CuO reduction or
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65

oxidation reaction depending on the reaction evaluated, C_{gi} the reacting gas concentration for gas i (in mol m^{-3}), n is the reaction order for each gas and k_{si} the kinetic constant for the reaction with gas i . The reaction rate constant k_{si} follows an Arrhenius form, where the pre-exponential factor k_0 is in $\text{mol}^{1-n} \text{m}^{3n-2} \text{s}^{-1} \text{bar}^d$, and the activation energy (E_A is in kJ mol^{-1}). The kinetic parameters for the oxidation and reduction reactions of the CuO-based material have been included in Table 1. The kinetic parameters have been incorporated in the reactor model described later in this paper.

Table 1. Cu-based material oxidation and reduction kinetic parameters.

Reacting gas	O ₂	H ₂	CO	CH ₄
n	1	1	0.9	0.5
k₀ , $\text{mol}^{1-n} \text{cm}^{3n-2} \text{s}^{-1}$	42	35	32	5
E_A , kJ mol^{-1}	21.8±0.6	10±0.3	25±0.4	60±0.6
b	2	1	1	4
d	0.08			

Different amounts of the three materials described above (50 g. Cu-based material, 25 g. sorbent and 8 g. catalyst) has been mixed to produce a bed containing 43.3 % wt. CuO, 25.6 % wt. CaO and 1.7 % wt. Ni, being the rest of the bed inert for the reactions involved in the process (29.4 % wt., the Al₂O₃ from the Cu-based material, the Ca₁₂Al₁₄O₃₃ from the sorbent and the CaAl₂O₄ support from the catalyst). According to the typical SER and Ca/Cu processes nomenclature, this mixture corresponds to a sorbent-to-catalyst weight ratio (Z) of 3 and a Cu/active Ca molar ratio of 2, which has been calculated considering a CO₂ carrying capacity for the fresh sorbent of 0.4 g CO₂/g calcined sorbent. Based on the published work on modelling of the H₂ production stage via SER [38, 43], this would allow achieving SER equilibrium for a relatively wide range of operating pressures, CH₄ space velocities and steam-to-carbon (S/C) molar ratios. In a previous work [23], it was experimentally proved that for the

1 sorbent/catalyst system used in this work, SER equilibrium was reached for a bed
2 containing 1.7 % wt. Ni, at 10 bar and a CH₄ space velocity of 2.5 kg CH₄/h kg cat.
3
4 With respect to the Cu/Ca molar ratio, a value of 2 would allow fulfilling the calcination
5 of the CaCO₃ formed during the H₂ production stage with a reducing gas with a
6 composition 58 % vol. H₂, 29 % vol. CH₄ and 13 % vol. CO (free of N₂), which
7 corresponds to the typical syngas composition obtained in a subsequent CH₄
8 reforming/cooling step at high temperature and low S/C ratio as proposed in [15].
9
10
11
12
13
14
15
16
17
18
19

20 Experimental routine:

21
22
23 Up to 3 consecutive cycles consisting of the three main reaction stages of the Ca/Cu
24 cycle were performed in the experimental rig shown in Figure 1. Table 2 compiles the
25 experimental conditions of pressure, initial bed temperature and gas composition for the
26 stages tested. Before starting with the cycles, the materials were in-situ reduced and
27 calcined by bringing the bed up to 875 °C in 10 %vol. H₂ in N₂, ensuring in this way that
28 all the Cu and Ni in the bed were in the metallic form and that no CaCO₃ was present in
29 bed. The reduction and calcination period was extended until no consumption of H₂ and
30 CO₂ was observed in the online gas analyser.
31
32
33
34
35
36
37
38
39
40
41
42

43 In every cycle, before each reaction stage (i.e. SER, Cu oxidation and
44 reduction/calcination), it was introduced a period to accommodate bed temperature and
45 pressure to those needed in the subsequent reaction stage. In a large scale Ca/Cu looping
46 process, pressurization and depressurisation stages, as well as rinse stages for cleaning
47 up the solid bed from hydrogen before the oxidation stage, would be needed for
48 ensuring an adequate operation of the process. Moreover, in the Ca/Cu looping scheme
49 there are intermediate non-reactive stages needed for heating and cooling the solid bed
50 before the reduction/calcination and SER stages, respectively, which use some of the
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

process gas streams involved. However, in the lab-scale facility, the implementation of such intermediate stages is limited and it has been done through these accommodation stages. Operation conditions of these accommodation stages are also included in Table 2. Finally, it is important to highlight that it has been allowed the complete breakthrough of the gases at every reaction stage. This has been done in order to elucidate through the gas outlet composition the presence of any reaction when the solid bed has been fully converted. This is only relevant at lab scale since at a larger scale the transition between process stages in a Ca/Cu looping cycle would take place just before the beginning of the gas breakthrough. Figure 2 shows an example of product gas composition as measured by the online analyser for a complete cycle. The figure also shows the duration of the main reaction stages as well as the break-through periods and accommodation periods.

Table 2. Operation conditions for the different stages in the Ca/Cu cycle.

	Adaptation A	A: H ₂ production stage	Adaptation B	B: Oxidation stage	Adaptation C	C:Reduction/ calcination stage
P (bar)	1-10	10	10	10	10-1	1
T _{initial bed} (°C)	Up to 675	675	Up to 700	700	Up to 820	820
Gas comp. (% vol.)	10 H ₂ , 90 N ₂	23 CH ₄ , 72 H ₂ O and 5 N ₂	100 N ₂	5 O ₂ , 95 N ₂	40 CO ₂ , 60 N ₂	54 H ₂ , 27 CH ₄ , 12 CO, 7 N ₂
Gas spatial velocity (h ⁻¹)		7950		8188		4300

As appreciated in Figure 2, at the beginning of each cycle there is an accommodation stage, where the bed is heated up to 675 °C in a mixture of 10% vol. H₂ in N₂ to avoid any catalyst oxidation, and it is pressurized at 10 bar. Once the desired temperature and

pressure are reached, the gas composition is changed to a mixture of CH₄/steam with an S/C molar ratio of 3 and a total gas flow of 120 l_N/h, and the H₂ production stage begins. In a larger scale Ca/Cu process, this stage would end with the beginning of the breakthrough period, but in the cycles performed in the lab-scale rig the mixture CH₄/steam has been maintained beyond that moment to follow the breakthrough of the bed and to observe the product gas composition obtained once the sorbent is totally saturated and only the SMR of CH₄ is taking place. Once the product gas composition is stable under SMR conditions, the CH₄/steam flow is cut off and N₂ is introduced at 10 bar with the same total flow to sweep the bed. At the same time the bed is heated up to 700 °C, as this will be the initial bed temperature for the oxidation stage. When the bed is at such temperature, the inlet gas composition is set as 5 % vol. O₂ in N₂ with a total gas flow of 120 l_N/h and 10 bar. As mentioned before, the oxidation stage would finish just before the breakthrough, but in these experiments it has been extended to let the breakthrough evolve and stabilize the outlet gas composition to that of the feed gas. Finally, there is a third accommodation stage to increase the solid bed temperature up to 820 °C and to reduce the total operating pressure down to 1 bar. To avoid any prompt CaCO₃ decomposition during this accommodation stage, this stage has been performed with a gas composition of 40 % vol. CO₂ in N₂. Once the bed is at the proper temperature and pressure, the set point of the control system is set at 750 °C to avoid any heat input from the electric wire and the inlet gas composition has been set as 54 % vol. H₂, 27 % vol. CH₄, 12 % vol. CO, 7 % vol. N₂ with a total flow of 57.5 l_N/h. Once the reduction/calcination is finished, and the gas composition at reactor outlet is stabilized at that of the SMR feed gas, the Ca/Cu cycle is completed. For starting a new cycle, the temperature of the solid bed is increased in a flow of H₂/N₂ to prove that no

additional CO₂ emissions or H₂ consumption take place and so that the bed remains reduced and fully calcined for the following cycle.

Figure 2. Evolution of raw product gas with time for a complete Ca/Cu cycle under operation conditions of Table 2.

3. Reactor model description

A pseudo-homogeneous fixed-bed reactor model has been used to describe the performance of the reactor along the three reaction stages of the Ca/Cu looping process. This dynamic model is able to predict at every process stage the evolution of the product gas composition with time, as well as the evolution of the temperature profiles throughout the solid bed for a set of initial conditions. A multi-component system with overall mass and energy balances including pressure drop is considered in this model, adopting the following common assumptions: plug flow with mass and thermal dispersion in the axial direction, negligible radial temperature and radial concentration gradients, negligible inter-particle concentrations and temperature gradients at the scale of millimeters, ideal gas behavior, a constant bed void fraction, perfect mixing of the solids and a uniform particle size. A detailed description of the reactor model used can be found elsewhere [8, 9, 38]. It is important to highlight that the model has been validated against experimental data on SER [23], and simultaneous CuO reduction/calcination [19] in fixed beds.

An overview of the mass and energy balances is given in Table 3. Table 4 compiles the literature considered in the dynamic model for the calculation of axial dispersion, equilibrium conditions and reaction kinetics.

Table 3. General mass and energy balance equations

Component molar balances	
$\frac{dN_i}{dt} = \sum_j \nu_{ij} R_j - \sum_k F_{ik}$	(6)
Energy balance	
$\frac{dU}{dt} = \sum_j F_j h_j - \sum_k F_k h_k + \sum_j \dot{Q}_{j,w}$	(7)
Momentum balance, Ergun equation	
$\frac{dP}{dz} = -\frac{150(1-\epsilon)^2 \mu U}{\epsilon^3 d_p^2} - \frac{1.75(1-\epsilon) \rho U^2}{d_p}$	(8)

Table 4 Bibliography considered for the calculation of dispersion coefficients and reaction kinetics.

	References
Axial mass and heat dispersion	Edwards and Richardson [44], Vortmeyer and Berninger [45], Gunn [46]
CaCO ₃ /CaO/CO ₂ equilibrium	Baker [47]
Ca(OH) ₂ /CaO/H ₂ O equilibrium	Criado et al. [48]
Kinetics of SMR and WGS	Xu and Froment [49]
Kinetics of CH ₄ decomposition	Borghei et al. [50]
Kinetics of carbon gasification by CO ₂ and steam	Snoeck et al. [51]
Kinetics of carbonation of CaO	Rodriguez et al. [52]
Kinetics of calcination of CaCO ₃	Martínez et al. [53]
Kinetics of Cu-material oxidation and reduction reactions	Díez-Martín et al. [41, 42]

The wall-bed heat transfer coefficient (h_w) has been experimentally determined as described in the description of the rig. It has been determined as 9.5 W/m²K and allowed for an accurate fitting of the energy balance in the model. The kinetics of steam reforming and WGS reactions have been extensively studied in the literature [54,

55]. On the basis of previous works about SER [56-59], the kinetics reported by Xu and Froment [49, 60] were assumed in this work to model the H₂ production stage of the cycle. The model also incorporates these reactions to the calcination/reduction stage as steam is present due to the reduction of CuO with H₂ and/or methane. The presence of CaO in the bed should minimize the formation of carbon by methane decomposition [61]. However, particles of the Ni- and Cu-based oxygen carriers already reduced may catalyze this reaction to some degree. For this reason, the kinetic correlation calculated for a Ni-Cu/MgO catalyst by Borghei et al. [50] has been considered in the model. Moreover, carbon gasification may occur by the presence of CO₂ and steam [62]. The kinetics proposed by Snoeck et al. [51] for both gasification reactions have been also assumed. The bibliography considered for the calculation of dispersion coefficients and reaction kinetics is listed in Table 4.

The carbonation of CaO is described using the empirical equation obtained by Rodriguez et al. [63], which is consistent with earlier studies published on carbonation of CaO [64-66]. The effect of the operation at a high pressure on carbonation kinetics is also incorporated in the model through the q factor, as it is assumed in a recent work on SER in pressurized fixed beds [18]. The calcination of CaCO₃ is described using the shrinking core model (SCM) under chemical reaction control proposed by Martínez et al. [53]. For the kinetics of the Cu oxidation and CuO reduction, an SCM with cylindrical geometry recently published for the material involved in this work has been considered (See Table 1, [30, 42]). The amount of Ni present in bed is low (less than 2 % wt.), but its effect has been considered in the model formulation (SCM model with cylindrical geometry as for the Cu-based material). A factor (η) has been introduced in the model for the SMR reaction to tackle the mass transfer resistances at particle level, and also to describe the possible reduction of catalyst activity with respect to the

kinetics obtained by Xu and Froment [49], simplification that has been adopted by different authors in the literature [57, 66]. A value of η of 0.3 has been considered in this work for all the reactions involved in the SER stage (i.e. SMR, WGS and CaO carbonation reactions); a factor η of 0.8 has been considered for the Cu oxidation reaction, η of 0.7, 0.8 and 0.3 for the reduction of CuO with H₂, CO and CH₄ respectively.. The volume fraction of CO₂ in the equilibrium is estimated using the equation obtained by Baker [47]. The equations used to calculate the gas-solid reaction kinetics and the CaCO₃/CaO/CO₂; Ca(OH)₂/CaO/H₂O equilibriums are also listed in Table 4.

The mathematical model is mainly composed of partial differential equations, algebraic equations, and initial and boundary conditions. The partial differential equations for each gas component (i. e. CH₄, H₂O, H₂, CO, CO₂) were converted to a set of ordinary differential equations with initial conditions by discretizing the spatial derivative in axial direction (z) using finite differences both for the first and for the second order. For finite differences, the reactor length was divided into 50 sections with 51 nodes, which allows a reasonable speed calculation to be achieved together with good accuracy in the simulations. The initial and boundary conditions in the equations listed in Table 3 are as follows:

$$(9)$$

$$(10)$$

The system formed by the differential and algebraic equations was simultaneously solved in MATLAB using a MATLAB tool called “ode15s.m”, which is a function implemented to calculate initial value problems in stiff differential equations.

4. Experimental results

The selection of the experimental conditions for the different reaction stages of the Ca/Cu looping cycle was based on previous works on the modelling of the complete Ca/Cu cycle [8, 12, 19, 38, 67] and on the experimental work recently published on the different reaction stages in fixed bed reactor [19, 23]. The following paragraphs will be dedicated to analyse in detail the operation conditions and results obtained in the individual reaction stages under cyclic operation.

Stage A: Methane Sorption Enhanced Reforming Stage.

The main operation variables in this stage that influence the equilibrium gas composition are: operating pressure, temperature and the S/C ratio in the gas feed. Regarding the pressure, H₂ production through SER reactions is favoured at low pressures according to thermodynamics. However, when producing hydrogen at large scale, high pressures are preferred in order to reduce the installation cost and to avoid a subsequent hydrogen compression stage to be used in the chemical industry. Therefore, a trade-off between both facts may be reached. Secondly, temperatures above 750 °C would reduce CO₂ capture efficiency in this process stage, being the H₂ production negatively affected. Finally, concerning the S/C ratio, high values improve CH₄ conversion and H₂ yield, but increases the risk of sorbent hydration that could affect the mechanical stability of the material [10, 15]. A recent published paper by our group has focussed on studying experimentally the SER stage in a fixed bed reactor using the same sorbent and catalyst as in this work. The work analysed the effect of important operation variables as the CH₄ spatial velocity referred to the amount of catalyst in bed;

the sorbent-to-catalyst ratio (Z), the effect of the ageing of the catalyst on H_2 production and the effect that total operating pressure had on materials performance and H_2 yield [23]. The results showed that the system (sorbent/catalyst) was able to convert up to 2.5 kg CH_4/h kg_{cat} at an S/C of 3 and up to 10 bar producing a gas with 94.5 % vol. H_2 , 5.14 % vol. CH_4 , 0.23 % vol. CO and 0.13 % vol. CO_2 on dry basis and free of N_2 . On the other hand, these conditions of S/C and pressure were recently demonstrated by Fernández and Abanades [15] as those optimising the operation of an improved Ca/Cu looping scheme, which may reach H_2 production efficiencies and CO_2 capture rates noticeably higher as those achieved by commercial hydrogen production plants based on FTR. Therefore, these have been the selected conditions to operate the H_2 production stage in this work.

Before describing the results obtained along cycling, the possible effect of the presence of the Cu-based material in the performance of the SER stage is carefully analysed.

In principle, the presence of Cu in the reactor should not alter the thermodynamic SER equilibrium because, although Cu is a well known catalyst for the WGS reaction, it would have very low activity at the operation temperature for this process stage [68], remaining as an inert from the point of view of reactions. However, the presence of this Cu-based material in the solid bed reduces the amount of sorbent and catalyst materials that can be allocated in a given reactor volume, affecting in this way to the duration of the pre-breakthrough period, and so the duration of the stage. Figure 3 shows the evolution of the product gas composition with time at 10 bar, 650°C, with an S/C of 3.2 and a CH_4 space velocity of 2.5 kg CH_4/h kg_{cat} for two different experiments: one with a solid bed containing the three functional materials (i.e. total solid bed weight: 83 g, consisting of 44% wt. of CuO, 15.3 % wt. of active CaO and 1.7% wt. of Ni, being the remaining fraction inert), and a second one including exclusively the sorbent and

1 catalyst mixture (i.e. . total solid bed weight: 27 g, consisting of 37 % wt. of active CaO
2 and 3 % wt. Ni, being the rest inert). This figure corroborates that in both cases the
3
4 system fulfils the SER equilibrium with a gas product that contains 93.5 % vol. H₂,
5
6 being the main difference between both tests the shorter duration of the pre-
7
8 breakthrough for the experiment that contains the Cu-based material. This outcome is
9
10 due to the higher CH₄ flow (in l_N/h) introduced in the reactor for the experiment using
11
12 the three functional materials to maintain the CH₄ space velocity at 2.5 kg CH₄/h kg_{cat}
13
14 (i.e. the amount of reforming catalyst increases by 74% with respect to the experiment
15
16 with only CO₂ sorbent and reforming catalyst, which makes the CH₄ flow fed to the
17
18 reactor increase proportionally). Regarding the post-breakthrough period once the
19
20 sorbent is saturated and SMR equilibrium is reached, differences can be observed in the
21
22 gas concentrations at reactor outlet for both experiments. The H₂ and CO concentrations
23
24 exceed (around 3.5 % p.p. in the case of CO) that of the SMR thermodynamic
25
26 predictions in the experiment done with the three functional materials, while CH₄
27
28 concentration is slightly lower. This might indicate that once the sorbent is saturated,
29
30 the presence of Cu enhances the thermal decomposition of CH₄ into C and H₂ [69], and
31
32 then the gasification of C may take place to form CO. These reactions were not
33
34 significant while there is active CaO in bed since the product gas composition obtained
35
36 during the pre-breakthrough period of both tests (with and without Cu) was very
37
38 similar. However, in the initial part of the solid bed where there is no active CaO and
39
40 exclusively SMR occurs, carbon formation could occur according to this mechanism,
41
42 resulting in higher CO₂ emissions than expected during the subsequent oxidation stage
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Figure 3. Evolution of product gas composition with time a) H₂ and CO₂; b) CO and CH₄ (CuO-CaO-cat bed: total weight 83 g with a bed composition of 44% wt. of CuO, about 15.3 % wt. active CaO and 1.7% wt. Ni; CaO-cat bed total bed weight of 27 g with a bed composition that corresponds to 37 % wt. active CaO, 3 % wt. Ni).

Regarding the experimental results obtained with the three functional materials, Figure 4 a) shows the evolution of product gas composition with time (H₂, CO₂, CO and CH₄ included, on dry basis and free of N₂). As previously demonstrated by Grasa et al. 2017 [23], the system is able to fulfil SER equilibrium conditions at 2.5 kg CH₄/h kg_{cat}, at 675 °C, 10 bar and an S/C of 3, which corresponds to a linear gas velocity of 0.045 m/s. Figure 4c) shows the evolution of temperature profile measured along the bed with time. At the beginning of the H₂ production stage, the mixture CH₄/steam reaches the bed surface and the SMR and WGS reactions take place producing CO, H₂ and CO₂ that will react with the active CaO present in the bed. The global enthalpy of these reactions is slightly exothermic (-13.7 kJ/mol) under the conditions tested, and this results into an increment of the bed temperature in the reaction front, whose evolution within the solid bed can be followed by the thermocouples immersed throughout the solid bed. As the active CaO in the solid bed is progressively converted, the initial part of the bed cools down as a consequence of the SMR reaction as can be appreciated in the set of temperature values registered by the first thermocouple placed at 2.5 cm from the upper part of the reactor in Figure 4c). The CO₂ formed is mostly captured in the carbonation

front that rises the temperature of the following slice in bed. The heat generated during the carbonation of the sorbent is exchanged with the bed downstream. Given the fact that the rig is not completely adiabatic, the heat losses in the reactor avoids the formation of the heat plateau that is widely described in published papers on SER stage reactor modelling [6, 18, 20]. The maximum temperature registered during SER stage was 720 °C, recorded in the thermocouple located in the middle of the bed length. At this temperature conditions the carbonation reaction rate is still fast, and product gas composition is not noticeably affected by the temperature profile in bed during the pre-breakthrough, being barely constant at reactor outlet at 93.5 % vol. H₂, 5.83 % vol. CH₄, 0.33 % vol. CO and 0.34 % vol. CO₂ (see Figure 4 a)). The arrival of the carbonation front to the end of the solid bed implies that the active CaO is exhausted, which makes the product gas composition evolve towards a composition corresponding to SMR (i.e. 66.5 % vol. H₂, 16.88 % vol. CH₄, 10.92 % vol. CO₂ and 5.69 % vol. CO). According to the mass balances solved to the system, the H₂ yield was 2.9 mol H₂/mol CH₄ introduced and the sorbent was able to capture 0.39 g CO₂/g calcined material.

The experimental data have been fitted with the pseudo-homogeneous reactor model described above. Model predictions have been plotted as continuous lines with the experimental data shown in Figure 4. As appreciated, the model predicts fairly well the evolution of product gas composition with time, the evolution of temperature profiles along the bed, as well as the maximum temperature achieved in bed.

The figures on the right (4 b and d) show the experimental results obtained for three SER stages carried out in the three consecutive complete Ca/Cu cycles. The figures show the evolution of the gas product composition and the temperature profiles along the bed with time. As can be noticed, the results obtained in the different cycles are highly reproducible. Figure 4 b) shows that SER equilibrium is reached in the 3 cycles,

but the pre-breakthrough length is slightly shortened as the number of cycles increases due to a slight decrease in sorbent CO_2 carrying capacity. As demonstrated in [23], the sorbent CO_2 carrying capacity did not remain stable after 3 calcination/carbonation cycles and tended to 0.2 g CO_2/g calcined sorbent after a long number of carbonation/calcination cycles. According to the mass balances performed to the data registered in each cycle, the sorbent CO_2 carrying capacity was estimated at 0.39, 0.37 and 0.35 g CO_2/g calcined sorbent in the three consecutive cycles, respectively. This behaviour is consistent with the temperature profiles registered in cycles 2 and 3 (see Figure 4 c), where it can be appreciated that the slightly lower CO_2 carrying capacity of the material in each cycle results in a lower temperature reached along the bed since the extension of the carbonation reaction becomes less. Despite of these changes, it can be noticed that the evolution of the reaction front along the bed remains unchanged along the cycles, which evidences the reproducibility of the process.

Figure 4. H₂ production stage. a) Evolution of product gas composition with time for the first Ca/Cu cycle. b) Evolution of H₂ and CO₂ in the gas product with time for the three consecutive cycles. c) Evolution of the temperature profiles with bed length and time for the first Ca/Cu cycle. d) Experimental evolution of the temperature profiles with bed length and time for the three consecutive Ca/Cu cycles. Experimental conditions reported in Table 1.

Stage B: Oxidation stage B.

Cu oxidation is a highly exothermic reaction ($\Delta H_{298\text{ K}} = -156\text{ kJ/mol Cu}$), and therefore a careful control of the temperature is required to avoid hot spots in the solid bed that could damage the materials' mechanical and chemical stability and also reduce the CO₂ capture efficiency of the Ca/Cu looping process [70]. In principle, to moderate the temperature in the reaction front the tools available are: the gas inlet temperature, the O₂ partial pressure in the feed gas and the Cu content in the solid bed [6, 71]. Moreover, the calcination reaction can be limited by increasing the operating pressure [72]. According to the definition of the Ca/Cu looping process, the Cu content in the solid bed is fixed by the heat balance of the calcination/reduction process stage, and it cannot be therefore arbitrarily selected. In this way, the Ca/Cu looping scheme has been typically designed with a N₂ recycle from the oxidation stage outlet to dilute the O₂ content at the reactor's inlet and so limit the maximum temperature achieved in the reactor [6, 70, 71]. For the Cu oxidation stage conditions in this work, 5 % vol. of O₂ in

the gas feed to this stage has been chosen for the total operating pressure of 10 bar, which is slightly higher than the values typically proposed in the literature [6, 10, 15]. Considering that the thermal losses to the environment of the experimental rig in this work are not negligible (and the reactor cannot be therefore considered as adiabatic), a slightly higher O₂ concentration has been finally chosen. A total flow of 114 l_N/h was used in this stage, which corresponded to a gas linear velocity of 0.045 m/s at 725 °C.

Before starting the oxidation stage, the bed is heated up to 725 °C, and then the control temperature of the electric wire is set at 700 °C to avoid introducing electrical power to the reactor while the reacting gas is introduced in the bed. Figure 5 a) shows the evolution of product gas composition with time. As noticed, all the O₂ introduced in the feed gas is reacting, as no O₂ is measured in the gas product. There is a CO₂ leak that is slightly above the CO₂ predicted by calcination equilibrium [47], which corresponds to 0.85 % vol. at the highest temperature measured (i.e. 770 °C) and 10 bar. This CO₂ release can be related with the carbon deposition occurring at the end of the SER stage when no active CaO was present, as explained previously.

Figure 5 c) shows the evolution of the solid bed temperature with time. The evolution of the reaction front along the solid bed can be followed by the displacement of the maximum bed temperature along the bed length in this figure. The space velocity of these tests is below that proposed in the literature for the Ca/Cu looping process at a higher scale [8, 15, 70], and therefore there is no uncoupling between the reaction and the heat exchange fronts in this step, which contributes also (together with the heat losses) to the fact that no temperature plateau is observed. Regarding the CO₂ concentration, it can be noticed that it decreases slightly before the breakthrough arrives to the end of the reactor. As appreciated in Figure 5 (c) the temperature of the last portion of bed decreases with respect to the maximum reached in the bed, which makes

that the CO_2 released in the reaction front is reacting again with the available CaO to form CaCO_3 . Figures 5 a and c) include also the output results from the reactor model that incorporates the oxidation kinetics of the material (and calcination kinetics), and it can be noticed that the temperature profiles are fairly well predicted. Figures 5 b and c) show the results obtained for three consecutive cycles, and it can be seen that both the breakthrough and the evolution of temperature profiles in bed are highly reproducible. A maximum ΔT of 50 °C was observed in the thermocouple in the middle part of the bed.

Figure 5. Oxidation stage. a) Evolution of O_2 and CO_2 in the gas product with time for the first Ca/Cu cycle. Dotted lines correspond to experimental data, solid lines to model predictions. b) Evolution of O_2 and CO_2 in the gas product with time for the three consecutive cycles. c) Evolution of the temperature profiles with bed length and time for three consecutive cycles.

the first Ca/Cu cycle. d) Experimental evolution of the temperature profiles with bed length and time for the three consecutive Ca/Cu cycles. Experimental conditions reported in Table 1.

Given the fact that the stage duration is longer than it would be at conditions of higher space velocity in the oxidation stage of the Ca/Cu looping cycle, there is a relevant fraction of CaCO_3 calcined during this oxidation stage in the experimental rig (i.e. 9%wt. according to mass balance considering the equilibrium for the CaO/CaCO_3 at process stage conditions). In order not to reduce the moles of CaCO_3 to be calcined in stage C and to avoid any further CaCO_3 decomposition, the conditioning step to stage C has been performed in a concentrated CO_2 atmosphere. In this way, a re-carbonation of the CaO present in bed takes place, and the total amount of moles of CaCO_3 at the end of the conditioning step was 0.24, 0.24 and 0.23 in the three consecutive cycles, which correspond to complete conversion of the active CaO present in the solid bed.

Stage C: Reduction/calcination stage.

In the last reacting stage of the Ca/Cu looping process, the calcination of the CaCO_3 present in bed takes place thanks to the exothermic reduction of the CuO formed during the oxidation stage. This stage represents the core of the process since regenerates the sorbent and allows the system to face a new H_2 production cycle. It is operated at atmospheric pressure to reduce the temperature required for the calcination of the CaCO_3 . The reducing gas stream used for the experiments contains 58 % vol. H_2 , 29 % vol. CH_4 and 13 % vol. CO (free of N_2). This composition has been taken from [15], and it corresponds to a gas stream generated from the mixture of a syngas produced by SMR at high temperature in a subsequent cooling/reforming stage and the off gas from the PSA that purifies the H_2 produced in the SER stage of the process. A total gas flow of 55.76 $\text{l}_\text{N}/\text{h}$ was introduced in the reactor, which corresponds to a linear gas velocity of

0.24 m/s at 800 °C. Before starting this stage, the solid bed was heated up to 825 °C in a 40 % vol. CO₂ as explained before. When the bed was at temperature, the set point of the control of temperature of the bed was lowered to 760°C to avoid any external power input to the reactor. At the same moment the reducing gas was introduced in the rig.

Figures 6 a) and c) show the evolution of the exit gas composition and the temperature profile along the bed with time, respectively. As it can be observed, as soon as the reacting gas reaches the bed surface the reduction of CuO takes place, the reducing gases are converted in a narrow reaction front and the solid bed temperature increases, favoring in this way the calcination of the CaCO₃. As a consequence of these reduction reactions, the composition of the gas exiting the reactor is a mixture steam/CO₂ and only CO₂ is analyzed since the steam has been condensed before the online gas analyzer. It can be also appreciated that both reaction and heat exchange fronts reach the end of the reactor at the same time (i.e. at around 5 min in Figure 6 (a) for the reaction front and in Figure 6 (c) for the heat exchange one), which is in line with the model predictions of this stage [9] The CO₂ concentration rapidly increases from the moment when reducing gases are introduced and it reaches maximum concentration when the reaction fronts reach the middle of the bed. This CO₂ concentration would correspond to 50 % vol. of the outlet gas stream. The maximum bed temperature registered is 852 °C that has been measured by the thermocouple in the middle part of the bed.

When all the oxygen in the solid bed is exhausted (i.e. all the CuO has been reduced to Cu), the reducing gases exit the bed without being converted. It is observed that the breakthrough of H₂ and CO evolve similarly, but the slope of the breakthrough of the CH₄ is much slower. In addition CO and H₂ concentrations show a maximum before being stabilized to the inlet concentration of both gases, this might indicate that once the oxygen in bed is depleted the CH₄ could be thermally decomposed to C and H₂, and the

C would react via WGS with the remaining steam formed during H_2 oxidation to produce CO. A similar reaction has been observed during the post-breakthrough of the H_2 production stage, and this seems to corroborate that the presence of metallic Cu would enhance CH_4 thermal decomposition.

Figure 6. Calcination/reduction stage. a) Evolution of gas composition at the reactor exit with time for the first Ca/Cu cycle. b) Evolution of gas composition at the reactor exit with time for the three consecutive cycles. c) Experimental evolution of the temperature profiles with bed length and time for the first Ca/Cu cycle. d) Evolution of the temperature profiles with bed length and time for the three consecutive Ca/Cu cycles. Experimental conditions reported in Table 1.

Figures 6 b and d) show the good reproducibility that presents the evolution of gas concentration and temperature profiles with time along consecutive cycles. The breakthrough of the gases is almost identical, the CH_4 breakthrough is slower in every case and the CO and H_2 concentration measured exceeds the gases introduced in the

system indicating the possible thermal decomposition of CH_4 and later gasification of C.

The evolution of the temperature profile along the solid bed for the three consecutive Ca/Cu cycles remains practically unchanged, which shows the good reproducibility and stability of the solid behavior along cycles. According to the mass balances to the process stage, all the CuO and NiO present in the solid bed at the beginning of this calcination/reduction stage have been reduced to Cu and Ni, respectively, and calcination efficiencies of over 85 % (molar basis) have been obtained at the CO and H_2 breakthrough, and 95 % of the CO_2 has exited the reactor when the CH_4 breaks-through.

On the whole for the cycles performed, the sorbent was able to capture 0.35 g CO_2 /g calcined sorbent during the H_2 production stage according to the mass balances calculated to the process stages, and all the Cu and Ni present in the reactor were both oxidized in stage B of the process and reduced in stage C of the process.

The bed material has been discharged after the experimental campaign performed and characterized via XRD to determine any possible interaction between active phases that could affect the materials along cycling, as well as to observe the mechanical stability of them. Materials were separated by sieving and using a magnet due to the magnetic properties of Ni metal. XRD analysis of particle size cut of 1-2 mm (figure 7 a) showed reduced Cu as the only phase present in this fraction and containing 85 %wt. of the original mass of Cu material. Fraction with a particle size cut of 0.6-1 mm (figure 7 b) showed the characteristic phases of the CO_2 sorbent material (i.e. calcium carbonate, calcium oxide and mayenite) with a slightly contamination of reduced Cu. The fraction of Cu-based material in the cut 0.6-2 mm represents more than 97 % wt. of the Cu introduced in the bed. 70 %wt. of the original sorbent material was recovered in the particle size cut 0.6-1 whilst the remaining 30 %wt. was recovered in the fraction with a particle size cut of 0.2-0.6 mm, pointing out a good mechanical stability. The fraction

obtained by magnetic separation (figure 7 c) was characterized by the presence of typical phases related with the Ni catalyst (i.e. reduced Ni, Al_2O_3 and CaAl_4O_7). It is worth to highlight that no mixed phases from the different active materials were detected showing the absence of any chemical interaction between the different materials along cycling.

Figure 7. XRD diffractograms of used materials. a) Cu-based material, b) Ca-based sorbent and c) Ni-based catalyst.

Conclusions

The three main reaction stages of a complete Ca/Cu cycle have been successfully performed in a fixed bed reactor at lab scale in consecutive cycles. Promising results have been obtained for the mixture of three functional materials: commercial Ni-based catalyst, $\text{CaO-Ca}_{12}\text{Al}_{14}\text{O}_{33}$ CO_2 sorbent and $\text{CuO-Al}_2\text{O}_3$ material. The presence of Cu in the reactor has been proved to be an inert during the H_2 production stage, and a bed

1 containing 43.3 % wt. CuO, 25.6 % wt. CaO and 1.7 % wt. Ni, being the rest inert
2 materials for the reactions involved, was able to convert 13.5 kg CH₄ h⁻¹ kg Ni⁻¹ at 675
3 °C producing a gas stream with a 93.5 % vol. H₂ at 10 bar. The Cu-based material
4 presented fast oxidation kinetics, being totally converted in a narrow reaction front with
5 a highly diluted air stream at 10 bar. The CO₂ leakage during the oxidation stage is
6 slightly over the predicted equilibrium for the CaO/CaCO₃ system at the operation
7 conditions tested, due to the deposition of carbon upstream the breakthrough of the H₂
8 production stage. The Cu-based material presented fast reduction kinetics and it was
9 completely converted with a fuel gas with typical composition of a SMR stage at high
10 temperature. A Cu/Ca molar ratio of 2 was sufficient to allow for calcination
11 efficiencies over 85 % molar basis at the CO and H₂ break-through, and 95 % at CH₄ break-
12 through. The results obtained along cycles were highly reproducible indicating the
13 stability of the materials tested along cycling. Only a slightly decrease of the CO₂
14 sorbent carrying capacity was observed, as it was expected according to previous results
15 on materials testing. No mixed phases from the different active materials were detected,
16 indicating the absence of any chemical interaction between the different materials along
17 cycling. The reactor model was able to predict the gas composition, breakthrough and
18 temperature profiles in the solid bed for all the process reaction stages.

19 **Acknowledgments**

20 This work acknowledges the support by European Union Seventh Frame Programme
21 FP7 under grant agreement n° 608512 (ASCENT Project). Laura Díez acknowledges
22 the FPI fellowship (ENE 2012-37936-CO2-01, BES-2013-064616 financed by

MICINN). The authors want also to thank the support from the Regional Aragon Government (DGA) under the research groups support program.

Nomenclature

C_i	concentration of component i in the reactor, kmol/m ³
$C_{i,in}$	concentration of component i in the feed, kmol/m ³
$C_{i,0}$	initial concentration of component i, kmol/m ³
C_{pg}	specific heat capacity of the gas, kJ/kg K
C_{ps}	specific heat capacity of the solid, kJ/kg K
D_{eff}	axial mass dispersion coefficient, m ² h ⁻¹
d_p	particle diameter, m
D_r	inner diameter of the reactor, m
h_{fs}	fluid-gas heat transfer coefficient, kJ/(h m ² K)
H_{ri}	heat of reaction, kJ/kmol
h_w	heat transfer coefficient through the reactor wall, kJ/(h m ² K)
k	sorbent deactivation parameter with number of calcination/carbonation cycles, dimensionless
k_{carb}	rate constant of CaO carbonation, h ⁻¹
k_g	thermal gas conductivity, kJ/(h m K)
k_j	rate constant of reaction j (j= I, II, III), kmol bar ^{0.5} /kg h
K_i	adsorption constant of component i, i=CO, H ₂ , CH ₄ bar ⁻¹ ; i=H ₂ O dimensionless
K_j	equilibrium constant of reaction j, j=I, II bar ² ; j=3 dimensionless
k_{fs}	fluid-gas mass transfer coefficient, m/h
L	reactor length, m
M_{CaO}	molecular weight of CaO, kg/kmol
M_g	molecular weight of the gas, kg/kmol
N	number of calcination/carbonation cycles
P	total pressure, bar

Pe_{az}	Peclet number, dimensionless
P_i	partial pressure of component i, bar
P_{in}	pressure at the reactor entrance, bar
Pr	Prandtl number, dimensionless
r_{carb}	rate of CaO carbonation, kmol/kg _{cat} h
Re	Reynolds number, dimensionless
r_i	rate of formation/consumption of component i, kmol/kg h
R	ideal gas constant, kJ/kmol K
R_j	rate of reaction j (j=I, II, III), kmol/kg h
Sc	Schmidt number, dimensionless
t	time, h
T	temperature, K
T_w	reactor wall temperature, K
T_{gin}	feed gas temperature, K
T_{in}	feed gas temperature, K
T_0	initial temperature of the solids in the reactor, K
T_{s0}	initial solid temperature, K
u	superficial velocity of gas, m/h
x_i	gas-phase mole fraction of component i, dimensionless
X_{carb}	fractional carbonation conversion of CaO, dimensionless
X_{max}	maximum fractional carbonation conversion of CaO, dimensionless
X_N	carbonation conversion at cycle N (g. CaCO ₃ /g. calcined sorbent)
$X_{red,ox}$	CuO reduction conversion, or Cu oxidation conversion respectively, dimensionless
X_r	carbonation conversion at infinite number of cycles (mol CaCO ₃ /mol CaO)
z	axial coordinate in bed, m
Greek letters	
ε	bed void fraction, dimensionless

Φ_{ij}	stoichiometric coefficient of component i, dimensionless
ρ_{CaO}	apparent density of CaO-based material, kg/m^3
ρ_{cat}	apparent density of reforming catalyst, kg/m^3
ρ_g	gas phase density, kg/m^3
ρ_s	apparent density of the two mixed solids in the reactor, kg/m^3
η	effectiveness factor, dimensionless
v_{CO_2}	gas-phase mole fraction of CO_2 , dimensionless
$v_{\text{CO}_2,\text{eq}}$	gas-phase equilibrium mole fraction of CO_2 , dimensionless
μ_g	viscosity of gas, bar h

References:

- [1] IEAGHG, 'Techno-economic evaluation of SMR based standalone (merchant) plant with CCS' 2017/02. February 2017, in.
- [2] Hydrogen and Fuel Cells, in: I. Publications (Ed.) Technology Roadmap, IEA, Paris, France, 2015.
- [3] J.R. Rostrup-Nielsen, J. Sehested, J.K. Norskov, Hydrogen and synthesis gas by steam and CO₂ reforming, *Adv. Catalysis*, 47 (2002) 65-139.
- [4] J.C. Abanades, R. Murillo, Method for recovering CO₂ by means of CaO and the exothermic reduction of a solid. PCT/ES2010/070585, in, 2009.
- [5] J.C. Abanades, R. Murillo, J.R. Fernández, G. Grasa, I. Martínez, New CO₂ capture process for hydrogen production combining Ca and Cu chemical loops., *Environ. Sci. Technol.*, 44 (2010) 6901-6904.
- [6] J.R. Fernández, J.C. Abanades, R. Murillo, G. Grasa, Conceptual design of a hydrogen production process from natural gas with CO₂ capture using a Ca-Cu chemical loop, *Int. J. Greenhouse Gas Control*, 6 (2012) 126-141.
- [7] M. Martini, Investigation of the process operability windows for Ca-Cu looping for hydrogen production with CO₂ capture, *Chem. Eng. J.*, 303 (2016) 73-88.
- [8] J.R. Fernández, J.C. Abanades, R. Murillo, Modelling of Cu oxidation in adiabatic fixed-bed reactor with N₂ recycling in a Ca/Cu chemical loop., *Chem. Eng. J.*, 232 (2013) 442-452.
- [9] J.M. Alarcón, J.R. Fernández, CaCO₃ calcination by the simultaneous reduction of CuO in a Ca/Cu chemical looping process, *Chem. Eng. Sci.*, 137 (2015) 254-267.
- [10] I. Martínez, M.C. Romano, J.R. Fernández, P. Chiesa, R. Murillo, J.C. Abanades, Process design of a hydrogen production plant from natural gas with CO₂ capture based on a novel Ca/Cu chemical loop, *Appl. Energy*, 114 (2014) 192-208.
- [11] J.R. Fernández, J.C. Abanades, Overview of the Ca-Cu looping process for hydrogen production and/or power generation. , *Current Opinion in Chemical Engineering.*, 17 (2017) 1-8.
- [12] I. Martinez, R. Murillo, G. Grasa, J.R. Fernández, J.C. Abanades, Design of a hydrogen production process for power generation based on a Ca-Cu chemical loop, *Energy Procedia*, 37 (2013) 626-634.
- [13] D.C. Ozcan, A. Macchi, D.Y. Lu, A.M. Kierzkowska, H. Ahn, C.R. Müller, S. Brandani, Ca-Cu looping process for CO₂ capture from a power plant and its comparison with Ca-looping, oxy-combustion and amine-based CO₂ capture processes., *Int. J. Greenhouse Gas Control*, 43 (2015) 198-212.
- [14] B. Duhoux, P. Mehrani, D.Y. Lu, R.T. Symonds, E.J. Anthony, A. Macchi, Combined Calcium Looping and Chemical Looping Combustion for Post-Combustion Carbon Dioxide Capture: Process Simulation and Sensitivity Analysis., *Energ. Tech.*, 4 (2016) 1-14.
- [15] J.R. Fernández, J.C. Abanades, Optimized design and operation strategy of a Ca-Cu chemical looping process for hydrogen production., *Chem. Eng. Sci.*, 166 (2017) 144-160.
- [16] I. Martínez, D. Armaroli, M. Gazzani, M.C. Romano, Integration of the Ca-Cu Process in Ammonia Production Plants, *Ind. Eng. Chem. Res.*, 56 (2017) 2526-2539.
- [17] J.R. Fernández, I. Martínez, J.C. Abanades, M.C. Romano, Conceptual design of a Ca-Cu chemical looping process for hydrogen production in integrated steelworks, *Int. J. Hydrogen Energy*, 42 (2017) 11023-11037.
- [18] M. Martini, A. van den Berg, F. Gallucci, M. van Sint Annaland, Investigation of the process operability windows for Ca-Cu looping for hydrogen production with CO₂ capture, *Chem. Eng. J.*, 303 (2016) 73-88.

- [19] J.R. Fernández, J.M. Alarcón, J.C. Abanades, Investigation of a Fixed-Bed Reactor for the Calcination of CaCO_3 by the Simultaneous Reduction of CuO with a Fuel Gas. , *Ind. Eng. Chem. Res.*, 55 (2016) 5128-5132.
- [20] M. Martini, I. Martínez, M.C. Romano, P. Chiesa, F. Gallucci, M. van Sint Annaland, Increasing the carbon capture efficiency of the Ca/Cu looping process for power production with advanced process schemes, *Chem. Eng. J.*, 328 (2017) 304-319.
- [21] <http://www.ascentproject.eu/>, in.
- [22] J.M. Alarcón, J.R. Fernández, J.C. Abanades, Study of a $\text{Cu}-\text{CuO}$ chemical loop for the calcination of CaCO_3 in a fixed bed reactor, *Chem. Eng. J.*, 325 (2017) 208-220.
- [23] G. Grasa, M.V. Navarro, J.M. López, L. Díez-Martín, J.R. Fernández, R. Murillo, Validation of the H_2 production stage via SER under relevant conditions for the Ca/Cu reforming process practical application, *Chem. Eng. J.*, 324 (2017) 266-278.
- [24] A.M. Kierzkowska, R. Pacciani, C.R. Müller, CaO -Based CO_2 Sorbents: From Fundamentals to the Development of New, Highly Effective Materials. , *ChemSusChem*, 6 (2013) 1130-1148.
- [25] M. Erans, V. Manovic, E.J. Anthony, Calcium looping sorbents for CO_2 capture, *Appl. Energy*, 180 (2016) 722-742.
- [26] V. Manovic, E.J. Anthony, The long-term behavior of CaO -based pellets supported by calcium aluminate cements in long series of CO_2 capture cycles, *Ind. Eng. Chem. Res.*, 48 (2009) 8906-8912.
- [27] C. Luo, Y. Zheng, C. Zheng, J. Yin, C. Qin, B. Feng, Manufacture of calcium-based sorbents for high temperature cyclic CO_2 capture via a sol-gel process., *Int. J. Greenhouse Gas Control*, 12 (2013) 193-199.
- [28] S.S. Kazi, A. Aranda, J. Meyer, J. Mastin, High performance CaO -based sorbents for pre- and post- combustion CO_2 capture at high temperature, *Energy Procedia*, 63 (2014) 2207-2215.
- [29] J. Adánez, A. Abad, F. García-Labiano, P. Gayán, L.F. de Diego, Progress in Chemical-Looping Combustion and Reforming technologies, *Prog. Energ. Combust.*, 38 (2012) 215-282.
- [30] L. Díez-Martín, G. Grasa, R. Murillo, A. Scullard, G. Williams, Development of suitable CuO -based materials supported on Al_2O_3 , MgAl_2O_4 and ZrO_2 for Ca/Cu H_2 production process, *Ind. Eng. Chem. Res.*, 57 (2018) 2890-2904.
- [31] V. Manovic, E.J. Anthony, Integration of Calcium and Chemical Looping Combustion using Composite CaO/CuO -Based Materials., *Environ. Sci. Technol.*, 45 (2011) 10750-10756.
- [32] A.M. Kierzkowska, C.R. Müller, Development of calcium-based, copper-functionalised CO_2 sorbents to integrate chemical looping combustion into calcium looping., *Energy Environ. Sci.*, 5 (2012) 6061-6065.
- [33] C. Qin, B. Feng, J. Yin, J. Ran, L. Zhang, V. Manovic, Matching of kinetics of CaCO_3 decomposition and CuO reduction with CH_4 in $\text{Ca}-\text{Cu}$ chemical looping., *Chem. Eng. Sci.*, 262 (2015) 665-675.
- [34] F.N. Ridha, D. Lu, A. Macchi, R.W. Hughes, Combined calcium looping and chemical looping combustion cycles with $\text{CaO}-\text{CuO}$ pellets in a fixed bed reactor. , *Fuel*, 153 (2015) 202-209.
- [35] S.S. Kazi, A. Aranda, L. di Felice, J. Meyer, R. Murillo, G. Grasa, Development of Cost Effective and High Performance Composite for CO_2 Capture in $\text{Ca}-\text{Cu}$ Looping Process, *Energy Procedia*, 114 (2017) 211-219.
- [36] C.S. Martavaltzi, A.A. Lemonidou, Hydrogen production via sorption enhanced reforming of methane: Development of a novel hybrid material—reforming catalyst and CO_2 sorbent, *Chem. Eng. Sci.*, 65 (2010) 4134-4140.
- [37] A.L. García-Lario, G. Grasa, R. Murillo, Performance of a combined CaO -based sorbent and catalyst on H_2 production, via sorption enhanced methane steam reforming, *Chem. Eng. J.*, 264 (2015) 697-705.
- [38] J. Fernandez, J. Abanades, G. Grasa, Modeling of sorption enhanced steam methane reforming-Part II: Simulation within a novel Ca/Cu chemical loop process for hydrogen production, *Chem. Eng. Sci.*, 84 (2012) 12-20.

- [39] A.L. García-Lario, M. Aznar, I. Martínez, G.S. Grasa, M. R., Experimental study of the application of a NiO/NiAl₂O₄ catalyst and a CaO-based synthetic sorbent on the Sorption Enhanced Reforming process., *Int. J. Hydrogen Energy*, 40 (2015) 219-232.
- [40] M.V. Navarro, J.M. López, T. García, G. Grasa, R. Murillo, Catalyst evaluation for high-purity H₂ production by sorption-enhanced steam-methane reforming coupled to a Ca/Cu process, *J. Power Sources*, 363 (2017) 117-125.
- [41] L. Díez-Martín, G. Grasa, R. Murillo, M. Martini, F. Gallucci, M. van Sint Annaland, Determination of the oxidation kinetics of high loaded CuO-based materials under suitable conditions for the Ca/Cu H₂ production process, *Fuel*, 219 (2018) 76-87.
- [42] L. Díez-Martín, I. Martínez, G. Grasa, R. Murillo, Investigation of the reduction kinetics of high loaded CuO-based materials suitable for the Ca/Cu looping process, *Fuel*, under revision, (2018).
- [43] J.R. Fernandez, Abanades, J.C., Grasa, G. , Modeling of sorption enhanced steam methane reforming in an adiabatic fixed bed reactor, *Chem. Eng. Sci.*, 84 (2012) 1-11.
- [44] M.F. Edwards, J.F. Richardson, Gas dispersion in packed beds., *Chem. Eng. Sci.*, 23 (1968) 109-123.
- [45] D. Vortmeyer, R. Berninger, Comments on the paper, theoretical prediction of effective heat transfer parameters in packed beds by Anthony Dixon and D. L. Cresswell [*AIChE J.*, 25, 663 (1979)], *AIChE J.*, 28 (1982) 508-510.
- [46] D.J. Gunn, Axial and radial dispersion in fixed beds., *Chem. Eng. Sci.*, 42 (1987) 363-373.
- [47] E.H. Baker, The calcium oxide-calcium dioxide system in the pressure range 1-300 atmospheres., *Journal of the Chemical Society* (1962) 464-470.
- [48] Y.A. Criado, M. Alonso, J.C. Abanades, Kinetics of the CaO/Ca(OH)₂ Hydration/Dehydration Reaction for Thermochemical Energy Storage Applications., *Ind. Eng. Chem. Res.*, 53 (2014) 12594-12601.
- [49] J. Xu, G.F. Froment, Methane steam reforming, methanation and water-gas shift: I. Intrinsic kinetics., *AIChE J.*, 35 (1989) 88-96.
- [50] M. Borghei, R. Karimzadeh, A. Rashidi, N. Izadi, Kinetics of methane decomposition to CO_x-free hydrogen and carbon nanofiber over Ni-Cu/MgO catalyst, *Int. J. Hydrogen Energy*, 35 (2010) 9479-9488.
- [51] J.W. Snoeck, G.F. Froment, M. Fowles, Steam/CO₂ reforming of methane. Carbon filament formation by the boudouard reaction and gasification by CO₂, by H₂, and by steam: kinetic study, *Ind. Eng. Chem. Res.*, 41 (2002) 4252-4265.
- [52] N. Rodríguez, M. Alonso, J.C. Abanades, A. Charitos, C. Hawthorne, G. Scheffknecht, D.Y. Lu, E.J. Anthony, Comparison of experimental results from three dual fluidized bed test facilities capturing CO₂ with CaO, *Energy Procedia*, 4 (2011) 393-401.
- [53] I. Martínez, G. Grasa, R. Murillo, B. Arias, J.C. Abanades, Kinetics of calcination of partially carbonated particles in a Ca-looping system for CO₂ capture, *Energy Fuels*, 26 (2012) 1432-1440.
- [54] J.P. Van Hook, Methane-Steam Reforming, *Catalysis Reviews: Science and Engineering.*, 21 (1980) 1-51.
- [55] S.S.E.H. Elnashaie, A.S. Al-Ubaid, M.A. Soliman, A.M. Adris, On the kinetics and reactor modelling for the steam reforming of methane-a review. , *J. Eng. Sci.*, 14 (1988) 247-273.
- [56] M. Halabi, M. de Croon, J. van der Schaaf, P. Cobden, J. Schouten, Reactor modeling of sorption-enhanced autothermal reforming of methane. Part II: Effect of operational parameters, *Chem. Eng. J.*, 168 (2011) 883-888.
- [57] D.K. Lee, I.H. Baek, W.L. Yoon, Modeling and simulation for the methane steam reforming enhanced by in situ CO₂ removal utilizing the CaO carbonation for H₂ production, *Chem. Eng. Sci.*, 59 (2004) 931-942.
- [58] Z.S. Li, N.S. Cai, J.B. Yang, Continuous Production of Hydrogen from Sorption-Enhanced Steam Methane Reforming in Two Parallel Fixed-Bed Reactors Operated in a Cyclic Manner, *Ind. Eng. Chem. Res.*, 45 (2006) 8788-8793.

- [59] E. Ochoa-Fernandez, G. Haugen, T. Zhao, M. Ronning, I. Aartun, B. Borresen, Process design simulation of H₂ production by sorption enhanced steam methane reforming: evaluation of potential CO₂ acceptors, *Green Chem.*, 9 (2007) 654-662.
- [60] M.V. Twigg, *Catalyst Handbook*, Wolfe Publishing Ltd., United Kingdom, 1989.
- [61] D.P. Harrison, Sorption-Enhanced Hydrogen Production: A Review., *Ind. Eng. Chem. Res.*, 47 (2008) 6486–6501.
- [62] Z. Zhou, L. Han, G.M. Bollas, Model-based analysis of bench-scale fixed-bed units for chemical-looping combustion, *Chem. Eng. J.*, 233 (2013) 331-348.
- [63] N. Rodríguez, M. Alonso, J.C. Abanades, Experimental investigation of a circulating fluidized-bed reactor to capture CO₂ with CaO, *AIChE J.*, 57 (2011) 1356-1366.
- [64] S.K. Bhatia, D.D. Perlmutter, Effect of the product layer on the kinetics of the CO₂-lime reaction, *AIChE J.*, 29 (1983) 79-86.
- [65] J.S. Dennis, A.N. Hayhurst, The effect of CO₂ on the kinetics and extent of calcinations of limestone and dolomite particles in fluidized beds., *Chem. Eng. Sci.*, 42 (1987) 2361-2372.
- [66] Z. Li, N. Cai, Modeling of Multiple Cycles for Sorption-Enhanced Steam Methane Reforming and Sorbent Regeneration in Fixed Bed Reactor., *Energy Fuels*, 21 (2007) 2909-2918.
- [67] J.R. Fernández, J.C. Abanades, CO₂ capture from the calcination of CaCO₃ using iron oxide as heat carrier., *J. Clean Prod.*, 112 (2016) 1211-1217.
- [68] L. Gradisher, B. Dutcher, M. Fan, Catalytic hydrogen production from fossil fuels via the water gas shift reaction, *Appl. Energy*, 139 (2015) 335-349.
- [69] P. Ammendola, R. Chirone, G. Ruoppolo, G. Russo, Production of hydrogen from thermo-catalytic decomposition of methane in a fluidized bed reactor, *Chem. Eng. J.*, 154 (2009) 287-294.
- [70] J.R. Fernández, J.C. Abanades, R. Murillo, Modeling of Cu oxidation in an adiabatic fixed-bed reactor with N₂ recycling., *Appl. Energy*, 113 (2014) 1945-1951.
- [71] S. Noorman, M. van Sint Annaland, H. Kuipers, Packed bed reactor technology for chemical-looping combustion, *Ind. Eng. Chem. Res.*, 46 (2007) 4212.
- [72] R. Barker, The reversibility of the reaction CaCO₃ → CaO+CO₂, *Journal of Applied Chemistry and Biotechnology*, 23 (1973) 733-742.