Morphology and ferroelectric properties of semiconducting/ferroelectric polymer bilayers.

*Edgar Gutiérrez-Fernández,¹ Esther Rebollar,² Jing Cui,¹⁺ Tiberio A Ezquerra,¹ Aurora
Nogales^{1*}*

¹Instituto de Estructura de la Materia, IEM-CSIC. C/ Serrano 121, Madrid 28006, Spain

² Instituto de Química Física Rocasolano, IQFR-CSIC. C/ Serrano 119, Madrid 28006,
Spain.

aurora.nogales@csic.es

+ Present address: Key Laboratory of Surface & Interface Science of Henan Province,
School of Material and Chemical Engineering, Zhengzhou University of Light Industry,
No. 136, Science Avenue, Zhengzhou, Henan, 450002, China.

SUPPORTING INFORMATION

THICKNESSES OF THE STUDIED SAMPLES

Polymer	Solvent	Solution Concentration (g/L)	Thickness (nm)
P3HT	CHLOROFORM	8	41 ± 15
P3HT	CHLOROFORM	16	85 ± 16
P3HT	CHLOROFORM	20	162 ± 12
P3HT	CHLOROFORM	24	196 ± 19
P(VDF- TrFE)	METHYL ETHLY KETONE	5	21 ± 5

Figure SI_1. Imaging of the out of phase amplitude of the PFM response of written domains by a bias indicated by the inner labels, applied to the substrate while the tip is grounded, in P(VDF-TrFE) over n-type doped silicon (a) and over a P3HT thin film (b).

Figure SI_2. Writing and reading scheme pointing out the depolarization effect after removing the polarizing field, and the effect of the field due to the PN junction in improving/destroying the retention of the polarization after upward/downward polarization.

CALCULATION OF THE SURFACE TENSION COMPONENTS.

According to the Young's equation there is a relationship between the CA (θ), the surface free energy of the liquid (γ_l), the surface free energy between the liquid and solid (γ_{sl}) and the surface free energy of the solid (γ_s):

$$\gamma_s = \gamma_{sl} + \gamma_l \cos\theta \quad 1$$

γ_{sl} is calculated based on the two surface free energies γ_s and γ_l and the interactions between the phases. From the CA measurements it is possible to calculate the surface free energy by using different methodologies.

We have used the method based on the Young-Dupre theory that was later improved by van Oss, Chaudhury and Good.²⁹ This model gives information on the Liftshitz-van der Waals and electron-donor and electron-acceptor components, allowing the assessment of both apolar and polar interactions respectively. To that purpose the following equation is used:

$$\gamma_l(1 + \cos\theta) = 2\sqrt{\gamma_s^d \gamma_l^d} + 2\sqrt{\gamma_s^+ \gamma_l^-} + 2\sqrt{\gamma_s^- \gamma_l^+} \quad 2$$

γ_s^+ and γ_l^+ are the electron-acceptor, while γ_s^- and γ_l^- are the electron-donor components of the surface free energy of solid and liquid, respectively. The term γ_s^d of a solid surface is calculated using the CA value of an apolar liquid probe. The total liquid free energy is the sum of the apolar component and the polar one, and since for apolar liquids $\gamma_l^+ = \gamma_l^- = 0$ then, $\gamma_l = \gamma_l^d$. In this case equation 2 can be rewritten as:

$$\gamma_s^d = \gamma_l (1 + \cos\theta)^2 / 4 \quad 3$$

In this work, the use of paraffin oil as apolar liquid allowed us to calculate γ_s^d , employing the values of the surface free energy components listed in Table S.1. Once γ_s^d is known, the unknown values of γ_s^+ and γ_s^- were calculated by solving the equation 4 for the pair water-glycerol (using again the corresponding parameters listed in table S.1).

Finally, to determine the total surface energy of the polymer films (γ_s) equations 2 and 3 are used, which relate the total surface energy with dispersion (γ_s^d) and acid-base (γ_s^p) components:

$$\gamma_s = \gamma_s^d + \gamma_s^p \quad 4$$

$$\gamma_s^p = 2\sqrt{\gamma_s^+ \gamma_s^-} \quad 5$$

Table S.1 Surface free energy components of the liquid probes (mJ m⁻²).

Liquid	γ_l	γ_l^d	γ_l^p	γ_l^+	γ_l^-
Water	72.8	21.8	51	25.5	25.5
Glycerol	64	34	30	3.92	57.4
Paraffin Oil	28.9	28.9	0	0	0

In this work, the CA measurements were carried out at room temperature and ambient humidity using a pocket goniometer PG2 (FIBRO system).¹³ The CA values were determined by the sessile drop technique. Two polar liquids, water and glycerol, and one apolar liquid, paraffin oil, were chosen (glycerol and paraffin oil were supplied by Sigma-Aldrich). During measurements, a droplet of each liquid probe with a volume of around 5 μ L was deposited on a dry and clean polymer surface. Static CA values were measured immediately after the formation of sessile drops of liquid on the surface. For each sample,

at least three measurements were carried out and the results readily averaged. In our work, the obtained contact angles are presented in table S.2

Table S.2 Measured contact angles

	CA Water (°)	CA Glycerol (°)	CA Paraffin Oil (°)
Silicon	63 ± 5	69 ± 2	18 ± 4
P3HT 40nm	107 ± 1	83 ± 1	35 ± 1
P3HT 80 nm	107 ± 0	80 ± 6	38 ± 1
P3HT 160 nm	107 ± 1	81 ± 4	37 ± 1
P3HT 200 nm	107 ± 1	93 ± 6	43 ± 1

Table S.3 Amount of edge-on crystallites in every sample of P3HT.

	Amount of edge-on crystallites
P3HT 40nm	0.24
P3HT 80 nm	0.36
P3HT 160 nm	0.36
P3HT 200 nm	0.47

The amount of edge-on crystallites was calculated following the same protocol as Petsagkourakis et al³⁰. First the GIWAXS patterns were integrated along the whole azimuthal range. Then, the Bragg peaks and the amorphous halo were fitted to Voigt or Gaussian functions. A value of relative crystallinity for every sample was calculated as the relation between the area of fitted Bragg peaks and the total area. Then, a radial (or polar) integration of the 100 peak of P3HT between $\chi=0^\circ$ (out-of-plane axis) and $\chi=90^\circ$ (in-plane axis) was done (Fig. S1 (a,b)). The value of the relative amount of edge-on crystallites was calculated as the relation between the integral of $I(\chi) \cdot \sin(\chi)$ between $\chi=0^\circ$ and $\chi=45^\circ$, and the same integral between $\chi=0^\circ$ and $\chi=90^\circ$. $I(\chi)$ is the intensity function calculated by radial integration of the 100 peak of P3HT (Fig.S1c,d). Finally, the real value comparable between samples is the total amount of edge-on crystallites that is obtained by multiplying the relative amount of edge-on crystallites by the relative crystallinity of the sample.

Figure S-3: (a) GIWAXS pattern of a P3HT thin film (thickness=200 nm), (b) thickness=40 nm, (c) intensity profiles of GIWAXS in function of azimuthal angle $\chi(^{\circ})$, P3HT thickness=200 nm (black curve), 40 nm (red curve) , (c) $I \cdot \sin(\chi)$ profile, P3HT thickness=200 nm (black curve), 40 nm (red curve).