Mn²⁺ Doping Level Dependence on the Magnetic Hyperthermia Response of Mn Ferrite Nanoparticles

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

Xabier Iasheras^a, Maite Insausti^{a,b}, Eneko Garaio^c, Laura De Matteis^d, Jesús M. de la Fuente^{d,e} and Luis Lezama^{a,b}

Manganese/iron ferrite nanoparticles with different Mn²⁺ doping grades have been prepared by a thermal decomposition optimized approach so as to ascertain the doping effect in magnetic properties and, specially, in the magnetic hyperthermia response. The particle size effect in this response has been studied by growing one of the prepared samples by a seed mediated growth mechanism. After analyzing the main structural and chemical parameters as Mn/Fe rate, crystalline structure, particle diameter, shape and organic coating grade, some Mn doping induced changes have been observed in particle shapes, as the insertion of Mn²⁺ cations yielded more anisotropic conformations. The magnetic properties analysis performed by M (H), M(T) and EMR techniques has shown interesting differences between different ferrites, obtaining higher saturation magnetization values at lower Mn doping levels and decreasing the magnetocrystalline anisotropy constant value increasing the Mn content. The homogeneous magnetic response under applied magnetic fields, besides the great effect of nanoparticle size and shape in such response, has been verified by the EMR analysis. Finally, a deep magnetic hyperthermia analysis has demonstrated the great effect of NP size and shape in the magnetic hyperthermia response and has presented the optimized Mn_{0.13}Fe_{2.87}O₄_G growth sample as an interesting candidate for future magnetic hyperthermia mediated biomedical treatments.

Introduction

Superparamagnetic nanoparticles, specially ferrite structure based iron oxides (magnetite Fe₃O₄), are being broadly investigated since their special magnetic behaviour was discovered,^{1,2} and are considered and tested for many and diverse applications as colour imaging, data storage, metal separation, catalysis, magnetic inks, biomedical applications and so forth.^{2,3} This last application area is the mostly explored one as many serious diseases, as some kind of cancer, could eventually be more easily diagnosed and treated by magnetic nanoparticle based therapies.^{4,5} In fact, these kind of magnetic nanosystems are currently being used as contrast agents in MRI diagnosis techniques.^{6,7} Nowadays, the goal that magnetic nanoparticle (MNP) biomedical research is trying to reach is, on the one hand, to develop a magnetically directed drug delivery system so as to increase the specificity and efficiency of drug activity.^{8,9,10} On the other hand, the development of a MNP mediated new kind of cancer treatment is possible through their magnetic hyperthermia response, what is based on the tumoral cell apoptosis or necrosis through the MNP mediated controlled heating.^{4,11} These treatments are directed to

generate heat by MNPs locally in tumors, without damaging the surrounding healthy tissues. Furthermore, these two possibilities can be combined in order to achieve a drug delivery and magnetic hyperthermia triggered controlled release therapy.^{12,13}

All these potential applications of MNPs arise from their magnetic hyperthermia response, what is based on their ability to generate heat under the influence of an applied alternating magnetic field.¹⁴ The heat generation can be controlled by modifying the synthesis parameters to prepare different sized, shaped and composed MNPs or by modifying the amplitude (H) and the frequency (ν) of the alternating magnetic field.¹⁵ Ferro-/ferrimagnetic and superparamagnetic particles become heated by hysteresis or relaxation loss under the applied magnetic field, depending on their magnetocrystalline anisotropy, saturation magnetization, average particle size, shape and size dispersion.^{16,17}

The mostly used material for such applications is the magnetite Fe₃O₄, a ferrimagnetic material (superparamagnetic below ≈40 nm) with a great magnetic susceptibility and saturation magnetization, which does not show a great toxicity in human body, as its decomposition follows the body's iron cycle.¹⁸ Therefore, its use in biomedicine is approved by the Food and Drug Administration (FDA).¹⁹ Magnetite has an inverse spinel structure (G. E.: Fd-3m), with O²⁻ anions forming a Face Centered Cubic arrangement, one eighth of the tetrahedral holes (8) are occupied by Fe³⁺ cations and one half of octahedral O_h holes (16) are occupied by Fe³⁺ cations (8) and Fe²⁺ cations (8).²⁰ One way that many authors are following to enhance the magnetic hyperthermia response of magnetite is by doping the inverse spinel structure with different paramagnetic atoms as zinc, nickel, cobalt or manganese.^{15,21,22} This chemical and structural modification produces changes in the intrinsic magnetic couplings and net magnetization, what result in different saturation magnetization and magnetocrystalline

^a BCMaterials, Parque Científico y Tecnológico de Bizkaia, E-48160 Derio, Spain

^b Departamento de Química Inorgánica, Universidad del País Vasco, UPV/EHU, P.O. Box 644, E-48080 Bilbao, Spain.

^c Departamento de Electricidad y Electrónica, Universidad del País Vasco, UPV/EHU, P.O. Box 644, E-48080 Bilbao, Spain.

^d Instituto de nanociencia de Aragón (INA), Universidad de Zaragoza, c/Mariano Esquillor s/n, 50018 Zaragoza, Spain.

^e Instituto de Ciencia de Materiales de Aragón, CSIC/Universidad de Zaragoza, c/Pedro Cebruna 12, 50009 Zaragoza, Spain

† Footnotes relating to the title and/or authors should appear here.

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

anisotropy values, comparing with magnetite. In this manner, the amount of this or these inserted paramagnetic atoms also has a major significance, as the doping effect can be limited.²¹ The control of such factors is the key to obtain materials with enhanced magnetic hyperthermia response, which could produce more heat with less concentration and approach to their application in humans.

In order to perform this research efficiently, magnetic characterization techniques able to predict accurately the magnetic hyperthermia response are required. In this way, many authors have focused their research on developing new characterization techniques to achieve a greater understanding of the studied MNP systems.^{4,23} The usefulness of the Electronic Magnetic Resonance (EMR) spectroscopy, for instance, to study small differences between different magnetic nanosystems based on its short time window has been proved, and is currently being widely employed to analyze the homogeneity of MNP systems magnetic response.^{15,24,25} The instrument developed by Garaio et al has also revealed as an useful tool to predict intrinsically what the materials response under different alternating magnetic fields would be.²⁶

The aim of this work is to explore the possibilities that the nanoparticulate Mn ferrite systems bring to the biomedicine field, by studying the magnetic behaviour and *in vitro* magnetic hyperthermia response of manganese ferrite nanoparticles with different Mn doping grades. Thus, by means of an optimized metal acetylacetonate precursors based thermal decomposition synthesis, four NP systems with different Mn/Fe rates have been prepared, in order to obtain different doping grade Mn ferrites. Basic parameters as particle diameters and Mn/Fe rates have been determined by a deep chemical and structural characterization to identify possible changes induced by the Mn doping. The magnetic characterization has been performed by means of field and temperature dependant magnetization measurements, besides a microscopic magnetic analysis via Electronic Magnetic Resonance (EMR) spectroscopy. Finally, the effect of Mn²⁺ doping grade in the magnetic hyperthermia response has been studied. Moreover, the particle size effect in the magnetic properties and hyperthermia response has also be analyzed in a higher diameter seed mediated growth Mn ferrite nanoparticle system.

Experimental section

Materials

1,2-Hexadecanediol (90%), dibenzyl ether (98%), toluene (99.5%), manganese (II) acetylacetonate (Mn(acac)₂, 100%) and iron (III) acetylacetonate (Fe(acac)₃, 99%) were purchased from Sigma-Aldrich. Oleylamine (80-90%) was from Acros Organic, oleic acid (100%) from Fluka and ethanol (96%) from Panreac. All chemicals were used as received.

Mn_xFe_{3-x}O₄ nanoparticle synthesis

Manganese ferrites with different Mn amounts were synthesized by an optimized thermal decomposition method. Different amounts of Mn(acac)₂ and Fe(acac)₃ acetylacetonates

reagents were mixed to form ferrite phases with different Mn doping levels. The used reagent amounts for all prepared samples are shown in [Table S1](#). Briefly, a total of 2.2 mmol of two metal precursor mixture (Fe(acac)₃ and Mn(acac)₂), 1.3 g of oleic acid (4.4 mmol), 1.7 g of oleylamine (4.4 mmol) and 2.5 g of 1,2-hexadecanediol (8.8 mmol) were mixed and dissolved in 25 mL of benzyl ether in a 250 mL three neck flask. Under Ar atmosphere and mechanical stirring, the mixture was heated to 200 °C at 5.5 °C/min heating rate and maintained for 30 min to nucleate the NPs. The mixture colour turn from reddish brown to black. The solution was then heated to 290 °C at 3 °C/min heating rate and maintained boiling for 90 min to complete the NP growth. The obtained NPs were precipitated by adding 30 mL of ethanol and redispersed in toluene. Unstable aggregates and possibly formed co-phases were removed by centrifugation at 3 000 rpm over 60 min. NPs were precipitated with ethanol and resuspended in toluene 3 times to remove the reagents and solvent remainders. Thus, Mn_{0.13}Fe_{2.87}O₄, Mn_{0.18}Fe_{2.82}O₄, Mn_{0.27}Fe_{2.73}O₄ and Mn_{0.36}Fe_{2.64}O₄ nanoparticle samples were obtained and stored at 4 °C in 2 mg/mL toluene dispersions with 1 % of oleic acid and oleylamine in volume.

Mn_{0.13}Fe_{2.87}O₄_G nanoparticle seed mediated growth

The sample which showed the most suitable magnetic properties to generate the highest magnetic hyperthermia response (Mn_{0.13}Fe_{2.87}O₄) was growth by means of a modified seed mediated growth technique developed by Castellanos et al.¹⁵ Just after the initial "seed" MNP synthesis process, the solution was cooled and kept at room temperature for 30 min. Then, 1.97 mmol of Fe (acac)₃, 0.22 mmol Mn(acac)₂, 3.02 mmol of oleic acid, 3.02 mmol of oleylamine and 2.25 mmol of 1,2-hexadecanediol were added. This mixture was heated to 200 °C first for 30 min and to reflux for 90 min, as in the first step. After cooling and keeping at room temperature for 30 min, the process was repeated other two times modifying the reagents amounts, as can be seen in the [Table S1](#). The same washing process performed for main samples was repeated for the growth MNPs. The group of highest diameter MNPs present in the mixture was isolated by adding a small amount of ethanol (0.25:1 in ethanol:toluene rate) to NP toluene dispersion. The obtained sample was labelled as Mn_{0.13}Fe_{2.87}O₄_G and stored at 4 °C in 2 mg/mL toluene dispersions with 1 % of oleic acid and oleylamine in volume.

Chemical and structural characterization

Metal content analysis. Manganese and iron content rates were determined measuring the metal concentrations by Inductively Coupled Plasma-Mass Spectrometry technique in a ICP-MS (7700x, Agilent Technologies, Palo Alto, USA) spectrometer using a Micro Mist micro-uptake glass concentric nebulizer (Glass Expansion, Victoria, Australia) spectrophotometer by previously digesting the MNPs in 1% nitric acid solution.

Size and Shape analysis. MNP size and shape have been determined by Transmission Electronic Microscopy (TEM), in a Philips CM200 microscope at an acceleration of 200 kV. MNP toluene diluted dispersions (0.05 mgFe/mL) were dropped-cast onto copper grid. Nanoparticle dynamic diameters have been

measured by Dynamic Light Scattering technique in a Malvern's Zetasizer Nano ZS instrument which works in 0.3 nm - 10 μ m range using a He-Ne laser (633 nm). Measurements were performed in the following conditions: 0.01 mg/mL, 90°, 6 runs and 3 min/run.

Crystalline structure determination. The samples crystalline structure was analyzed by X Ray Diffraction (XRD), measuring the samples in powder in a Philips PW1710 diffractometer equipped with copper anodes. The X-ray source operated at 40 kV and 40 mA, and the 2 θ scan was performed in the 10° <2 θ <90° range each 0.02° with scan step speed of 1.25 s.

NP coating analysis. The NP coating grade has been determined by Thermogravimetric analysis (TG), performed in a NETZSCH STA 449 C thermogravimetric analyzer, by heating $\approx$ 10 mg of sample in powder to 800 °C at 10 °C/min heating rate under dry Ar atmosphere.

Magnetic characterization

Field dependant magnetization measurements. Magnetization measurements as a function of applied field (M(H)) have been recorded in two different manners. To determine the saturation magnetization and superparamagnetic nature of NPs, samples were measured in powder ($\approx$ 30 mg) at 300 and 5 K in a VSM magnetometer from Cryogenic Ltd. up to a maximum field of 100 kOe. Sample powders were compressed in a gelatin capsules to avoid vibrations during the measurement. To determine accurately the NPs coercive fields at 5 K, samples were measured in a SQUID magnetometer from Quantum Design (MPMS-7K) up to a maximum magnetic field of 70 kOe. In this case, diluted sample colloidal dispersions (0.05 mgFe/mL) were deposited and dried in a filter paper to avoid interactions between MNPs.

Temperature dependant magnetization measurements. Magnetization measurements as a function of temperature after cooling at zero field and field (10 Oe, ZFC-FC curve) were performed in a commercial SQUID magnetometer from Quantum Design (MPMS-7T). Sample dispersions were deposited in filter paper, in the same way as in M (H) measurements.

Electronic magnetic Resonance (EMR) measurements. EMR spectra of samples in 0.05 mgFe/mL toluene dispersions at room temperature were recorded on a Bruker ELESYS spectrometer, equipped with a standard Oxford low-temperature device operating at X band.

Magnetic Hyperthermia *in vitro* experiments

As an *in vitro* magnetic hyperthermia experiment, the thermal energy generated by Mn ferrites has been measured at different frequencies and magnetic field amplitudes to analyze their behaviour and to find the sample with the best magnetic hyperthermia response. The measurements were carried out in a home-made instrument designed and described by Garaio et al.²⁶ The Specific Absorption Rate (SAR) of different samples have been directly measured from the dynamic hysteresis cycles measured by exposing MNP toluene colloidal dispersions (1 mgSAMPLE/mL) to the alternating magnetic field.²⁷

Results and discussion

Based on a thermal decomposition synthetic procedure, ferrites with different amounts of Mn ($\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$, $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$, $\text{Mn}_{0.27}\text{Fe}_{2.73}\text{O}_4$ and $\text{Mn}_{0.36}\text{Fe}_{2.64}\text{O}_4$) have been prepared and chemically, structurally and magnetically characterized to achieve an outline of these kind of nanostructured ferrite materials behaviour and the Mn doping grade effect on their structural and magnetic properties. The one which showed the most suitable magnetic properties to produce a great magnetic hyperthermia response was grown by an optimized seed mediated growth process ($\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G), in order to obtain a MNP sample with the optimized Mn doping grade and higher diameter which generates an enhanced magnetic hyperthermia response and to verify its suitability for future treatments.

Chemical and structural properties

As a previous step before start analyzing any structural or magnetic properties of MNPs, the doping level, which determines the chemical formula of the synthesized phases, has been determined by ICP measurements of previously digested Fe and Mn amounts present in nanoparticles. The nominal formula employed to label the samples ($\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$, $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$, $\text{Mn}_{0.27}\text{Fe}_{2.73}\text{O}_4$ and $\text{Mn}_{0.36}\text{Fe}_{2.64}\text{O}_4$) have been calculated from the relative metal amounts in molarity obtained from the ICP measurements. However, the obtained relative Mn amounts are nearly three times lower than the theoretical values, according to the metal rates added during the synthesis, as can be seen in the Table 1. There are two possible reasons that could explain this phenomenon. On the one hand, the formation of a manganese oxide secondary phase which would have been removed during the washing process, would explain the lack of manganese in the ferrite structure. On the other hand, the higher cationic radius of Mn^{2+} (91 pm) comparing with Fe^{2+} (82 pm) and Fe^{3+} (67 pm) cation could reduce the probability of Mn^{2+} cations to occupy the octahedral or tetrahedral holes of the inverse spinel structure due to the limited space to fix the Mn^{2+} cations.

The X Ray Diffraction (XRD) technique was employed to verify the presence of the inverse spinel structure and to discard the existence of possible impurities or secondary phases. Furthermore, an increase of Mn doping level in the inverse spinel structure could modify the unit cell parameters of the crystalline structure, inducing a measurable displacement of Bragg diffraction peaks. As can be observed in the diffractograms shown in Figure 1A, all prepared Mn ferrite systems are composed by the inverse spinel structure without impurities or secondary phases, in good agreement with the face centred cubic pattern of magnetite crystalline structure (S.G.: Fd-3m, PDF number 89-0691). The most intense peak, corresponding to (311) plane, was fitted in order to measure the Mn doping induced peak displacements and to estimate the crystal size by means of the Debye-Scherrer formula.²⁸ The fitting of the (311) reflexion peak for $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ and $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G samples is shown in Figure 1B, and the obtained 2 θ values of all sample (311) peaks and the estimated crystal sizes are represented in Table 1.

Figure 1. Mn rates, Mn_{0.13}Fe_{2.87}O₄

SAMPLE	% Mn theor.	% Mn ICP	(311) pos. (2θ °)	D _{XRD} (nm)	D _{TEM} (nm)	D _{DLS} (nm)	Org. Matter (%)
Mn _{0.13} Fe _{2.87} O ₄	10	4.3	35.63	11.7	10.1 ±1.6	10.0 ±2.0	19
Mn _{0.18} Fe _{2.82} O ₄	14	6.0	35.59	11.8	7.0 ±1.2	8.7 ±2.1	20
Mn _{0.27} Fe _{2.73} O ₄	18	9.0	35.55	10.2	8.5 ±1.2	7.5 ±1.8	19
Mn _{0.36} Fe _{2.64} O ₄	30	12.3	35.58	12.1	7.4 ±1.0	9.3 ±2.0	19
Mn _{0.13} Fe _{2.87} O ₄ _G	14	6.6	35.52	19.5	15.5 ±1.5	16.1 ±3.1	18

Due to the comparable ionic radius of Fe²⁺, Fe³⁺ and Mn²⁺ cations no representative differences between ferrites 2θ peak positions can be observed. Hence, the cation substitution does not induce measurable effects in the unite cell dimensions. Furthermore, by measuring the (311) peak width at half height an estimation of the crystal diameter was performed as is shown in Table 1. The particle average diameters, considering them as monocrystals, are in the 10-13 nm range for main ferrites and around 19 nm for the Mn_{0.13}Fe_{2.87}O₄_G growth sample. As can be seen in Figure 1B, the growth samples (311) peak is considerably narrower than the Mn_{0.13}Fe_{2.87}O₄ seed samples peak, what is related with its higher crystal size.²⁸

The monodomain nature of the prepared MNP samples and the obtained shape and size have been analyzed by visualizing the samples through TEM (Figure 2). The average diameters of main Mn ferrite samples, measured from the histograms presented in Figure S1, go from 7 to 11 nm for Mn_{0.13}Fe_{2.87}O₄, Mn_{0.18}Fe_{2.82}O₄, Mn_{0.27}Fe_{2.73}O₄ and Mn_{0.36}Fe_{2.64}O₄ samples. MNP size distributions fit well to a gaussian profile, with deviations around 1.5 nm. Particle shapes in all cases are similar, not being perfectly spherical. Magnetite MNPs prepared from acetylacetonate precursors are normally spherical,^{15,29} whereas these Mn ferrites have a tendency to form more anisotropic shapes, as can be easily appreciated in Mn_{0.18}Fe_{2.82}O₄ sample micrograph. This effect is even more apparent in the Mn_{0.13}Fe_{2.87}O₄_G growth sample, which shows a completely prismatic shape and a main diameter of 15.5 nm with also a narrow size distribution.

The prismatic shape of this growth sample shows a transformation from the 10 nm seed spherical particles. The spin coupling increase inside nanoparticles at higher particle

diameters is related to a higher ferromagnetic behaviour of MNP, which induces anisotropy in particles.³⁰ This anisotropy increase can also be verified by the strong tendency to self assembling that nanoprisms show in Figure 2. The applied growth process, besides the different particle size separation performed to obtain Mn_{0.13}Fe_{2.87}O₄_G, has been highly successful as bigger MNPs have been obtained, maintaining the narrow size distribution. In all cases, the obtained average NP sizes are comparable to the crystal sizes obtained from the XRD, hence, the monodomain nature of all samples can be assured. The particle dynamic diameter in toluene colloidal dispersion has also been measured by DLS to discard the presence of

d Mn rates (% Mn ICP, determined by ICP measurements), positions of (311) peaks in XRD from the XRD (D_{XRD}), average diameters measured from TEM micrographs (D_{TEM}), average rcentages (Org. Matter) for Mn_{0.13}Fe_{2.87}O₄, Mn_{0.18}Fe_{2.82}O₄, Mn_{0.27}Fe_{2.73}O₄, Mn_{0.36}Fe_{2.64}O₄

aggregates and to assure that the MNPs behave as single particles in colloidal suspension. The measured dynamic size dispersions represented in Figure S2 are in all cases in good agreement with the sizes obtained from TEM and XRD, what discards the aggregation of particles dispersed in toluene.

Figure 3. Thermogravimetric curves of $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$, $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$, $\text{Mn}_{0.27}\text{Fe}_{2.73}\text{O}_4$, $\text{Mn}_{0.36}\text{Fe}_{2.64}\text{O}_4$ and $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4\text{-G}$ samples and oleic acid and oleylamine as controls, measured under Ar atmosphere in 25–800 °C range by 10 °C/min heating rate.

Figure 2. TEM micrographs of $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ (A), $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$ (B), $\text{Mn}_{0.27}\text{Fe}_{2.73}\text{O}_4$ (C), $\text{Mn}_{0.36}\text{Fe}_{2.64}\text{O}_4$ (D) and $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4\text{-G}$ (E) with their calculated average diameters and size distributions.

To perform a complete structural and chemical characterization of the prepared MNPs not only the magnetic core needs to be

analyzed. The organic coating, formed in this case by oleate chains, has a vital role in the colloidal and chemical stability of the magnetic nuclei. The organic coating density has been analyzed by thermogravimetric analysis, which is shown in Figure 3 for all Mn ferrites and oleic acid and oleylamine as controls. In all cases, thermogravimetric curves show a well-defined mass loss profile over the temperature range of 200–600 °C. The profile, that is similar for all samples, is related to the decomposition of organic matter, what happens in the same way in all prepared MNPs. Losses below 150 °C correspond to adsorbed humidity, present in all samples. Slight mass losses can also be appreciated below 300 °C in most samples correlated with benzyl ether solvent reminders. The presence of two different slopes at 400 and 550 °C suggests two different kind of interactions between oleic acid and MNP surface, which produces different dissociations at two different temperatures. Oleic acid molecules are chemically absorbed on the surface of ferrite nanoparticles through the chemical interaction between their -COOH groups and -OH surface groups. Some authors have attributed this two step degradation to a double oleate layer in the MNP surface.³¹ An excess of oleic acid induces the formation of a new oleic acid layer by Van der Waals induced dipole interactions between oleate chains, what would be the reason of the appearance of two different dissociation temperatures. Thus, the first slope refers to the secondary oleate layer decomposition, only attached by dipolar interactions, what occurs at 300–400 °C, same as oleic acid decomposition temperature, whereas the second drop refers to the decomposition of the primary oleate layer, chemically attached to NP surface. The organic mass losses are summarized in Table 1.

All organic matter rates are in the 18–20% range. These high oleate density in particle surfaces maintain the MNPs stable in colloidal dispersion in non polar solvents, avoiding the aggregation by hydrophobic and steric repulsions. In this way, no great changes can be appreciated between different samples. Higher diameter MNPs, which have been synthesized by seed mediated growth method ($\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4\text{-G}$) show the lowest amount of organic mass. Thus, the coating proportion of nanoparticles is directly related to their size and shape, as these factors limit the proportion of superficial area available to be coated.

Magnetic behaviour

As the aim of these systems is to be eventually applied as magnetic hyperthermia inductors, their ability to produce thermal energy under an alternating magnetic field needs to be analyzed, what is directly related with their magnetic properties, as saturation magnetization (M_s) and magnetocrystalline anisotropy (K). Hence, such properties needs to be deeply studied.

As can be seen in the magnetization versus field cycles at 5 K shown in Figure 4A, all samples show the usual superparamagnetic behaviour of soft ferrite MNPs, with high M_s values and small remanence at low temperatures and no remanence at 300 K (Figure S3). As was expected, the

magnetization of ferrites at an applied constant magnetic field was higher at 5 K, since the absence of thermal fluctuation allows the blocking of magnetic moments oriented to magnetic field. As can be seen in Table 2, the M_s reached a maximum value of 92 emu/gFerrite in the lowest Mn proportion ($Mn_{0.13}Fe_{2.87}O_4$ and $Mn_{0.13}Fe_{2.87}O_4_G$) at 5 K, what is a quite high value for ferrite nanostructured materials, comparing with magnetite MNPs reported in literature.^{17,32} However, a slight linear decrease of M_s can be appreciated when increasing Mn content. Considering that Mn^{2+} cations are inside the ferrite structure, the substitution of Fe^{3+} cations of octahedral holes by the magnetically equal Mn^{2+} ($5 \mu_B$) ions would be an acceptable explanation for such behaviour, as has been previously discussed.³³ However, changes in Mn oxidation state during this kind of synthesis to conform more stable compounds have also been reported in literature.³² Hence, an oxidation from Mn^{2+} to Mn^{3+} ($4 \mu_B$) could yield a net magnetization decrease, explaining the linear slight decrease at higher Mn proportions observed in our ferrites.

Differences between coercive fields at 5 K usually provides useful information about the obtained material properties. However, due to the great magnetic and dipolar interactions that occur between MNPs in powder, such H_c measurements must be performed avoiding these interactions. In our case, the MNP toluene dispersion has been deposited and dried on filter paper. The original equation which explains the magnetic behaviour of monodomain magnetic systems was developed by Stoner and Wohlfarth, and explains the relation between the H_c at 5 K and the materials anisotropy constant (explained in SI).^{34,30} As can be seen in Figure 4B and Table 2, the differences between ferrites coercive fields are minimum. However, a weak decreasing tendency in the anisotropy constant calculated from the H_c values by Stoner and Wohlfarth equation can be noticed when increasing the Mn doping level (Table 2). Mn^{2+} doping induce a softening effect in ferrite structure. It is known that the insertion of some paramagnetic cations as Ni^{2+} , Mn^{2+} , Mn^{3+} or Co^{2+} in the inverse spinel structure produce an important effect in magnetic remanence and coercive values of resultant ferrites, dividing them between hard ferrites (higher M_r and H_c values than Fe_3O_4) and soft ferrites (lower M_r and H_c values than Fe_3O_4), depending on if the inserted cations favour (hard ferrites) or not (soft ferrites) the spin orientation in a preferential direction inside the crystalline structure, related to the density and orientation of spin orbitals.³⁵ Thus, less preferential orientation is caused by the presence Mn cation spin orbitals comparing with Fe and, therefore, the anisotropy of material is reduced by presence of such cations.³⁶

By measuring the temperature dependant magnetization after Zero (ZFC) and field (10 Oe, FC) cooling, important magnetic hyperthermia response related factors as blocking temperature (T_B) and magnetocrystalline anisotropy constant (K) have been determined. All measured samples present superparamagnetic behaviour, with several differences between their average blocking temperatures and T_B distribution, as can be seen in Figure 5A. The direct dependence of T_B value with particle diameter can be appreciated in the average T_B values exposed in Table 2, as the $Mn_{0.13}Fe_{2.87}O_4_G$ growth sample doubles the

T_B value of its seed sample ($Mn_{0.13}Fe_{2.87}O_4$). Furthermore, the observed blocking temperatures are significantly lower than those corresponding magnetites,¹⁵ mainly due to the softening effect that Mn cation presence induces in ferrite crystalline structure, aiding the easy rotation of particle magnetic moment in both directions of the easy magnetization axis. Although apparently different manganese contents do not affect strongly the blocking temperature, the anisotropy constants, which are independent of particle size, decrease at increasing manganese doping grade (Table 2). A lower coupling between magnetic moments is caused by the insertion of Mn atoms into ferrite structure, what decreases the anisotropy barrier value (KV).^{20,17} Thus, less preferential orientation is caused by the presence of Mn atoms spin orbitals comparing with Fe^{2+} and Fe^{3+} orbitals and, therefore, the anisotropy of the material is reduced by presence of these cations, as has been commented in the H_c analysis.³⁶

More information about microscopic changes in MNPs magnetic behaviour has been obtained from the Electronic Magnetic Resonance (EMR) spectroscopy measurements. Previous works have demonstrated the high influence of MNP diameter in the EMR signal and the corresponding g_{eff} values.¹⁵ As can be seen in Figure 5B, all spectra show mostly single peaks (double the case of $Mn_{0.13}Fe_{2.87}O_4_G$ growth sample). The signal broadness is related to differences in resonant magnetic fields (H_r) of all MNPs present in the sample. This H_r value can be strongly influenced by differences in MNP size, shape, structure or chemistry. Thus, heterogeneity in size, shape or Mn

Figure 4. M (H) cycles for all prepared Mn ferrite nanoparticles measured at 5. A. M (H) cycles measured in the VSM magnetometer in powder to visualize properly the materials saturation magnetization value. The matrix effect in the final magnetization value has been discarded by diminishing the mass corresponding to organic matter. B. M (H) cycles measured in the SQUID magnetometer dispersed in filter paper to avoid interactions and determine accurately the coercive field (H_c).

doping levels would lead to a great broadening effect in EMR signal.³⁷ The signal broadness is determined by measuring the peak to peak distance (ΔH_{pp}), expressed in Table 2. The similarity between the ΔH_{pp} is related to their similar size distributions and structural homogeneity. The only sample which shows two different peaks is the $Mn_{0.13}Fe_{2.87}O_{4_G}$ growth sample. These two peaks could have been produced by two different size, shape or chemistry particle groups. In this case, according to the size homogeneity verified by DLS and TEM, this distortion could be attributed to the presence of a

Oe applied magnetic field. This signal appears frequently in MNP samples EMR spectra and is representative of a little population of small size (≈ 4 nm) particles.³⁸ The ferromagnetic contribution of each sample can be tested by measuring the effective gyromagnetic factor (g_{eff}) deviation from the ideal value for a paramagnet, that is 2.0 in the case of Fe_3O_4 .³⁹ On the one hand, the strong influence of particle size in the g_{eff} value can be clearly appreciated in the great difference between the g_{eff} values of $Mn_{0.13}Fe_{2.87}O_4$ and $Mn_{0.13}Fe_{2.87}O_{4_G}$ samples, 2.02 and 2.60 respectively.

Table 3. Saturation magnetization values at 5 K (M_s , discarding the organic matter weight), coercive field at 5 K measured by SQUID (H_c), Blocking temperatures (T_B), magnetocrystalline anisotropy constant values measured from blocking temperatures ($K_{M(T)}$), gyromagnetic effective values calculated from EMR measurements (g_{eff}) and peak to peak distance in EMR spectra (ΔH_{pp}) for $Mn_{0.13}Fe_{2.87}O_4$, $Mn_{0.18}Fe_{2.82}O_4$, $Mn_{0.27}Fe_{2.73}O_4$, $Mn_{0.36}Fe_{2.64}O_4$ and $Mn_{0.13}Fe_{2.87}O_{4_G}$ samples.

SAMPLE	M_s 5K (emu/gFerrite)	H_c 5K (Oe)	$K_{M(H)}$ (kJ/m ³)	T_B (K)	$K_{M(T)}$ (kJ/m ³)	g_{eff}	ΔH_{pp} (Oe)
$Mn_{0.13}Fe_{2.87}O_4$	92	251	19.72	34	20.11	2.02	720
$Mn_{0.18}Fe_{2.82}O_4$	88	224	19.02	26	20.17	2.01	1072
$Mn_{0.27}Fe_{2.73}O_4$	87	216	17.29	26	20.26	2.01	883
$Mn_{0.36}Fe_{2.64}O_4$	85	215	17.14	28	16.49	2.04	628
$Mn_{0.13}Fe_{2.87}O_{4_G}$	96	209	19.61	75	21.03	2.6	756

spherical shape MNP group in the sample. This proves once again the high sensibility of this technique, as this distortion was no detected with any other characterization techniques. A small peak can be observed in most of Mn ferrite samples at a 3300

However, this difference is even higher than the expected according to previous studies.^{21,15} Having discarded great differences in anisotropy constants, calculated from $M(T)$ and $M(H)$ experiments, this difference could have been increased by the anisotropy in particle shape observed in TEM micrographs. This anisotropy could induce stronger interparticle interactions, interfering in the magnetic moment orientation with the applied magnetic field. On the other hand, the values obtained for main Mn ferrite samples are nearly the same in all cases. The different Mn doping levels influence the MNP rotation and, therefore, the g_{eff} value. However, different factors which are having effect in the final result as particle size, shape and doping level make impossible to analyze properly the Mn doping influence in the main g_{eff} value.

Magnetic hyperthermia response

Magnetic hyperthermia response of MNPs is the key factor to determine their potential applicability in future magnetic hyperthermia anticancer therapies. Firstly, according to the equations explained in the SI, Neél, Brown and effective relaxation times were calculated for all NP samples in order to ascertain which is the predominant mechanism in each case, and to anticipate which one would show the highest hyperthermia response (Table S2). According to the calculated data, the NP size has a great influence in τ_N values, as was expected according to its exponential dependence with the volume and anisotropy constant. The growth sample, according to its higher volume, show a much higher τ_N value. The effective relaxation times obtained by combining contributions of both mechanisms show that the growth MNP sample is the most promising one for hyperthermia treatments due to its higher MNP main diameter that leads to a τ_{eff} value more similar to resonance condition, represented in Figure S4A for $Mn_{0.13}Fe_{2.87}O_{4_G}$ sample. The obtained SAR values at

Figure 5. A. Temperature dependant magnetization curves measured after zero field (ZFC) and field (FC, 10 Oe) cooling for $Mn_{0.13}Fe_{2.87}O_4$, $Mn_{0.18}Fe_{2.82}O_4$, $Mn_{0.27}Fe_{2.73}O_4$, $Mn_{0.36}Fe_{2.64}O_4$ and $Mn_{0.13}Fe_{2.87}O_{4_G}$ samples measured dispersed in filter paper in the 5- 300 K range. B. Electronic Magnetization Resonance (EMR) spectroscopy measurements for all prepared Mn ferrite NPs measured in toluene dispersions (0.05 mgFe/mL) at room temperature in 1.5-4 kOe range.

relaxation times that are incomparable to the period time of the experiment are negligible. However, at values close to the experiments time window, from 10^{-7} to 10^{-5} , the line fits to a gaussian profile, which reaches the maximum value at $\tau_{\text{eff}} = 1.9 \cdot 10^{-6}$ s, called resonance condition.⁴⁰

The thermal energy generated by different samples has been measured at different frequencies and magnetic field amplitudes (H_{app}) and compared to identify the most promising sample.²⁷ Besides the dependence of hyperthermia response with the applied frequency that can be appreciated in Figure S4A and Figure S4B, the produced thermal energy also depends on the amplitude of the H_{app} . As can be seen in Figure 6A, all SAR values increase linearly with the field amplitude. SAR values are in the same range in all samples, excepting $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G growth sample, which shows much higher magnetic hyperthermia response due to its higher average particle size and anisotropic shape, which induce a much higher hyperthermia response, as was proved by other authors.¹⁶ The linear SAR response shown by the main samples is in the same range as the signals shown by similar ferrite nanoparticles.¹⁵

Furthermore, there is a slight SAR increasing tendency at higher Mn^{2+} doping levels, specially at higher applied magnetic field amplitudes. Nevertheless, as was explained in the EMR analysis, is difficult to relate the SAR results directly to the Mn^{2+} doping levels, as the obtained values are very close and many factors as particle average size, shape, and size dispersion are involved in this hyperthermia response.

Figure 6. A. Magnetic field amplitude dependant Specific Absorption Rate (SAR) measurements at 1 mg/mL concentration in toluene for different Mn ferrite NP samples at 532 kHz frequency alternating magnetic field. B. Magnetic field dependant magnetization measurements of $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$ _G sample in different magnetic field amplitudes under an 1030 kHz frequency alternating magnetic field in the home-made magnetic hyperthermia instrument.

Moreover, from this magnetic field dependent SAR evolution, an estimation of the anisotropy constant can be carried out to check their agreement with the values determined from blocking temperatures in the M (T) analysis. These data have been obtained by fitting the H dependent SAR values in the linear response at low H values, generally below 10 kA/m, as can be seen in Figure S5. Although the anisotropy constants estimated from SAR measurements, 18.0, 24.3, 18.8, 18.4 and 9.3 for $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$, $\text{Mn}_{0.18}\text{Fe}_{2.82}\text{O}_4$, $\text{Mn}_{0.27}\text{Fe}_{2.73}\text{O}_4$, $\text{Mn}_{0.36}\text{Fe}_{2.64}\text{O}_4$ and $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G samples respectively, do not suit perfectly with the ones obtained from FC-ZFC, all non growth samples are in the same value range. Thus, the well concordance of the obtained results with the non interacting superparamagnetic model can be assured for main Mn ferrite samples. In contrast, the $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G growth sample show much lower anisotropy value than it was expected. This effect could be induced by ferromagnetic interactions between particles with bigger sizes, according to their high effective relaxation times.

The SAR value evolution could be also displaced from the linear response at high applied magnetic field amplitudes. In order to verify that, $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G sample magnetization values under a constant field frequency (1030 kHz) at different field amplitudes have been represented in Figure 6B. The strong magnetization hysteresis increase at higher H_{app} is directly related to the specific absorption rate as the area inside each cycle represents the absorbed magnetic energy. This linear relation between the SAR and H_{app} can be identified in these cycles by the presence of ellipse shape magnetization curves. This elliptical cycle shape can only be observed in the cycle measured at the lowest field amplitude, 2.8kA/m. This cycle shows by far the lowest magnetic hyperthermia response, as the area inside the cycle is much smaller than the others. At higher field amplitude measurements the area inside cycles rises powerfully, what implies a greater absorbed magnetic energy. But these intense magnetic fields induces also a displacement from the linear response as a consequence of the saturation of magnetic moments.

Conclusions

In balance, the influence of the Mn doping in the magnetite nanoparticles inverse spinel structure has been proved, being the doping grade a vital factor to tune many of its magnetic properties and, therefore, its hyperthermia response. The Mn presence has demonstrated to induce a transformation in MNP shape, from spherical in the case of magnetite counterpart to more anisotropic shapes in Mn ferrites, being completely prismatic in the case of the $\text{Mn}_{0.13}\text{Fe}_{2.87}\text{O}_4$ _G seed mediated growth sample. This phenomena has not been observed in any magnetite NP sample prepared by this method. The results obtained from the magnetic characterization have provided a well overview about the effect of the Mn doping grade in essential values for magnetic hyperthermia response such as magnetocrystalline anisotropy and saturation magnetization, besides in many other points which increase our understanding on this kind of materials. Thus, low proportions of Mn in the structure provide higher values of M_s and K , increasing also the magnetic hyperthermia response. This response has been proved to be quite strong by magnetic hyperthermia measurements, comparing with magnetite and other ferrite values reported in literature. Finally, the great size dependence of magnetic hyperthermia response has been proved, as the growth samples much higher SAR value, besides its g_{eff} value measured from EMR, makes the difference for magnetic hyperthermia related applications, presenting this as a great candidate for future biomedical applications.

Acknowledgements

This work was supported by institutional funding from the Ministerio de Educacion y Ciencia and Basque Government under Projects MAT2013-41128-R and GIC-IT-570-13. We are grateful for Dr. Iñaki Orue for his orientation in the magnetic

properties analysis. Technical and human support provided by SGiker (UPV/EHU) is also gratefully acknowledged.

Notes and references

- 1 M. Knobel, W. C. Nunes, L. M. Socolovsky, E. De Biasi, J. M. Vargas and J. C. Denardin, *J. Nanosci. Nanotechnol.*, 2008, **8**, 2836–2857.
- 2 M. Faraji, Y. Yamini and M. Rezaee, *J. Iran. Chem. Soc.*, 2010, **7**, 1–37.
- 3 C. Burda, X. Chen, R. Narayanan and M. A. El-Sayed, *Chem. Rev.*, 2005, **105**, 1025–102.
- 4 C. Apoptosis, E. Zhang, M. F. Kircher, X. M. Koch, L. Eliasson and S. N. Goldberg, *ACS Nano*, 2014, **8**, 3192–3201.
- 5 J. L. Corchero and A. Villaverde, *Trends Biotechnol.*, 2009, **27**, 468–76.
- 6 C. Corot, P. Robert, J.-M. Idée and M. Port, *Adv. Drug Deliv. Rev.*, 2006, **58**, 1471–504.
- 7 W. Wei, W. Zhao, Y. Taekyung, J. Changzhong and K. Woo-Sik, *Sci. Technol. Adv. Mater.*, 2015, **16**, 23501.
- 8 S. a. Agnihotri, N. N. Mallikarjuna and T. M. Aminabhavi, *J. Control. Release*, 2004, **100**, 5–28.
- 9 S. Azarmi, W. H. Roa and R. Löbenberg, *Adv. Drug Deliv. Rev.*, 2008, **60**, 863–75.
- 10 S. Gelperina, K. Kisich, M. D. Iseman and L. Heifets, *Am. J. Respir. Crit. Care Med.*, 2005, **172**, 1487–90.
- 11 A. Jordan, R. Scholz, P. Wust, H. Schirra, Thomas Schiestel, H. Schmidt and R. Felix, *J. Magn. Magn. Mater.*, 1999, **194**, 185–196.
- 12 C. S. Brazel, *Pharm. Res.*, 2009, **26**, 644–56.
- 13 S. D. Kong, W. Zhang, J. H. Lee, K. Brammer, R. Lal, M. Karin and S. Jin, *Nano Lett.*, 2010, **10**, 5088–92.
- 14 R. E. E. Rosensweig, *J. Magn. Magn. Mater.*, 2002, **252**, 370–374.
- 15 I. Castellanos-Rubio, M. Insausti, E. Garaio, I. Gil de Muro, F. Plazaola, T. Rojo and L. Lezama, *Nanoscale*, 2014, **6**, 7542–7552.
- 16 S.-H. Noh, W. Na, J.-T. Jang, J.-H. Lee, E. J. Lee, S. H. Moon, Y. Lim, J.-S. Shin and J. Cheon, *Nano Lett.*, 2012, **12**, 3716–21.
- 17 V. Blanco-Gutiérrez, M. Virumbrales, R. Saez-Puche and M. J. Torralvo-Fernandez, *J. Phys. Chem. C*, 2013, **117**, 20927–20935.
- 18 M. E. De Sousa, M. B. Ferna, V. Raap, P. C. Rivas, P. Mendoza, P. Girardin, G. A. Pasquevich, J. L. Alessandrini, D. Muraca and F. H. Sa, *J. Phys. Chem. C*, 2013, **117**, 5436–5445.
- 19 K. M. Krishnan, *IEEE Trans. Magn.*, 2010, **46**, 2523–2558.
- 20 B. Cullity, *Introduction to Magnetic Materials*, Addison-Wesley, Massachusetts, 1972.
- 21 X. Lasheras, M. Insausti, I. Gil de Muro, E. Garaio, F. Plazaola, M. Moros, L. De Matteis, J. M. de la Fuente and L. Lezama, *J. Phys. Chem. C*, 2016, **120**, 3492–3500.
- 22 J. Jang, H. Nah, J.-H. Lee, S. H. Moon, M. G. Kim and J. Cheon, *Angew. Chem. Int. Ed. Engl.*, 2009, **48**, 1234–8.
- 23 L. Gutiérrez, M. P. Morales and F. J. Lázaro, *Phys. Chem. Chem. Phys.*, 2014, **16**, 4456–64.

- 24 J. Salado, M. Insausti, L. Lezama, I. G. De Muro and E. Goikolea, *Chem. Mater.*, 2011, **23**, 2879–2885.
- 25 J. Salado, M. Insausti, I. Gil de Muro, L. Lezama and T. Rojo, *J. Non. Cryst. Solids*, 2008, **354**, 5207–5209.
- 26 E. Garaio, J. M. Collantes, F. Plazaola, J. A. Garcia and I. Castellanos-Rubio, *Meas. Sci. Technol.*, 2014, **25**, 115702.
- 27 E. Garaio, O. Sandre, J.-M. Collantes, J. A. Garcia, S. Mornet and F. Plazaola, *Nanotechnology*, 2015, **26**, 015704-.
- 28 A. L. Patterson, *Phys. Rev.*, 1939, **56**, 978–982.
- 29 J. Salado, M. Insausti, L. Lezama, I. Gil de Muro, M. Moros, B. Pelaz, V. Grazu, J. M. de la Fuente and T. Rojo, *Nanotechnology*, 2012, **23**, 315102.
- 30 S. Oyarzún, A. Tamion, F. Tournus, V. Dupuis and M. Hillenkamp, *Sci. Rep.*, 2015, **5**, 14749.
- 31 L. Zhang, R. He and H. C. Gu, *Appl. Surf. Sci.*, 2006, **253**, 2611–2617.
- 32 R. Chen, M. G. Christiansen and P. Anikeeva, *ACS Nano*, 2013, **7**, 8990–9000.
- 33 F. L. Deepak, M. Bañobre-López, E. Carbó-Argibay, M. F. Cerqueira, Y. Piñeiro-Redondo, J. Rivas, C. M. Thompson, S. Kamali, C. Rodríguez-Abreu, K. Kovnir and Y. V. Kolen'ko, *J. Phys. Chem. C*, 2015, **119**, 11947–11957.
- 34 E. P. W. E. C. Stoner, *philosophical Trans. R. Soc. A Math. Phys. Eng. Sci.*, 1948, **240**, 599.
- 35 Q. Zhang, I. Castellanos-rubio, R. Munshi, I. Orue, B. Pelaz, K. I. Gries, W. J. Parak, P. Pino and A. Pralle, *Chem. Mater.*, 2015, **27**, 7380–7387.
- 36 Sòshin Chikazumi, *Physics of Ferromagnetism*, Oxford Science Publications, Oxford, U.K., 2009.
- 37 A. Coene, G. Crevecoeur and L. Dupré, *J. Appl. Phys.*, 2015, **117**, 17D105.
- 38 F. Gazeau, J. . Bacri, F. Gendron, R. Perzynski, Y. . Raikher, V. . Stepanov and E. Dubois, *J. Magn. Magn. Mater.*, 1998, **186**, 175–187.
- 39 P. G. Bercoff and H. R. Bertorello, *J. Magn. Magn. Mater.*, 1997, **169**, 314–322.
- 40 J. Carrey, B. Mehdaoui and M. Respaud, *J. Appl. Phys.*, 2011, **109**, 0–17.