Impact of Nanomorphology in Surface Doping of Organic Semiconductors: The Pentacene-C₆₀F₄₈ Interface

*Francesco Silvestri,¹ Mauricio J. Prieto,² Adara Babuji,¹ Liviu C. Tănase,² Lucas de Souza
Caldas,² Olga Solomeshch,³ Thomas Schmidt,² Carmen Ocal,^{1*} and Esther Barrena^{1*}*

¹ Instituto de Ciencia de Materiales de Barcelona (ICMAB-CSIC), 08193 Bellaterra, Barcelona,
Spain

² Department of Interface Science, Fritz-Haber Institute of the Max Planck Society, 14195 Berlin,
Germany

³ Electrical Engineering Department, Nanoelectronic Center, Technion, Haifa 32000, Israel

Abstract

Establishing the rather complex correlation between structure and charge transfer in organic-organic heterostructures is of utmost importance for organic electronics and requires spatially resolved structural, chemical and electronic details. Insight in this issue is provided here by combining atomic force microscopy, Kelvin probe force microscopy, photoemission electron microscopy and low-energy electron microscopy for investigating a case study. We select the interface formed by pentacene (PEN), benchmark among the donor organic semiconductors, and a p-type dopant from the family of fluorinated fullerenes. As for Buckminsterfullerene (C₆₀), the

growth of its fluorinated derivative C₆₀F₄₈ is influenced by thickness and crystallinity of the PEN buffer layer, but the behaviour is markedly different. We provide a microscopic description of the C₆₀F₄₈/PEN interface formation and analyse the consequences in the electronic properties of the final heterostructure. For just one single layer of PEN, a laterally complete but non-compact C₆₀F₄₈/PEN interface is created, importantly affecting the surface work function. Nonetheless, from the very beginning of the second layer formation, the presence of epitaxial and non-epitaxial PEN domains dramatically influences the growth dynamics and extremely well packed two-dimensional C₆₀F₄₈ islands develop. Insightful element maps of the C₆₀F₄₈/PEN surface spatially resolve the non-uniform distribution of the dopant molecules, which leads to a heterogeneous work function landscape.

Keywords: organic semiconductors, molecular doping, interface, nanomorphology, pentacene, C₆₀F₄₈, AFM, XPEEM

Introduction

Organic materials have raised great interest in the scientific community in the last decades for emerging technologies exploiting their unique capabilities to fabricate low-cost, lightweight, flexible and large area devices. Organic semiconductors (OSCs) thus widely amplify the technological horizons in many different applications based on devices such as solar cells, transistors and light emitting diodes.^{1–4} A vast amount of basic and applied research has focused on ameliorating the intrinsic properties of OSCs and designing strategies for improving the performance of devices. In analogy to inorganic semiconductors, doping of OSCs represents one of the most efficient methods to gain control over their electrical properties. Specifically, molecular doping, which implies the addition of an organic electron acceptor (donor) for p-type (n-type) doping, is a suitable approach and, at the same time, a playground for studying the physics

of OSC materials.^{5–8} Most studies concern bulk doping in which the dopants are intermixed with the OSC, for example by co-evaporation. These works have revealed a complex scenario where different doping mechanisms operate depending on the specific interaction between dopant and OSC.^{9–12} Nevertheless, doping can also be accomplished by charge exchange between a semiconductor and a dopant adlayer located at its surface. The so-called contact doping or surface transfer doping relies on interfacial charge transfer between the dopant molecules and the underlying semiconductor and has been employed for inorganic as well as for organic semiconductors.¹³ For p-type doping, the lowest-unoccupied-molecular-orbital (LUMO) of the adsorbed species must be close to or below the highest-occupied-molecular-orbital (HOMO) of the OSC, resulting in the formation of holes at the dopant/OSC interface. Such selective doping represents one of the most promising strategies to improve charge carrier injection in organic field effect transistors (OFETs), where minimizing the contact resistance is a great challenge and remains a bottleneck for developing high performance devices.^{14–18} However, it also raises prominent issues related to the optimization and stability of the doped interfaces and fundamental questions about the underlying physical mechanisms for improving the charge injection. The dopant introduces electronic changes at the interface (interfacial dipole, band bending, charge reorganization) and sometimes even on the microstructure of the semiconductor layer (by diffusion and/or intermixing) that will largely determine the contact properties. Numerous studies by spectroscopic methods have focused on the electronic properties of the dopant/OSC interface.^{19–23} Nevertheless, a microscopic insight is lacking in most cases. Inhomogeneity of the dopant/OSC interface at the sub-micrometre scale, non-detectable by spectroscopic techniques providing averaged properties but accessible for spatial resolution microscopies, would entail uncontrolled

device performances. It is largely unknown how the interaction between the dopant and the OSC surface influences the interface structure.

In this work we demonstrate the crucial role that the nanomorphology of the OSC layer has on the characteristics and formation of the dopant/OSC interface for the case of pentacene. As p-type dopant (acceptor) we have chosen $C_{60}F_{48}$, the highest in fluorine content²⁴ among the fluorofullerenes, a class of organic p-type dopants with large attractive potential for the lifetime improvement of organic electronic devices due to its low volatility and bulky shape (i.e. expected low diffusion and intermixing with the OSC).²⁵ While the importance of the acceptor/donor interface morphology has long been recognized and investigated for C_{60} /pentacene as prototype case study,^{26–30} the system $C_{60}F_{48}$ /pentacene remains unexplored. Here, the role of the epitaxial quality and morphological characteristics of the OSC layer on the nucleation and growth mode of the dopant as well as the effects on the electronic properties of the interface are investigated. We combine different spatially-resolved techniques, such as atomic force microscopy (AFM), Kelvin probe force microscopy (KPFM),^{31,32} X-ray photoemission electron microscopy (XPEEM), and low-energy electron microscopy (LEEM), to have a comprehensive view of the intimate relation between microstructure and electronic effects at the created interfaces.

Experimental section

Pentacene was purchased from Sigma Aldrich and purified by gradient-sublimation; the fluorinated fullerene $C_{60}F_{48}$ was synthesized as per the method developed at the Josef Stefan Institute (Slovenia).²⁴ The product was characterized by chemical analysis, electron-ionization mass spectrometry and IR-spectroscopy and its purity was estimated to be 95%. The two molecules were sublimated under high vacuum conditions (10^{-6} - 10^{-7} mbar) by organic molecular beam

deposition (OMBD). As monitored by quartz crystal microbalance (QCM), deposition rates of about 2-3 Å/min were achieved by resistively heating the Knudsen cells up to about 180 °C and 200 °C for PEN and C₆₀F₄₈, respectively. Native silicon oxide on arsenic n-doped silicon substrates were cleaned by ultra-sonication (10 min in acetone plus 10 min in ethanol) before being introduced in the evaporation chamber, where they were degassed (15 min at 250 °C) and then maintained at room temperature (RT) during deposition. The coverage for pentacene is determined from the AFM topographic images and expressed in monolayers, being one monolayer (ML) a single full layer of nearly standing up molecules, corresponding to a nominal layer thickness of ~15 Å. For C₆₀F₄₈ we estimate that 10 Å of nominal thickness is approximately equivalent to one closed-packed monolayer.

AFM measurements in contact and dynamic modes were performed at RT using a commercial head from Nanotec Electronica. Si₃N₄ V-shaped cantilevers (Veeco) with nominal force constant ranging between 0.03 and 0.5 N/m were employed for contact mode while Cr/Pt coated silicon tips on rectangular cantilevers (BudgetSensors) with nominal resonance frequency of 75 kHz and force constant of 3 N/m were used for dynamic mode. Contact mode data were collected in a non-invasive manner by applying the lowest possible load, i.e., in the attractive regime and as close as possible to the pull off force, thus preventing any tip-induced damage and providing accurate topographic data. Lateral force measurements, in the friction force microscopy (FFM)³³ and in the Torsion Shear Microscopy (TSM)³⁴ imaging modes, were used to determine packing details of the PEN layers.^{35–37} Frequency modulation KPFM³⁸ was employed to measure local surface contact potential differences (CPD). In our set up the voltage is applied to the tip, therefore, higher CPD values indicate lower work function (ϕ).³⁹ Tip-sample conditions were systematically checked by force versus distances curves. All AFM images were analysed by using the WSxM freeware.⁴⁰

Ultraviolet photoelectron spectroscopy (UPS) was employed to measure the density of states at the Fermi-edge valence band (VB) and the secondary electron cut-off (SECO) of in-situ prepared samples, using an ultra-high-vacuum (UHV) system equipped with a SPECS Phoibos 150 hemispherical energy analyser and a helium lamp ($h\nu = 21.22$ eV). To have access to the work function of the samples from the SECO, the corresponding spectra were taken with the samples biased at -10 V. An Au(111) single crystal was used as reference for the determination of the Fermi energy.

LEEM/LEED and XPEEM measurements were carried out in the SMART spectromicroscope operating at the UE49-PGM beamline at the synchrotron radiation facility BESSY II of the Helmholtz-Zentrum Berlin (HZB). The aberration corrected and energy filtered LEEM/PEEM instrument combines microscopy, diffraction and spectroscopy techniques for comprehensive characterization. The instrument achieves an experimentally demonstrated lateral resolution of 2.6 nm in LEEM and 18 nm in energy-filtered XPEEM mode, respectively.^{41,42}

To address the extent of beam damage, X-ray photoelectron emission spectroscopy (XPS) was applied. This was done in a fast way (one spectrum every two seconds) by imaging over time the dispersive plane of the energy filter of the SMART spectromicroscope from pristine areas of the sample (initially not irradiated). The line shape, intensity and position (binding energy, BE) of F1s and C1s photoemission lines were monitored, under different X-ray dosage, in order to identify changes in the chemical environment of the C₆₀F₄₈ and PEN molecules. This assessment allowed us to identify the optimal beamline conditions that would guarantee a minimal damage to the organic films. For example, the optimal conditions adopted were such that even though the higher BE line of the C1s signal, assigned to fluorinated sp³ carbons (C-F) of C₆₀F₄₈,⁴³ decreased as a function of irradiation over time as a result of radiation damage, all features observed under the

F1s line remained unchanged, thus indicating that the fluorine atoms stayed at the surface after C₆₀F₄₈ breaking. In such a way, despite the fact that the damage induced by the X-ray beam could not be avoided completely, experimental conditions were such that it was possible to produce maps of spatial chemical distribution on the surface.

Results and Discussion

Pentacene on SiO₂ is known to follow the Stranski-Krastanov growth mode during thin film formation, with the completion of one or two complete layers followed by three-dimensional (3D) islands formation through nucleation and growth of dendritic islands.^{44–48} Within the plane, molecules arrange in a face-to-edge herringbone packing. The molecular orientation is nearly standing up in the monolayer, with their axis perpendicular to the SiO₂ surface, and then tilted in the subsequently stacked layers leading to slightly varying layer heights of ~1.5-1.6 nm.^{49–52} This structural transition is the result of different interlayer interactions between PEN–SiO₂ and PEN–PEN. Since controlling microstructure of organic donor/acceptor interfaces is relevant for performance and stability of devices, we address here the role of the PEN thickness, below and above the monolayer as well as the ulterior deposition of diverse amounts of C₆₀F₄₈ on their top. Due to the favourable mismatch in electronic levels, electron charge transfer across the interface is expected from the HOMO of pentacene (~4.7-5.0 eV)^{53–58} to the LUMO of C₆₀F₄₈ (~5.0-5.5 eV).^{43,59}

Figure 1. (a) Molecular structures of pentacene and C₆₀F₄₈. Topographic and KPFM images for (b, c) 0.8 ML of PEN, (d, e) 0.8 ML of PEN + 8 Å C₆₀F₄₈ and (f, g) 0.8 ML of PEN + 14 Å C₆₀F₄₈. Colour scale ranges are (b) 0-7 nm, (d) 0-14 nm, (f) 0-16 nm in the topographic images and -1.5-2.0 V in all KPFM images (c, e, g). (h) Surface potential difference between PEN islands for diverse C₆₀F₄₈ depositions; the surrounding SiO₂ is taken as reference and the red data point corresponds to C₆₀F₄₈ crystallites (see text). Note: lower surface potential corresponds to higher work function (see experimental section). (i) Schematic model of the sub-monolayer pentacene film covered with C₆₀F₄₈.

In the sub-monolayer range, round islands with single layer (1L) height and few hundred nanometres in diameter cover the surface (Figure 1b), though some two-layer (2L) high islands could also be found. Since the amorphous silica surface does not impose any preferential in-

plane direction during PEN growth, the 1L islands adopt equivalent packing but random azimuthal orientations. Those observed 2L nuclei exhibit lower friction in the lateral force images (Figure S1 in the Supporting Information), a fact that is attributed to the formation of a bilayer structure with epitaxial order.⁶⁰ We will come to this point later again. KPFM allows a quantitative mapping of the surface potential with nanoscale spatial resolution (Figure 1c, 1e, 1g). As known, tunnelling across the thin native silicon oxide allows Fermi level equilibrium with PEN and, therefore, the surface potential contrast for bare pentacene depends on substrate doping.⁶¹ In the present case, the surface potential of bare PEN is lower by 0.2 V than that of the surrounding SiO₂ reference. After depositing 8 Å of C₆₀F₄₈ (Figure 1d), a certain roughness of the islands surface is accompanied by a homogeneous decrease of ~0.4 V in their surface potential, which is attributed to the formation of a non-compact C₆₀F₄₈ layer onto the pentacene. For the 14 Å coverage of fluorinated molecules (Figure 1f), the topographical images reveal a dense layer of C₆₀F₄₈ on pentacene that is accompanied by a rise in the local work function of $\Delta\phi \approx 0.95$ eV with respect to the surrounding SiO₂ with little contrast among the whole set of islands. The monotonous increase of $\Delta\phi$ as a function of coverage (Figure 1h), points to a charge transfer between C₆₀F₄₈ and PEN molecules proportional to the amount of dopant in direct contact with the OSC. At high local coverage, C₆₀F₄₈ molecules assemble densely in the form of flat aggregates (1 nm high), mostly at the edges of the PEN islands (Figure S2 in the Supporting Information), with a large $\Delta\phi$ of ~1.35 V (red point in Figure 1h) likely arising from intrinsic contact potential differences between the silicon dioxide layer and C₆₀F₄₈ crystallites. Although the value of the work function measured upon deposition of C₆₀F₄₈ on pentacene is also influenced by charge transfer with the Si substrate,⁶² this fact does not affect the conclusions of this work.

Figure 2. Topographic and lateral force images for (a, b) 1.3 ML PEN and (c, d) 1.3 ML PEN + 14 Å C₆₀F₄₈. Colour scale ranges are 0-5 nm (a) and 0-11 nm (c) in the topographic images. (e) Line profile across C₆₀F₄₈ grown on one of the 2L islands. (f) Schematics of a 2L island in which the central epitaxial domain (core) is not covered by C₆₀F₄₈. Note: 1L stands for the PEN layer in contact with the substrate.

Approaching the PEN monolayer, the 1L islands at the SiO₂ surface coalesce leading to a nearly featureless closed first layer with a polycrystalline microstructure dictated by domains with different azimuthal orientation.^{36,63,64} Occasionally the domain boundaries of the first layer can be discerned as a network in topography.⁶⁵ The so-called transverse force microscopy allows the visualization of rotational domains in the first and successive layers⁶⁰ (Figure S3 in the Supporting

Information). Figure 2 shows the topographical and lateral force images for 1.3 ML of pentacene before and after the deposition of 14 Å of C₆₀F₄₈. The pentacene islands in the second layer exhibit the typical fractal-like shape reported in the literature^{60,66} (Figure 2a) formed due to a diffusion-limited aggregation growth (DLA) with poor edge molecular diffusion.⁶⁷ The branched islands exhibit a noteworthy internal contrast in conventional FFM imaging that strongly differ from the faint friction anisotropy of the 1st layer (Figure 2b). Specifically, the islands appear to have a core with lower friction (Figure S3 in the Supporting Information), which can be attributed to regions with epitaxial order with the underlying domain,⁶⁰ having therefore a more compact packing. Importantly, this observation suggests that over the monolayer, impinging PEN molecules nucleate and laterally aggregate to the 2L epitaxial regions that constitute the low-friction cores of the dendrites (darker areas in Figure 2b). Hence, the second layer pentacene islands have a polycrystalline nature consisting in coexisting domains with epitaxial and non-epitaxial stacking (with respect to the underlying PEN layer). These domains have been reported to show a difference of some tens of mV in KPFM, arising from a diverse electrostatic coupling between consecutive layers in each case.⁶⁰ We will demonstrate next that layer stacking is relevant for molecular doping since the epitaxial or non-epitaxial PEN interlayer relationship affects the ulterior C₆₀F₄₈ growth and, importantly, the electronic response of the dopant/OSC interface. After depositing C₆₀F₄₈ (Figure 2c, 2d), several things immediately catch one's attention. On the one hand, the PEN first layer, covered now with C₆₀F₄₈, develops marked cracks leaving some SiO₂ uncovered most likely reflecting the domain boundaries of the first layer. The thickness of this cracked layer is ~2.5 nm as it would correspond to a single PEN layer (~1.5 nm) plus one C₆₀F₄₈ molecule overlayer (~1 nm). We hypothesize that, due to the fluorinated fullerene interaction with PEN, a certain densification within the molecular domains plus local restructuration of the less packed and

defective boundary regions take place, as it occurs for the aged PEN monolayer⁶⁵ (see Figure S4 in the Supporting Information). Nevertheless, the most remarkable finding relates the hindered growth of C₆₀F₄₈ at the crystalline (epitaxial) core of the dendrites (Figure 2f). Due to the extreme sensitivity of FFM to local chemical differences, we can guarantee that the PEN at the islands' centres remain uncovered while overall dopant uptake occurs on the first layer and on the dendritic arms of the islands. The C₆₀F₄₈ deposits have a height difference with respect to the bare PEN core about twice the fullerene size (2C₆₀F₄₈) (height profile in Figure 2e) and are extremely flat indicating higher compactness than the C₆₀F₄₈ layer on the PEN first layer. As important factors for the growth of molecules on surfaces are the adsorption dynamics and energy dissipation, we argue that the different stacking of PEN in core and branches may affect the residence time of the dopant molecules, being therefore at the basis of the selective nucleation observed. Impinging molecules experience the surface energy corrugation and accommodate at distinct favourable sites. Therefore, the low energy dissipation at the epitaxial cores would facilitate diffusion towards highly dissipative non-epitaxial locations where the dopants accumulate forming compact islands, due to a cohesion between C₆₀F₄₈ molecules (C₆₀F₄₈–C₆₀F₄₈) larger than with the PEN film (C₆₀F₄₈–PEN–PEN).

Figure 3. AFM topography and respective KPFM maps of (a, b) 5 Å and (c, d) 14 Å of $C_{60}F_{48}$ deposited on 1.3 ML of PEN. Labels 1L and 2L in topography stand for the layer in contact with the substrate and the second layer, respectively. Note: lower/higher surface potential corresponds to higher/lower work function.

As Figure 3 shows for two coverages of $C_{60}F_{48}$, the surface electrostatic potential is determined by the distribution and packing of $C_{60}F_{48}$ at the nanoscale. Upon 5 Å of $C_{60}F_{48}$ deposition, while the PEN first layer (1L) gets homogeneously covered by a rough $C_{60}F_{48}$ layer due to a scattered distribution of the fullerenes, small clusters selectively nucleate only at the non-epitaxial arms of the islands (Figure 3a). These $C_{60}F_{48}$ /PEN–PEN areas exhibit a contact potential with an intermediate value between $C_{60}F_{48}$ /PEN– SiO_2 and bare epitaxial regions of PEN in agreement with an intermediate coverage of dopant (Figure 3b). For a coverage of 14 Å (Figure 3c, 3d), a noticeable increase of the work function is visible in those areas covered by $C_{60}F_{48}$ molecules. The compact $C_{60}F_{48}$ bilayer now covering the branches of the 2L PEN islands is responsible for a

notable electrostatic imbalance in the surface potential of ~ 0.65 V between covered arms and uncovered cores (Figure 3d and Figure S5 in the Supporting Information).

Figure 4. UPS spectra of the (a) SECO and (b) HOMO regions for silicon substrate (black squares), 2 ML pentacene (orange circles), and 2 ML pentacene + 6 Å C₆₀F₄₈ (red triangles) and (c) the corresponding energy level diagram schematics with a drawing of the evaporation sequence. (d) AFM topography and (e) respective KPFM maps of the same sample. (f) Schematic model and line profiles along dashed segments in the corresponding images.

To evaluate the effect of the dopant on the electronic properties of the interface, the near Fermi-edge VB density of states and the SECO were measured in-situ before (bare native SiO₂) and after the preparation of a PEN thin film (≈ 2 ML nominal thickness) as well as upon deposition of 6 Å of C₆₀F₄₈ (Figure 4). The as-prepared PEN film (orange data) shows the typical secondary electrons emission (Figure 4a) and the emergence in the VB of a well-developed HOMO at 0.7 eV (Figure

4b) corresponding to an ionization potential of 4.7 eV in agreement with previously reported data for (001) oriented pentacene films on silicon oxide.^{53,54} As indicated by the SECO shift towards lower binding energy with respect to that of the clean substrate (black data) the PEN layer causes an increase of the surface work function in accordance with our KPFM data (Figure 1h). Outstandingly, a further SECO shift of ~0.9 eV reflects the dramatic increase of the surface work function after the fluorinated fullerene deposition (red data). Simultaneously, a relevant shift of the HOMO by 0.4 eV towards lower energy is observed. The schematic diagram of Figure 4c presents the whole energetics picture derived from these measurements. Being aware of the averaging nature of UPS and the influence of the particular local morphology on the interfacial properties, the same sample was analysed by ex-situ AFM (Figure 4d, 4e). As commented above, after an initial layer-by-layer mechanism, which usually involves one or two complete layers, the growth of PEN at RT overcomes a 2D-3D transition commonly occurring by the formation of pyramidal grains.^{44,49} The pyramid-like structure characteristic of such transition is visible in Figure 4d. The different surface levels are indicated by Roman numerals starting from the full molecular PEN first layer in contact with the SiO₂. As expected from a homogeneous but non-compact distribution of the dopant, the 1st layer (I) exhibits a certain roughness (rms ≈ 0.3 nm) and uniform surface potential. This is not the case for the 2nd layer (II), where flat (IIA) and rough (IIB) areas give evidence of a non-homogeneous distribution of the dopant that is directly correlated with local differences of few hundred mV in the surface potential (see line profiles in Figure 4f), i.e. higher work function for higher dopant coverage. Within the error, all the other pentacene terrace levels (3rd to 5th) show a surface potential which is similar to the uncovered region IIA (Figure 4e). A side view schematic drawing of the proposed model is also shown. The lack of C₆₀F₄₈ in the upper layers suggests a low interlayer diffusion barrier for step descending that

permits downward interlayer mass transport of $C_{60}F_{48}$ at this stage. We note that in spite of the heterogeneous work function landscape at the nanoscale, only one SECO is observed by UPS that corresponds to the higher work function areas, a phenomenon that has been examined in detail by Schultz et al.⁶⁸

We have corroborated the local distribution of dopant molecules in correlation with the PEN morphology by local elemental analysis using XPEEM and spatially resolved near edge X-ray absorption fine structure (NEXAFS). In XPEEM, the sample is illuminated with photons of known energy, and an image is formed with the emitted photoelectrons. By selecting the kinetic energy of the imaging electrons, it is possible to obtain maps showing the distribution and chemical state of the different elements across the sample surface. The 1s core level and absorption edge of fluorine, present in $C_{60}F_{48}$ and absent in PEN, were the signals employed to determine unambiguously the initial adsorption of the dopant molecules.

Figure 5. 3 ML pentacene + 2 Å $C_{60}F_{48}$: (a) LEEM and (b) NEXAFS XPEEM @ F1s (692 eV) images. Field of View (F.O.V): 12.2 μm . (c) Topographic AFM image and (d) topography magnification with (e) the respective KPFM map. Each point of the curves in (f) results from integrating the F1s XPEEM intensity, at a different photoelectron energy, in the areas highlighted in (b); equivalent regions are indicated by similar coloured circles in the other images.

The growth of ~ 3 ML of pentacene resulted in the formation of typical 3D mounds consisting of single layer dendritic terraces on top of a fairly closed monolayer with only few exposed substrate (see C1s and Si2p maps in Figure S6 of the Supporting Information). Additional deposition of ~ 2 Å $C_{60}F_{48}$ is not easy to identify in the large-scale LEEM images (Figure 5a). However, the comprehensive correlation with the spatially resolved fluorine distribution observed

in the XPEEM map (Figure 5b) allows us to unequivocally claim that the dopant molecules reside at the lower regions of the PEN film surface with negligible fluorine content on the upper film levels. This observation is confirmed by the intensity-integrated signal across the absorption F K-edge (Figure 5f) at the marked areas in the XPEEM map and by the subsequent acquisition of ex-situ AFM data, i.e., measured at a different non-irradiated sample location. Note the straightforward correlation between the large-scale AFM topography of Figure 5c and the LEEM image in Figure 5a. The morphologic details (Figure 5d) and the corresponding surface potential difference (Figure 5e) are in agreement with a local coverage of $C_{60}F_{48}$ (red circle) at the lower PEN layer while higher terraces (blue circle) remain uncovered. We note that in this particular case, a certain step decoration, likely by one dimensional (1D) $C_{60}F_{48}$ chains, conciliates the lower CPD signal at the lower step edges seen at the lower right corner of Figure 5e.

Figure 6. 9 ML pentacene + 6 Å $C_{60}F_{48}$: (a) contact mode topography and friction (inset) images of PEN terraces partially covered with $C_{60}F_{48}$, (b) line profile and (c) schematics showing clearly how two $C_{60}F_{48}$ layers are decorating the PEN step edges; red dashed lines indicate PEN steps and

terraces. (d) Dynamic mode topography and (e) KPFM images (colour scale: -1.0-0.7 V). See also Figure S7 in the Supporting Information.

For thicker PEN films, in addition to the horizontal DLA within each level, an Ehrlich-Schwoebel barrier effect comes into play so that irregular mounds formation persists and the surface typically consists of pyramidal structures.⁶⁹ Figure 6 illustrates the $C_{60}F_{48}$ growth on a 9 ML PEN film, where PEN exhibits the characteristic 3D mounds-like morphology. At this growth stage, the 1st layer of the PEN film is not exposed at the surface (Figure 6a) where otherwise up to ten terrace levels can be seen. Line profile analysis (Figure 6b) demonstrates that the PEN terraces, separated by one single layer steps, are partially covered by flat aggregates (~2 nm high) with respect to the lower terrace. As revealed by the FFM contrast of the lateral force image (inset in Figure 6a), the chemical nature of such flat areas differs from that of the terraces. As indicated by their height, the compact patches correspond to two layers of fullerene molecules ($2C_{60}F_{48}$) that outcrop from the upper terrace level. We argue that $C_{60}F_{48}$ islands grow from the 1D chains of same composition that decorate the lower step edges (seen in the FFM inset), confirming the existence of a step-edge crossing barrier. An inhomogeneous distribution of $C_{60}F_{48}$ over the surface of thick PEN films is reflected in a bimodal work function landscape (Figure 6e), with a variation of ~0.5 eV, which looks uncorrelated with the pentacene morphology at this scale (Figure 6d). This observation is due, on the one hand, to the barrier for mass transport across steps and, on the other hand, to the complex epitaxial and non-epitaxial interlayer relationship developed at these PEN thicknesses (see Figure S7 in the Supporting Information).

In summary, from the different nucleation characteristics observed for the fluorinated fullerene as a function of PEN thickness, it turns out that the $C_{60}F_{48}$ – $C_{60}F_{48}$ cohesion varies from being lower than for $C_{60}F_{48}$ –PEN– SiO_2 (where the dopant disperses) to being larger than for $C_{60}F_{48}$ –PEN–PEN (where the dopant forms close-packed aggregates). We have seen the importance of crystallographic issues influencing molecular diffusion, residence time, adhesion and energy dissipation, which ultimately determine the different behaviour of $C_{60}F_{48}$ on PEN films of different thickness. In line with our results, we note that for the buckminsterfullerene (C_{60}), a PEN thickness of at least two monolayers is required to induce crystalline growth.²⁷ In the case of the PEN monolayer, one should not neglect the effect of charge transfer with the substrate that can contribute to diminish the $C_{60}F_{48}$ – $C_{60}F_{48}$ cohesion due to repulsion between charged molecules. Conversely, the presence of bilayer $C_{60}F_{48}$ aggregates on partially covered PEN terraces not in contact with the substrate is clear evidence of uncharged $C_{60}F_{48}$.

Conclusions

Considered as a fundamental issue in contact doping, this work provides a microscopic view of the dopant/OSC interface for the case of $C_{60}F_{48}$ as p-type dopant deposited on top of pentacene. To explore the effect of the PEN film morphology, we have employed AFM, KPFM, UPS, LEEM and XPEEM for investigating the deposition of $C_{60}F_{48}$ on diverse PEN films with varying nominal thickness and morphology. We find that for the PEN layer in direct contact with the native SiO_2 , a non-compact $C_{60}F_{48}$ overlayer is formed, independently of whether the PEN layer is complete (monolayer) or not (2D islands) with a subsequent change in the surface potential that increases with the dopant coverage. Conversely, the heterojunction strongly differs for the second layer of PEN where epitaxial and non-epitaxial domains coexist. Outstandingly, this crystallographic

characteristic of the film surface dramatically affects the growth dynamics of C₆₀F₄₈ that selectively aggregates on the non-epitaxial domains forming compact islands. For thicker PEN films, other mechanisms come into play such as step-edge crossing barrier for downward transport of C₆₀F₄₈. Although a single SECO (only one work function value) is seen and the HOMO of the pentacene is shifted with respect to the bare film, KPFM maps give evidence of heterogeneous electronic properties of the interface correlated with the distribution and packing of the dopant. Moreover, elemental maps permit spatially resolved observation of the local distribution of the acceptor molecules.

The results of this work show that the morphology and microstructure of the PEN film have a strong influence on the nucleation and distribution of the dopant, with the consequent impact on the electronic properties of the interface. The optimization of contact doping to reduce the contact resistance in devices will depend on the morphology of the PEN film under the contacts. In other words, the microscopic understanding of the interface enables a better control of the PEN film morphology and structure allowing a rational optimization of interface doping.

Supporting Information

Additional topographic, lateral force in the FFM and TSM modes as well as KPFM data are provided to further illustrate how to elucidate epitaxial PEN domains and C₆₀F₄₈-covered domains; complementary LEEM and XPEEM images show the spatial distribution of carbon and silicon (PDF).

Acknowledgments

This work has been supported by the Spanish government under the projects MAT2016-77852-C2-1-R (AEI/FEDER, UE) and the ‘‘Severo Ochoa’’ Program for Centres of Excellence in R&D

(SEV-2015-0496) and by the European Union's Horizon 2020 Research and Innovation Program under grant agreement No. 730872 and the Marie Skłodowska-Curie Grant Agreement No. 722651 (SEPOMO project). We also acknowledge the Generalitat de Catalunya grant 2017 SGR668. F. S. has been developing this work as part of his doctorate in Materials Science at the Universitat Autònoma de Barcelona (UAB). The SMART instrument was financially supported by the Federal German Ministry of Education and Research (BMBF) under the contract 05 KS4WWB/4, as well as by the Max-Planck Society. We thank the Helmholtz-Centre Berlin for Materials and Energy (HZB) for the allocation of beamtime 192-08486-ST. L. S. C. is grateful for the funding through the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) under Germany's Excellence Strategy – EXC 2008 – 390540038 (UniSysCat). O.S. acknowledges the support of the Israel Ministry of Science, the Center for Absorption in Science of the Ministry of Immigrant Absorption, the Committee for Planning and budgeting of the Council for Higher Education under the framework of the KAMEA Program.

References

- (1) Sekitani, T.; Someya, T. Stretchable, Large-Area Organic Electronics. *Adv. Mater.* **2010**, *22*, 2228–2246.
- (2) Inganäs, O. Organic Photovoltaics over Three Decades. *Adv. Mater.* **2018**, *30*, 1800388.
- (3) Lee, E. K.; Lee, M. Y.; Park, C. H.; Lee, H. R.; Oh, J. H. Toward Environmentally Robust Organic Electronics: Approaches and Applications. *Adv. Mater.* **2017**, *29*, 1703638.
- (4) Ostroverkhova, O. Organic Optoelectronic Materials: Mechanisms and Applications. *Chem. Rev.* **2016**, *116*, 13279–13412.

- (5) Jacobs, I. E.; Moulé, A. J. Controlling Molecular Doping in Organic Semiconductors. *Adv. Mater.* **2017**, *29*, 1703063.
- (6) Lüssem, B.; Riede, M.; Leo, K. Doping of Organic Semiconductors. *Phys. Status Solidi Appl. Mater. Sci.* **2013**, *210*, 9–43.
- (7) Mityashin, A.; Olivier, Y.; Van Regemorter, T.; Rolin, C.; Verlaak, S.; Martinelli, N. G.; Beljonne, D.; Cornil, J.; Genoe, J.; Heremans, P. Unraveling the Mechanism of Molecular Doping in Organic Semiconductors. *Adv. Mater.* **2012**, *24*, 1535–1539.
- (8) Duva, G.; Pithan, L.; Zeiser, C.; Reisz, B.; Dieterle, J.; Hofferberth, B.; Beyer, P.; Bogula, L.; Opitz, A.; Kowarik, S.; Hinderhofer, A.; Gerlach, A.; Schreiber, F. Thin-Film Texture and Optical Properties of Donor/Acceptor Complexes. Diindenoperylene/F6TCNNQ vs Alpha-Sexithiophene/F6TCNNQ. *J. Phys. Chem. C* **2018**, *122*, 18705–18714.
- (9) Tietze, M. L.; Benduhn, J.; Pahner, P.; Nell, B.; Schwarze, M.; Kleemann, H.; Krammer, M.; Zojer, K.; Vandewal, K.; Leo, K. Elementary Steps in Electrical Doping of Organic Semiconductors. *Nat. Commun.* **2018**, *9*, 1–9.
- (10) Méndez, H.; Heimel, G.; Winkler, S.; Frisch, J.; Opitz, A.; Sauer, K.; Wegner, B.; Oehzelt, M.; Röthel, C.; Duhm, S.; Többens, D.; Koch, N.; Salzmann, I. Charge-Transfer Crystallites as Molecular Electrical Dopants. *Nat. Commun.* **2015**, *6*, 8560.
- (11) Salzmann, I.; Heimel, G. Toward a Comprehensive Understanding of Molecular Doping Organic Semiconductors (Review). *J. Electron Spectros. Relat. Phenomena* **2015**, *204*, 208–222.
- (12) Salzmann, I.; Heimel, G.; Oehzelt, M.; Winkler, S.; Koch, N. Molecular Electrical Doping

- of Organic Semiconductors: Fundamental Mechanisms and Emerging Dopant Design Rules. *Acc. Chem. Res.* **2016**, *49*, 370–378.
- (13) Chen, W.; Qi, D.; Gao, X.; Wee, A. T. S. Surface Transfer Doping of Semiconductors. *Prog. Surf. Sci.* **2009**, *84*, 279–321.
 - (14) Waldrip, M.; Jurchescu, O. D.; Gundlach, D. J.; Bittle, E. G. Contact Resistance in Organic Field-Effect Transistors: Conquering the Barrier. *Adv. Funct. Mater.* **2019**, *1904576*, 1–31.
 - (15) Hou, J. L.; Kasemann, D.; Widmer, J.; Günther, A. A.; Lüssem, B.; Leo, K. Reduced Contact Resistance in Top-Contact Organic Field-Effect Transistors by Interface Contact Doping. *Appl. Phys. Lett.* **2016**, *108*, 103303.
 - (16) Ante, F.; Kälblein, D.; Zschieschang, U.; Canzler, T. W.; Werner, A.; Takimiya, K.; Ikeda, M.; Sekitani, T.; Someya, T.; Klauk, H. Contact Doping and Ultrathin Gate Dielectrics for Nanoscale Organic Thin-Film Transistors. *Small* **2011**, *7*, 1186–1191.
 - (17) Lüssem, B.; Keum, C. M.; Kasemann, D.; Naab, B.; Bao, Z.; Leo, K. Doped Organic Transistors. *Chem. Rev.* **2016**, *116*, 13714–13751.
 - (18) Xu, Y.; Sun, H.; Liu, A.; Zhu, H. H.; Li, W.; Lin, Y. F.; Noh, Y. Y. Doping: A Key Enabler for Organic Transistors. *Adv. Mater.* **2018**, *30*, 13–19.
 - (19) Olthof, S.; Tress, W.; Meerheim, R.; Lüssem, B.; Leo, K. Photoelectron Spectroscopy Study of Systematically Varied Doping Concentrations in an Organic Semiconductor Layer Using a Molecular P-Dopant. *J. Appl. Phys.* **2009**, *106*, 103711.
 - (20) Gao, W.; Kahn, A. Controlled p Doping of the Hole-Transport Molecular Material N,N'-Diphenyl-N,N'-Bis(1-Naphthyl)-1,1'-Biphenyl-4,4'-Di Amine with

- Tetrafluorotetracyanoquinodimethane. *J. Appl. Phys.* **2003**, *94*, 359–366.
- (21) Tietze, M. L.; Pahner, P.; Schmidt, K.; Leo, K.; Lüssem, B. Doped Organic Semiconductors: Trap-Filling, Impurity Saturation, and Reserve Regimes. *Adv. Funct. Mater.* **2015**, *25*, 2701–2707.
- (22) Nakayama, Y.; Mizuno, Y.; Hosokai, T.; Koganezawa, T.; Tsuruta, R.; Hinderhofer, A.; Gerlach, A.; Broch, K.; Belova, V.; Frank, H.; Yamamoto, M.; Niederhausen, J.; Glowatzki, H.; Rabe, J. P.; Koch, N.; Ishii, H.; Schreiber, F.; Ueno, N. Epitaxial Growth of an Organic P-n Heterojunction: C₆₀ on Single-Crystal Pentacene. *ACS Appl. Mater. Interfaces* **2016**, *8*, 13499–13505.
- (23) Salzmann, I.; Duhm, S.; Opitz, R.; Johnson, R. L.; Rabe, J. P.; Koch, N. Structural and Electronic Properties of Pentacene-Fullerene Heterojunctions. *J. Appl. Phys.* **2008**, *104*, 114518.
- (24) Kepman, A. V.; Sukhoverkhov, V. F.; Tressaud, A.; Labrugere, C.; Durand, E.; Chilingarov, N. S.; Sidorov, L. N. Novel Method of Synthesis of C₆₀F₄₈ with Improved Yield and Selectivity. *J. Fluor. Chem.* **2006**, *127*, 832–836.
- (25) Li, J.; Rochester, C. W.; Jacobs, I. E.; Friedrich, S.; Stroeve, P.; Riede, M.; Moulé, A. J. Measurement of Small Molecular Dopant F4TCNQ and C₆₀F₃₆ Diffusion in Organic Bilayer Architectures. *ACS Appl. Mater. Interfaces* **2015**, *7*, 28420–28428.
- (26) Breuer, T.; Witte, G. Diffusion-Controlled Growth of Molecular Heterostructures: Fabrication of Two-, One-, and Zero-Dimensional C₆₀ Nanostructures on Pentacene Substrates. *ACS Appl. Mater. Interfaces* **2013**, *5*, 9740–9745.

- (27) Huttner, A.; Breuer, T.; Witte, G. Controlling Interface Morphology and Layer Crystallinity in Organic Heterostructures: Microscopic View on C₆₀ Island Formation on Pentacene Buffer Layers. *ACS Appl. Mater. Interfaces* **2019**, *11*, 35177–35184.
- (28) Muccioli, L.; D'Avino, G.; Zannoni, C. Simulation of Vapor-Phase Deposition and Growth of a Pentacene Thin Film on C₆₀ (001). *Adv. Mater.* **2011**, *23*, 4532–4536.
- (29) Fu, Y. T.; Risko, C.; Brédas, J. L. Intermixing at the Pentacene-Fullerene Bilayer Interface: A Molecular Dynamics Study. *Adv. Mater.* **2013**, *25*, 878–882.
- (30) Kyndiah, A.; Cramer, T.; Albonetti, C.; Liscio, F.; Chiodini, S.; Murgia, M.; Biscarini, F. Charge Transfer and Percolation in C₆₀/Pentacene Field-Effect Transistors. *Adv. Electron. Mater.* **2015**, *1*, 1–7.
- (31) Melitz, W.; Shen, J.; Kummel, A. C.; Lee, S. Kelvin Probe Force Microscopy and Its Application. *Surf. Sci. Rep.* **2011**, *66*, 1–27.
- (32) Musumeci, C.; Liscio, A.; Palermo, V.; Samorì, P. Electronic Characterization of Supramolecular Materials at the Nanoscale by Conductive Atomic Force and Kelvin Probe Force Microscopies. *Mater. Today* **2014**, *17*, 504–517.
- (33) Park, J. Y.; Salmeron, M. Fundamental Aspects of Energy Dissipation in Friction. *Chem. Rev.* **2014**, *114*, 677–711.
- (34) Last, J. A.; Ward, M. D. Electrochemical Annealing and Friction Anisotropy of Domains in Epitaxial Molecular Films. *Adv. Mater.* **1996**, *8*, 730–733.
- (35) Perez-Rodriguez, A.; Barrena, E.; Fernández, A.; Gnecco, E.; Ocal, C. A Molecular-Scale Portrait of Domain Imaging in Organic Surfaces. *Nanoscale* **2017**, *9*, 5589–5596.

- (36) Kalihari, V.; Tadmor, E. B.; Haugstad, G.; Frisbie, C. D. Grain Orientation Mapping of Polycrystalline Organic Semiconductor Films by Transverse Shear Microscopy. *Adv. Mater.* **2008**, *20*, 4033–4039.
- (37) Paradinas, M.; Munuera, C.; Buck, M.; Ocal, C. In-Situ Scrutiny of the Relationship between Polymorphic Phases and Properties of Self-Assembled Monolayers of a Biphenyl Based Thiol. *J. Phys. Chem. B* **2018**, *122*, 657–665.
- (38) Glatzel, T.; Lux-Steiner, M. C.; Strassburg, E.; Boag, A.; Rosenwaks, Y. Principles of Kelvin Probe Force Microscopy. In *Scanning Probe Microscopy*; 2007.
- (39) Paradinas, M.; Garzón, L.; Sánchez, F.; Bachelet, R.; Amabilino, D. B.; Fontcuberta, J.; Ocal, C. Tuning the Local Frictional and Electrostatic Responses of Nanostructured SrTiO₃-Surfaces by Self-Assembled Molecular Monolayers. *Phys. Chem. Chem. Phys.* **2010**, *12*, 4452–4458.
- (40) Horcas, I.; Fernández, R.; Gómez-Rodríguez, J. M.; Colchero, J.; Gómez-Herrero, J.; Baro, A. M. WSXM: A Software for Scanning Probe Microscopy and a Tool for Nanotechnology. *Rev. Sci. Instrum.* **2007**, *78*, 013705.
- (41) Schmidt, T.; Marchetto, H.; Lévesque, P. L.; Groh, U.; Maier, F.; Preikszas, D.; Hartel, P.; Spehr, R.; Lilienkamp, G.; Engel, W.; Fink, R.; Bauer, E.; Rose, H.; Umbach, E.; Freund, H. J. Double Aberration Correction in a Low-Energy Electron Microscope. *Ultramicroscopy* **2010**, *110*, 1358–1361.
- (42) Schmidt, T.; Sala, A.; Marchetto, H.; Umbach, E.; Freund, H. J. First Experimental Proof for Aberration Correction in XPEEM: Resolution, Transmission Enhancement, And

Limitation by Space Charge Effects. *Ultramicroscopy* **2013**, *126*, 23–32.

- (43) Mitsumoto, R.; Araki, T.; Ito, E.; Ouchi, Y.; Seki, K.; Kikuchi, K.; Achiba, Y.; Kurosaki, H.; Sonoda, T.; Kobayashi, H.; Boltalina, O. V.; Pavlovich, V. K.; Sidorov, L. N.; Hattori, Y.; Liu, N.; Yajima, S.; Kawasaki, S.; Okino, F.; Touhara, H. Electronic Structures and Chemical Bonding of Fluorinated Fullerenes Studied by NEXAFS, UPS, and Vacuum-UV Absorption Spectroscopies. *J. Phys. Chem. A* **1998**, *102*, 552–560.
- (44) Ruiz, R.; Choudhary, D.; Nickel, B.; Toccoli, T.; Chang, K. C.; Mayer, A. C.; Clancy, P.; Blakely, J. M.; Headrick, R. L.; Iannotta, S.; Malliaras, G. G. Pentacene Thin Film Growth. *Chem. Mater.* **2004**, *16*, 4497–4508.
- (45) Meyer zu Heringdorf, F. J.; Reuter, M. C.; Tromp, R. M. Growth Dynamics of Pentacene Thin Films. *Nature* **2001**, *412*, 517–520.
- (46) Wang, S. D.; Dong, X.; Lee, C. S.; Lee, S. T. Molecular Orientation and Film Morphology of Pentacene on Native Silicon Oxide Surface. *J. Phys. Chem. B* **2005**, *109*, 9892–9896.
- (47) Mannsfeld, S. C. B.; Virkar, A.; Reese, C.; Toney, M. F.; Bao, Z. Precise Structure of Pentacene Monolayers on Amorphous Silicon Oxide and Relation to Charge Transport. *Adv. Mater.* **2009**, *21*, 2294–2298.
- (48) Fritz, S. E.; Martin, S. M.; Frisbie, C. D.; Ward, M. D.; Toney, M. F. Structural Characterization of a Pentacene Monolayer on an Amorphous SiO₂ Substrate with Grazing Incidence X-Ray Diffraction. *J. Am. Chem. Soc.* **2004**, *126*, 4084–4085.
- (49) Ruiz, R.; Nickel, B.; Koch, N.; Feldman, L. C.; Haglund, R. F.; Kahn, A.; Scoles, G. Pentacene Ultrathin Film Formation on Reduced and Oxidized Si Surfaces. *Phys. Rev. B* -

Condens. Matter Mater. Phys. **2003**, *67*, 125406.

- (50) Dimitrakopoulos, C. D.; Brown, A. R.; Pomp, A. Molecular Beam Deposited Thin Films of Pentacene for Organic Field Effect Transistor Applications. *J. Appl. Phys.* **1996**, *80*, 2501–2508.
- (51) Jones, A. O. F.; Chattopadhyay, B.; Geerts, Y. H.; Resel, R. Substrate-Induced and Thin-Film Phases: Polymorphism of Organic Materials on Surfaces. *Adv. Funct. Mater.* **2016**, *26*, 2233–2255.
- (52) Cheng, H. L.; Mai, Y. S.; Chou, W. Y.; Chang, L. R.; Liang, X. W. Thickness-Dependent Structural Evolutions and Growth Models in Relation to Carrier Transport Properties in Polycrystalline Pentacene Thin Films. *Adv. Funct. Mater.* **2007**, *17*, 3639–3649.
- (53) Salzmann, I.; Duhm, S.; Heimel, G.; Oehzelt, M.; Kniprath, R.; Johnson, R. L.; Rabe, J. P.; Koch, N. Tuning the Ionization Energy of Organic Semiconductor Films: The Role of Intramolecular Polar Bonds. *J. Am. Chem. Soc.* **2008**, *130*, 12870–12871.
- (54) Fukagawa, H.; Kera, S.; Kataoka, T.; Hosoumi, S.; Watanabe, Y.; Kudo, K.; Ueno, N. The Role of the Ionization Potential in Vacuum-Level Alignment at Organic Semiconductor Interfaces. *Adv. Mater.* **2007**, *19*, 665–668.
- (55) Sun, H.; Ryno, S.; Zhong, C.; Ravva, M. K.; Sun, Z.; Körzdörfer, T.; Brédas, J. L. Ionization Energies, Electron Affinities, and Polarization Energies of Organic Molecular Crystals: Quantitative Estimations from a Polarizable Continuum Model (PCM)-Tuned Range-Separated Density Functional Approach. *J. Chem. Theory Comput.* **2016**, *12*, 2906–2916.
- (56) Watkins, N. J.; Gao, Y. Interface Formation and Energy Level Alignment of Pentacene on

- SiO₂. *J. Appl. Phys.* **2003**, *94*, 5782–5786.
- (57) Lee, Y. M.; Kim, J. W.; Min, H.; Lee, T. G.; Park, Y. Growth Morphology and Energy Level Alignment of Pentacene Films on SiO₂ Surface Treated with Self-Assembled Monolayer. *Curr. Appl. Phys.* **2011**, *11*, 1168–1172.
- (58) Han, W.; Yoshida, H.; Ueno, N.; Kera, S. Electron Affinity of Pentacene Thin Film Studied by Radiation-Damage Free Inverse Photoemission Spectroscopy. *Appl. Phys. Lett.* **2013**, *103*, 123303.
- (59) Nell, B.; Ortstein, K.; Boltalina, O. V.; Vandewal, K. Influence of Dopant–Host Energy Level Offset on Thermoelectric Properties of Doped Organic Semiconductors. *J. Phys. Chem. C* **2018**, *122*, 11730–11735.
- (60) Kalihari, V.; Ellison, D. J.; Haugstad, G.; Frisbie, C. D. Observation of Unusual Homoepitaxy in Ultrathin Pentacene Films and Correlation with Surface Electrostatic Potential. *Adv. Mater.* **2009**, *21*, 3092–3098.
- (61) Chen, L.; Ludeke, R.; Cui, X.; Schrott, A. G.; Kagan, C. R.; Brus, L. E. Electrostatic Field and Partial Fermi Level Pinning at the Pentacene-SiO₂ Interface. *J. Phys. Chem. B* **2005**, *109*, 1834–1838.
- (62) Park, S.; Schultz, T.; Xu, X.; Wegner, B.; Aljarb, A.; Han, A.; Li, L. J.; Tung, V. C.; Amsalem, P.; Koch, N. Demonstration of the Key Substrate-Dependent Charge Transfer Mechanisms between Monolayer MoS₂ and Molecular Dopants. *Commun. Phys.* **2019**, *2*, 1–8.
- (63) Zhang, J.; Rabe, J. P.; Koch, N. Grain-Boundary Evolution in a Pentacene Monolayer. *Adv.*

Mater. **2008**, *20*, 3254–3257.

- (64) Wu, Y.; Toccoli, T.; Zhang, J.; Koch, N.; Iacob, E.; Pallaoro, A.; Iannotta, S.; Rudolf, P. Key Role of Molecular Kinetic Energy in Early Stages of Pentacene Island Growth. *Appl. Phys. A Mater. Sci. Process.* **2009**, *95*, 21–27.
- (65) Amassian, A.; Pozdin, V. A.; Desai, T. V.; Hong, S.; Woll, A. R.; Ferguson, J. D.; Brock, J. D.; Malliaras, G. G.; Engstrom, J. R. Post-Deposition Reorganization of Pentacene Films Deposited on Low-Energy Surfaces. *J. Mater. Chem.* **2009**, *19*, 5580–5592.
- (66) Puntambekar, K.; Dong, J.; Haugstad, G.; Frisbie, C. D. Structural and Electrostatic Complexity at a Pentacene/Insulator Interface. *Adv. Funct. Mater.* **2006**, *16*, 879–884.
- (67) Zhang, Z.; Chen, X.; Lagally, M. G. Bonding-Geometry Dependence of Fractal Growth on Metal Surfaces. *Phys. Rev. Lett.* **1994**, *73*, 1829–1832.
- (68) Schultz, T.; Lenz, T.; Kotadiya, N.; Heimel, G.; Glasser, G.; Berger, R.; Blom, P. W. M.; Amsalem, P.; de Leeuw, D. M.; Koch, N. Reliable Work Function Determination of Multicomponent Surfaces and Interfaces: The Role of Electrostatic Potentials in Ultraviolet Photoelectron Spectroscopy. *Adv. Mater. Interfaces* **2017**, *4*, 1700324.
- (69) Hlawacek, G.; Puschnig, P.; Frank, P.; Winkler, A.; Ambrosch-Drax, C.; Teichert, C. Characterization of Step-Edge Barriers in Organic Thin-Film Growth. *Science* **2008**, *321*, 108–111.

TOC

Supporting Information

Impact of Nanomorphology in Surface Doping of Organic

Semiconductors: The Pentacene-C₆₀F₄₈ Interface

Francesco Silvestri, Mauricio J. Prieto,² ¹Adara Babuji,¹ Liviu C. Tănase,² Lucas de Souza Caldas,² Olga Solomeshch,³ Thomas Schmidt,² Carmen Ocal,^{1} and Esther Barrena^{1*}*

¹ Instituto de Ciencia de Materiales de Barcelona (ICMAB-CSIC), 08193 Bellaterra, Barcelona,
Spain

² Department of Interface Science, Fritz-Haber Institute of the Max Planck Society, 14195 Berlin,
Germany ³ Electrical Engineering Department, Nanoelectronic Center, Technion, Haifa 32000,
Israel

*ebarrena@icmab.es

As mentioned in the main text, for a sub-monolayer coverage, pentacene grows on SiO₂ forming rounded single layer (1L) islands but some double layer (2L) islands are also observed. Friction Force Microscopy (FFM) allows imaging the friction properties of the surface, which can give a hint on the order and packing of the molecules. As shown in Figure S1, the islands appearing lighter in colour (higher) in the topographic images (a,c) give a darker contrast (lower friction) in the corresponding forward lateral force images (b,d). This is attributed to the epitaxial relationship between the two layers. Importantly, such epitaxial 2L islands will be the cores of the dendritic islands forming once the 1st layer is complete.

Figure S1. (a) Topographic and (b) simultaneously measured forward lateral force images of a sub-monolayer of pentacene on native SiO₂. (c) and (d) are magnified images of the areas marked by dashed squares in (a) and (b), respectively.

Figure S2. Topographic image of 0.8 ML PEN + 14 Å C₆₀F₄₈ on native SiO₂. Blue lines are used to indicate in one of the PEN islands, the formation of dense C₆₀F₄₈ aggregates.

The working principles of Transverse Shear Microscopy (TSM) imaging are the same as for FFM where the lateral deflection of the cantilever is detected while scanning over the surface to produce the final images. The only difference is that, while in FFM the cantilever is scanned perpendicularly to its axis, in TSM the cantilever is scanned parallel to its axis. This simple practical difference results in interesting advantages of such imaging tool, as discussed in [1], which can complement the conventional FFM measurements. Figure S3 shows the comparison between FFM (Figure 2 of the main text) and TSM. While in FFM (b) the 1st layer domains with random azimuthal orientation are only vaguely distinguished and the boundaries quite blurry, TSM (c) allows to sharply visualize such domains due to a higher sensitivity to the azimuthal orientation of the domains.

Figure S3. (a) Topography, (b) FFM and (c) TSM images of a 1.3 ML pentacene film. 1st and 2nd layer are indicated by the white arrows, while black arrows in the sketches indicate the scanning direction. Magnified (d) topography and (e) lateral force (forward) images of a pentacene island. Note: dark areas in the lateral force image correspond to lower friction areas.

Figure S4 shows the topographic image of the same 1.3 ML pentacene film shown in Figures 2 in the manuscript and S3, measured 3 months after film deposition. The sample was stored in air.

We observe a general increase of the surface roughness in both 1st and 2nd layers and the clear appearance of cracks in the 1st layer. By comparing with Figures S3 we can safely state that the cracks appear at the boundaries of the 1st layer rotational domains. The opening of such cracks can be attributed to a densification process within the domains to the detriment of the less-packed and highly defective domain boundaries after prolonged storage in air. Interestingly, a similar effect seems to occur upon C₆₀F₄₈ deposition due to the interaction between pentacene and the dopant.

Figure S4. Topographic image of the same 1.3 ML pentacene film shown in Figures 2 of the main text and S3, taken 3 months after deposition (stored in air at room temperature).

Figure S5 shows the AFM images of another island from the same sample depicted in Figure 3c-d of the main text. This island shows the same features of what is shown in the main text, such as a 2L pentacene island selectively covered with C₆₀F₄₈ in the non-epitaxial domains, plus the presence of the 3rd pentacene layer partially covering the core of the island. The presented line profile confirms the expected height difference between 2nd and 3rd layers to be about 1.5 nm. Furthermore, the height difference between uncovered 2L core and covered branches is estimated

to be about 2.0-2.3 nm, in agreement with the presence of two layers of $C_{60}F_{48}$. The corresponding line profile of the KPFM image indicates a difference in contact potential difference (CPD) of about 0.5 V between uncovered core and covered branches.

Figure S5. (a) Topographic and (b) KPFM images of another island of the same sample shown in the main text, Figures 3c-d (PEN (1.3 ML) + $C_{60}F_{48}$ (14 Å)); (c) Line profiles along the arrows drawn in the corresponding images.

Figure S6 shows the case of a ~3 ML pentacene film by comparing LEEM, Si2p- and C1s-XPEEM images. This case illustrates how putting together the complementary information extracted from the different images we are able to precisely define chemically the investigated system. As shown by XPEEM @ C1s (c), the whole surface is covered with carbon apart from

small (darker) areas which exactly correspond to the bright areas in the XPEEM @ Si2p image (b), meaning they correspond to uncovered silicon oxide. Consistently, in the same image (b) we also see medium-dark and dark areas representing the 1st and the following pentacene layers (darker in Si2p meaning thicker layer on top, i.e. higher carbon content), respectively. Finally, LEEM allows us to adscribe those areas to the different levels of the 3D pyramid-like mounds.

Figure S6. (a) LEEM, (b) XPEEM @ Si2p, and (c) XPEEM @ C1s images of a 3 ML pentacene film. Field of View in all cases is 12.2 μm .

As commented in the main text, for thicker pentacene films, $\text{C}_{60}\text{F}_{48}$ distributes non-homogeneously on the surface and, at large scale, it is not trivial to define a clear correlation between topography and KPFM images. Figure S7a-b shows contact mode AFM images of a 4 ML pentacene film + $\text{C}_{60}\text{F}_{48}$ (6 Å) where the friction landscape appears quite varied and not easy to correlate to topographic features, in agreement with the inhomogeneity observed in KPFM images. Darker areas in the FFM friction correspond to uncovered pentacene domains, likely due to a selective growth similar to the one observed in the 2nd layer islands (Figure 3 in the manuscript). The large z-range needed to scan several microns wide areas, makes it difficult to distinguish locally between bare and $\text{C}_{60}\text{F}_{48}$ covered pentacene terraces and, therefore, the appearance of the KPFM is inhomogeneous (Figure 6e in the manuscript). For smaller scale images

though, as the ones presented in Figure S7c-d, the correlation is actually evident. The line profile in Figure S7e demonstrates the presence of compact islands of $C_{60}F_{48}$ with height corresponding to two layers ($2 C_{60}F_{48}$); such areas appear darker in the KPFM image. The difference in CPD between covered and uncovered areas is of about 0.2 V, as shown in the histogram of Figure S7f.

Figure S7. (a) Topographic and (b) lateral force images of pentacene (4 ML) + $C_{60}F_{48}$ (20 Å). (c) Topographic and (d) KPFM images of the sample shown in the main text Figure 6 (PEN (9 ML) + $C_{60}F_{48}$ (6 Å)) with (e) line profile and (f) CPD histogram, respectively along the segment and over the rectangle in the corresponding images.

References

- (1) Perez-Rodriguez, A.; Barrena, E.; Fernández, A.; Gnecco, E.; Ocal, C. A Molecular-Scale Portrait of Domain Imaging in Organic Surfaces. *Nanoscale* **2017**, 9, 5589–5596.