**EFFECT OF AN OBSTACLE DURING PROCESSING ON
THE WELD LINE OF INJECTION-MOLDED GLASSY
POLYSTYRENE: MICROHARDNESS STUDY**

T. Nguyen-Chung and G. Mennig

*Lehrstuhl fuer Kunststoffverarbeitungstechnik, Technische Universitaet
Chemnitz, Reichenheiner Str. 70, 09126 Chemnitz, Germany*

M. Boyanova*, S. Fakirov*, F.J. Balta Calleja**

*Instituto de Estructura de la Materia, CSIC, Serrano 119, 28006 Madrid,
Spain*

Paper submitted to: *Journal of Applied Polymer Science*

October 2003

* Permanent address: Sofia University, Laboratory on Polymers,
1126 Sofia, Bulgaria

** Author for correspondence. E-mail: imtb421@iem.cfmac.csic.es

ABSTRACT

The microhardness (H) technique is used to characterize the quality of the weld line in injection-molded glassy polystyrene (PS) by means of a cylindrical obstacle. In particular, the effect of the indentation location (closer or further from the obstacle edge parallel to the injection direction and across the weld line), both, on the surface and in the bulk has been examined. Only for surface measurements close to the obstacle (up to 10 mm) a well pronounced H-decrease (around 30%) followed by a sharp increase in a narrow distance (0.20 – 0.25 mm), is observed. For the bulk measurements on the same location a slight decrease in H is detected. Additional H measurements made up to 60 mm from the obstacle for both cases show that the weld line remains undetectable. The results obtained reveal that the presence of a cylindrical obstacle causes the formation of a weld line on and near the surface only at distances not exceeding the obstacle diameter. At larger distances, due to the effective mutual inter-diffusion of polymer chains, the two parallel fronts coming from the two sides of the obstacle develop a homogeneous material without any weld line according to the microhardness test.

Key words: Microhardness, Polystyrene, Injection molding with obstacle, Weld line

INTRODUCTION

The use of microhardness (H) to characterize the changes in microstructure, molecular orientation and micromechanical properties of injection-molded polymer materials has been the object of increasing interest.¹⁻⁴ In addition, it is known that process variables induce important changes in the microstructure and properties of injection molded materials.^{5,6} Hardness variations often occur in the surface and across the thickness of the molded samples. As a result, the mechanical properties can be controlled by processing variables such as melt and mold temperature, injection pressure, mold design, etc.²

Earlier studies⁷ have been shown that microhardness may give useful information about the correlation between processing parameters near and at the weld line or knit line, i.e. the region at which the separated melt fronts reunite. In practice, this occurs in injection molding, e.g. after a flow obstacle or in case of multiple gating for melt streams of the same material or in case of two-component injection molding for melt streams of different polymer materials.⁸

In a previous study we reported⁹ on the H variation across the weld line arising when the two opposite flow fronts fill the cavity of the mold using two glassy polymers, polycarbonate (PC) and polystyrene (PS). A large hardness difference between H measured away from the weld line and H measured at $z = 0$ ($H_{\min}$) was found. For PC this difference was about 20 MPa ($\sim 14\%$) while for PS it was larger than 50 MPa ($\sim 30\%$).⁹ The measurement of H along the injection direction and across the weld line for the PC and PS samples containing a pigment for better visualization of the flow front, was also performed.⁹ For both polymers, the measured higher H values on the side containing the pigment show the hardening effect of the pigment within the polymer. Such an asymmetry is contrasting to the case without using pigment.⁹

In a more recent work we extended the above studies on the same two glassy polymers (PC and PS) processed using a two-component injection molding system.¹⁰ Specifically, the influence of processing temperature on the H value across the weld line arising when the two opposite flow fronts meet cohen filling the cavity of the mold, was examined. It was found¹⁰ that the broadening of the weld line (expressed in the microhardness changes across the line $z = 0$) depends primarily on opportunities for mutual chain diffusion from the two polymer fronts coming from opposite sides. Such a case is very close to the well studied phenomenon of physical healing^{11,12} where the mutual inter-diffusion is determined by chain flexibility and diffusion conditions (temperature, molecular weight, etc.). Furthermore, it was shown¹⁰ that the main factors affecting the quality of the welding at the line $z = 0$ are the glass transition temperature (T_g) of the polymer under investigation and the processing conditions: melt temperature, mold temperature, injection speed and others.

The aim of the present report is to extend the above studies^{9,10} on glassy PS processed by injection molding using a mold with a cylindrical obstacle. In addition, for the sake of comparison, the measurements are carried out on the surface of the molded plate as well as on the “bulk” surface after cutting and polishing at different locations with reference to the obstacle edges across the injection direction.

EXPERIMENTAL

Materials

High molecular weight polystyrene (PS 165 H, BASF) ($T_g = 100^\circ\text{C}$) samples were used in this study. The moldings were prepared in the form of rectangular plates of 100 x 80 x 2 mm with a circular obstacle (diameter of 12 mm). The plates were molded using a melt temperature (T_m) of 240°C and a mold temperature (T_w) of 50°C . The injection rate was $10 \text{ cm}^3/\text{s}$. From the central part of an injection molded plate, containing the weld line, six test samples were cut and embedded in a thermoset resin in order to enhance their fixing during polishing and subsequent measurements.

Techniques

Microhardness was measured across the boundary (weld line) at the surface of every test sample using a microindentation tester with a Vickers diamond indenter. The hardness value (in MPa) was computed from the residual projected diagonal impression, using $H = kP/d^2$, where P is the applied force in N, k is a geometrical constant equal to 1.854, and d is the length of the projected indentation diagonal in m. A load of $P = 25$ mN and a loading cycle of 6 s were used. Indentations were made on a line (designated further as z) perpendicular to the injection direction (Fig. 1).

Two types of H measurements were carried out:

1) Measurements on the surface of the plates (Fig. 1)

One indentations series was performed at five different positions (O1 to O5) behind the obstacle (O), and one indentation series before the obstacle (O-1), as depicted in Fig. 1. The location of each series on the weld line is shown in Fig. 1. At every series the respective test distance z across the weld line is 2 mm (1 mm from each side).

2) Measurements in the planes perpendicular to the weld line (on the "bulk" surface) (Fig. 2)

Six test samples (P1 to P6, Fig. 2a) were taken from a plate in such a way that the cut surfaces (S1 to S6, Fig. 2a) are equidistant. On every cut surface two test series were performed. The first one was carried out along a line which is parallel to the surface of the sample at a distance of 0.1 mm from the edge and designated further as S1 A. The second test sequence was run through the middle of the gap of the sample and designated further as S1 B. The two test series have a length $z = 2$ mm across the weld line. This situation is schematically presented in Fig. 2b.

Optical micrographs from the indentation surface (Fig. 1) were taken using a Leitz (Germany) light microscope in the reflection mode.

RESULTS AND DISCUSSION

Figure 3 illustrates an optical micrograph of several indentations made on the vicinity of the weld line. In contrast to previous measurements⁹ in which practically only one indentation characterized the steep decrease of H near the weld line, in the present case, according to our recent experience,¹⁰ the same line is defined by at least 5 indentations which makes the reported H -decrease more reliable.

Furthermore, the H -values are plotted as a function of the distance z from the weld line for the two types of measurements – on the mold surface (Fig. 1) and on the bulk surface (Fig. 2b).

Microindentation hardness on the surface

Figure 4 illustrates the H -variation as a function of z , for various indentation series placed at various distances from the obstacle (up to 60 mm) on the surface of the molding along the injection direction (Fig. 1). For the sake of comparison a measurement before the obstacle (O-1, Fig. 1) was also carried out. The indentation series were performed perpendicular to the weld line as shown in Fig. 1, and denoted by O-1 to O5. The (O) point denotes the center of the obstacle, and the (O-1) – the indentation series before the obstacle. We denote the position of the weld line as $z = 0$.

Results show a rather different microhardness behavior depending on the location, before or after the obstacle (O) and particularly how far the test location was from the obstacle (Fig. 1). First of all, one has to stress the fact that, in accordance with expectation, before the obstacle there is no indication for the existence of any weld line (Fig. 4, curve O-1), where rather constant values of H of about 210 MPa are observed.

The situation changes drastically with the first measurement after the obstacle (Fig. 1, O1) being situated closest to the obstacle. Figure 4, curve O1 shows the *gradual* decrease of H along the z direction, until a minimum value at $z = 0$ is reached. Then, one observes a further increase of H when

indenting away from $z = 0$. The weld line zone containing the H changes is defined within a 0.20 – 0.25 mm region which is much smaller than the previously reported one (1 mm) for the same polymer⁹ and about the same in a more recent measurement (0.20 – 0.30 mm).¹⁰

Most interesting is to note the large hardness difference found between H measured away from the weld line and H measured at $z = 0$ ($H_{\min}$). This difference is about 70 MPa ($\sim 30\%$) (Fig. 4, curve O1). The same difference is getting smaller (about 35 MPa) for the next measurement series being further away from the obstacle (Fig. 4, curve O2).

The H values measured at even larger distances from the obstacle (O) (Fig. 1) look completely different as can be concluded from the rest of results presented also in Fig. 4 (curves O3 - O5). There is no drop in the H values around the weld line ($z = 0$) larger than the observed scattering of the experimental points. What is more, the lines observed (Fig. 4, curves O3 – O5) as well as the H values obtained are the same as those for the test before the obstacle (Fig. 4, curve O-1). These results appear to indicate that after some distance from the obstacle (around 5 – 10 mm in the present case, being of order of magnitude of the obstacle diameter), the obstacle does not have any further influence on the melt flow in the sense of formation of a weld line. Similar findings are known from literature (e.g. ref. 13).

Microindentation hardness on the bulk surface

The results from H evaluation performed on the bulk surface after cutting and polishing (Fig. 2) lead to the same conclusion (see Fig. 5).

It should be noted again that H measurements at a distance of 0.1 and 1 mm from the starting (Fig. 2a) sample surface edge (as shown in Fig. 2b) were performed. The values obtained are practically the same (compare curves S1A and S1B in Fig. 5).

The H values from the closest location to the obstacle show again a minimum around $z = 0$ (Fig. 5, curves S1A and S1B) similarly to the case

with the measurements on the surface of the injection molded plates (Fig. 4, curve O1). The main difference between the two cases (Figs. 4 and 5) is the degree of the H changes. In the last case the drop in H is only a few percent and indicates only not a very well defined weld line.

H measurements at larger distances from the obstacle (Fig. 2a, samples P2 – P6) show that even this small decrease in H (Fig. 5, curves S1A and S1B) is not anymore present (Fig 5, curves S2 to S6) (the data obtained from samples S3 and S5 are not plotted in Fig.5). From the results of the bulk surface measurements (Fig. 5) one can conclude that very close to the obstacle edge (around 5 mm) only a slight indication for the existence of weld line can be detected. For larger distances there are no hints for the existence of such a weld line.

Influence of the temperature

Regarding the influence of the indentation's location, namely, closer or further apart from the obstacle (or with other words from the formed hole edge) it should be noted that the differences observed (Figs. 4 and 5) are mostly related to the temperature of the two fronts at the instant they meet. Let us try to get an idea about the temperature difference of the melt closer or further from the obstacle wall.

When the polymer melt comes in contact with the cylindrical obstacle, it splits into two fronts. What is of particular importance for these two fronts is that being in contact with the obstacle (with a temperature $T_w = 50^{\circ}\text{C}$) they decrease significantly their initial starting temperature of 240°C . For this reason when the two fronts meet immediately after the obstacle there is no mutual chain diffusion resulting in a randomization and homogenization. As a consequence a more or less well developed weld line can be detected at the locations closest to the obstacle.

The reminder of the two melt flows being not in contact with the obstacle do not experience its cooling effect and for this reason when they meet behind

the obstacle they preserve their cavity temperature typical for this part of the mold which allows their homogenization without formation of any weld line.

This consideration is supported also by the observation that even for measurement locations being closest to the obstacle but performed on the original sample surface (Fig. 4) or on the "bulk" surface (Fig. 5) the weld line is differently expressed (compare curves O1 and O2 of Fig. 4 with curves S1 A and S1 B of Fig. 5). Since the melt in the middle part of the sample is not in a direct contact with the mold cavity walls, their welding conditions are more favorable as compared with those on the sample surface.

The above interpretation (effect of melt temperature and location of the microindentations across the welding line as derived from the H measurements on the surface and in the bulk of glassy PS processed using a mold with cylindrical obstacle) supports the analogous measurements on PS and PC both processed at two melt temperatures but the same mold temperature on a two-component injection molding machine. Again the dominating role of the melt temperature, particularly when the two polymer fronts meet, is stressed. One should note here that the case under discussion is very close to the well studied phenomenon of physical healing^{11,12} where the mutual interdiffusion is determined by chain flexibility and diffusion conditions (temperature, molecular weight, etc.).

CONCLUSIONS

1. In agreement with preceding results,^{9,10} microhardness is showing to be an appropriate technique which can accurately define the region across the weld line in injection molded parts and can furnish information about the local degree of mutual inter-diffusion within the weld boundary.
2. The broadening of the weld line, as well as its appearance and disappearance (expressed in the microhardness changes across the $z = 0$), depends primarily on the possibility for mutual chain diffusion from the two polymer fronts meeting behind the obstacle.

3. It is shown that welding behind the obstacle is more effective in the bulk than on the surface of the injection molded sample.

ACKNOWLEDGEMENTS

Grateful acknowledgement is due to the MCYT, Spain (Grant BFM2000-1474) and DFG, Germany (Me 563/22-2) for the generous support of this investigation. One of us (S.F.) deeply appreciates the financial support of NATO – Spain for the award of a fellowship making possible his stay at Instituto de Estructura de la Materia, CSIC, Madrid, where this study was carried out. S.F. and M.B. acknowledge also the hospitality of the same Institute.

REFERENCES

1. Baltá Calleja, F.J.; Baranowska, J.; Rueda, D.R.; Bayer, R.K. *J Mater Sci* 1993, 28, 6074.
2. Rueda, D.R.; Kubera, L.; Baltá Calleja, F.J.; Bayer, R.K. *J Mater Sci Lett* 1993, 12, 1140.
3. Flores, A.; Bayer, R.K.; Krawitz, K; Baltá Calleja, F.J. *J Macromol Sci Phys* 2000, B 39, 749.
4. Ania, F; Dunkel, M; Bayer, R.K.; Baltá Calleja, F.J. *J Appl Polym Sci* 2002, 85, 1246.
5. Birley, A.W.; Hawort, B.; Batchelor, J. *Physics of Plastics: Processing, Properties and Materials Engineering*; Hanser Publ: Munich, 1992
6. Eder, G.; Janeschitz-Kriegl, H.; Liedauer, S. *Prog Polym Sci* 1990, 15, 629
7. Heck, S.; Poellet, P. *VDI-Bericht* 1989, 731, 167
8. Nguyen-Chung, T.; Plichta, C.; Mennig, G. *Rheol Acta* 1998, 37, 299
9. García Gutiérrez, M.C.; Rueda, D.R.; Baltá Calleja, F.J.; Kuehnert, I.; Mennig, G. *J Mater Sci Lett* 1999, 18, 1237
10. Boyanova, M.; Baltá Calleja, F.J.; Fakirov, S.; Kuehnert, I.; Mennig, G. *Adv Polym Technol* (submitted).
11. Kausch, H.H. *Polymer Fracture*, Springer: Heidelberg-New York, 1987
12. Wool, R.P. *Polymer Interfaces*, Hanser: Munich-New York, 1996
13. Mennig, G. *Angew Makromol Chem* 1991, 185/186, 179

FIGURE CAPTIONS

Figure 1: Schematics of an injection molded plate with an obstacle. The weld line is parallel to the injection direction and the indentation measuring directions are perpendicular to the weld line.

Figure 2: Schematics of the location of six test samples for microindentation measurements: a) in the plane perpendicular to the weld line, and b) test positions with respect of the weld line and edge of the sample.

Figure 3: Micrograph showing indentation on the surfaces of the injection molded plate near the weld line area (see Fig. 1).

Figure 4: Microhardness, H , as a function of distance z from the weld line measured on the surface of the molded plate with obstacle for glassy PS. The curves are denoted according to Fig. 1.

Figure 5: Microhardness, H , as a function of distance z from the weld line measured on the “bulk” surface of the molded plate with obstacle for glassy PS. The curves are denoted according to Fig. 2a.

Fig. 2

Fig 3

Fig 4

Fig 5.