**Importance of biomass and binder selection for coking briquette preparation.
Their effect on coal thermoplastic properties.**

L. Florentino-Madiedo^a, E. Díaz-Faes^a, C. Barriocanal^{a*}, M. Castro-Díaz^b, C. E. Snape^b

^a Instituto Nacional del Carbón, INCAR-CSIC, Apartado 73, 33080 Oviedo, Spain

^b Department of Chemical and Environmental Engineering, University of Nottingham,
Nottingham NG7 2RD, United Kingdom

*Corresponding author: carmenbr@incarc.csic.es

Abstract

Blends consisting of a high volatile bituminous coal, biomass and binder that were used in the preparation of briquettes were analyzed in order to select the best components from the viewpoint of their influence on the coal's thermoplastic properties. The raw materials were studied by means of thermogravimetry, high-temperature rheometry, high-temperature proton nuclear magnetic resonance (¹H NMR) and Fourier transform infrared (FTIR) spectroscopy. In addition, the fluidity of the blends was determined with the standard Gieseler plastometer test method (ASTM D 2639-74). Various parameters derived from these different techniques were used to explain the effects of biomass and binder on the fluidity of the blends with coal. It was found that the deleterious effect of biomass was mainly related to its physical properties, whereas the effect of the binder was controlled by its chemical composition. Coal tar, coal tar sludge, pine sawdust and a bio-coal derived from hydrothermally treated waste biomass obtained from pruning were the best materials for the preparation of briquettes for cokemaking.

Keywords

Biomass, coal, binder, briquettes, fluidity.

1. Introduction

The use of additives has been common practice for many years in the cokemaking industry as a means to reduce costs, widen the range of raw materials that can be introduced into blends used for the preparation of metallurgical coke and recycle wastes produced in-situ and ex situ.¹⁻⁶

In recent years, the use of biomass as an additive to coal blends, in order to produce metallurgical coke, has been envisaged as a possible solution for reducing the generation of non-renewable CO₂ emissions by the steel industry and for promoting the use of low-cost raw materials to replace expensive prime coking coals.⁷⁻⁹ The direct addition of sawdust to industrial coal blends has been investigated but the resultant decrease in bulk density diminishes the quality of the coke.⁷ It was also found that biomass produces a decrease in the fluidity of coal even at low addition levels of 0.75 wt%.

It has been proposed that the decrease in bulk density caused by the introduction of biomass in coal blends can be overcome with the use of briquettes. The quality of the coke produced from blends containing briquettes has been compared with the direct addition of un-briquetted components, with favorable results towards the use of briquettes.¹⁰

The use of coal tar as binder in the briquettes can compensate to some extent for the decrease in fluidity produced by the biomass. However, coal tar also leads to the formation of a large amount of polycyclic aromatic hydrocarbons (PAHs) during carbonization,¹¹ which are considered to be dangerous to human health by the US Environmental Protection Agency (EPA). Hence, in the present research work other

binders that are less pollutant, such as paraffin,¹² have been studied and compared with coal tar. Moreover, the thermoplastic properties of blends containing coal and biomass differ depending on the type of biomass used.¹³ Therefore, four different biomass samples have been selected in this study in order to obtain a more comprehensive understanding of the mechanisms that control fluidity development in the blends.

Due to the importance of the coal plastic stage in the formation of the structure of coke, several conventional methods are currently used to measure coal thermoplasticity. Among these methods, the Gieseler¹⁴ and Brabender¹⁵ plastometers provide information about the softening, maximum fluidity and resolidification stages of coal. Novel techniques such as proton magnetic resonance thermal analysis (PMRTA)¹⁶ and high-temperature ¹H NMR¹⁷ have been used to measure the concentration and mobility of fluid hydrogen of carbonaceous materials during pyrolysis. High-temperature small-amplitude oscillatory-shear (SAOS) rheometry is another technique that can provide direct information about the viscoelastic properties of the bulk mass of coals in their thermoplastic temperature range.¹⁸

The aim of the present work is to determine the combination of biomass and binder that has the least deleterious effect on the thermoplastic properties of a low rank bituminous coal, and whenever possible, to correlate the results with the properties of the raw materials.

2. Materials and Methods

2.1. Materials

An American low rank bituminous coking coal with high volatile matter content (ca. 31.5 wt%) and high Gieseler maximum fluidity (ca. 26000 ddpm) was used to prepare binary and ternary blends using eight different additives, namely four biomass wastes and four binders. The biomass samples were a pine sawdust obtained as waste from the timber industry (SP), the pine sawdust torrefied in a rotary oven of 95 mm diameter at 300 °C for half an hour under a 250 ml/min N₂ flow (SPT), pine Kraft lignin from the production of cellulose (Lg), and a commercial bio-coal derived from hydrothermally-treated waste biomass obtained from pruning (BIOC). The binders used included molasses from the sugar industry (Mol), paraffin (Par), coal tar (T) and coal tar sludge (CTS). T, CTS and Mol are liquids and Par is solid at room temperature. The bituminous binders T and CTS were obtained as by-products in an industrial coke plant. T was separated from the raw coke oven gas in the by-products plant and CTS was collected at the sole of the tar decanter. CTS not only contains tar and water but also fine particles of coal and coke, which are drawn away and deposited at the bottom of the tar decanter. Mol and CTS can be considered as waste materials while Par and T are commercial products. All these materials were characterized through proximate and ultimate analysis. Proximate analysis was carried out following the standard ISO 562 and ISO 1171 procedures for humidity, ash and volatile matter, respectively. Ultimate analysis was performed using the standard method ASTM D 5373-02 for the determination of C, H and N using a LECO CHN-2000 instrument and the standard method ASTM D 5016-98 for the determination of S using a LECO S-144 DR instrument. The characteristics of the materials are presented in **Table 1**. The maceral composition of the bituminous coal is as follows: 77.9% vitrinite, 8.4% liptinite, 8.0% semifusinite, 2.0% fusinite and 3.7% inertinite.

2.2. Thermogravimetric analysis

Thermogravimetric analysis (TGA) was carried out using a TA Instruments SDT 2960 thermobalance. Approximately 10 mg of sample with a particle size < 0.212 mm were heated under a N₂ flow of 100 ml/min from room temperature to 1000 °C at a rate of 3 °C/min.¹⁹

2.3. Fourier transform infrared

Fourier transform infrared (FTIR) spectra were recorded on a Nicolet Magna-IR560 spectrometer equipped with a multi-bond ZnSe crystal attenuated total reflection (ATR) accessory and a DTGS detector. The spectra were collected over 128 scans at a resolution of 4 cm⁻¹ in the 4000–500 cm⁻¹ range. In order to facilitate comparison of the spectra, two semi-quantitative indices were defined (Table 2). The degree of aromaticity can be calculated by dividing the area of aromatic C–H groups (A_{ar}) by the sum of the areas of aromatic and aliphatic C–H groups ($A_{ar} + A_{al}$). However, some biomass samples did not present a visible peak for aromatic C–H groups (i.e. $A_{ar} \approx 0$). Thus, the area of aromatic C=C groups ($A_{C=C}$) divided by the area of aliphatic C–H groups (A_{al}) was used instead to determine the degree of aromaticity of the samples.

2.4. High-temperature ¹H nuclear magnetic resonance

A Doty 200 MHz ¹H nuclear magnetic resonance (NMR) probe was used in conjunction with a Bruker MSL300 instrument to determine the development of fluidity in the raw materials. A detailed description of this technique has been published elsewhere.²⁰ Approximately 140–150 mg of sample (63–212 μm) was loosely packed inside a boron nitride container, and 100 scans were accumulated using a recycle delay of 0.3 s. All samples were analyzed at a heating rate of 3 °C/min. Spectra were acquired from 25 °C to 400 °C for the biomass samples, from 25 °C to 500 °C for the binders and from 360 °C

to 500 °C for the coal. The spectra were deconvoluted into Gaussian and Lorentzian distribution functions. The area of the Lorentzian peak multiplied by 100 and divided by the total area of the NMR signal represents the concentration of fluid H in the sample, and the width of the Lorentzian peak at half height is inversely proportional to the mobility of the fluid H or spin-spin relaxation time (T_{2L}).

2.5. High-temperature SAOS rheometry

High-temperature small-amplitude oscillatory shear (SAOS) measurements were performed using a Rheometrics RDA-III high-torque controlled-strain rheometer²¹. Approximately 1.5 g of sample with a particle size of 63–212 μm were compacted with a hydraulic press under a 5-ton force to form discs of 25 mm in diameter. The biomass and coal samples, as well as the 95:5 wt/wt blends of coal with biomass and coal with binder were analyzed. Also, blends of coal pre-heated in N₂ to 466 °C (C466) with binder in the same ratio (95:5 wt/wt) were tested in order to assess the degree of viscosity of the binder. The coal was pre-heated to reduce its volatile matter content, which causes scattering of the data, and to make clear the influence of the binder on the complex viscosity of the blend. The pre-heating of the coal was conducted following fast heating at 40 °C min⁻¹ from room temperature to 520°C. In this process the coal temperature was monitored using a thermocouple inside the furnace, the final temperature detected for the sample was 466 $\pm$ 2 °C. During the experiments, the biomass samples were heated from 50 °C to 400 °C at 3 °C/min. The coking coal and the blends of coal with binders or biomass samples were heated from room temperature to 330 °C at around 85 °C/min and from 330 °C to 500 °C at 3 °C/min. The complex viscosity was calculated using Eq. (1), where G' is the storage or elastic modulus, G'' is the loss or viscous modulus and ω is the frequency.²¹

$$\eta^*(\text{Pa.s}) = \frac{\sqrt{\{G'(\text{Pa})\}^2 + \{G''(\text{Pa})\}^2}}{\omega} \quad (1)$$

2.6. Briquette preparation

In order to optimize the composition of the briquettes, various trial runs were carried out in a briquetting press under a constant pressure of 100 bar. The briquettes were cylindrical in shape with 40 mm in diameter. The coal content in the briquette was always 70 wt%. The amount of biomass was kept at 15 wt% except when molasses were used as binder, in which case 20 wt% was the quantity employed. The briquettes also contained 15 wt% of binder except in the case of briquettes containing molasses, for which 10 wt% was used. Different amounts of binder were tested in the preparation of the briquettes but the total percentage of biomass plus binder was kept constant in order to compare the individual effects of these components. None of the liquid binders drained during pressing. The nomenclature used was, for example, T-Lg for a briquette prepared with coal, lignin and coal tar as binder and T/CTS-BIOC for a briquette prepared with coal, BIOC and a 1:1 wt/wt blend of coal tar and coal tar sludge.

2.7. Gieseler fluidity of briquette mixtures

The thermoplastic properties of the mixtures that made up the briquettes were measured by means of the Gieseler test (ASTM D2639-74).²²⁻²⁴ The samples (5 g), with a particle size < 0.425 mm, were heated at a rate of 3 °C/min up to a final temperature of 550 °C, while constantly applying a torque to the stirrer inside the crucible containing the sample. The parameters derived from this test were: (i) softening temperature, Ts; (ii) temperature of maximum fluidity, Tf; (iii) resolidification temperature, Tr; (iv) plastic range, Tr-Ts; and (v) maximum fluidity, MF, expressed as dial divisions per minute (ddpm).

3. Results and Discussion

3.1. Thermogravimetric analysis of raw materials

The TGA curves corresponding to the mass loss and the derivative of the mass loss curves of the briquette components are shown in **Figure 1**. The plots are presented in wet basis. The vertical dash line in the plots represents the temperature of maximum fluidity or minimum viscosity of coal (435 °C), calculated as the average of Gieseler plastometry (440 °C) and rheometry (430 °C) results. The curves for the variation of mass loss of the biomass with temperature indicate that, at 435 °C, the highest char yield corresponds to Lg (55 wt%), followed by BIOC and SPT (43 wt% and 40 wt%, respectively) and by SP (21 wt%), which is in agreement with the carbon contents (**Table 1**). With regard to the binders, the highest coke yield at 435 °C corresponds to T (38 wt%), followed by CTS and Mol (28 wt% and 24 wt%, respectively) and Par (0.2 wt%), with the latter almost volatilizing completely at 400 °C. The maximum devolatilization rate occurs at around 450 °C in the coal, 330 °C in SP, SPT, BIOC and Lg, 300 °C in Par and 200 °C in Mol. T and CTS do not show a clear maximum in the devolatilization rate.

3.2. Infrared spectroscopy of raw materials

The chemical composition of the additives is important as it might influence coal fluidity. Tsubouchi et al.²⁵ reported that the Gieseler maximum fluidity (MF) values tend to decrease with the increase in the total amount of evolved oxygenated species during carbonization (mainly CO, CO₂ and H₂O). These authors attributed the release of these species to the presence of carboxyl and acid anhydride groups. On the other hand, another study on the development of fluidity in biomass and coal blends¹⁸ reported that the higher the carbonyl groups and the lower the aromatic carbon in biomass, the lower the detrimental effect on

coal fluidity. Aromaticity has also been reported to be an important factor in the enhancement of fluidity. Polycondensed aromatics can provide a pathway for the transfer of hydrogen to radical sites in bituminous coals, and thereby, act as intermediates in the transformation of coal to coke.^{26,27} Sharma et al.²⁸ also emphasized the importance of the C/H atomic ratio of the binder because it has a decisive effect on the strength of the briquettes under differing thermo-chemical conditions of curing and carbonization. These authors indicated that binders with C/H ratios above 1 are preferable for the production of briquettes.

Table 1 shows that Mol has the highest oxygen content (55.9 wt%), followed by SP (44.7 wt%). As expected, the heat-treated sample SPT has lower amounts of oxygen than SP (35.5 wt% cf. 44.7 wt%). The oxygen content in Lg (26.3 wt%) is comparable to that in BIOC (25.5 wt%). T and CTS have lower oxygen contents than those in the biomass samples (3.0 wt% and 8.2 wt%, respectively). The oxygen content in paraffin is almost insignificant (0.3 wt%). Regarding the C/H ratio (**Table 1**), both bituminous binders have a ratio between 1.3–1.6, which is desirable (i.e. > 1). In the case of the other two binders the ratios are lower (< 0.5), being the lowest C/H ratio that of Mol (0.3).

Figures 2 and 3 display the FTIR spectra of the biomass samples and the binders, respectively. The FTIR spectrum of the bituminous coal is also presented in **Figure 3** for comparison purposes. Several bands can be observed in the ATR infrared spectra of the biomass samples (**Figure 2**). The broad and intense peak around 3300 cm^{-1} is attributed to the stretching of the O–H group due to inter and intramolecular hydrogen bonding of cellulosic compounds, such as alcohols and phenols.²⁹ The range between 2990 cm^{-1} and 2765 cm^{-1} is assigned to the aliphatic stretching of C–H, the $1770\text{--}1650\text{ cm}^{-1}$ range

originates from C=O bonds and the 1600 cm⁻¹ band is assigned to C=C stretching vibrations of the aromatic rings.¹² The absorption bands at around 1230 cm⁻¹ and 1060 cm⁻¹ correspond to C–O stretching, and at 1027 cm⁻¹ there is a strong C–O bond attributed to the ether group of cellulose.^{29,30} The spectra for SP and SPT are fairly similar. Mol, BIOc and Lg possess higher concentrations of C=O groups (1770–1650 cm⁻¹) and C=C bonds of aromatic rings (1600 cm⁻¹) than SP and SPT. Mol presents the highest content of O–H groups (3300 cm⁻¹).

Figure 3 shows the ATR infrared spectra of the low rank coal, paraffin, coal tar and coal tar sludge. The aromatic and aliphatic C–H stretching modes appear at 3100–2990 cm⁻¹ and 2990–2765 cm⁻¹, respectively.¹² The C=O band appears between 1800–1633 cm⁻¹ and C=C stretching modes appear between 1633–1538 cm⁻¹.¹² Flexions in methylene and methyl groups are observed at 1450 cm⁻¹ and 1375 cm⁻¹, respectively. The 900–700 cm⁻¹ range corresponds to the out-of-plane aromatic C–H vibration modes and reveals differences in the substitution patterns of the aromatic structures.³¹ The strong peak in the spectrum of paraffin at 720 cm⁻¹ has been ascribed to the in-plane rocking vibration of the –CH₂ group.³² The spectra of T and CTS are fairly similar and very different to those of Par and the bituminous coal. Par is mainly constituted by aliphatic C–H groups whereas T and CTS mainly contain aromatic C–H groups.

Table 3 presents the semi-quantitative indices previously defined in **Table 2**. The A_{OH}/A_{C=O} index, which gives information about the distribution of oxygen functionalities, decreases in the following order for the biomass samples: SP (23.82) >> Mol (13.40) >> BIOc (8.37) ≈ SPT (7.45) = Lg (7.45). Most of the oxygen species present in SP are O–H groups. Mol shows a large amount of both O–H and C=O groups, which is in agreement with the results from other authors.³⁰ The heat-treated biomass samples SPT and BIOc have lower

proportions of the O–H bond as indicated by the low $A_{OH}/A_{C=O}$ index values (< 9). This index was not calculated for the coal, due to the interference of mineral matter, or for the bituminous binders and Par, as the band due to O–H is not apparent in the spectra (Figure 3).

The $A_{C=C}/A_{al}$ index was calculated to determine semi-quantitatively the degree of aromaticity of the samples. Mol and BIOc are the most aromatic biomass samples (0.43 and 0.46), whereas SP has the lowest value (0.33). The highest aromaticity corresponds to T (0.74) and CTS (0.63). Coal has a lower $A_{C=C}/A_{al}$ ratio (0.35) than some biomass samples due to the large amount of aliphatic hydrogen in the coal used due to its rank.³³ This index was not calculated for paraffin because it does not show a band at 1600 cm^{-1} .

3.3. High-temperature ^1H NMR of raw materials

3.3.1. Changes in the concentration of fluid H

Figure 4 shows the development of fluid H as a function of temperature for the raw materials. Mol, T and CTS have not been included in the graph because they remain liquid (i.e. 100% fluid H) throughout the test. The fluid H profiles of BIOc, SP and SPT are very similar and show two maxima: one at around $100\text{ }^{\circ}\text{C}$, mainly due to the evaporation of water, and the other one at around $300\text{ }^{\circ}\text{C}$. The maximum percentages of fluid H and the temperatures of maximum fluid H for BIOc, SP and SPT are similar to those of miscanthus (i.e. 25% fluid H and $330\text{ }^{\circ}\text{C}$).²⁰ Lignin develops fluidity between $200\text{--}400\text{ }^{\circ}\text{C}$ and reaches a maximum of 80% fluid H at around $300\text{ }^{\circ}\text{C}$. The fluid phase development of coal takes place at higher temperatures ($375\text{--}500\text{ }^{\circ}\text{C}$), reaching a maximum of 90% fluid H at $460\text{ }^{\circ}\text{C}$, in agreement with results from the literature.³⁴ Paraffin becomes completely fluid at $75\text{ }^{\circ}\text{C}$, and remains fluid until it completely devolatilizes at around $400\text{ }^{\circ}\text{C}$.

3.3.2. Changes in the mobility of the fluid H

Figures 5a and 5b show the changes in the spin-spin relaxation time (T2L), or mobility of the fluid H, as a function of temperature for the raw materials. Similarly to the development of fluid H, SP, SPT and BIOC display similar mobility profiles (Figure 5a). These biomass samples have three maxima: the first one at around 75 °C; the second one depends on the biomass (SPT at 150 °C and SP and BIOC at 200 °C); and the third one at 325 °C. Lg only has two maxima, one at around 75 °C and the other at around 300 °C. These changes in mobility seem to be related to the evaporation of water (75 °C) and the decomposition of hemicellulose, cellulose and lignin constituents. A previous study³⁵ has shown that the T2L of cellulose reaches a maximum of 300 μ s at 150 °C. The same authors found that xylan, which represents 90% of the hemicellulose, reaches the maximum T2L of 450 μ s at a higher temperature than cellulose (around 175 °C cf. 150 °C) and that Lg maintains a T2L value of around 200 μ s between 250–350 °C. In light of this, the maximum T2L at 150 °C of SPT could be related to the mobility of cellulose, whereas the wide T2L peak of SP at 200 °C could be due to the combination of cellulose and hemicellulose mobilities. The changes in mobility of the fluid H in the case of miscanthus³⁵ are similar to the results for SP reported in the present research work. The maximum T2L of 200 μ s at around 300 °C could be associated with the aromatic structures in biomass (i.e. lignin).

The development of T2L for the low rank bituminous coal takes place between 400–500 °C, reaching a maximum of 150 μ s at around 450 °C (Figure 5b). Among the binders, molasses develops the lowest maximum T2L (ca. 115 μ s). Paraffin exhibits a maximum T2L of 276 μ s at 75 °C, but also reaches mobilities of 220 μ s between 300–400 °C. T presents a maximum T2L of 286 μ s at 100 °C. The T2L profiles of T and CTS are very similar from

200 °C onwards, remaining constant at around 160 μ s and 150 μ s, respectively. Out of all these additives, only coal tar and coal tar sludge develop mobility of fluid H that is equal to or higher than the mobility of fluid H in the coal during its plastic stage (80–150 μ s).

3.4. High-Temperature Rheometry

Figure 6a shows the variation in complex viscosity as a function of temperature for the biomass samples and the coal. SP and SPT display a small decrease in complex viscosity, which reaches a minimum of 1×10^6 Pa.s at around 343 °C. The development of viscosity for sawdust and miscanthus follows a similar trend,¹⁸ in line with the similarities previously mentioned for the fluid phase and mobility developments of these samples. The complex viscosity of lignin is very similar to the elastic and viscous moduli described in the literature.²⁰ Lignin shows a lower minimum in complex viscosity (1×10^4 Pa.s) than the other biomass samples. In contrast, BIOc did not experience any decrease in viscosity during the thermal treatment, although it showed fluid H and T2L development. This finding suggests that the fluid H in BIOc is not able to alter the viscoelastic properties of the bulk material. Coal reached a minimum of 6×10^3 Pa.s at 427 °C, in agreement with the results found for other coals with high volatile matter.³⁶

The rheometry analyses of the high volatile coal and its blends with the additives (5 wt%) are shown in the Supplementary Material section (Figure SM1). Only a few noteworthy changes were observed. Biomass samples cause a slight shift of the softening and minimum viscosity temperatures of the coal to higher temperatures and the resolidification of the blend containing SP is the slowest in the series.

The coal was pre-heated to reduce data scattering and to clearly elucidate the influence of the binders on the viscosity of the blends. **Figure 6b** shows the complex viscosity analysis of blends made up of 5 wt% binder and 95 wt% pre-heated coal (C466). Under these conditions, coal tar and coal tar sludge cause a remarkable decrease in the softening temperature range and the minimum viscosity temperature (413 °C vs. 423 °C), in agreement with data from the literature.³⁷ Par also causes a reduction in the softening temperature range (360–385 °C) but additional heating does not entail any significant change compared to that of the pre-heated coal up to the temperature of minimum viscosity (423 °C). Melendi et al.³⁸ showed that polyolefins and hydrocarbon oil are weaker modifiers of coal's rheological properties, which is in agreement with our results for Par. Finally, the softening and minimum viscosity temperatures of the blend with molasses rise (435 °C vs. 423 °C). A previous research work focusing on the effect of biomass (i.e. pine wood, sugar beet, miscanthus) on fluidity development in coking blends did not show this effect for blends with a coal of moderate VM content (25.2 wt% daf) and a Gieseler fluidity of 817 ddpm.¹⁸ However, similar results were obtained by these authors through rheometry analysis of a high volatile bituminous coal (31.9 wt% db) mixed with miscanthus. This effect has also been reported during the analyses of blends of a bituminous coal (VM, 25.2 wt% db) with charcoal, wood and other additives.³⁴ The addition of coal tar sludge or paraffin causes a decrease in the resolidification temperature. On the contrary, the resolidification stage takes place at a higher temperature when molasses are added. The values of the minimum complex viscosity for C466 and its blends is about 1.5×10^4 Pa.s, except with molasses, which is less viscous (3×10^4 Pa.s).

3.5. Thermoplastic properties of ternary blends constituting the briquettes

The results of the Gieseler fluidity tests in this work are shown in Table 4 and Figure 7. The high volatile, high fluidity bituminous coal (26000 ddpm) was chosen in this work to prepare the briquettes taking into consideration the deleterious effect of biomass on the plastic properties of coal. It is envisaged that the resultant briquettes should be capable of developing suitable levels of fluidity.^{8,18,39} The importance of this feature cannot be underestimated since the lack of fluidity can affect the integration of briquettes into the coke matrix, which would increase the possibility of fissures, affecting the quality of the final coke product.⁴⁰ The components of a coal blend soften independently and, as a consequence, the plastic range of a blend may be wider than that of the base coal. It is also necessary to bear in mind that the properties of the softened mass may be influenced by interactions between the softened and inert components of the blend.³⁷ In the present research work, the blends used were complex and made up of products that, when individually added to the coal, can have opposite effects. In summary, biomass has been found to decrease fluidity and move the plastic stage to higher temperatures, T and CTS produce a decrease in the softening range of the coal, and Par has very little effect on coal fluidity.

The softening, maximum fluidity and resolidification temperatures of the ternary blends are displayed in Table 4. No systematic trend can be observed for the softening temperature of the blends containing T and CTS compared with blends containing Par. On the other hand, blends with Mol show the highest softening temperatures. However, examination of the temperature of maximum fluidity (Tf) and the Gieseler curves in Figure 7 shows lower Tf values for blends with aromatic binders than with Par. In fact, the maximum fluidity temperatures of blends containing Par and Mol are very close to each other. Mol also produces resolidification at the lowest temperatures. As a result, their blends have the narrowest plastic range, which is defined by the difference between the

resolidification and softening temperatures (Tr-Ts). This finding is in agreement with the rheometry results (Figure 6b). The Gieseler plastometer results in Table 4 also indicate that the Tr of coal is always equal to or higher than the Tr of the blends.

For the same binder, the following order of increasing deleterious effect of the biomass upon the thermoplastic properties of the coal has been established:

$$SP < BIOC < SPT < Lg$$

Although there are some exceptions, SP and BIOC develop similar MF with T/CTS as binder, as in the case of SPT and BIOC with blends containing Par. A previous research work established that torrefied sawdust produced a slightly greater reduction in Gieseler maximum fluidity than sawdust that had not been heat-treated.⁸ It would appear that this result is related to the char yield of the biomass, as shown in Figure 8a. BIOC is an exception to this correlation because it produces only a small deleterious effect in blends with bituminous binders. For this reason, these blends have not been taken into account when calculating the correlation coefficients.

There is some debate as to the influence of the oxygen content on fluidity. Previous studies by Tsubouchi et al.²⁵ have shown that oxygen species can have a deleterious effect. Whereas, other authors have shown using ¹³C NMR that, the aromatic carbon in the biomass could have a detrimental effect and/or the carboxyl groups from hemicellulose could have a beneficial effect on coal fluidity¹⁸. Our results show that an increase in oxygen species is accompanied by smaller loss in MF (Figure 8b). However, there is also an inverse linear relationship between the coke yield and the oxygen content of biomass ($R^2 = 0.82$). The oxygen species are highly reactive compounds that reduce the char yield from biomass.

As a result, the contact area between the evolving char and the fluid material of coal decreases and the impairment in coal fluidity is reduced by reducing the amount of biomass char, which might act as a sink for the fluid entities evolving in the coal.

Although it might appear that oxygen content has a positive effect, if two biomass samples with a similar char yield are compared, such as BIOC and SPT that produce char yields of around 42%, the less deleterious effect is caused by the biomass with lower oxygen content (i.e. BIOC, with 25.5% cf. 35.5% of SPT, Table 1). These results prove that oxygen species in biomass have a negative effect on coal fluidity.

The results in **Figures 8a and 8b** for blends containing the same biomass sample indicate that the binders cause a greater increase in fluidity in the following order:

$$T > T/CTS > Par > Mol$$

These results do not seem to be related to the coke or char yields of the binders. Mol and CTS yield similar amounts of solid residue at the temperature of maximum fluidity of the coal, but they have completely opposite effects on the fluidity of the coal. However, a relationship has been found between the effect of the binders on the coal plastic properties and their C/H atomic ratio (**Figure 9**). In the case of Lg, the factor discussed above does not appear to be very significant, as can be seen by the low value of the correlation coefficient ($R^2 = 0.672$), which suggests that the effect of this biomass constituent is predominant over that of the binder.

These results also confirm that the greater the char yield of the biomass, the greater the reduction in blend fluidity. Furthermore, the effect is even more pronounced in the case of the binders that have a greater C/H atomic ratio, and consequently, a greater effect on

the plastic properties of the coal. A combination of physical and chemical effects explains these results. On the one hand, the inert additives that are blended with the softening coal possibly reduce fluidity by adsorbing the primary decomposition compounds responsible for the development of fluidity.^{41,42} On the other hand, the binders with higher C/H values are able to supply aromatic compounds that serve as stabilizers of the radicals formed during coal decomposition, compensating for the deleterious effect of chars present in the reaction system. Polycondensed aromatics can provide a pathway for the transfer of hydrogen to radical sites in bituminous coals, and thereby, act as intermediates in the transformation of coal to coke.^{26,27} For any particular biomass, the least deleterious effect is produced if an aromatic binder is used.

Therefore, the biomass samples studied in this work that are more suitable for the preparation of the briquettes, considering their effect on the thermoplastic properties of coal, are SP and BIOC. In the case of the binders, T and CTS are the binders that best compensate for the deleterious effect of biomass on coal fluidity.

4. Conclusions

Four biomass samples and four binders have been blended with a low rank bituminous coal to determine their effect on the thermoplastic properties of the coal. The biomass samples comprised of pine sawdust (SP), torrefied pine sawdust (SPT), pine Kraft lignin (Lg) and a bio-coal derived from hydrothermally treated waste biomass obtained from pruning (BIOC). The binders included molasses (Mol), paraffin (Par), coal tar (T) and coal tar sludge (CTS). The analysis of blends composed of coal, biomass and binder using the Gieseler plastometer has shown that the binder's effects, as identified by rheometry analysis, are sometimes modified by interaction with biomass. For the same binder, the following order of

increasing deleterious effect of the biomass upon the maximum fluidity of the coal has been established: $SP < BIOC < SPT < Lg$. It can also be deduced that for the same biomass the order of increasing deleterious effect of the binder on the coal maximum fluidity is as follows: $T < T/CTS < Par < Mol$. The coke yields of the biomass samples together with the chemical composition of the binders help to explain the fluidity of the blends.

The oxygen species in biomass have a negative effect on coal fluidity, these species are associated to highly reactive compounds that reduce the char yield from biomass. As a result, the contact area between the char from biomass and the fluid material of coal decreases and the impairment in coal fluidity is reduced.

Coal tar, coal tar sludge, pine sawdust and BIOC appear to be the best briquette components. Nevertheless, paraffin can be considered as a good alternative to bituminous binders because it does not cause any significant impairment of the thermoplastic properties of coal and it is less polluting. Future work must address other important factors such as optimum concentrations of biomass and binder in the briquettes and the impact of coal rank and coal blend composition in order to preserve coke quality and safeguard coke oven operation.

Acknowledgements

The research leading to these results has received funding from the European Union's Research Fund for Coal and Steel (RFCS) research programme under grant agreement No. [RFCS-CT-2014-00006].

References

- (1) Alvarez, R.; Barriocanal, C.; Díez, M. A.; Cimadevilla, J. L. G.; Casal, M. D.; Canga, C. S. Recycling of Hazardous Waste Materials in the Coking Process. *Environ. Sci. Technol.* **2004**, *38* (5), 1611–1615.
- (2) Díez, M. A.; Alvarez, R.; Melendi, S.; Barriocanal, C. Feedstock Recycling of Plastic Wastes/Oil Mixtures in Cokemaking. *Fuel* **2009**, *88* (10), 1937–1944.
- (3) Duffy, J. J.; Mahoney, M. R.; Steel, K. M. Influence of Coal Thermoplastic Properties on Coking Pressure Generation: Part 2 – A Study of Binary Coal Blends and Specific Additives. *17th Int. Symp. Alcohol Fuels* **2010**, *89* (7), 1600–1615.
- (4) Fernández, A. M.; Barriocanal, C.; Alvarez, R. The Effect of Additives on Coking Pressure and Coke Quality. *Fuel* **2012**, *95*, 642–647.
- (5) Mochida, I.; Matsuoka, H.; Korai, Y.; Fujitsu, H.; Takeshita, K. Carbonization of Coals to Produce Anisotropic Cokes. 1. Modifying Activities of Some Additives in the Co-Carbonization of Low-Rank Coals. *Fuel* **1982**, *61* (7), 587–594.
- (6) Świetlik, U.; Gryglewicz, G.; Machnikowska, H.; Machnikowski, J.; Barriocanal, C.; Alvarez, R.; Díez, M. A. Modification of Coking Behaviour of Coal Blends by Plasticizing Additives. *J. Anal. Appl. Pyrolysis* **1999**, *52* (1), 15–31.
- (7) Montiano, M. G.; Díaz-Faes, E.; Barriocanal, C.; Alvarez, R. Influence of Biomass on Metallurgical Coke Quality. *Fuel* **2014**, *116*, 175–182.
- (8) Montiano, M. G.; Barriocanal, C.; Alvarez, R. Effect of the Addition of Waste Sawdust on Thermoplastic Properties of a Coal. *Fuel* **2013**, *106* (4), 537–543.
- (9) Norgate, T.; Haque, N.; Somerville, M.; Jahanshahi, S. Biomass as a Source of Renewable Carbon for Iron and Steelmaking. *ISIJ Int.* **2012**, *52* (8), 1472–1481.

- 494 (10) Montiano, M. G.; Díaz-Faes, E.; Barriocanal, C. Partial Briquetting vs Direct
495 Addition of Biomass in Coking Blends. *Fuel* **2014**, *137*, 313–320.
- 496 (11) Montiano, M. G.; Fernández, A. M.; Díaz-Faes, E.; Barriocanal, C. Tar from
497 Biomass/Coal-Containing Briquettes. Evaluation of PAHs. *Fuel* **2015**, *154*, 261–
498 267.
- 499 (12) Florentino-Madiedo, L.; Díaz-Faes, E.; García, R.; Barriocanal, C. Influence of
500 Binder Type on Greenhouse Gases and PAHs from the Pyrolysis of Biomass
501 Briquettes. *Fuel Process. Technol.* **2018**, *171*, 330–338.
- 502 (13) Castro-Díaz, M.; Zhao, H.; Kokonya, S.; Dufour, A.; Snape, C. E. The Effect of
503 Biomass on Fluidity Development in Coking Blends Using High-Temperature
504 SAOS Rheometry. *Energy Fuels* **2012**, *26* (3), 1767–1775.
- 505 (14) Menéndez, J. A.; Pis, J. J.; Alvarez, R.; Barriocanal, C.; Fuente, E.; Díez, M. A.
506 Characterization of Petroleum Coke as an Additive in Metallurgical Cokemaking.
507 Modification of Thermoplastic Properties of Coal. *Energy Fuels* **1996**, *10* (6),
508 1262–1268.
- 509 (15) Mulligan, M. J.; Thomas, K. M. Some Aspects of the Role of Coal
510 Thermoplasticity and Coke Structure in Coal Gasification: 3. The Effect of Rank,
511 Pitch and Sodium Carbonate on Brabender Plastometry Parameters. *Fuel* **1987**,
512 *66* (9), 1289–1298.
- 513 (16) Lynch, L. J.; Sakurovs, R.; Barton, W. A. The Influence of Iron on Proton
514 Nuclear Magnetic Resonance Measurements of Coals. *Fuel* **1986**, *65* (8), 1108–
515 1111.
- 516 (17) Maroto-Valer, M. M.; Andrésen, J. M.; Snape, C. E. In-Situ ^1H NMR
517 Investigation of Particle Size, Mild Oxidation, and Heating Regime Effects on

- 518 Plasticity Development during Coal Carbonization. *Energy Fuels* **1997**, *11* (1),
519 236–244.
- 520 (18) Castro-Díaz, M.; Zhao, H.; Kokonya, S.; Dufour, A.; Snape, C. E. The Effect of
521 Biomass on Fluidity Development in Coking Blends Using High-Temperature
522 SAOS Rheometry. *Energy Fuels* **2012**, *26* (3), 1767–1775.
- 523 (19) Barriocanal, C.; Díez, M.; Alvarez, R.; Casal, M.; Canga, C. On the Relationship
524 between Coal Plasticity and Thermogravimetric Analysis. *J. Anal. Appl.*
525 *Pyrolysis* **2003**, *67* (1), 23–40.
- 526 (20) Dufour, A.; Castro-Díaz, M.; Marchal, P.; Brosse, N.; Olcese, R.; Bouroukba, M.;
527 Snape, C. In Situ Analysis of Biomass Pyrolysis by High Temperature Rheology
528 in Relations with ¹H NMR. *Energy Fuels* **2012**, *26* (10), 6432–6441.
- 529 (21) Steel, K. M.; Castro-Díaz, M.; Patrick, J. W.; Snape, C. E. Use of Rheometry and
530 ¹H NMR Spectroscopy for Understanding the Mechanisms behind the
531 Generation of Coking Pressure. *Energy Fuels* **2004**, *18* (5), 1250–1256.
- 532 (22) Melendi, S.; Díez, M. A.; Alvarez, R.; Barriocanal, C. Plastic Wastes, Lube Oils
533 and Carbochemical Products as Secondary Feedstocks for Blast-Furnace Coke
534 Production. *Fuel Process. Technol.* **2011**, *92* (3), 471–478.
- 535 (23) Fernández, A. M.; Barriocanal, C.; Díez, M. A.; Alvarez, R. Influence of
536 Additives of Various Origins on Thermoplastic Properties of Coal. *Fuel* **2009**, *88*
537 (12), 2365–2372.
- 538 (24) Barriocanal, C.; Patrick, J. W.; Walker, A. The Laboratory Identification of
539 Dangerously Coking Coals. *Fuel* **1998**, *77* (8), 881–884.
- 540 (25) Tsubouchi, N.; Mochizuki, Y.; Naganuma, R.; Kamiya, K.; Nishio, M.; Ono, Y.;
541 Uebo, K. Influence of Inherent Oxygen Species on the Fluidity of Coal during
542 Carbonization. *Energy Fuels* **2016**, *30* (3), 2095–2101.

- 543 (26) Grint, A.; Mehani, S.; Trehwella, M.; Crook, M. J. Role and Composition of the
544 Mobile Phase in Coal. *Fuel* **1985**, *64* (10), 1355–1361.
- 545 (27) Díez, M. A.; Domínguez, A.; Barriocanal, C.; Alvarez, R.; Blanco, C. G.; Canga,
546 C. S. Hydrogen Donor and Acceptor Abilities of Pitches from Coal and
547 Petroleum Evaluated by Gas Chromatography. *J. Chromatogr. A* **1999**, *830* (1),
548 155–164.
- 549 (28) Sharma, A. K.; Das, B. P.; Tripathi, P. S. M. Influence of Properties of
550 Bituminous Binders on the Strength of Formed Coke. *Fuel Process. Technol.*
551 **2002**, *75* (3), 201–214.
- 552 (29) Kaya, M. Evaluation of a Novel Woody Waste Obtained from Tea Tree Sawdust
553 as an Adsorbent for Dye Removal. *Wood Sci. Technol.* **2018**, *52* (1), 245–260.
- 554 (30) El Darra, N.; Rajha, H. N.; Saleh, F.; Al-Oweini, R.; Maroun, R. G.; Louka, N.
555 Food Fraud Detection in Commercial Pomegranate Molasses Syrups by UV–VIS
556 Spectroscopy, ATR-FTIR Spectroscopy and HPLC Methods. *Food Control* **2017**,
557 *78*, 132–137.
- 558 (31) Fernández, A. M.; Barriocanal, C.; Díez, M. A.; Alvarez, R. Evaluation of
559 Bituminous Wastes as Coal Fluidity Enhancers. *Fuel* **2012**, *101*, 45–52.
- 560 (32) Chai, Y.; Zhao, T.; Gao, X.; Zhang, J. Low Cracking Ratio of Paraffin
561 Microcapsules Shelled by Hydroxyl Terminated Polydimethylsiloxane Modified
562 Melamine-Formaldehyde Resin. *Colloids Surf. Physicochem. Eng. Asp.* **2018**,
563 *538*, 86–93.
- 564 (33) Casal, M. D.; Canga, C. S.; Díez, M. A.; Alvarez, R.; Barriocanal, C. Low-
565 Temperature Pyrolysis of Coals with Different Coking Pressure Characteristics.
566 *J. Anal. Appl. Pyrolysis* **2005**, *74* (1-2), 96–103.

- 567 (34) Castro Díaz, M.; Steel, K. M.; Drage, T. C.; Patrick, J. W.; Snape, C. E.
 568 Determination of the Effect of Different Additives in Coking Blends Using a
 569 Combination of in Situ High-Temperature ^1H NMR and Rheometry. *Energy*
 570 *Fuels* **2005**, 19 (6), 2423–2431.
- 571 (35) Dufour, A.; Castro-Díaz, M.; Brosse, N.; Bouroukba, M.; Snape, C. The Origin of
 572 Molecular Mobility during Biomass Pyrolysis as Revealed by in Situ ^1H NMR
 573 Spectroscopy. *ChemSusChem* **2012**, 5 (7), 1258–1265.
- 574 (36) Castro Díaz, M.; Duffy, J. J.; Snape, C. E.; Steel, K. M. Use of High-
 575 Temperature, High-Torque Rheometry to Study the Viscoelastic Properties of
 576 Coal during Carbonization. *J. Rheol.* **2007**, 51 (5), 895–913.
- 577 (37) Elliott, M. A. *Chemistry of Coal Utilization. Second Supplementary Volume*; John
 578 Wiley and Sons: Toronto, 1981; Vol. 6.
- 579 (38) Melendi-Espina, S.; Díez, M. A.; Alvarez, R.; Castro Díaz, M.; Steel, K.; Snape,
 580 C. Rheological Behaviour of Coal Modified by Waste Plastics and Lubricating-
 581 Oils; *Proceedings of the International Conference on Coal Science and*
 582 *Technology*, The University of Nottingham, August 28th - 31th, 2007; p. 2P45.
- 583 (39) Montiano, M. G.; Díaz-Faes, E.; Barriocanal, C. Effect of Briquette Composition
 584 and Size on the Quality of the Resulting Coke. *Fuel Process. Technol.* **2016**, 148,
 585 155–162.
- 586 (40) Barriocanal, C.; Hanson, S.; Patrick, J. W.; Walker, A. The Characterization of
 587 Interfaces between Textural Components in Metallurgical Cokes. *Fuel* **1994**, 73
 588 (12), 1842–1847.
- 589 (41) Sakurovs, R. Some Factors Controlling the Thermoplastic Behaviour of Coals.
 590 *Fuel* **2000**, 79 (3), 379–389.

591 (42) Fernández, A. M.; Barriocanal, C.; Díez, M. A.; Alvarez, R. Importance of the
592 Textural Characteristics of Inert Additives in the Reduction of Coal
593 Thermoplastic Properties. *Fuel* **2010**, 89 (11), 3388–3392.
594

595

596 Table 1. Proximate and ultimate analysis of the briquette components.

	Coal	SP	SPT	BIOC	Lg	Mol	T	CTS	Par
Ash (wt% db) ^a	7.3	0.2	0.4	6.1	2.5	2.8 ^c	0.4 ^c	1.7 ^c	0.1 ^c
VM (wt% db) ^{a,b}	31.5	84.3	71.1	68.0	64.0	94.4 ^c	65.9 ^c	71.1 ^c	99.6 ^c
C (wt% db) ^a	81.2	50.9	59.8	59.8	64.7	26.5	90.3	84.2	85.1
H (wt% db) ^a	5.0	6.2	5.7	6.0	5.7	8.0	4.7	5.3	14.5
N (wt% db) ^a	1.6	0.3	0.3	1.2	0.9	1.7	0.8	1.3	0.2
S (wt% db) ^a	1.03	< 0.05	<0.05	0.15	1.52	0.18	0.40	0.60	<0.05
O (wt% db) ^a	4.8	44.7	35.5	25.5	26.3	55.9	3.0	8.2	0.3
C/H ^d	1.35	0.68	0.87	0.83	0.95	0.28	1.60	1.32	0.49

597

598 a: dry basis; b: volatile matter; c: determined in a thermobalance; d: atomic ratio

599 Table 2. Definition of the semi-quantitative indices derived from ATR infrared spectra.

Index	Description	Band region (cm ⁻¹)
Aromaticity ($A_{C=C}/A_{al}$)	ν C=C/ ν C-H aliphatic	A1600/A(3000–2800)
Oxygen distribution ($A_{OH}/A_{C=O}$)	ν OH/ ν C=O	A3000/A(1770–1650)

600 ν : stretching vibration; σ : bending vibration

601

602

Table 3. Values for the semi-quantitative indices of the briquette components.

	Coal	SP	SPT	BIOC	Lg	Mol	T	CTS	Par
$A_{OH}/A_{C=O}$	-	23.82	7.45	8.37	7.45	13.40	-	-	-
$A_{C=C}/A_{al}$	0.35	0.33	0.39	0.46	0.36	0.43	0.74	0.63	0.00

Table 4. Parameters derived from the Gieseler fluidity test of the coal and briquettes.

Sample	Ts (°C)	Tf (°C)	Tr (°C)	Tr-Ts (°C)	MF (ddpm)	MF loss (%)
Coal	382	439	484	102	26055	-
T-BIOC	386	434	479	93	2268	91.3
T/CTS-BIOC	384	433	481	97	2125	91.8
Mol-BIOC	404	443	466	62	69	99.7
Par-BIOC	384	444	479	95	395	98.5
T-Lg	342	433	475	133	389	98.5
T/CTS-Lg	342	436	475	133	340	98.7
Mol-Lg	-	-	-	-	-	100
Par-Lg	412	448	481	69	284	98.9
T-SP	387	432	483	96	3173	87.8
T/CTS-SP	392	434	482	90	2046	92.1
Mol-SP	403	442	475	72	242	99.1
Par-SP	378	441	486	108	922	96.5
T-SPT	394	438	481	87	962	96.3
T/CTS-SPT	389	440	476	87	999	96.2
Mol-SPT	416	446	467	51	11	99.9
Par-SPT	382	442	484	102	526	98.0

Figure 1. Mass loss of the raw materials as a function of temperature.

Figure 2. Infrared spectra of SP, SPT, Lg, BIOC and Mol.

Figure 3. Infrared spectra of coal, Par, T and CTS.

Figure 4. Fluid H development as a function of temperature.

Figure 5. Changes in the mobility of fluid phase (T2L) as a function of temperature.

Figure 6. Complex viscosity as a function of temperature for a) coal and biomass samples and b) blends of coal pre-heated up to 466 °C with binders.

Figure 7. Gieseler fluidity curves as a function of temperature for the briquette blends.

Figure 8. Variation of maximum fluidity loss with a) biomass char yield, from left to right SP, SPT, BIOC and Lg and b) oxygen content of the biomass samples, from left to right BIOC, Lg, SPT and SP.

Figure 9. Relationship between the MF loss and the C/H atomic ratio of the binders.
Binders from left to right: Mol, Par, T/CTS and T.