Polymorphic transitions in oligo(aryl ether ketone)s studied by real time X-ray scattering

D. R. Rueda, F. Ania, F. J. Baltá-Calleja, I. Sics
Inst. Estructura de la Materia, CSIC. Serrano 119, 28006 Madrid. Spain

Abstract

The crystal phase transitions occurring in two oligo(aryl ether ketone) samples were studied, in real time, by means of X-ray scattering using synchrotron radiation. The first one is a typical molecular compound with 7 aryl units (m7). The second one, with 11 aryl units (p11), exhibits the presence of additional polymeric chains. In relation to the polymorphic transition previously reported for aromatic polyketones, the phase transition study of the sample p11 clarifies the role of chain length in the thermal behaviour of aromatic polyketones. The structural variations, due to crystal phase transitions, as revealed by X-ray diffraction during heating of the samples are not accompanied by the parallel changes in the DSC thermograms. This is due to the isoenthalpic character of the two crystal polymorphs I and II of polyketones. The two endothermic peaks observed for the samples p11 and m11 are associated to the melting of crystals with short and polymeric chains. The polymer component of samples p11 and m11 has been considered of interest to examine the origin of the double melting phenomenon commonly observed for aromatic polyketones. A structural mechanism is suggested to explain the absence of such phenomenon for the p11 and m11 samples.

Introduction

Poly(aryl ether ketone)s as high-performance thermoplastic materials have received special attention in the last decade [1],[2]. Gardner et al. reported on the polymorphism of aromatic polyketones with different keto/ether molar ratios [3],[4] crystallized under different conditions and more recently for polyketones containing isophthalic units (1-3 substituted phenylene) [5]. Two main crystal polymorphs have been observed in aromatic polyketones: form I and form II following Gardner's notation [4]. The most stable crystal phase, the form I, corresponds to the orthorhombic unit cell similar to that of poly(phenylene oxide) [6] and PEEK [7],[8]. The chain packing proposed for the form II is also orthorhombic with the a and b axes exchanged with each other [9] or "pseudoorthorhombic" with a single chain per unit cell [4]. The conversion of the crystal phase II into phase I, during heating of aromatic polyketones, has been recently studied using synchrotron radiation [10]. It is noteworthy that the polymorphic transition (II into I) is clearly detected by X-ray diffraction but cannot be resolved by DSC calorimetry [11], i.e. the crystal phase transition is an isoenthalpic transition.

The study of oligomer compounds, as models for aromatic polyketones, is of great validity [12],[13],[14],[15],[16],[17]. The influence of the keto/ether molar ratio on the lattice unit cell parameters, melting temperature and fusion enthalpy observed for two series of oligo(aryl ether ketone)s with 5, 7, 9 and 11 aryl units per molecule has been previously reported [18]. While one series of compounds is made of all 1-4 substituted phenylene rings (series p) the second series has a 1-3 substituted phenylene (isophthalic group) as the central aryl unit (series m). Due to the presence of the isophthalic unit a remarkable polymorphism was observed for the shortest ($n=5$) member of the series m [15],[16]. However, the longer members of the m-series and all members of the p-series assume a linear, extended conformation when recrystallized from solution [18]. These oligomer compounds, with a keto/ether molar ratio > 0.5 , crystallize from solution preferably in the more stable crystal polymorph form I in contrast to what has been observed for aromatic polyketones which exhibit the crystal form II [11].

Throughout the structural study of these oligo(aryl ether ketone)s, it was found out that the longest members ($n=11$) of both m and p series showed DSC traces with two melting peaks which were attributed to the melting of crystallites built up with short and polymeric chains [18]. Thus, the concurrent appearance of phases I and II and the two melting peaks (at 327 and

373°C) in case of the p11 sample has aimed us to follow the crystal phase transition, in real time, as it was done for the aromatic polyketones [10]. Furthermore, we think that these samples (p11 and m11), because of their blend nature, could be also good models to check the *double melting phenomenon* largely discussed in the field of aromatic polyketones [19],[20],[21],[22]. This phenomenon entails the appearance, in the thermograms of annealed polyketones, of an additional endothermic peak at about 15°C above the annealing temperature, T_a , used [23],[11].

The aim of this work is twofold: a) to furnish an improved description of the crystal phase transition of phases II into I, previously reported for aromatic polyketones [10]. b) to contribute to the understanding of the double melting phenomenon of aromatic polyketones. We trust that both objectives are covered by the study of the selected samples together with the application of synchrotron radiation techniques.

Experimental

Materials

The oligo(aryl ether ketone)s samples were synthesized by Prof. de Abajo and coworkers. A description of the preparation, thermal properties and crystalline structure for the samples can be found in reference [18]. Molecular compounds were denoted by mn and pn where n is the number of aryl units and m and p refer to the 1-3 and 1-4 substituted phenylene ring in the center of the molecule, respectively. The schematic chemical formula of the samples investigated are:

where ϕ is the 1-4 substituted phenylene ring and E and K refer to the ether (O) and ketone (CO) groups respectively.

While m7 is a pure molecular compound m11 and p11 also contain a fraction of *polymeric* chains. Consequently, the latter two samples showed two endothermic peaks at 240 and 265 °C (sample m11) and at 327 and 373

°C (sample p11)(see below in Fig. 11).

Experimental techniques

For the thermal study a Perkin-Elmer DSC-4 calorimeter was used. Thermograms were recorded at usual conditions: a heating rate of 10K/min, under nitrogen flow, and about 5-10 mg of sample. The calorimeter was calibrated with Indium standard. Thermal treatments of the samples were carried out inside the calorimeter. For the X-ray investigation of the crystal phase transition the facilities of the Synchrotron radiation beamline A2 at HASYLAB (DESY, Hamburg, Germany) were used. Wide and small angle X-ray scattering (WAXS and SAXS) patterns were simultaneously recorded, in real time, during heating of the sample. A wavelength $\lambda = 0.15$ nm was used. Frames were collected during 10 s (for m7) and 20 s (for p11 and m11) using a waiting time of 1 ms. Sintered samples were wrapped with aluminium foil to improve thermal contact and to prevent or at least reduce the loss of material when molten. A heating rate of 10K/min was used in a vacuum oven throughout the experiments. The analysis of consecutive WAXS and SAXS frames concerning peak intensity and angular position was done by means of a fit program in order to give a detailed description of the structural variations during heating of the sample. The WAXS crystallinity index was measured as the ratio between the area of Bragg's reflections and the total area for each consecutive X-ray pattern.

Results

Time resolved structural variations during heating

a) Crystal phase transition of the molecular compound m7

Fig. 1 shows the changes of the WAXS intensity profiles for the sample m7 during heating, at 10K/min, up to above the melting temperature. The WAXS pattern for the starting material mainly corresponds to the polymorph of phase II as revealed by the lower angle reflection at about 15.5° (010^{II}). The WAXS patterns of Fig. 1 reveal an abrupt change in intensity at about 164°C . Fig. 2 shows the intensity peak variation observed for three of the reflections at about 15.5 , 17.5 and $22.5^\circ(2\theta)$ which were indexed as 020, 023-024, and 110 respectively of an orthorhombic unit cell (form II) [18]. For

simplicity these reflections were denoted considering their angular position by the increasing numbers 1, 2, and 3. A slight increase of intensity during heating up to 150°C is observed for the three reflections. At about 164°C a crystal-crystal phase transition occurs. Thus, while the first reflection nearly disappears, the second one becomes the most intense reflection 110 of the new orthorhombic unit cell (form I) and the third reflection losses intensity and changes into the 200 reflection. From Fig. 2 and considering the heating rate used and data collection time one can say that the phase transition takes place within a narrow interval ($\leq 10K$) of temperature. The new crystal phase is stable up to about 220°C. Then a drastic loss of intensity of all crystalline peaks, associated to the melting of the sample, is observed. It is noteworthy the sharpness of both processes, crystal phase transition and melting, for this oligomer compound. Fig. 3 shows the variation of the lattice spacings calculated for the three reflections above mentioned. A small discontinuity in the spacing variation around 164°C is observed for the three reflections.

b) Crystal phase transition of sample p11

Fig. 4 shows the variation of WAXS (top) and SAXS (bottom) intensity profiles recorded simultaneously during heating of the sample p11 at 10K/min from 300°C till the complete melting of the sample. This sample clearly shows important variations of the SAXS intensity profiles with temperature. This result supports the partial polymeric nature of the sample. The WAXS pattern also confirms the coexistence of both crystal polymorphs II and I (reflections at about 15.5° (010^{II}) and about 20.5° (111^I)). Figs. 5 and 6 show the variation with temperature of the peak intensity and lattice spacings observed for the main Bragg's reflections. Concerning the peak intensity (Fig. 5), a slight increase is observed for all reflections up to about 280°C. For higher temperatures, while 010^{II} decreases till a complete disappearance at about 340°C, the other reflections increase and go through a maximum. This maximum is followed by a rapid intensity decrease till the total disappearance of the reflections at about 380°C. An inflexion point in intensity at temperatures around 340°C is observed. WAXS patterns of p11 above the latter temperature (340°C) exclusively show reflections from the crystal phase I. Concerning the lattice spacings (Fig. 6) a distinct change around 280°C is also detected suggesting the starting of crystal reorganization. For temperatures below 280°C the spacing of 010^{II} remains nearly constant or it

decreases while the spacing of the other reflections increases. This increase which could be related to a thermal lattice expansion seems to be larger for reflections related to phase II than for reflections of phase I (111^I). Above 280°C the increasing rate for the lattice spacing is smaller. Particularly, the plot corresponding to the 100^{II} – 200^I reflection (see Fig. 6) shows a minimum near 340 – 350°C and then slightly increases up to the melting temperature of the sample.

Fig. 7 shows the variation of the crystallinity index during heating of the p11 sample. The starting crystallinity value is about 50% which remains constant up to temperatures near to 300°C . Above this temperature a slight increase is observed up to 330°C followed by a rapid decrease down to 25% at about 340°C . Finally the crystallinity further decreases and becomes zero after melting of the sample.

Simultaneous WAXS and SAXS experiments were also carried out on the sample m11 (Fig. 8). In contrast to sample p11, sample m11 did not show any crystal phase transition during heating. This would be consistent with the presence of the phase I in the starting material. Let us recall the absence of the reflection 111^I (at about 20.5°) characteristic of the orthorhombic phase I in the case of aromatic polyketones based on the isophthalic unit [5]. Fig. 9 shows the intensity variation observed for the most representative reflections: 110^I (18°) and 200^I (23.5°). The intensity increases above 100°C ($T_g = 95^\circ\text{C}$) and remains constant up to the first melting temperature (240°C). Then the intensity abruptly decreases about $3/4$ of its value at 255°C and finally decreases down to zero at 270°C . The intensity variation of WAXS reflections during heating is consistent with the DSC trace reported [18] for sample m11 and shown below in Fig. 11.

c) SAXS development during heating for the p11 and m11 samples

The SAXS intensity profiles of Figs. 4 and 8 (bottom), were analyzed after Lorentz correction [24] by s^2 (where $s = 2\sin(\theta)/\lambda$) by using a fit program. A single SAXS maximum (Gaussian peak) with a long period L1 of about 6nm, is resolved for the lower temperatures. L1 remains nearly constant up to 200°C . Above this temperature and particularly for p11, the shape of the SAXS maximum changes by increasing its intensity mainly from the inner side (lower angular region). Therefore, a second maximum L2 is used to analyze the SAXS intensity profiles. From the angular position of peaks, the long periods L1 and L2 were calculated. The temperature dependence

of L1 and L2 is shown in Fig. 10. In case of sample m11 there is no such a clear resolution of the SAXS maximum L2 before disappearance of L1. Consequently, only a L curve (triangles) is drawn for m11.

Influence of molecular weight on the thermal behaviour

From the SAXS information presented here for samples p11 and m11 and the two endotherm peaks of their DSC traces [18](see below Fig. 11) it appears that p11 and m11 can be considered as blends of oligo- and polymeric materials. Taking into account the endothermic area of both peaks we can say that the relative content of polymeric material for m11 is less than for p11. In spite of being aware of the lack of information regarding molecular weight and chain distribution of the polymeric fraction, we think that these samples could be interesting to study the thermal behaviour of the polymeric fraction in the presence of short molecules (11 aryl units). Thus, in order to check the "double melting phenomenon" sample p11 and m11 were thermally treated at different temperatures for some period of time. Fig. 11 illustrates the first DSC traces for p11 and m11, respectively, before and after annealing at different temperatures. While the DSC traces from annealed m11 remain "unchanged" those from annealed p11 show a new endothermic peak, which appears at the same temperature (about 210°C) for the different T_a values used. Therefore, it can be said that the "double melting phenomenon of polyketones" is not observed for the above samples even if they contain a polymeric fraction. The structural meaning of the new endothermic peak observed for p11 is under investigation. In advance, we can say that there are no significant differences between the X-ray diffractograms recorded at room temperature and those for the samples annealed at different T_a .

Discussion

a) Isoenthalpic crystal phase transitions.

Taking into account the single endothermic peak of DSC thermograms of normal aromatic polyketones [11] and the crystal phase transition observed by X-ray diffraction [10], we can talk about the isoenthalpic character of the crystal phase transition involved (conversion of form II into I). Through-

out the study of oligo(aryl ether ketone)s the shortest molecular compound m5 exhibits a rich polymorphism (2 different polymorphs when recrystallized from solution and other 2 polymorphs after crystallization from the glassy state) [15],[16]. All these polymorphs show a distinct melting temperature. Consequently, the corresponding crystal phase transitions are non-isenthalpic. However, the polymorphism detected for the next member of the series, m7 [18] (Fig. 1) entails an isoenthalpic transition. The crystal phase transition of m7 (Fig. 2) is better defined than that observed for p11 (Fig. 5). The temperature interval of the phase transition is very much dependent of the perfection and size distribution of crystallites which ought to be poorer for a polymer material in relation to a molecular compound.

b)Influence of the blend nature on the thermal and structural variations during heating

The results presented in Figs. 5 and 7 for p11 point to a separate, independent melting of both the oligomer and polymer fractions. The structural data of Fig. 7 suggest that the melting of the oligomer crystals($< 340^{\circ}\text{C}$) occurs before the melting of the polymer crystalline fraction. This is in agreement with the two endothermic peaks observed for p11 (327 and 373°C); the lower temperature is associated to the melting of crystals from the oligomer component. Thus, the two endothermic peaks cannot be related to the crystal phase transition (II to I). Indeed, the crystal phase transition occurs during melting of the oligomer fraction. This becomes evident by comparison of the results shown here for p11 (Figs. 5 and 7) with those reported for the aromatic polyketones (Fig. 3 and 5 in reference [10]). In the case of a polymer material a crystal-crystal phase transition occurs and the intensity of reflections of phase I is maximum when reflections of phase II disappear. On the contrary, for p11 the maximum intensity of the reflections of phase I occurs some degrees before the total disappearance of phase II.

A question arises about which crystal polymorph (I or II) is present in the two components of sample p11 (according to Fig. 2 top, both crystal polymorphs I and II are present): does the oligomer component assume crystal phase II as well?. We know that aromatic polyketones with a keto/ether molar ratio similar to that of p11 (0.6) assume crystal phase II [11]. Thus, we believe this is the most probable situation for the polymer component of p11. Furthermore, oligomers of series p directly crystallize in the crystal

form I [18]. Therefore, the presence of phase I in the original sample should be attributed to the oligomer component. This oligomer component would be responsible of the lower temperature peak (327°C) observed for p11. Just at this temperature the maximum intensity of WAXS reflections is observed (Fig. 5). The higher melting peak (373°C) should be exclusively related to the polymer component whose contribution is about 50% of the crystalline material according to Fig. 7. The data shown in Fig. 5 are shifted to lower temperatures by about 10°C in relation to those reported for PEKEKK [10]. This may be due to a lowering temperature effect caused by the molten oligomeric material.

The variation of SAXS patterns during heating of the samples p11 (Fig. 4 bottom) and m11 (Fig. 8 bottom) and the calculated long periods (Fig. 10) can be also explained in the light of the nature of blend materials. Thus, the presence of a SAXS maximum of about 6nm (equal to the molecular length for 11 aryl units) which remains nearly constant during heating can be related to the oligomeric component that does not undergo chain reorganization upon annealing. The emerging SAXS intensity during heating, responsible for the L2 period, increases and shifts towards smaller scattering angles with temperature. The SAXS intensity variation associated to L2, as well as that observed for m11 above 225°C, is typical of a polymeric material which undergoes lamellar thickening upon annealing [25], [26].

c) Absence of a double melting phenomenon in the polymer component

In contrast to the common observation for annealed aromatic polyketones, (presence of a new endothermic peak correlated to the annealing temperature) [19],[23], the DSC results shown in Fig. 11 indicate a dissimilar behaviour of the polymeric component for p11 and m11 samples in relation to that exhibited by aromatic polyketones. In addition to the observed structural changes (crystal thickening and crystal perfection) in the microstructure of annealed polyketones [22] some rearrangement of disordered chain segments appears to occur upon annealing of the polymer [21]. Thus, we think that the endothermic peak related to T_a could be visualized as an "enthalpy excess" localized in chain segments of disordered material. According to the morphology of a polymer sample many of the amorphous segments should lie in between adjacent lamellar crystallites which prevent from a

propagation of the stored segmental relaxation, via free chain ends. In the case of samples m11 and p11, probably due to the presence of a considerable amount of short molecules, the fraction of polymeric chains should be more detached and/or disentangled from each other. Consequently, an improved propagation of localized segmental states along the chain could occur. This might be a main reason for the absence of a new endothermic peak related to the annealing temperature in the DSC traces shown in Fig. 11.

Conclusions

From the above results we can draw the following conclusions:

- The polymorphic transition (form II to I) of the molecular compound m7 is very sharp, as revealed by WAXS, in comparison to the phase transition of the polymer component of sample p11 or that reported for PEKEKK [10].
- The phase transition for the sample p11 occurs about 10–25°C below the temperature reported for PEKEKK samples [10]. This can be attributed to the influence of the oligomer crystals which melt during the chain rearrangement occurring in the polymer crystals of form II.
- The variation of the two long periods during heating of p11 confirms the blend nature of the sample. L1 (6nm) is associated to the lamellar thickness of crystals with linear, extended molecules. The L1 value remains nearly constant with increasing temperatures and it disappears when melting of the molecular crystals. On the other hand L2 is associated to the polymer component and becomes resolved at temperatures near 200°C. Above this temperature L2 continuously increases till the SAXS maximum disappears because of the structural reorganization after melting of short molecular crystals.
- No "double melting phenomenon" was observed for the samples p11 and m11 even if they contain a polymer chain component. It is proposed that, due too the presence of short molecules, there is an enhanced propagation of relaxed segmental states created on sample annealing. This propagation takes place along the polymer chains which, in our case, are more detached from each other than for typical polyketone samples.

Acknowledgements

The authors acknowledge the facilities found at the Polymer beamline A2 of HASYLAB, DESY, Hamburg and the funding from the Program Human Capital and Mobility, Access to Large Installations EC. Grateful acknowledgement is due to DGICYT, Spain, for the support of this investigation (grant PB94-0049)

References

- [1] Sataniland, P.A. in *"Comprehensive Polymer Science"* G. Allen, J.C. Bevington, Eds; Pergamon: Oxford, UK, 1989 Vol. 5, pp 483–497
- [2] Mullins, M.J.; Woo, E.P. *JMS-Rev. Macromol. Chem. Phys.* **1987**, C27, 313
- [3] Gardner, K.H.; Hsiao, B.S.; Matheson, R.R. Jr.; Wood, B.A. *Polymer* **1992**, 33, 3483
- [4] Gardner, K.H.; Hsiao, B.S.; Faron, K.L. *Polymer* **1994**, 35, 2290
- [5] Cheng, S.Z.D; Ho, R.M; Hsiao, B.S.; Gardner, K.H. *Macromol. Chem. Phys.* **1996**, 197, 185
- [6] Boon, J; Magre, E.P. *Makromol. Chem.* **1969**, 126, 130
- [7] Dawson, P.C; Blundell, D.J. *Polymer* **1980**, 21, 577
- [8] Rueda, D.R.; Ania, F.; Richardson, A.; Ward, I.M.; Baltá Calleja, F.J. *Polymer Commun.* **1983**, 24, 258
- [9] Blundell, D.J.; Newton, A.B. *Polymer* **1991**, 32, 308
- [10] Rueda, D.R.; García Gutiérrez, M.C.; Ania, F.; Zolotukhin, M.G.; Baltá Calleja, F.J. *Macromolecules* **1998**, 31(23), 8201
- [11] Rueda, D.R.; Zolotukhin, M.G.; Cagiao, M.E.; Baltá Calleja, F.J.; Villers, D.; Dosièrè, M. *Macromolecules* **1996**, 29(22), 7016
- [12] Jonas, A; Legras, R.; Devaux, J. *Macromolecules* **1992**, 25, 5841
- [13] Jonas, A.; Legras, R.; Scherrenberg, R.; Reynaers, H. *Macromolecules* **1993**, 26, 526
- [14] Shibata, M.; Yosomiya, R.; Zheng, Y.B.; Ke, Y.C. *Macromol. Chem. Phys.* **1996**, 197, 3297
- [15] Rueda, D.R.; Zolotukhin, M.G.; Andrè, I.; Martínez-Ripoll, M.; de Abajo, J.; Alvarez, J.C. *Macromol. Chem. Phys.* **1997**, 198, 2089
- [16] Rueda, D.R.; Zolotukhin, M.G. *Macromol. Chem. Phys.* **1997**, 198, 3517

- [17] Baxter, I.; Colquhoun, H.W.; Kohnke, F.H.; Lewis, D.F.; Williams, D.J. *Polymer* **1999**, 40, 607
- [18] Rueda, D.R.; Zolotukhin, M.G.; Neulqueo, G; García, C.; de la Campa, J.G.; de Abajo, J. *Macromol. Chem. Phys.* **in press**
- [19] Blundell, D.J.; Osborn, B.N. *Polymer* **1983**, 24, 953
- [20] Cheng, S.Z.D.; Cao, M.Y.; Wunderlich, B. *Macromolecules* **1986**, 19, 1868
- [21] Lee, Y.; Porter, R.S. *Macromolecules* **1987**, 20, 1336
- [22] Bassett, D.C.; Olley, R.H.; Al Raheil, I.A.M. *Polymer* **1988**, 29, 1745
- [23] Lee, Y; Porter, R.S.; Lin, J.S. *Macromolecules* **1989**, 22, 1756
- [24] Baltá Calleja, F.J.; Vonk, C.G. "*X-ray Scattering of Synthetic Polymers*" Elsevier, Amsterdam 1989, pp 271.
- [25] Wunderlich, B. "*Macromolecular Physics: 2 Crystal Nucleation Growth, Annealing*" Academic Press, N.Y. London 1978
- [26] Fischer, E.W.; Schmidt, G.F. *Angw. Chem.* **1962**, 74, 551

Caption to Figures

- Fig. 1 Change of WAXS intensity profiles during heating of the sample m7.
- Fig. 2 Variation of the peak intensity for three main reflections at Fig. 1 during heating of m7. (1, 2 and 3 denote the main reflections of increasing diffraction angle, respectively). The melting point of the sample is indicated.
- Fig. 3 Variation of the lattice spacings for the three reflections of Fig. 2 during heating of sample m7.
- Fig. 4 Change of WAXS (top) and SAXS (bottom) intensity profiles, recorded simultaneously, during heating of the sample p11.
- Fig. 5 Variation of the peak intensity of the 4 lowest angle reflections of Fig. 4 (top) during heating of the sample p11.
- Fig. 6 Temperature dependence of the lattice spacings calculated for the 4 reflections of Fig. 5.
- Fig. 7 Change of the WAXS crystallinity index observed during heating of p11. The two melting points are indicated.
- Fig. 8 Change of WAXS (top) and SAXS (bottom) intensity profiles, recorded simultaneously, during heating of the sample m11.
- Fig. 9 Variation of the peak intensity of the two main reflections of Fig. 8 (top) during heating of m11. The two melting points are indicated.
- Fig. 10 Variation of SAXS long periods as a function of temperature observed for the samples p11 and m11 (triangles).
- Fig. 11 First DSC traces recorded for the samples p11 (top) and m11 (bottom) before and after annealing at different temperatures.

Rueda et al.
Fig. 1

Rueda et al.
Fig. 2

Rueda et al.
Fig. 3

Rueda et al.
Fig. 4

Rueda et al.
Fig. 5

Rueda et al.
Fig. 6

Rueda et al.
Fig. 7

Rueda et al.
Fig. 8

Rueda et al.
Fig. 9

Rueda et al.,
Fig. 10

Rueda et al.
Fig. 11