**MICROSTRUCTURE OF BULK CRYSTALLIZED LINEAR POLYETHYLENE:
CORRELATION OF MICROHARDNESS AND YIELD STRESS**

F.J. Baltá Calleja and L.Giri

Instituto de Estructura de la Materia, CSIC
Serrano 119. 28006 Madrid, Spain

I.M. Ward and D.L.M. Cansfield

IRC in Polymer Science and Technology, University of Leeds,
Leeds LS2 9JT, UK

Abstract

The effect of molecular weight on the yield behaviour and microhardness of melt crystallized polyethylene has been studied. The influence of the crystallization conditions on the mechanical properties have been examined. It is shown that Tabor's relationship between microhardness and yield stress applies if the strain rate of the tensile tests is comparable to that employed in the hardness indentation tests. Results are discussed in terms of surface free energy which depends on the number of molecular entanglements segregated onto the surface of the lamellar crystals controlling the yield behaviour of the polymer.

INTRODUCTION

In recent years microindentation hardness (H) has been shown to be a powerful technique to accurately determine changes in morphology and microstructure of semicrystalline polymers [1,2]. The indentation process involves a permanent deformation on a very small scale at the polymer surface. Consequently the microhardness is directly correlated with the mechanisms of plastic deformation of the semicrystalline solid and depends on the average thickness (l_c) of the densely stacked lamellae within the polymer. The hardness of the crystals themselves (H_c), when indentation is done at $T_g < T$, can be derived from the hardness of the polymer by using the relation:

$$H_c = H/\alpha \quad (1)$$

where α is the degree of crystallinity. This equation assumes that the semicrystalline polymer is a two-phase system and that yield is due to plastic deformation taking place only in the crystalline regions [3]. Young et al. have demonstrated that the amorphous regions in PE undergo only elastic deformation at room temperature [4]. Recent research by Brooks, Duckett and Ward [5] shows that the yield behaviour of polyethylene is complex and that two deformation processes can be identified. The high stress process defines the onset of permanent deformation and has been associated with the c-slip process which is consistent with the

conclusions of these previous studies. The crystal hardness, H_C , has been additionally correlated to the thickness of the lamellae by Baltá Calleja and Kilian [6] using a heterogeneous model of deformation. The hardness of the crystals can be accordingly described by:

$$H_C = H_0^\infty / (1 + b/l_C) \quad (2)$$

where H_0 is the hardness of an infinitely thick crystal and b is a parameter equal to $2\sigma_e/\delta h$, where σ_e is the surface free energy and δh is the enthalpy of the crystal destruction. This model has been successfully applied for different lamellar structures [7-10]. Equation (2) describes the depression of crystal hardness due to finite crystal thickness and is characterized by the above b -parameter which is related to the equilibrium properties of the crystals.

The microhardness of a material can, furthermore, be derived macroscopically by a yield stress (Y) measurement using Tabor's relation [11],

$$H \approx 3Y \quad (3)$$

By combination of equations 1, 2 and 3, Tabor's relation can be rewritten in a more general form as,

$$Y \approx H/3 = \alpha H_0^\infty / (1 + b/l_C) \quad (4)$$

Hence, microhardness can be considered as a bridging parameter between microstructural quantities (l_c, α, b), on the one hand, and bulk mechanical properties (Yield stress, elastic modulus etc.) on the other. In a previous work, the microhardness of a series of melt-crystallized linear polyethylene having a wide range of molecular weights (M_w) was investigated [12]. The X-ray long period was measured to study the variation of hardness derived constant b as a function of M_w . The obtained data indicated an increase of b with M_w showing a final leveling-off of b for $M_w > 200000$, which was parallel to the concurrent increase in surface free energy derived from calorimetric experiments. Comparison of experimental and calculated data favoured the view that the number of chain defects (molecular entanglements) segregated on to the defective surface of the crystals influenced the shearing mechanism under the point indenter controlling the yield behaviour of the material.

The aims of the present study are the following:

- i) To extend the above investigations to the case of polyethylene (PE) materials, crystallized under different cooling rates in order to examine the influence of molecular weight and, hence, of the number of molecular defects, on the mechanical parameter b .
- ii) To carry out parallel yield stress measurements on the same samples and investigate the influence of the strain rate on Tabor's relationship.

EXPERIMENTAL

i) Materials

The polymers used were either commercial grades of linear polyethylene homopolymer manufactured by BP Chemicals International Ltd or Fabwerke Hoechst A.G., or experimental grades kindly provided by BP chemicals, Polymer Sciences Branch, Grangemouth UK. The molecular weight characteristics of the polymers are given in Table 1. Both M_w and M_n were obtained by gel permeation chromatography, for all samples.

Isotropic sheets of approximately 0.5 mm thickness were obtained by compression moulding polymer pellets (powder in the case of 7 and 8) between polished copper plates at 160°C. The procedure has been described in more detail in previous publications [13,14].

For the present investigation two standard cooling procedures were adopted:

i) The molten product was immediately quenched into water at ambient temperature (20°C). These samples are designated as **quenched**.

ii) The sheets containing the polymer were cooled slowly at about 10°C per minute to 110°C, and then quenched into cold water. These samples are designated as **slow cooled**.

ii) Techniques

Measurements of microhardness

Microhardness was measured at room temperature using a Leitz Tester adapted with a square based diamond indenter. The H-value was derived from the residual projected area of indentation according to the expression $H = kP/d^2$ (MPa), where d is the length of the impression diagonal in meters, P the contact load applied in N and k is a geometrical factor equal to 1.854. Four loads (0.1, 0.2, 0.5, and 1 N) and various loading cycles of 0.5, 0.1, 1 and 5 minutes were used to correct for the instant elastic recovery.

Measurements of yield stress

Dumbbell shaped samples with gauge dimensions 2 x 0.5 cm were cut from the isotropic sheets. For the measurements of yield stress these were extended in an Instron tensile testing machine at two cross head speeds of 2 cm/min and 0.02 cm/min at a temperature of $21 \pm 1^\circ\text{C}$. The yield stress was measured arbitrarily as the peak force on the load-extension curve.

RESULTS

The values of hardness (H) (derived from the average of 10 indentations on each polymer), crystal hardness (H_c), crystal thickness (l_c) and the mechanical parameter b together with M_w and crystallinity (α) derived from density are given in Table 2. The l_c values were calculated from the long spacing L , according to: $l_c = L\alpha$ using the data from Capaccio et al [15,16]. Fig.1 clearly shows the gradual decrease of H with M_w for both cooling rates. However, the quenched samples show lower H -values than the slowly cooled ones.

The yield stress data and the H/Y ratio are shown in Tables 3a and 3b, where each value of the yield stress is the mean of three tests on each polymer. The yield stress is seen to be strain rate dependent, as expected [17]. The strain rate for a cross head speed of 0.02 cm/min is $1.6 \times 10^{-4} \text{ sec}^{-1}$, which is comparable to that employed in the hardness indentation tests. When the ratio H/Y is computed for this strain rate, it is seen that the ratio is very close to 3 as proposed by Tabor [11]. Fig.2 shows the corresponding straight line with slope 3. For a higher strain rate the H/Y ratio is much lower (~ 2) than predicted according to Tabor's relation. It is also observed that similar to H -value, the Y -value tends to decrease slightly with increasing molecular weight and that the yield stress is higher for the slow cooled samples than for the rapidly quenched ones.

DISCUSSION

Previous studies [14,15] have shown that there are remarkable differences in morphology between samples of different initial thermal treatment, and that these differences depend on the molecular weight characteristics. The rapidly quenched samples show the typical banded spherulitic texture. Crystallization has occurred under conditions of high supercooling, producing a complex spherulitic geometry with twisting and branching as the lamellae grow radially from the point of nucleation. On the other hand in the slowly cooled samples, crystallization takes place initially at high temperatures i.e. low supercooling and a more regular texture is produced, with the additional complexity that high molecular weight polymer crystallizes first, and low molecular weight on subsequent cooling i.e. there is segregation by molecular weight. The implication of these observations on the drawing behaviour have been discussed in the previous publication [14]. Popli and Mandelkern [18] found, however, that spherulite size does not have direct influence upon yield in PE. In preceding studies we recognized the direct influence of crystal thickness (l_c) upon microhardness H in case of chain-folded and chain-extended PE samples [1,6]. Popli et al [18] and Crist et al [19] have also given evidence for the dependence of yield stress on l_c .

However, in the present work, l_c , for the quenched and slow cooled samples, is shown to be independent of M_w and thus, it does not affect the H_c values in eqn.(2). (see Table 2). Therefore, the decrease in hardness observed in Fig.1 is obviously only due to the decrease in crystallinity with increasing M_w . On the other hand, since H_c does not depend on crystallinity, the initial decrease of H_c and final leveling off with M_w (Fig.3) can be straightforwardly explained in terms of the variation of the b -parameter with M_w shown in Fig.4.

Holl et al [20] have pointed out that the fraction of permanent defects in the semicrystalline state of polymers is related to the average density of the entanglements in the melt. However, after crystallization defects are permanently located at the crystal surface and cannot be removed as occurs in the molten state. The surface free energy, σ_e , of the folded chain lamellae with chain defects corresponds to the lowest free energy and is proportional to b . Consequently σ_e ought to increase with increasing concentration of defects. It is known that the concentration of entanglements in the melt is always constant for a given molecular weight. Because the slow cooled materials show thicker crystals due to the slow cooling rate and lower supercooling, there is, therefore, a greater concentration of entanglements on the crystal surface, compared with the quenched materials where the entanglements are largely concentrated in the amorphous phase. From Fig.4 one sees that the quenched samples

have lower b -values as compared to those of the slow cooled ones. On the other hand, if the length of the chains is increased, then, the number of defects increases and, above a critical molecular weight value of M_c , the defective surface layer is saturated with defects. If the chain length is further increased beyond M_c the density of the entanglements and the chain loops which are in the melt cannot be located any further at the crystal surface. These equilibrium defects are then rejected into the amorphous phase. Hence, for slow cooled samples the parameter b remains constant beyond $M_w > 200,000$. However, the quenched samples also show a clear influence of the M_w on the b parameter, although for very high M_w , the saturation value of b is not achieved. This suggest that at the higher cooling rate, the number of chain defects and entanglements at the crystal surface is still lower than for the slowly crystallized samples.

We have seen that Tabor relation [11] applies for the yield stress experiments in which the strain rate is similar to that under the indenter. These results show that Tabor's relation applies well for PE materials with widely varying morphologies, when recoverable viscoelastic deformation is minimized (loading time=few secs.)(see Fig.2). The data of Fig.2 emphasize that crystallinity, on one hand, and surface free energy (molecular weight), on the other, are mainly the two parameters which are monitoring the yield stress values of these PE samples. The deviation from the $H \approx 3Y$ predictions for the slow cooled high

molecular weight sample could have the following reason: the yield point for this sample is not so well defined and, therefore, some uncertainty concerning the Y value is involved. On the other hand, the high H/Y ratio obtained for the slowly crystallized sample with lowest molecular weight could be due to the influence of a strain hardening effect, during the indentation of this highly crystalline sample.

CONCLUSIONS

From the above discussion, we can conclude that, Tabor's relation applies when the strain rate of the tensile test is comparable to that employed in the hardness test. The rate of cooling affects the crystallinity and the b parameter and consequently the hardness value (H). Results confirm for the slow cooled samples the increase of b parameter with increasing M_w , showing a final levelling off for $M_w > 200,000$. However, for the quenched samples this levelling off is not so clear.

Acknowledgments

Grateful acknowledgment is due to CICYT (Grant MAT94-0740-E) Spain for the generous support of this Investigation. We wish to thank Dr. C. Santa Cruz for carrying out the microhardness measurements. One of us (L. Giri) wishes to thank the tenure of a grant of the Ministerio de Educación y Ciencia, Spain.

REFERENCES

1. F.J. BALTA CALLEJA, Adv. Polym. Sci. **66** (1985) 117.
2. J. BOWMANN and M. BEVIS, Colloid & Polym. Sci. **255** (1977) 954
3. C. SANTA CRUZ, F.J. BALTA CALLEJA, H.G. ZACHMANN, N. STRIBECK and T. ASANO, J. Polym. Sci.; Polym. Phys. **B29** (1991) 819.
4. R.J. YOUNG, P.S. BOWDEN, J.M. RITCHIE and J.G. RIDER, J. Mater. Sci. **8** (1973) 23.
5. N.W. BROOKS, R.A. DUCKETT and I.M. WARD, Polymer **33** (1992) 1872.
6. F.J. BALTA CALLEJA and H.G. KILIAN, Colloid & Polym. Sci. **263** (1985) 697.
7. F.J. BALTA CALLEJA, D.R. RUEDA, J. GARCIA, F.P. WOLF and V.H. KARL, J. Mater. Sci. **21** (1986) 1139.
8. F. ANIA, H.G. KILIAN and F.J. BALTA CALLEJA, J. Mater. Sci. Lett. **5** (1986) 1183.
9. M.E. CAGIAO, D.R. RUEDA and F.J. BALTA CALLEJA, Colloid & Polym. Sci. **265** (1987) 37.
10. Y. DESLANDES, E. ALVA ROSA, F. BRISSE and T. MENEHINI, J. Mater. Sci. **26** (1991) 2769.
11. D. TABOR, "Gases, Liquids and Solids", 2nd ed. (Cambridge Univ. Press 1979), p. 188.
12. F.J. BALTA CALLEJA, C. SANTA CRUZ, R.K. BAYER and H.G. KILIAN, Colloid & Polym. Sci. **268** (1990) 440.
13. G. CAPACCIO and I.M. WARD, Polymer **15** (1974) 233.

14. G. CAPACCIO, T.A. CROMPTON and I.M. WARD, J. Polym. Sci.; Polym. Phys. Edn. **14** (1976) 1641.
15. G. CAPACCIO and I.M. WARD, Polymer **16** (1975) 241.
16. G. CAPACCIO, I.M. WARD, M.A. WILDING and G.W. LONGMAN, Macromolecular Sci.Phys. **B15** (1978) 381.
17. D.L.M. CANSFIELD, I.M. WARD, D.W. WOODS, J.M. PIERCE and J.L. WESLEY, Polymer Communications **24** (1983) 130.
18. R. POPLI and L. MANDELKERN, J. Polym. Sci.; Polym. Phys. **25** (1987) 441.
19. B. CRIST, C.J. FISHER and P.R. HOWARD, Macromolecules **22** (1989) 1709.
20. B. HOLL, B. HEISE and H.G. KILIAN, Colloid & Polym. Sci. **261** (1983) 978.

TABLE 1

Molecular Weight Characteristics of Polymers

Sample	Polymer Grade	Melt flow Index [*]	M _n	M _w	M _w /M _n
1	140-60 ^a	12.7	13,300	67,800	5.1
2	BXP 10 ^b	4.6	16,800	93,800	5.6
3	R 25 ^a	3.0	12,950	98,800	7.6
4	R 50 ^a	6.0	6,530	101,400	15.5
5	R 9 ^a	1.1	6,060	126,600	20.9
6	BP 206 ^b	0.23	16,600	213,000	12.8
7	HO20-54P ^a	2.2	33,000	312,000	9.5
8	GUR ^c		383,000	2.3x10 ⁶	6.0

- * BS 2782 Method 105C
a BP Chemicals Int. Ltd.
b Experimental polymer
c Farbwerke Hoechst A.G.

TABLE 2

Values of H , α , H_C , l_C and b as a function of M_w

2a. Quenched samples

Sample no.	M_w	H (MPa)	α	H_C (MPa)	l_C (Å)	b (Å)
1.	67800	58	0.67	86	137	133
2.	93800	56	0.66	85	-	-
3.	98800	53	0.64	83	138	145
4.	101450	54	0.67	81	127	141
5.	126600	52	0.67	78	160	189
6.	213000	47	0.64	73	-	-
7.	312000	45	0.63	71	152	210
8.	2.3×10^6	33	0.48	69	165	241

2b. Slowly cooled samples

Sample no.	M_w	H (MPa)	α	H_C (MPa)	l_C (Å)	b (Å)
1.	67800	71	0.77	92	213	183
2.	93800	65	0.74	88	-	-
3.	98800	64	0.76	84	213	218
4.	101450	64	0.78	82	195	208
5.	126600	62	0.76	82	195	212
6.	213000	58	0.72	81	-	-
7.	312000	57	0.71	80	243	276
8.	2.3×10^6	44	0.57	77	225	271

TABLE 3a

Yield Stress Data for the Quenched Samples

Sample	Yield Stress (MPa) 2 cm/min	H/Y ₂	Yield Stress (MPa) 0.02 cm/min	H/Y _{0.02}
1	26.7	2.17	18.1	3.20
2	25.5	2.19	17.5	3.20
3	24.8	2.13	17.5	3.02
4	26.9	2.0	18.1	2.98
5	25.0	2.08	17.4	2.98
6	24.3	1.93	16.9	2.78
7	21.8	2.07	15.9	2.81
8	18.0 ^x	1.83		

^x no definite yield point only change in slope.

TABLE 3b

Yield Stress Data for Slow Cooled Samples

Sample	Yield Stress (MPa) 2 cm/min	H/Y ₂	Yield Stress (MPa) 0.02 cm/min	H/Y _{0.02}
1	31.12	2.28	22.09	3.21
2	28.76	2.26	21.46	3.03
3	30.14	2.13	21.77	2.93
4	30.79	2.08	21.62	2.96
5	28.86	2.15	22.03	2.81
6	27.75	2.11	20.23	2.86
7	28.22	2.02	19.70	2.89
8	22.84 ^x	1.93	11.98 ^x	3.67

^x no definite yield point change of slope only.

Figure Captions

- Fig.1. Variation of microhardness (H) as a function of molecular weight (M_w) for melt crystallized PE: (o) quenched, ($\blacktriangle$) slow cooled.
- Fig.2. Correlation between microhardness (H) and yield stress (Y) for melt crystallized PE: (o) quenched, ($\blacktriangle$) slow cooled.
- Fig.3. Variation of crystal hardness (H_c) as a function of molecular weight (M_w). (o) quenched, ($\blacktriangle$) slow cooled.
- Fig.4. Dependence of the mechanical parameter b upon molecular weight (M_w). (o) quenched, ($\blacktriangle$) slow cooled.

Fig-1.

Fig 2

Fig 3

FIG. 41.