CURIE TRANSITION OF THE 70/30 POLYVINYLIDENE-TRIFLUOR ETHYLENE COPOLYMER AS REVEALED BY X-RAY SYNCHROTRON RADIATION

E. LOPEZ CABARCOS^{*}, A. GONZALEZ ARCHE[†], J. MARTINEZ SALAZAR[†], F.J. BALTA CALLEJA[†]

^{*}Dpto. Química Física, Facultad de Farmacia, U.C.M. 28040 Madrid.

[†]E.U.I.T. Telecomunicaciones, 28031 Madrid.

⁺Instituto de Estructura de la Materia, C.S.I.C., Serrano 119. 28006 Madrid.

SYNOPSIS

Real time WAXD and SAXS experiments from a 70/30 Polyvinylidene-Fluoride-Trifluor ethylene copolymer are reported as a function of temperature. The Curie transition (ferro-paraelectric) detected in the 80-110°C interval, is associated to a sudden decrease of the invariant. Comparison of the experimental and calculated invariant data assuming a simple model support the view of the two phases coexisting within the crystalline material, throughout the transition range studied.

1. INTRODUCTION

Since the early work of Lando and Doll¹ showing that vinylidene fluoride (VF₂)-trifluorethylene (F₃E) copolymer adopt the β -phase conformation of PVF₂, much attention has been recently directed towards these materials because of their relevant piezoelectric and pyroelectric properties. It is known that for concentrations of VF₂ between 50 and 80% these copolymers exhibits a Curie transition². The ferroelectric paraelectric transition occurs at a temperature which depends on the copolymer concentration. Most of the work carried out on these materials has been devoted to their dielectric properties³. However, little effort has been done, as far as we know, on the actual mechanism of transformation. Lovinger et al⁴⁻⁷ and Tashiro et al⁸ have investigated the above transition in copolymers with 52/48, 65/35, 73/27 and 78/22 compositions using wide angle X-ray diffraction (WAXD). These authors conclude that the ferroelectric phase consists of chains in a polar trans conformation whereas in the

paraelectric phase the chains are partly disordered exhibiting tg, t $\bar{g}$ and tt sequences. Legrand et al⁹ investigated the 70/30 composition by NMR techniques suggesting that in the paraelectric phase each segment of the molecule has several possible equilibrium positions.

In the present study we report novel diffraction data concerning the microstructural behaviour through the Curie transition of the 70/30 copolymer. The present measurements have been carried out with help of a synchrotron radiation source having the advantage to yield real-time WAXD and SAXS patterns as a function of temperature.

2. EXPERIMENTAL

Commercial pellets of VF₂/F₃E (70/30) copolymer from Atochem were melted at 200°C during 8 minutes in a heating press. Films of about 100µm were subsequently crystallized by quenching the molten sample instantly into an ice-water bath. WAXD and SAXS measurements were performed using the synchrotron radiation which is produced by the positron beam of the DORIS storage ring at DESY. The machine was operated at 5.0GeV with beam currents between 10 and 30mA. The detector used was one-dimensional position sensitive proportional counter with a LC-delay line, filled with an Ar/CO-mixture at 3.5atm. pressure. Positional information from the counter was decoded using direct time digitalisation or a 500 MHz clock frequency. This information was fed into 256 position channels representing the 8cm length of the counter. The samples were heated at a rate of 10°C/min in a furnace, between two aluminium foils, to allow homogeneous heating from room temperature, through the transition temperature, beyond 110°C. DSC curves were recorded at 10°/min using a Mettler scanning calorimeter.

3. RESULTS AND DISCUSSION

Figure 1 illustrates the DSC transition from the ferro- to the paraelectric phase for the 70/30 copolymer in the 80-110°C range and the final endothermic melting peak at 153°C. Real time wide angle X-ray scattering (WAXS) patterns corresponding to the phase transition are shown in Figure 2 as a function of temperature. For the initial quenched sample, one observes the ferroelectric peak located at $2\theta=19.9^\circ$ coexisting with the amorphous halo together with an incipient shoulder which we attribute to the paraelectric phase. The shoulder gradually transforms into the paraelectric peak at $2\theta=18.2^\circ$ with increasing temperature. The transition is complete at about 110°C where the ferroelectric peak has totally vanished and only the paraelectric maximum remains.

Fig. 1. DSC endotherm of 70/30 copolymer showing the ferro-paraelectric transition (left) and the melting peak (right).

Fig. 2. WAXD patterns of the 70/30 copolymer as a function of increasing temperature showing the ferro-paraelectric transition.

The ferroelectric transition can also be conveniently detected following the small angle X-ray scattering (SAXS) maximum with increasing temperature. Figure 3 illustrates the evolution of the low angle scattering intensity with increasing heating temperatures. The intensity gradually rises from 50°C up to a maximum at about 96°C, shows a minimum at the end of the phase-transition and thereafter it increases with T up to the vicinity of the melting point, where it finally drops to zero. Figure 4 depicts the variation of the integrated intensity of the small angle peak in the temperature range studied. From these data it is concluded that the ferro-paraelectric transition is directly correlated with a sudden decrease of scattering intensity. The variation of the long period L, as a function of heating temperature is shown in Figure 5. The relevant result here is the nearly constancy of L over the transition region (90-110°C). Annealing beyond 110°C causes the long period to increase very rapidly as it occurs in common semicrystalline polymers¹⁰.

The above results can be discussed in terms of the following model: it should suffice to assume that the low angle maxima provides a measure of the stacking of crystalline lamellae in which the coexistence of paraelectric and ferroelectric phases is postulated. According to this concept the invariant quantity Q can be calculated from the expression:

$$Q = (\rho_c - \rho_a)^2 w_c (1 - w_c) \quad (1)$$

where ρ_a is the density of the amorphous layers sandwiched between the crystals, w_c is the crystallinity value and ρ_c is the average crystal density given by:

$$\bar{\rho}_c = \rho_c^f w_c^f + \rho_c^p w_c^p \quad (2)$$

where $\rho_c^f = 1.97 \text{ g/cm}^3$, $\rho_c^p = 1.83 \text{ g/cm}^3$ are the crystalline densities for para- and ferroelectric crystals, derived from the unit cell dimensions, $\rho_a = 1.68 \text{ g/cm}^3$ and w_c^f and w_c^p are the volume fractions of both phases. The values of w_c^f and w_c^p were derived from the WAXD patterns of Figure 2 with help of a curve analyzer using Gaussian profiles. The analysis of crystalline and amorphous phases yields a crystallinity value $w_c = 45-47\%$ which remains constant within the transition range investigated. In summary, it turns out that the parameters L and w_c are constant throughout the transition interval. Hence, the stepwise decrease of Q in Fig. 4 is mainly the result of the $\bar{\rho}_c$ decrease, owing to the rapid increase of w_c^p at expenses of w_c^f in eq. 2; comparison of experimental results (Fig. 4) with the calculated Q-data from eq. 1 in the transition range shows an excellent

Fig. 3. Variation of SAXS maximum of the 70/30 copolymer with increasing temperature.

Fig. 4. SAXS integral scattering intensity in relative units vs. temperature (the integration limits are $s=2 \times 10^{-3} \text{ \AA}^{-1}$ and $s=2 \times 10^{-2} \text{ \AA}^{-1}$).

Fig. 5. Long period of the copolymer vs. heating temperature

Fig. 6. Calculated invariant data from eq. 1 (Δ) as compared with experimental results ($\blacksquare$) from Fig. 4 in the transition region.

agreement as evidenced in Fig. 6, thus, supporting the model of the two coexisting crystalline phases throughout the transition interval investigated. The only question which still remains open is whether the ferro and paraelectric phases may coexist within a crystal or rather contribute to the scattering as randomly distributed stacks of independent lamellae.

4. CONCLUSIONS

A ferroelectric-paraelectric transition has been measured for the first time in the copolymer with 70/30 ($\text{CF}_2/\text{F}_3\text{E}$ % mol) composition in real time SAXS experiments. Small angle intensity data have been quantitatively interpreted in terms of a two-phase model assuming the coexistence of ferroelectric and paraelectric crystalline regions throughout the transition range of 80-110°C.

ACKNOWLEDGMENTS

Grateful acknowledgment is due to Prof. H.G. Zachmann for permitting the authors to use the synchrotron facilities at DESY and Messrs. P. Bosecke and S. Buchner for their valuable help during the experimental work. This work was partly supported by CAICYT, Spain.

REFERENCES

1. J.B. Lando, W.W. Doll, J. Macromol. Sci. Phys. B, 2, 205 (1968)
2. T. Yagi, M. Tatemoto, J. Sako, Polymer J., 12, 209 (1980)
3. N. Koizumi, N. Haikawa, H. Habuba, Ferroelectrics, 57, 99 (1984)
4. A.J. Lovinger, G.T. Davies, T. Furukawa, M.G. Broadhurst, Macromolecules, 15, 323 (1982)
5. A.J. Davies, T. Furukawa, A.J. Lovinger, M.G. Broadhurst, Macromolecules, 15, 329 (1982)
6. A.J. Lovinger, T. Furukawa, G.T. Davis, M.G. Broadhurst, Polymer, 24, 1225 (1983)
7. A.J. Lovinger, T. Furukawa, G.T. Davis, M.G. Broadhurst, Polymer, 24, 1233 (1983)
8. K. Tashiro, M. Kobayashi, Polymer, 27, 667 (1986)
9. J.F. Legrand, P.J. Schuele, V.H. Schmidt, M. Miniuer, Polymer, 26, 1683 (1985)
10. D.R. Rueda, J. Martinez Salazar, F.J. Baltá Calleja, J. Mater. Sci., 20, 834 (1985)