Thermal and dynamic mechanical properties of vitamin E infused and blended ultra-high molecular weight polyethylenes

J.A. Puértolas^{a,b}, M.J. Martínez-Morlanes^a, M.D. Mariscal^a, F.J. Medel^{b*}

^aDepartment of Materials Science and Technology, I3A, Universidad de Zaragoza, E-50018, Zaragoza, Spain.

^bDepartment of Materials Science and Technology, Instituto Ciencia de Materiales de Aragón, ICMA, Universidad de Zaragoza-CSIC, E-50018, Zaragoza, Spain.

*Correspondence to Prof. Francisco J. Medel
Department of Materials Science and Technology,
Centro Politécnico Superior-ICMA, Universidad de Zaragoza,
E-50018, Zaragoza, Spain
Tel. : +34 976 762521
Fax. : +34 976 761957
e-mail: fjmedel@unizar.es

ABSTRACT

Vitamin E (or α -tocopherol) is an alternative via to thermal treatments to achieve oxidative stability of gamma or electron beam irradiated ultra high molecular weight polyethylenes (UHMWPE) used in total joint replacements. Our aim was to study the effects of vitamin E on the molecular dynamics and microstructural properties of UHMWPE. We hypothesized that the antioxidant would plasticize UHMWPE. Vitamin E was incorporated into UHMWPE at different concentrations by diffusion and blending, and detected by ultraviolet and infrared spectroscopies from 500 ppm and 4000 ppm, respectively. Dynamic mechanical thermal analysis was used to characterize the influence of this antioxidant in the relaxations of the raw material. DSC and TEM served to characterize thermal and microstructure properties, respectively. Vitamin E concentrations above 3 % by weight significantly reduced the degree of crystallinity and increased the melting transition temperature of raw UHMWPE. The presence of increasing concentrations of α -tocopherol introduced and/or strengthened the beta relaxation, which was also shifted towards gradually lower temperatures and had rising activation energies up to 188 kJ/mol. In addition, the gamma relaxation remained unaltered upon vitamin E addition. Therefore, no plasticizing effects of vitamin E on the molecular dynamics of UHMWPE could be confirmed from mechanical spectroscopy data. However, the α relaxation was modified in intensity and location due to the changes in the degree of crystallinity introduced by the incorporation of vitamin E.

KEYWORDS: polyethylene (UHMWPE), antioxidants (vitamin E/ α -tocopherol), viscoelastic properties (DMTA), molecular mechanics, microstructure.

INTRODUCTION

Ultra-high molecular weight polyethylene (UHMWPE) remains as the most relevant material used in total joint replacements. However, long-term service of UHMWPE, and thus the life span of the whole joint replacement system are compromised by material limitations. Wear of the UHMWPE component has been accepted as the most prominent drawback in hip arthroplasty, with associated generation of debris particles, subsequent osteolysis, and eventual aseptic loosening of the implant¹. First-generation highly cross-linked polyethylenes were introduced in orthopaedic implants as a promising alternative to conventional, gamma sterilized, UHMWPE²⁻⁴. Thus, high irradiation doses are employed to promote a significant crosslink density within the amorphous phase of the polymer, which is responsible for a dramatic improvement in wear resistance⁴⁻⁵. However, concerns about long-term oxidation of highly crosslinked UHMWPE remain due to the generation of free radicals during irradiation, which may initiate oxidation reactions in the presence of molecular oxygen⁶⁻⁷, which, in turn, convert UHMWPE into a brittle polymer with a significant loss of satisfactory performance⁸. In the search of a method that would avoid the risk of long-term oxidation, orthopaedic manufacturers have combined the irradiation process with a subsequent thermal stabilization step at temperatures either below (annealing) or above (remelting) the melting transition temperature of UHMWPE. Both thermal stabilization processes seem to retain the wear resistance of highly crosslinked UHMWPEs. Nevertheless, remelting decreases the original crystallinity of the polymer, and therefore it affects detrimentally some of the polymer's mechanical properties⁹, while annealing preserves them better¹⁰. However, annealing methods may not assure a complete oxidative stability, because less mobile free radicals, located within the crystalline

1 region, are not able to recombine, since crystals do not melt completely during
2 annealing.

3 An alternative to the foregoing thermal stabilization methods has been found in
4 the use of α -tocopherol (vitamin E). This vitamin is a natural lipid, which acts as an
5 antioxidant *in vivo* by means of the donation of a hydrogen atom to free radical formed
6 on lipids hindering lipid peroxidation in cell membranes ¹¹. In irradiated UHMWPE,
7 vitamin E basically acts as a scavenger of radiation-induced free radicals, allowing for
8 the elimination of post-irradiation thermal processes and their associated shortcomings,
9 such as the reduction in toughness and fatigue resistance of the polymer ¹². Two
10 different techniques are currently in use to incorporate vitamin E into highly crosslinked
11 UHMWPE. On one hand, vitamin E is diffused into medical UHMWPE following high
12 dose irradiation in a two stage process ¹³⁻¹⁴. In the first stage, radiation crosslinked
13 UHMWPE is submerged in a vitamin E bath at about 120 °C. Then, the polymer is
14 taken out of the bath and subjected again to 120 °C to homogenize the antioxidant
15 concentration through the component thickness. On the other hand, trace concentrations
16 of vitamin E are blended with medical grade UHMWPE resins prior to consolidation
17 and irradiation to assure both oxidative stability and high efficiency in the crosslinking
18 generation, as higher vitamin E concentrations are known to inhibit radiation
19 crosslinking ¹⁵⁻¹⁶. Research on the use of vitamin E as antioxidant for highly crosslinked
20 polyethylenes has resulted in the recent clinical introduction of a second generation of
21 vitamin E stabilized highly crosslinked polyethylenes.

22 The design of new components for total hip and knee replacements based on
23 these new and promising materials requires good understanding of their microscopic
24 and macroscopic properties. While the mechanical, toughness and fatigue behaviors of

vitamin E stabilized polyethylenes are well known¹⁷⁻¹⁹, the influence of α -tocopherol on the thermal and viscoelastic behaviors as well as molecular dynamics of UHMWPE remains to be established. This work deals with the latter aspect and our purpose was to characterize the thermal and dynamic mechanical responses of vitamin E infused and vitamin E blended UHMWPE materials. FTIR and UV spectroscopies were employed in this study to assess the antioxidant concentration present within the vitamin E infused and blended UHMWPE sections prepared. We hypothesized that the presence of the antioxidant would introduce a plasticization effect in UHMWPE.

MATERIALS AND METHODS

Materials and Vitamin E detection methods

The raw materials used in this study were GUR 1020 UHMWPE supplied by Meditech (Fort Wayne, Indiana, USA) as several thin films and a compression-molded sheet of GUR 1050 UHMWPE (Perplas Medical Ltd., Lancashire, UK). Vitamin E was incorporated into the foregoing materials by blending and diffusion, respectively. The first method was used by Meditech to compression mold 0.250 mm thin films from virgin GUR 1020 UHMWPE and from blends of GUR 1020 UHMWPE resin and vitamin E, wherein the antioxidant was said to be present in two concentrations: 0.075 and 0.3 percent by weight. Hereafter, these materials will be referred to as PE20-E00, PE20-E0075 and PE20-E03, respectively, depending on the amount of vitamin E added to the UHMWPE resin. On the other hand, 0.2 mm thin sections were obtained with the use of a Leica SM2000R microtome from cubes (15x15x15 mm³), which were, in turn, machined from the GUR 1050 compression-molded sheet. The sections were weighed on a balance (Mettler Toledo; Switzerland) with a resolution of 0.0001 g, and then soaked in a bath of vitamin E (α -tocopherol, Aldrich Chemicals) at 120 °C for varying

1 durations, in a nitrogen gas atmosphere. At the end of the diffusion process, the sections
2 were taken out of the vitamin E bath, cleaned and subsequently homogenized at 120 °C
3 for 24 hours in nitrogen. After vitamin E doping, the sections were weighed again to
4 determine the antioxidant weight percentage. Thus, samples corresponding to
5 concentrations of vitamin E ranging from 2.0 to 9.0 percent by weight were prepared.
6 Calibration curves for infrared and ultraviolet spectroscopies vitamin E indices were
7 obtained using the foregoing UHMWPE sections. FTIR spectroscopy was performed
8 on them using a Perkin-Elmer model 1600 spectrometer (range: 4000-400 cm^{-1} ; 235
9 repeat scans per sample location; resolution 4 cm^{-1}). Vitamin E was detected in FTIR
10 spectra of infused UHMWPE sections as the vibrational band centered at 1262 cm^{-1} . A
11 vitamin E index (VI) was defined as the area ratio between the absorption peak at 1262
12 cm^{-1} (1275-1230 cm^{-1}) and the reference peak at 1895 cm^{-1} (1980-1850 cm^{-1})
13 corresponding to the polyethylene skeletal absorbance. The vitamin E concentration was
14 also detected by ultraviolet (UV) spectroscopy using an Aligent 8453 Diode Array
15 spectrophotometer at a range of 1100-190 nm. UV absorption spectra of vitamin-E
16 infused UHMWPE sections revealed the presence of a noticeable peak at 290 nm. To
17 obtain sections with very low antioxidant concentration (0.3% w), the previous vitamin
18 E doping process was performed on cubes. Then, 0.2 mm sections were cut parallel to
19 the cube faces using a microtome. FTIR spectroscopy was conducted from the edge of
20 these sections at every 100 microns to characterize the antioxidant concentration
21 through the cube thickness. Once the depth corresponding to the desired vitamin E
22 concentration was determined, perpendicular sections were cut at that depth to obtain
23 samples for further calorimetric and dynamic mechanical analysis (Figure 1). The
24 vitamin E content was also confirmed by UV spectroscopy for sections with the lowest
25 antioxidant concentrations. In summary, specimens corresponding to raw GUR 1050

UHMWPE and to concentrations of α -tocopherol ranging from 0.3 to 9.0 percent by weight were prepared for this study. These materials will be designated as PE50-E00, PE50-E03, PE50-E07, PE50-E23, PE50-E46, PE50-E50, PE50-60, PE50-E80 and PE50-E90, respectively.

Differential Scanning Calorimetry

Differential Scanning Calorimetry (DSC) was performed to assess thermal properties, namely crystallinity content and melting transition temperatures. Three specimens (n=3) per material group were heated from 20 to 200 °C at a rate of 10 °C/min in a Differential Scanning Calorimeter (Perkin Elmer). The area below the thermograms from 50 to 160 °C, normalized by 290 J/g as the enthalpy of melting of a 100 % crystalline UHMWPE²⁰, gave the crystallinity percentages for each material.

Transmission Electron Microscopy

Relevant material groups (PE50-E00, PE50-E23 and PE50-E46 materials) were chosen based on melting transition temperature results. Specimens belonging to those groups underwent specific preparation to obtain Transmission Electron Microscopy (TEM) images, which allowed the measurement of crystal thickness as well as the detection of changes in morphology caused by the presence of vitamin-E in a broad range of concentrations. First, 200 μ m sections of UHMWPE were stained with 99% chlorosulphonic acid at 60°C for 5 hours, which is thought to stabilize the amorphous regions. Samples were washed with acetone (at 0°C) and rinsed with distilled water. Stained samples were dried at 60°C for 1 hour and later embedded in epoxy and cured at 60°C for 2 days. Ultrathin sections (~ 60 nm thick) were cut with a diamond knife and collected in carbon grids. Then, the sections were post-stained with uranyl acetate in 1% methanol for 4 minutes. A Jeol 100CX TEM operating at 100 kV

was used to produce micrographs at 20000x and 60000x magnifications. The best TEM preparation samples were chosen from each group and analysed using the Digital Micrograph 3.3.1 software package (Gatan Inc., Pleasanton, CA, USA). At least fifteen measurements of lamellar thickness were done per 60000x images using the mentioned software. These images allowed the measurement of crystal thickness as well as the detection of changes in morphology caused by the presence of vitamin-E.

Dynamic Mechanical Thermal Analysis

Dynamic mechanical measurements were carried out on 15x4.5x0.2 mm³ prismatic test specimens employing a Dynamic Mechanical Thermal Analyser, model MKII of Polymer Laboratories. All the experiments were conducted working in tensile mode and the heating runs were performed at a rate of 1 °C/min from -130 to 125 °C. The frequencies used were 0.3, 3, 10, 30 and 50 Hz. Before heating, samples were first cooled down to -135 °C inside the cell. These measurements provided information about the dynamic mechanical properties, namely, storage modulus, E', loss modulus, E'', and loss tangent, tan δ. Activation energies were calculated from the temperature of the maximum values of loss modulus and tan δ at different frequencies based on an Arrhenius model for β and γ relaxations (Figure 2). In the case of the α relaxation, the behavior slightly departed from the Arrhenius model.

RESULTS AND DISCUSSION

Infrared and ultraviolet spectroscopic detection of vitamin E

In agreement with previous work²¹, linear correlations were found between the amount of vitamin E concentration as determined by weighing and both the infrared vitamin E index, VI, ($R^2=0.96$; Figure 3) and the area of the ultraviolet absorption peak at 290 nm normalized to the film thickness, A/t ($R^2=0.98$; Figure 3). In the case of

FTIR, a detection limit of 0.4 percent by weight of vitamin E was noted, and the use of different reference peaks (1895 and 2020 cm^{-1}) yielded similar linear correlations. On the other hand, the linear trend found for the normalized UV absorption, A/t , and the vitamin E content confirmed a Beer's law behavior, $A/t = \varepsilon c$, where ε is the dielectric constant, and c the concentration of vitamin E in a non-polar matrix such as UHMWPE. Previous research has also demonstrated that UV spectroscopy performed at temperatures above the melting point of UHMWPE ($\sim 140^\circ\text{C}$) helps to reach increased resolution avoiding the incident light scattering from UHMWPE crystals²¹.

DSC and TEM studies: Crystallinity, Melting Temperature and Crystal Thickness

Analysis of the thermograms provided the crystallinity content and the transition temperature for every material, as reflected in **Figures 4a and 4b, respectively**. The presence of vitamin E at high concentrations provoked two effects on the base material GUR1050, namely a significant drop in the degree of crystallinity and an increase in melting temperature. DSC complementary measurements at samples containing vitamin E concentrations ranging from 4.5 % to 9.0% wt% followed similar trends. Since vitamin E was diffused into the amorphous regions of the semicrystalline polymer, no effects on crystallinity were expected, except for a likely effect on the surface energy of UHMWPE lamellar crystals. The diffusion process, on the other hand, was performed at 120°C , and therefore an annealing process took place simultaneously to the diffusion of the antioxidant. In vitamin E free-samples this thermal process is known to produce a light increase in crystallinity due to lamellar rearrangements activated at the annealing temperature. Furthermore, two different lamellar rearrangement mechanisms have been identified by Matsuda and colleagues depending on the annealing temperature²². Thus, low temperature annealing ($T < 120^\circ\text{C}$) induces gradual thickening of the original

lamellar crystals without significant melting, whereas high temperature annealing ($T > 125\text{ }^{\circ}\text{C}$) causes partial melting and then rapid lamellar doubling. These mechanisms competitively coexist upon annealing over $120\text{ }^{\circ}\text{C}$, and their balance depends on the annealing temperature. Although the influence of vitamin E in both mechanisms has not been established, the antioxidant might partially inhibit lamellar rearrangements, especially lamellar doubling. However, some gradual thickening may still occur, accounting for the overall lamellar thickening observed in TEM micrographs. This last effect was also corroborated by the rise in transition temperature, T_m , which according to the Thomson-Gibbs equation involves an increase in lamellar thickness, L_c :

$$T_m = T_{m0} (1 - 2\sigma/L_c\rho_c\Delta H_m^0) \quad (\text{eq. 1})$$

where T_m is the melting point of the polymer, T_{m0} is the equilibrium melting point of a perfect crystalline polyethylene, σ the specific surface energy, ρ_c the crystallinity phase density, and ΔH_m^0 the enthalpy of melting of a perfect crystalline polyethylene. As mentioned before, potential changes in the surface energy of polyethylene lamellar crystals may not be discarded, and they might also influence the melting transition of the polymer. Finally, the reduction in crystallinity content due to the incorporation of vitamin E has been also observed by Oral and coworkers¹³, and this effect is more intense when the diffusion temperature approaches the melting point of the polymer.

TEM micrographs of virgin UHMWPE showed the typical features of semicrystalline polymers with randomly oriented crystal lamellae, $26.7 \pm 4.2\text{ nm}$ thick, immersed in a dark grey region, which is the amorphous region (**Figure 5a**). TEM micrographs of vitamin-E infused polyethylenes showed a small increase in lamellar thickness, with values of $28.0 \pm 2.9\text{ nm}$, and $29.6 \pm 3.8\text{ nm}$ for PE50-E23 and PE50-E46,

respectively (**Figures 5b and 5c**). This increase is in agreement with the observed trend for the melting point of samples with the highest vitamin-E contents. On the other hand, the qualitative observation of TEM images suggested that the lamellar density corresponding to PE50-E46 samples was lower than those of the PE50-E00 and PE50-E23 materials, in accordance with the fall in crystallinity registered by DSC measurements when vitamin-E was present in the material above 1 % approximately.

Dynamic Mechanical Thermal Analysis

The dynamic mechanical behavior of the two raw materials, PE50-00 and PE20-00, was basically the same. Two well-expressed relaxations, γ and α , characterized the temperature dependence of dynamic modulus properties. The γ relaxation was reflected by a weak stepwise change in the storage modulus and a maximum in $\tan \delta$ and E'' around -125 °C in both raw UHMWPEs regardless of their different molecular weights (**Figures 6 and 7**). This relaxation is associated with the amorphous region of the polymer. On the other hand, the α relaxation, which is related to the crystalline region, appeared as a strong and wide decrease in E' and a rounded and small maximum in E'' close to 50 °C (**Figures 6 and 7**). Despite the similar behavior of both polymers regarding the γ and α relaxations, a difference was noted between them, as a weak β relaxation appeared around -10 °C only for the higher molecular weight material, PE50-E00.

The incorporation of alpha-tocopherol into UHMWPE gave rise to a distinct relaxation around -25 °C, which was more evident at the highest concentrations (**Figures 6 and 7**). Specifically, this “new” beta transition associated with the presence of vitamin E appeared as a noticeable peak in the E'' plots for PE50-E90 samples, and it gradually lost intensity and was shifted towards higher temperatures as the vitamin E

concentration decreased for PE50-E07, PE50-E03, PE20-E03 and PE20-E0075 specimens. The activation energy of this transition calculated from the temperature of the maximum in $E''(T)$ plots ranged from 149 to 188 kJ/mol for 0.7% and 9% vitamin E doped GUR 1050 UHMWPEs. Regarding the effect of frequency, essentially similar results were observed at the highest frequencies (10, 30 and 50 Hz), as can be seen in the isochrone curves of raw and vitamin-E stabilized UHMWPEs (**Figures 8 and 9**).

The β relaxation has been observed not only in branched low-density polyethylenes (LDPE), but also in some linear polyethylenes in connection with the amorphous phase. However, due to constraints imposed by chain connections to, and confinement by crystal lamellae, the β process is greatly broadened in linear polyethylenes, and therefore much less prominent, in comparison to the main relaxation in wholly amorphous polymers (i. e. the glass transition). Thus, the temperature of the pronounced beta relaxation is generally considered the glass-rubber transition temperature (T_g) for LDPE, whereas the weak or even absent beta relaxation in linear polyethylenes induces to consider T_g as the temperature of the gamma relaxation²³. Different molecular mechanisms have been proposed to contribute to the β relaxation in specific polyethylenes, in addition to those related to the glass transition²⁴. In general, the beta relaxation is accepted to stem from the relaxation of chain units in the interfacial region via fold-surface, chain-end, branch-point molecular motions as well as chain rotation²⁵. Therefore, the higher interlamellar content (i.e. lower crystallinity) the stronger the beta relaxation as demonstrated for chlorinated and short-chain branched polyethylenes²⁵⁻²⁷. Moreover, the beta relaxation is absent in linear HDPEs in agreement with their much lower interlamellar content. In the case of high molecular weight polyethylenes, Nitta and Tanaka concluded that the β relaxation is a consequence of the activation of loop and loose tie molecules, as these elements arise in

1 these particular polyethylenes but they do not form in common linear HDPE²⁸. The
2 current findings appear to be consistent with this alternative explanation, as a weak β
3 transition was detected in raw GUR 1050 specimens but it was absent in the lower
4 molecular weight GUR 1020 specimens. The activation energy (ΔH) of β transition had
5 a value of 140 kJ/mol for PE50-E00 but with strong uncertainty due to the inherent
6 difficulty to determine the maximum from the plateau shape of this transition. The
7 addition of increasing vitamin E concentrations, on the other hand, was responsible for
8 the introduction and/or progressive strengthening of the originally absent or weak β
9 relaxation in vitamin E containing GUR 1020 and GUR 1050 UHMWPEs, respectively.
10 Also, the incorporation of increasing concentrations of the antioxidant resulted in a shift
11 towards lower temperatures of the beta relaxation, although with higher activation
12 energies. The presence of the beta relaxation in these materials seems to be related to
13 the crystallinity drop (i.e. increase in interlamellar content) provoked by the diffusion of
14 the antioxidant. Nevertheless, the existence of this transition cannot be exclusively
15 attributed to the thermal conditions used for antioxidant diffusion, as both GUR 1020
16 and GUR 1050 UHMWPEs exhibited no changes in both crystallinity and relaxation
17 behavior after thermal treatment at 120 °C. The current crystallinity results along with
18 the relaxation behavior also suggest that, upon diffusion at high temperature, vitamin E
19 is preferentially located on crystal surfaces. On the other hand, vitamin E doped GUR
20 1050 and 1020 UHMWPEs with similar antioxidant concentrations (0.3% w/w)
21 exhibited the beta relaxation at different temperatures (**Figure 10**).

22 With regard to a hypothetical role of alpha-tocopherol as plasticizer, the current
23 results did not provide evidence of such effect for the beta relaxation. In this sense, the
24 effects of various plasticizers on the relaxation behavior of different materials, such as
25 polyvinyl chloride, polyvinyl acetate, polystyrene, composite biopolymer caseinate-

pullulan, and blends of poly(3-hydroxybutyrate) and cellulose acetate among others, have been investigated by several researchers^{23,29-31}. The addition of a plasticizer generally results in a shift towards lower temperatures of the corresponding relaxation (in some cases T_g) and a decrease of the apparent energy of activation²⁹. In our study, the relaxation behavior of vitamin E containing UHMWPE specimens matched the former condition that is decreasing temperatures for the beta relaxation as the antioxidant concentration increased. However, the apparent activation energies were increasingly higher. The relatively high activation energy (188 kJ/mol) of the beta relaxation for the highest vitamin E content suggests a cooperative mechanism, with numerous chain units taking part in the relaxation. Despite the shift towards lower temperatures of the beta relaxation of UHMWPE, no evidence of a plasticizing effect upon antioxidant incorporation could be confirmed as the activation energy was increasingly higher. Moreover, vitamin E had no significant plasticizing effects (neither on temperature nor on activation energies) on the relaxation behavior of the present polymeric specimens for concentrations as low as those used in clinically available UHMWPE materials (**Figure 10**). The lower intensity of the beta relaxation in vitamin E blended GUR 1020 would stem from both the much lower concentration of the antioxidant and the lower molecular weight of the raw polymer, which in turn results in a lower fraction of tie and loop molecules.

Regarding the γ relaxation of the raw UHMWPEs, the calculated activation energies of the lower molecular weight material, PE20-E00, reached a value of 65 kJ/mol. The γ relaxation is commonly associated with the motion of polymethylene segments in amorphous regions of the polymer, which results in kink formation, inversion and migration or crankshaft motion³²⁻³³. The temperature location of the γ relaxation is also considered to be the subglass transition temperature for some

polyethylenes³⁴⁻³⁵. Although in some cases differences in the γ transition might be attributed to different crystallinity contents, the similar values of this parameter and intensities of the γ transition for both raw materials suggest that other cause may be involved. On the other hand, PE50-E00 and PE20-E00 also showed relatively small differences in the maximum values of the storage modulus (3.2 GPa and 1.6 GPa, respectively), at temperatures below the γ transition. It is also known that the stiffness of polyethylene can be also slightly influenced by molecular weight³⁶, as occurred in this case. The loose chain ends in the lamella, which are affected by the length of the polymer chains, could be another underlying cause of this different behavior.

With regard to vitamin E infused and blended UHMWPEs, no significant changes were observed in the temperature location, intensity or activation energies of the γ relaxation (**Figures 6 and 7**) for these materials. The fact that the presence of vitamin E in different concentrations did not significantly alter the γ transition induces to think that no plasticizing effects take place in vitamin E-UHMWPE systems even at relatively high concentrations of antioxidant. As mentioned above, the incorporation of the antioxidant was responsible for the introduction and/or strengthening of the beta relaxation. However, plasticization of the beta relaxation was also discarded due to the rising activation energies registered for increasingly higher vitamin E amounts. Therefore, our hypothesis tested negative as the present results confirmed both, vitamin E did not alter the internal friction of UHMWPE with regard to the gamma relaxation, and it actually generated more friction in the beta relaxation region especially at high antioxidant concentrations.

The incorporation of vitamin E into UHMWPE provoked changes in intensity and temperature shifts to the α relaxation. These changes depended on the technique

employed to obtain the vitamin E-UHMWPE system. While for vitamin E infused UHMWPEs the α relaxation shifted to lower temperatures and decreased in intensity with increasing vitamin E concentrations, vitamin E blended UHMWPEs exhibited shifts towards higher temperatures in this transition as the amount of vitamin E increased. The foregoing changes in intensity and temperature shifts were especially pronounced for PE50-E90 (**Figure 6**), which was characterized by the lowest crystallinity, close to 40%. However, the effect of vitamin E in the activation energy of the α process was similar for blended and infused UHMWPEs, since in both cases it increased the activation energies. The activation energies obtained were 92, 166, and 313 kJ/mol for PE20-E00, PE20-E0075, and PE20-E03, respectively, and 83 and 198 kJ/mol for PE50-E00 and PE50-E90, respectively.

The α transition is related to the crystal phase of the material by means of inter-lamellar shear mechanism, and its temperature location is an indication of the lamellar thickness³⁷⁻³⁸. Therefore, the shifts towards lower temperatures observed in vitamin E infused materials confirmed lower lamellar thickness in agreement with the present DSC results. This decrease in crystal thickness is probably a direct result of the synergism between the annealing conditions needed to diffuse and homogenize vitamin E into UHMWPE, and the influence of the antioxidant on the recrystallization mechanisms of the polymer. At the highest vitamin E concentration the activation of recrystallization mechanisms may be not favored and hence partial melting, without further lamellar doubling or gradual thickening, might be responsible for the drop in both crystallinity content and crystal size as well as the decreased intensity of the α relaxation. On the other hand, the effect of trace concentrations of antioxidant in the crystallization of UHMWPE during compression molding remains unclear. Thus, although the shift towards higher temperatures of the α transition suggests thicker

lamellar crystals regardless of concentration, the intensity variations followed opposite trends for blends with 0.075 and 0.3 percent by weight of vitamin E. More research is needed to determine the influence of trace concentrations of vitamin E on both crystal nucleation and further crystallization processes during compression molding of vitamin E blended UHMWPEs. **In this regard, and although it is logical to expect that the exclusive activation of vitamin E molecules should introduce a new relaxation at the same temperature regardless of polyethylene type and method of incorporation, the physicochemical interaction of the antioxidant and polyethylene molecules may significantly vary with concentrations and production conditions.** **Finally**, more studies must be undertaken in order to know the effect of radiation-induced crosslinking either by gamma radiation or electron-beam on the molecular dynamics of vitamin E blended UHMWPEs.

CONCLUSIONS

Vitamin E concentrations in blended GUR 1020 UHMWPE and infused GUR 1050 UHMWPE were detected by FTIR and UV from values of 0.3 and 0.075 %, respectively. A linear correlation appeared between the vitamin index related with the intensity of specific peaks in IR(1262 cm^{-1}) and UV(290 nm) spectra and the weight concentration. Vitamin E concentrations above 3 % reduced significantly the degree of crystallinity and increased the melting transition temperature of the raw material, aspects which were confirmed by DSC measurements and observation of microstructural features on TEM micrographs.

The dynamical and mechanical thermal analysis showed the presence of two well-expressed relaxations, γ and α , about $-125\text{ }^{\circ}\text{C}$ and $50\text{ }^{\circ}\text{C}$, which were associated to the amorphous and crystalline parts of these semicrystalline polymers, respectively. A weak β relaxation at $-10\text{ }^{\circ}\text{C}$ was detected in the high molecular weight GUR 1050

polyethylene. The presence of vitamin E in different concentrations did not significantly alter the intensity and location of the γ transition. The introduction of increasing alpha-tocopherol amounts generated and/or progressively strengthened the beta relaxation in UHMWPE, the transition being shifted towards lower temperatures and having rising activation energies as the antioxidant concentration increased (up to -25 °C, and 188 kJ/mol activation energy for the highest concentration). Due to the unaltered gamma relaxation and the increasing activation energies of the beta transition, potential plasticization effects were discarded in vitamin E-UHMWPE systems. Finally, another effect of the highest vitamin E concentrations in infused UHMWPE is the intensity decrease of the α relaxation, in accordance with the drop of crystallinity content observed in DSC measurements, and the shift towards lower temperatures.

ACKNOWLEDGEMENTS

Research funded by the Comisión Interministerial de Ciencia y Tecnología (CICYT), Spain. Project: MAT 2006-12603-C02-01 and Consolider-Ingenio CDS2008-0023 from the Ministerio de Ciencia e Innovación.

REFERENCES

1. Santavirta, S.; Konttinen, Y. T.; Bergroth, V.; Eskola, A.; Tallroth, K.; Lindholm, T. S., *Journal of Bone and Joint Surgery-American Volume* 72A, 252 1990.
2. Kurtz, S. M., *UHMWPE biomaterials handbook : ultra high molecular weight polyethylene in total joint replacement and medical devices*; Elsevier/Academic Press: Amsterdam ; Boston, 2009.
3. Jasty, M.; Rubash, H. E.; Muratoglu, O., *Journal of Arthroplasty* 20, 55 2005.
4. McKellop, H.; Shen, F. W.; Lu, B.; Campbell, P.; Salovey, R., *Journal of Orthopaedic Research* 17, 157 1999.
5. Muratoglu, O. K.; Bragdon, C. R.; O'Connor, D. O.; Jasty, M.; Harris, W. H.; Gul, R.; McGarry, F., *Biomaterials* 20, 1463 1999.
6. Premnath, V.; Harris, W. H.; Jasty, M.; Merrill, E. W., *Biomaterials* 17, 1741 1996.
7. Costa, L.; Luda, M. P.; Trossarelli, L.; del Prever, E. M. B.; Crova, M.; Gallinaro, P., *Biomaterials* 19, 659 1998.
8. Puertolas, J. A.; Larrea, A.; Gomez-Barrena, E., *Biomaterials* 22, 2107 2001.
9. Puertolas, J. A.; Medel, F. J.; Cegonino, J.; Gomez-Barrena, E.; Rios, R., *Journal of Biomedical Materials Research Part B-Applied Biomaterials* 76B, 346 2006.
10. Medel, F. J.; Pena, P.; Cegonino, J.; Gomez-Barrena, E.; Puertolas, J. A., *Journal of Biomedical Materials Research Part B-Applied Biomaterials* 83B, 380 2007.
11. Packer, L., *American Journal of Clinical Nutrition* 53, S1050 1991.
12. Oral, E.; Malhi, A. S.; Muratoglu, O. K., *Biomaterials* 27, 917 2006.
13. Oral, E.; Wannomae, K. K.; Rowell, S. L.; Muratoglu, O. K., *Biomaterials* 28, 5225 2007.
14. Wolf, C.; Maninger, J.; Lederer, K.; Fruhwirth-Smounig, H.; Gamse, T.; Marr, R., *J Mater Sci Mater Med* 17, 1323 2006.
15. Kurtz, S. M.; Dumbleton, J.; Siskey, R. S.; Wang, A.; Manley, M., *J Biomed Mater Res A* 90, 549 2009.
16. Oral, E.; Godleski Beckos, C.; Malhi, A. S.; Muratoglu, O. K., *Biomaterials* 29, 3557 2008.
17. Oral, E.; Beckos, C. A. G.; Lozynsky, A. J.; Malhi, A. S.; Muratoglu, O. K., *Biomaterials* 30, 1870 2009.
18. Oral, E.; Christensen, S. D.; Malhi, A. S.; Wannomae, K. K.; Muratoglu, O. K., *Journal of Arthroplasty* 21, 580 2006.
19. Wolf, C.; Krivec, T.; Blassnig, J.; Lederer, K.; Schneider, W., *Journal of Materials Science-Materials in Medicine* 13, 185 2002.
20. Buchanan, F. J.; White, J. R.; Sim, B.; Downes, S., *Journal of Materials Science-Materials in Medicine* 12, 29 2001.

21. Fu, J.; Oral, E.; Muratoglu, O. 54th Annual Meeting of the Orthopaedic Research Society, 2008.
22. Matsuda, H.; Aoike, T.; Uehara, H.; Yamanobe, T.; Komoto, T., *Polymer* 42, 5013 2001.
23. McCrum, N. G.; Read, B. E.; Williams, G., *Anelastic and dielectric effects in polymeric solids*; John Wiley & Sons: London, 1991.
24. Cerrada, M. L.; Benavente, R.; Perez, E., *Macromolecular Chemistry and Physics* 202, 2686 2001.
25. Suljovrujic, E., *Radiat. Phys. Chem.* 79, 751 2010.
26. Popli, R.; Glotin, M.; Mandelkern, L.; Benson, R. S., *Journal of Polymer Science Part B-Polymer Physics* 22, 407 1984.
27. Kolesov, I. S.; Androsch, R.; Radusch, H. J., *Macromolecules* 38, 445 2005.
28. Nitta, K. H.; Tanaka, A., *Polymer* 42, 1219 2001.
29. Kristo, E.; Biliaderis, C. G., *Food Hydrocolloids* 20, 1057 2006.
30. Ceccorulli, G.; Pizzoli, M.; Scandola, M., *Macromolecules* 26, 6722 1993.
31. van den Berg, O.; Wubbenhorst, M.; Picken, S. J.; Jager, W. F., *Journal of Non-Crystalline Solids* 351, 2694 2005.
32. Flocke, H. A., *Kolloid-Zeitschrift and Zeitschrift Fur Polymere* 180, 118 1962.
33. Heaton, N. J.; Benavente, R.; Perez, E.; Bello, A.; Perena, J. M., *Polymer* 37, 3791 1996.
34. Boyd, R. H.; Smith, G. D., *Polymer Dynamics and Relaxation*; Cambridge University Press, 2007.
35. Boyd, R. H., *Polymer* 26, 1123 1985.
36. Khanna, Y. P.; Turi, E. A.; Taylor, T. J.; Vickroy, V. V.; Abbott, R. F., *Macromolecules* 18, 1302 1985.
37. Laredo, E.; Suarez, N.; Bello, A.; de Gascue, B. R.; Gomez, M. A.; Fatou, J. M. G., *Polymer* 40, 6405 1999.
38. Zamfirova, G.; Perena, J. M.; Benavente, R.; Perez, E.; Cerrada, M. L.; Nedkov, E., *Polymer Journal* 34, 125 2002.

Figure 1. Schematic drawing depicting obtention of UHMWPE samples with specific vitamin E concentration at a depth d , as measured by means of FTIR spectroscopy.

68x61mm (600 x 600 DPI)

ew

Figure 2. Activation energies corresponding to γ , β and α relaxations were obtained by fitting to an Arrhenius model
76x76mm (600 x 600 DPI)

Figure 3. Correlation between Vitamin E index from FTIR and peak UV absorption as a function of the wt% vitamin E.
74x72mm (600 x 600 DPI)

Figure 4. Crystallinity content, a), and melting transition temperature, b), results obtained from DSC experiments.
127x98mm (300 x 300 DPI)

Figure 4. Crystallinity content, a), and melting transition temperature, b), results obtained from DSC experiments.
127x98mm (300 x 300 DPI)

Figure 5. TEM micrographs (x60.000) of a) PE50-E00, b) PE50-E23 and c) PE50-E46
79x79mm (300 x 300 DPI)

Figure 5. TEM micrographs (x60.000) of a) PE50-E00, b) PE50-E23 and c) PE50-E46
80x80mm (300 x 300 DPI)

Figure 5. TEM micrographs (x60.000) of a) PE50-E00, b) PE50-E23 and c) PE50-E46
77x77mm (300 x 300 DPI)

Figure 6. Temperature dependence of storage modulus, E' , and loss modulus, E'' , at 3 Hz for virgin PE50-E00 (light gray line), and vitamin E infused polyethylenes samples PE50-07 (gray line) and PE50-90(black line).
177x137mm (300 x 300 DPI)

Figure 7. Temperature dependence of storage modulus, E' , and loss modulus, E'' , at 3 Hz for virgin PE20-E00 (light gray line), and vitamin E blended polyethylenes PE20-0075 (gray line) and PE20-03 (black line).
177x137mm (300 x 300 DPI)

Figure 8. Frequency dependence of loss modulus for virgin PE50-E00 and PE20-E00 samples at 0.3, 10, 30 and 50 Hz.
84x93mm (600 x 600 DPI)

Figure 9. Frequency dependence of loss modulus, E'' , for vitamin E infused and blended samples, PE50-90 and PE20-E03, respectively, at 0.3, 10, 30 and 50 Hz.
84x93mm (600 x 600 DPI)

Figure 10. Temperature dependence of storage modulus, E' , and loss modulus, E'' , at 3 Hz for vitamin E blended PE20-03 (dark gray line) and vitamin E infused PE50-03 (light gray line) polyethylenes.
177x120mm (300 x 300 DPI)