Hardness

Hardness defines the resistance to local deformation of a material when indented, drilled, sawed or abraded. It involves a complex combination of properties (elastic modulus, yield strength, strain-hardening capacity). The prevailing deformation mechanism depends upon the material and the type of tester. Hardness is either measured by: a) static penetration of the specimen with a standard indenter at a known force, b) dynamic rebound of a standard indenter of known mass dropped from a standard height, or c) scratching with a standard pointed tool under a load. The hardness tester, indenter shape and force employed strongly influence the hardness numbers [1].

Hardness is used in identification, classification and quality control. Hardness tests provide a rapid evaluation of variations in mechanical properties affected by changes in chemical or processing conditions, heat treatment, microstructure and aging. Since the hardness test usually produces an insignificant permanent change in the specimen, it is considered to be a non-destructive test.

The methods commonly used in determining the *hardness* of polymers are static indentation methods. Here, the indenter penetrates the test specimen at normal incidence under the application of a known force. Typical forces range from 10^{-2} to 1 kN leading to indentation widths of a few millimeters. The hardness is determined from the optical imaging of the residual width of indentation. Pyramidal indenters are preferred because the contact pressure is independent of the load applied and the indentation is less affected by elastic release than other indenters [1].

The *microhardness* technique is used when the specimen size is small or when a spatial map of the mechanical properties of the material within the micron range is required. Forces of 0.05 – 2 N are applied yielding indentation depths in the micron range.

More recently, *ultramicrohardness* and *nanohardness* testers have been developed with the purpose to mechanically characterize the surface of thin films [2]. Continuous load-displacement monitoring, as the indenter is driven into and withdrawn from the film, substitutes the imaging method used in conventional static indentation methods. Smaller loads can be applied ($10^{-1} - 2 \times 10^3$ mN) so that a minimum residual depth of several tens of nm can be achieved at best. The advantage of continuous depth-sensing recording entails a high level of precision due to automatic registering of data, thus, avoiding the error in determining the indentation size. In addition, each test gives a complete loading/unloading data cycle, rather than just a simple reading. This allows the elastic properties of the material to be investigated, in addition to the derivation of hardness numbers.

During the last two decades, studies of the hardness properties of polymers have evolved from topics of applied significance to fundamental studies aiming at acquiring an understanding of the structure-property relationship of polymer materials including glassy and semicrystalline polymers and copolymers, as well as polymer blends and composites [3-5]. Figure 1 illustrates the hardness of polymer materials as compared with typical values for metals and alloys.

[Figure 1 appears here]

Basic Aspects of Indentation

[Figure 2 appears here]

Figure 2 shows the contact geometry for a pyramid indenter at zero load, at maximum load and after unloading. The material under the indenter consists of a zone of plastic deformation (a few times the penetration depth distance) surrounded by a larger outer zone of elastic deformation. Several effects can be distinguished during the indentation process: 1) an instant elastic recovery of the indentation depth upon load release. The loss of contact with the indenter allows for a change in the shape of the indentation. 2) A permanent plastic deformation. Hardness, H , is related to the irreversible deformation, measured from the diagonal of the residual impression, d . 3) A time dependent contribution during loading. The plastic deformation in polymers is known to be influenced by the time at which the load is held (creep effect). To minimize the creep effect, indentation times of a few seconds are usually employed [3]. 4) A long delayed elastic recovery (viscoelasticity). The residual indentation should be measured immediately after load release in order to minimize the viscoelastic recovery of the material.

Microhardness of Polymer Glasses

The microhardness of glassy polymers decreases with increasing temperature due to thermal expansion [6]. At the glass transition temperature, T_g , the onset of liquid-like motions takes place. The motions of long segments above T_g require more free volume and lead to a fast decrease of microhardness with temperature. The microhardness of

several glassy polymers, measured at room temperature, has been shown to be directly proportional to its glass transition temperature [7].

Structure Development: The Role of Crystallinity

[Figure 3 appears here]

Hardness has been shown to be a useful technique to detect the structural changes occurring during crystallization [8, 9]. Figure 3 shows the hardness variation in the course of isothermal crystallization of poly (ethylene terephthalate) PET at various crystallization temperatures, T_c . A sigmoidal rapid hardness-increase with increasing time t_c is followed by a slower hardness increase. The comparatively rapid H increase, during primary crystallization, is connected with the growth of polycrystalline aggregates (spherulites) until they impinge on each other, finally filling up the sample completely. The much slower hardening process is denoted as secondary crystallization and is related with crystal thickening and formation of new crystals. For samples crystallized from the glassy state where spherulitic growth is incomplete, H can be described following [4]:

$$H = H_{sph} \Phi + H_a (1 - \Phi) \quad (1)$$

H_{sph} is here the hardness value of the spherulites, H_a is the hardness of the amorphous inter-spherulitic regions and Φ is the volume fraction of crystallized spherulites. During primary crystallization, H_{sph} remains constant and hardness is directly proportional to the volume occupied by the spherulites [9]. The hardness variation in the course of isothermal crystallization of PET and poly (ethylene naphthalene-2,6-dicarboxylate) (PEN) has been shown to follow Avrami law [10, 11].

For samples in which spherulitic growth is complete (secondary crystallization, $\Phi=1$), then, $H = H_{sph}$ and the hardness of the material can be accounted for using [9]:

$$H = H_c \alpha + H_a (1-\alpha) \quad (2)$$

Here, H_c is the hardness of the crystalline lamellae within the stacks, H_a is the hardness of the amorphous intra-spherulitic material and α is the fraction of crystalline material within the spherulites. Equation 2 is consistent with a parallel model of crystalline and amorphous regions which has been proved to be successful in a wide variety of polymeric materials [4].

Microhardness Dependence on Nanostructure

Equation 2 suggests that the volume fraction of crystalline material controls the microhardness value of a polymer. However, it was soon recognized the large influence of the crystalline lamellar thickness l_c upon microhardness in case of chain-folded and chain-extended polyethylene (PE) [3]. Based on a thermodynamic approach, Baltá Calleja and Killian derived the dependence of hardness on the average crystal thickness [12]:

$$H_c = \frac{H_c^\infty}{1 + \frac{b}{l_c}} \quad (3)$$

Here, H_c^∞ is the hardness of an infinitely thick crystal and b is a parameter related to the surface free energy of the crystal, σ_e , and to the energy required for plastic deformation of the crystal blocks, Δh ($b = 2\sigma_e/\Delta h$).

[Figure 4 appears here]

Figure 4 shows the plot of H_c^{-1} (derived using equation 2) versus l_c data for poly (ethylene oxide) (PEO), crystallized at various temperatures ($M_n = 13000$), and chain-folded PE, annealed at 130°C for different annealing times ($M_n = 11700$). Using equation 3, the plot of H_c^{-1} versus l_c^{-1} yields an ordinate intercept $(H_c^\infty)^{-1}$ and a slope b/H_c^∞ . Values of $H_c^\infty = 150$ MPa and $H_c^\infty = 170$ MPa are derived for PEO and PE respectively. The H_c^∞ value for PET, PEN, poly (butylene terephthalate) (PBT) and isotactic poly (propylene) (iPP) crystals has been also reported [13-16].

Microhardness Correlation to Thermal Properties

While the hardness depression due to finite thickness lamellae is given by equation 3, Thomson-Gibbs equation accounts for the melting point depression of a crystal of thickness l_c with respect to the equilibrium melting point T_m^0 [17]. It has been shown that by combination of Thomson-Gibbs equation and equation 3, the reciprocal value of the crystal hardness is directly proportional to the melting temperature of the crystals as seen in Figure 5 for PEO, PE and PET. The three series of H_c^{-1} versus T_m data fit into a straight line. From these linear regressions, one can derive the T_m^0 values for each polymer, provided H_c^∞ is known or viceversa.

[Figure 5 appears here]

Creep Behavior

An important aspect concerning the indentation mechanism in polymers is the time dependent part of the plastic deformation. Several studies on polymeric materials have shown that hardness decreases with indentation time following a function of the form [3, 18]:

$$H = H_i \Delta t^{-k} \quad (4)$$

H_i is here the hardness at a given reference time $\Delta t = 1$ and k is the so-called creep constant. The creep constant is a measure of the rate at which the material flows under the indenter and can be derived from the slope of a $\log H$ versus $\log \Delta t$ plot. Data near $\Delta t = 0.1$ min are usually adopted as the hardness value for polymers [3]. Recent research evidences the strong influence of temperature upon the k values [18]. At room temperature, the k -parameter has been shown to primarily depend on l_c [18].

Correlation of Microhardness to Macroscopic Mechanical Properties

According to the classical theory of plasticity, indentation hardness for a Vickers indenter is approximately equal to three times the yield stress measured in frictionless compression, Y_c [1]. However, recent data evidence that the theory fails when dealing with polymers [19]. Indeed, H/Y_c ratios of $H/Y_c \approx 2$ have been found for various chain-folded and chain-extended PE samples due to the non-negligible elastic strains of the indented material [19]. On the other hand, hardness to tensile yield stress ratios of $H/Y_t \approx 3$ have been obtained on a wide variety of PE samples, provided the strain rate of the tensile test is comparable to that employed in the hardness test [19, 20].

The correlation between microhardness and Young's modulus has been explored on various PE samples of different morphology [19, 21]. It has been shown that a H -increase parallels a rise in the Young's modulus values derived from tensile testing [19, 21]. Furthermore, the H/E_c ratio (E_c is the Young's modulus value determined from compression testing) was shown to be the lowest for highly crystalline samples such as chain-extended polyethylene (CEPE), in agreement with an enhanced plastic behaviour [19].

Microhardness of Blends

Hardness is a promising technique for the structural investigation of multicomponent blends. The hardness technique can provide information on the degree of interpenetration of the blend component. The case of blends of low density (LD) and high density (HD) polyethylene is an example where the microhardness can be very well described in terms of an additive (parallel) system of two independent components, H_1 (LD) and H_2 (HD) [4]:

$$H_{blend} = H_1 \phi + H_2 (1-\phi) \quad (5)$$

where ϕ is the fraction of LDPE component. Equation 5 emphasizes the existence of distinct H values for the two phases owing to a molecular segregation at a crystal level.

[Figure 6 appears here]

In other systems like, for example, in PE/iPP, iPP/polyamide (PA) and iPP/EPR blends, a deviation from the additivity law given by equation 5 is detected [4, 5, 16]. Figure 6 illustrates, as an example, the obtained deviation of H from the additivity law (dashed

line) for PE/iPP blends, ϕ being in this case the weight fraction of polypropylene. If one takes into account the measured crystallinity values for the H_1 and H_2 components within the blends, and the H_c values of the homopolymers, then, equation 5 leads to the dotted line in Figure 6. Still, the experimental data are clearly deviated from the predictions of equation 5. The low experimental H values found for the PE/iPP blends are due to a depression in the H_c^{PE} and H_c^{PP} values as a consequence of an increase in the surface free energy of the crystals (see equation 3) [4].

The use of the microhardness technique in blends of condensation polymers (PET/PEN and PET/polycarbonate (PC)) evidences the formation of copolymer sequences within the blends [5].

Indentation Anisotropy of Oriented Polymers

Uniaxial mechanical deformation produces a conspicuous anisotropic shape of the residual indentation [3]. The anisotropy depends on the orientation of the diagonals of indentation relative to the axial direction. Two well-defined hardness values emerge. One value (maximum for a Vickers indenter) can be derived from the indentation diagonal parallel to the fiber axis, $d_{\parallel}$. The second one (minimum) is deduced from the diagonal perpendicular to it, $d_{\perp}$. The former value responds to an instant elastic recovery of the fibrous network in the draw direction. The latter value defines the plastic component of the oriented material. It is useful to define the indentation anisotropy, ΔH , as $\Delta H = 1 - (d_{\parallel}/d_{\perp})$.

A ΔH increase with increasing draw ratio, λ , has been found for solid-state extruded and highly drawn polymers and a correlation between indentation anisotropy and Young's modulus has been found [3, 22]. Indentation anisotropy values of several carbon fiber composites have been reported [23]. Recently, the indentation anisotropy of cold-drawn PET, annealed at different temperatures, has also been examined [24].

[Figure 7 appears here]

Figure 7 illustrates the $H_{\parallel}$ and $H_{\perp}$ values as a function of annealing temperature, T_a , for cold-drawn PET. The $H_{\perp}$ increase with rising T_a reveals firstly, the gradual appearance of smectic domains (apparent at $T_a = 50^{\circ}\text{C}$) and secondly, the developing of a triclinic structure for $T_a \geq 80^{\circ}\text{C}$. The insert of Figure 7 shows the rapid decrease of ΔH with increasing T_a above 70°C . This result suggests that a molecular relaxation mechanism in the amorphous layers takes place above T_g ($T_g \approx 70^{\circ}\text{C}$), leading to a decrease in the elastic response of the fibrils to indentation along the chain direction.

Test Methods

Scratch Hardness Tests

The method is based on the ability of one solid to scratch another. A corner of a diamond cube is drawn across the sample surface under a force of 29.4 mN applied to the body diagonal of the cube; this creates a V-shaped groove of width, λ , which is measured microscopically [25]. The hardness is given by

$$HS = \frac{10,000}{\lambda^2} \quad (6)$$

The constant 10,000 is arbitrary and λ is in μm .

Dynamic Rebound Test: Scleroscope.

In this test, the rebound of a diamond-tipped weight dropped from a fixed height is measured [25]. There are two models of the instrument: Model C (HSc) uses a hammer of small mass (≈ 2.3 g) and a large height of fall (≈ 251 mm); Model D (HSd) uses a hammer of about 36 g and a short fall (≈ 18 mm).

Indentation Depth Reading: Rockwell Test.

In this test, the depth of the indentation is read from a dial indicator; no microscope is required [25]. In the Rockwell hardness tests, a load of 98 N is first applied to the surface and the depth of penetration is thereafter reckoned as the zero of measurement. A further load of 588 N, 980 N or 1470 N is applied and removed leaving the additional depth of indentation recorded on a dial. The hardness is then expressed in terms of the dial reading on an arbitrarily numbered scale. The indenter used may be a steel spherical penetrator or a diamond cone with a hemispherical tip. The scales, indenter and loads employed are chosen to adapt to the material properties. Results given by different testers are not readily interconverted.

Tests based on the Optical Imaging of Indentation

Hardened steel, tungsten carbide or diamond indenters are usually employed. Hardness values are determined from the load and the measurement of the residual indentation

after load removal [1]. The spacing between indents must be large enough (typically 2 times the width of the indentation) to be unaffected by deformation resulting from nearby indents. The sample thickness must be 10 times or 1.5 times thicker than the width of the residual impression for spherical or pyramidal indenters respectively. A microscope equipped with a micrometer eyepiece is used to measure the diameter of the impression up to 0.5 μm at most. The surface of the specimen must be flat, smooth, free of dirt and unlubricated.

Brinell. In the Brinell test, a hardened steel ball is forced into the specimen. The standard test uses a 10 mm ball and a force of 29.42 kN [25]. The Brinell hardness, HB , is equal to the applied force divided by the area of the indentation:

$$HB = \frac{2P}{\pi D \left[1 - \sqrt{1 - (d/D)^2} \right]} \quad (7)$$

in which P is the force in N, D is the diameter of the ball in mm, and d is the diameter of the impression in mm. The minimum radius of a curved specimen surface is 2.5 D . Published tables simplify the conversion from the hardness values obtained with one standard load to the other [25].

Pyramid Indenters. The most common pyramid indenters are the *Vickers*, *Knoop* and *Berkovich* indenters. The Vickers indenter consists of a square-based diamond pyramid of included angles α between non-adjacent faces of 136° . The Knoop test uses a rhombic-based diamond with included angles of 172° and 130° between opposite edges. The Berkovich indenter is a diamond trigonal pyramid whose facets form an angle of 65.3° with respect to the normal to the base.

Hardness value is calculated by dividing the load, P , by the facet or projected area of indentation, A :

$$H = \frac{P}{A} = C \frac{P}{d^2} \quad (8)$$

Here d is the average of both diagonal lengths, the length of the long diagonal or the height of the triangular impression for the Vickers, Knoop and Berkovich indenters respectively. Hardness values in equation 8 are given in MPa if the force is in N and d in mm. C is a geometric constant whose value depends on the indenter shape and whether the projected area or the facet contact area of indentation is being used to calculate the hardness number. For a Vickers indenter, the facet area is most commonly used ($C = 1.854$). Knoop and Berkovich microhardness values are traditionally derived using the projected area of indentation ($C = 14.23$ and 1.766 respectively).

The Vickers test gives a smaller indentation than the Knoop test for a given load. The latter is very sensitive to material anisotropy because of the twofold symmetry of the indentation. The Berkovich indenter is preferred to the four-side pyramids when extremely small indentations are produced.

Continuous Load-Depth Recording

In ultramicroindentation and nanoindentation devices the displacement and load are monitored continuously. It should be possible to vary the applied load, or imposed displacement, either in ramp mode or with a discontinuous increment (step mode) [26].

Figure 8 illustrates a loading-hold-unloading cycle obtained for PET using a

ultramicrohardness tester operating in ramp mode. The load is incremented at constant speed up to the maximum load, P_{max} , held thereafter for a period of time, Δt , and subsequently released at the same rate as in the loading cycle. Continuous depth-sensing recording does not give values of absolute hardness directly. This is because the area of indentation is not explicitly measured. However, the loading/unloading data can be processed on the basis of well-established assumptions to yield hardness and Young's modulus values [27, 28]. These approaches consider that the on-load maximum indentation depth, h_{max} , is the sum of the plastic and the elastic components of indentation, h_p and h_e respectively (see Figure 8). It is further assumed that the area of contact between the indenter and specimen is determined by the plastic deformation only. The h_p value is then calculated from the analysis of the unloading curve [27, 28]. For a Vickers indenter, $A = 26.4 h_p^2$, where A is the facet area of contact between the indenter and the specimen. Similar geometrical relationships between A and h_p can be derived for other indenters. Hardness is then calculated according to equation 8. The elastic modulus values may be derived from the analysis of the unloading curves.

Indentation studies on different polymeric materials suggest that the hardness values derived from continuous depth-sensing recording compare fairly well with the hardness numbers derived from the direct measurement of the size of indentation [29-31]. This result suggests that hardness numbers determined from the contact area under load are comparable to post-indentation hardness values.

The actual trend in hardness testing is to use the nanoindentation instruments in conjunction with atomic force microscopes [32]. Load-displacement measurements are

used to derive hardness and elastic modulus data while the atomic force microscope yields additional topographic information of the indentation area. Measurements at depths of 1 nm can be performed.

Bibliography

1. D. Tabor, *The Hardness of Metals*, Oxford University Press, New York, 1951.
2. J. B. Pethica, R. Hutchings and W. C. Oliver, *Phil. Mag. A.*, **48**, 593 (1983).
3. F. J. Baltá Calleja, *Adv. Polym. Sci.*, **66**, 117 (1985).
4. F. J. Baltá Calleja, *Trends Polym. Sci.*, **2**, 419 (1994).
5. F. J. Baltá Calleja and S. Fakirov, *Adv. Polym. Sci.*, **5**, 246 (1997).
6. F. Ania, J. Martínez-Salazar and F. J. Baltá Calleja, *J. Mater. Sci.*, **24**, 2934 (1989).
7. S. Fakirov, F. J. Baltá Calleja and M. Krumova, *J. Polym. Sci.: Polym. Phys.*, **37**, 1413 (1999).
8. J. M. Pastor, A. González and J. A. De Saja, *J. Appl. Polym. Sci.*, **38**, 2283 (1989).
9. C. Santa Cruz, F. J. Baltá Calleja, H. G. Zachmann, N. Stribeck and T. Asano, *J. Polym. Sci.: Polym. Phys.*, **29**, 819 (1991).
10. F. J. Baltá Calleja, C. Santa Cruz and T. Asano, *J. Polym. Sci.: Polym. Phys.*, **31**, 557 (1993).
11. J. Kajaks, A. Flores, M. C. García Gutiérrez, D. R. Rueda, F. J. Baltá Calleja, *Polymer*, **41**, 000 (2000).
12. F. J. Baltá Calleja and H. G. Kilian, *Colloid Polym. Sci.*, **263**, 697 (1985).
13. F. J. Baltá Calleja, O. Öhm and R. K. Bayer, *Polymer*, **35**, 4775 (1994).

14. F. J. Baltá Calleja, C. Santa Cruz, D. Chen and H. G. Zachmann, *Polymer*, **32**, 2252 (1991).
15. L. Giri, Z. Roslaniec, T. A. Ezquerro and F. J. Baltá Calleja, *J. Macromol. Sci. Phys. B*, **36**, 335 (1997).
16. A. Flores, J. Aurrekoetxea, R. Gensler, H. H. Kausch, F. J. Baltá Calleja, *Colloid Polym. Sci.*, **276**, 786 (1998).
17. B. Wunderlich, *Macromolecular Physics, vol.3: Crystal Melting*, Academic Press, New York, 1980, chapter 8.
18. F. J. Baltá Calleja, A. Flores, F. Ania and D. C. Bassett, *J. Mater. Sci.*, **35**, 1315 (2000).
19. A. Flores, F. J. Baltá Calleja, G. E. Attenburrow and D. C. Bassett, *Polymer*, **41**, 5431 (2000).
20. F. J. Baltá Calleja, L. Giri, I. M. Ward and D. L. M. Cansfield, *J. Mater. Sci.*, **30**, 1139 (1995).
21. V. Lorenzo, J. M. Pereña, J. M. G. Fatou, *Die Angewandte Makromolekulare Chemie*, **172**, 25 (1989).
22. V. Lorenzo, J. M. Pereña, *J. Appl. Polym. Sci.*, **39**, 1467 (1990).
23. W. P. Paplham, J. C. Seferis, F. J. Baltá Calleja and H. G. Zachmann, *Polymer Composites*, **16**, 424 (1995).
24. T. Asano, F. J. Baltá Calleja, A. Flores, M. Tanigaki, M. F. Mina, C. Sawatari, H. Itagaki, H. Takahashi and I. Hatta, *Polymer*, **40**, 6475 (1999).
25. *Annual Book of ASTM Standard Part 10*, American Society for Testing and Materials, Philadelphia, 1978.
26. H. M. Pollock, *ASTM Handbook*, **18**, 419 (1992).

27. M. F. Doerner and W. D. Nix, *J. Mater. Res.*, **1**, 601 (1986).
28. W. C. Oliver and G. M. Pharr, *J. Mater. Res.*, **7**, 1564 (1992).
29. B. J. Briscoe, K. S. Sebastian, S. K. Sinha, *Phil. Mag. A*, **74**, 1159 (1996).
30. B. J. Briscoe, K. S. Sebastian, *Proc. R. Soc. Lond. A*, **452**, 439 (1996).
31. A. Flores, F. J. Baltá Calleja, *Phil. Mag. A*, **78**, 1283 (1998).
32. A. V. Kulkarni and B. Bhushan, *Thin Solid Films*, **290-291**, 206 (1996).

F. J. BALTÁ CALLEJA

A. FLORES

Instituto de Estructura de la Materia, CSIC, Madrid, Spain

Captions to Figures

Figure 1. Typical microhardness values of polymers compared with data for metals.

LDPE, low-density polyethylene; HDPE, high-density polyethylene; iPP, isotactic polypropylene; CEPE, chain-extended polyethylene; POM, polyoxymethylene; aPS, atactic polystyrene; PET, poly (ethylene terephthalate); PEN, poly (ethylene naphthalene-2,6-dicarboxylate); CF composite, carbon- fiber composite. Hardness data of metals and alloys markedly depend on composition, degree of work-hardening, processing conditions, etc. For this reason, the values in Figure 2 should be considered as typical values rather than as absolute values. Most of the data for metals are taken from reference [1].

Figure 2. Schematic illustration of the contact geometry of a pyramid indenter during a static indentation test at zero load, under load and after load release.

Figure 3. Variation of microhardness for PET with crystallization time t_c for different crystallization temperatures T_c .

Figure 4. Plot of reciprocal crystal hardness H_c^{-1} as a function of reciprocal crystal thickness l_c^{-1} for PEO (∇) and PE ($\bullet$).

Figure 5. Variation of H_c^{-1} with T_m for different polymeric materials: PEO (∇), PE ($\bullet$) and PET ($\square$).

Figure 6. Microhardness of PE/iPP blended gel films as a function of the weight concentration of iPP. The dashed line follows equation 5, using the hardness values of the individual homopolymers. The dotted line is derived from the crystallinity values for each component within the blend.

Figure 7. $H_{\parallel}$ and $H_{\perp}$ as a function of annealing temperature for cold-drawn PET. The inset illustrates the plot of indentation anisotropy ΔH vs. T_a for the same material.

Figure 8. Typical compliance curve for glassy PET obtained from continuous depth-sensing recording.

Fig 1

Fig. 2

Fig. 3

Fig 4

fig. 5

Fig. 6

Fig. 7

Fig. 8