Article

Electrostatic Induced Molecular Tilting in Self-Assembled Monolayers of n-Octadecylamine on Mica

Jaime Oviedo, Miguel A. San-Miguel, Jose A. Heredia-Guerrero, and Jose Jesus Benitez

J. Phys. Chem. C, **Just Accepted Manuscript** • Publication Date (Web): 06 Mar 2012

Downloaded from <http://pubs.acs.org> on March 7, 2012

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

ACS Publications
High quality. High impact.

The Journal of Physical Chemistry C is published by the American Chemical Society, 1155 Sixteenth Street N.W., Washington, DC 20036
Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

**Electrostatic Induced Molecular Tilting in Self-Assembled Monolayers
of *n*-Octadecylamine on Mica**

Jaime Oviedo,¹ Miguel A. San-Miguel,¹ José A. Heredia-Guerrero,² José J. Beníte.^{2}*

¹Physical Chemistry Department, University of Seville, Seville (Spain)

²Materials Science Institute of Seville (ICMS), Spanish Research Council (CSIC)-
University of Seville

Americo Vespuccio 49. Isla de la Cartuja, 41092. Seville (Spain)

*Corresponding author: benitez@icmse.csic.es, phone: 34 954489551, fax: 34
954460665.

ABSTRACT

Self-assembled monolayers of *n*-octadecylamine on mica (ODA/mica SAMs) have been investigated by atomic force microscopy (AFM) and by attenuated total reflectance infrared (ATR-FTIR) and X-ray photoelectron (XPS) spectroscopies. Topographic data characterizes a stable configuration with the alkyl skeleton tilted $\approx 46^\circ$ from the surface normal that is rationalized according to a well established structural alkyl chain packing model. Extended contact with air increases molecular tilting up to $\approx 58^\circ$. ATR-FTIR and XPS reveals the presence of protonated amino groups within the monolayer and its increment upon exposure to air. The transition between both tilted states is explained assuming the protonation reaction as the driving force and introducing a model to evaluate an electrostatic repulsions term in the overall cohesive energy balance of the system. ODA molecules in the self-assembled monolayer respond to their spontaneous protonation by atmospheric water by tilting as a mechanism to relax the repulsions between $-\text{NH}_3^+$ heads.

Keywords: self-assembled monolayer, octadecylamine, SAM ripening, amine protonation.

INTRODUCTION

A monolayer of self-assembled molecules (SAM) on a flat surface is a typical example of a well ordered 2D system. The most widely studied are those constituted by linear long chain functionalized alkyl molecules.¹ The technological interest of these systems is based in its consideration as basic steps in a more complex and hierarchical process of nanostructures fabrication.² Most of these self-assembled systems are designed by the formation of a strong bond between the molecule and the support to ensure its stability. This is the case of alkythiols on gold and, in a lesser extent, alkylsilanes on silicon. In addition to this, the presence of a metallic or semiconductor support facilitates their integration in conventional lithographic procedures. For these very same reasons, much less attention has been paid to amphiphilic molecules weakly bonded to a non-metallic support. However, from a fundamental point of view, these are very adequate systems to investigate intermolecular interactions. In the absence of a support driving the structure of molecular packing, 2D ordering is ruled by molecule to molecule interactions, among them van der Waals, electrostatic forces and hydrogen bonding. Direct structural determination of self-assembled monolayers is commonly attained by high resolution scanning probe microscopies such as scanning tunneling (STM) and atomic force (AFM) microscopies.^{3,4,5} In the particular case of long chain alkyl SAMs weakly adsorbed on a non-conducting support, STM cannot be used. Furthermore, the mechanical effect caused by the scanning tip when operating an AFM microscope in lateral force mode, the usual conditions to obtain atomic resolution, favors the disruption and erosion of the SAMs.

Few years ago, a model describing the molecular packing of linear long chain alkyl molecules in SAMs was proposed.^{6,7,8} It is based on the maximum interlocking of the zig-zag arrays of methylene groups between adjacent alkyl chains; and it has

1
2
3 explained very successfully the experimentally observed step-wise topographic and
4
5 frictional changes of alkanethiols on gold and alkylsilanes on Si and mica SAMs under
6
7 the pressure exerted by the scanning probe. The model predicts the existence of specific
8
9 tilting angles and monolayer heights and, based exclusively on van der Waals
10
11 interactions, it estimates the activation energy required for the transition between tilted
12
13 states.
14
15
16

17
18 Due to the above mentioned difficulties in the structural characterization of
19
20 weakly adsorbed SAMs, this research takes advantage of the model to study the
21
22 molecular packing of delicate octadecylamine (ODA) SAMs on mica using the
23
24 topographic data obtained by AFM. In the particular case of ODA/mica SAMs there are
25
26 some experimental observations to be explained. For instance, the monolayer height is
27
28 significantly shorter if compared with analogous SAMs.^{6,8} This suggests a more tilted
29
30 configuration despite the associated cohesive energy loss of the packed layer.⁹ Second, a
31
32 characteristic and spontaneous height reduction is systematically observed when
33
34 ODA/mica SAMs are left in contact with air (ripening) for an extended period of
35
36 time.^{10,11} Progressive amino group ($-\text{NH}_2$) protonation and the derived electrostatic
37
38 repulsion between resulting ($-\text{NH}_3^+$) groups was early proposed to explain such height
39
40 reduction, however no additional data supporting this hypothesis has yet been provided.
41
42 To investigate these findings, in this article we have used ATR-FTIR and XPS to detect
43
44 and quantify amino protonation and we have introduced an electrostatic repulsive term
45
46 arising from the presence of protonated amino ($-\text{NH}_3^+$) groups in the energy balance of
47
48 ODA/mica SAMs. To our knowledge, it is the first time that such study is reported in
49
50 the literature.
51
52
53
54
55
56
57
58
59
60

EXPERIMENTAL

n-Octadecylamine (ODA, $C_{18}H_{37}NH_2$, Fluka >99%) was used as received with no further purification. ODA/mica SAM islands have been prepared by immersing the freshly cleaved mica (muscovite, New York Corp.) pieces in the 15 mM in chloroform (Panreac > 99.8% stabilized with 50 ppm of amylene) solution for 1 minute. They are removed with no rinsing and dried under dry N_2 for 2-3 minutes. After preparation, samples are allowed to ripen in contact with air for controlled periods of time (from 2 hours to 7 days) inside a Petri dish. No specific room humidity control is performed, but it ranges from 45% to 55% RH (temperature calibrated relative humidity HIH Series Honeywell sensor). This article is mainly focused on the study of islands topographic changes upon contact with air, thus, though tracking analysis are done along the process, fresh samples, i.e. those analyzed approximately 2 hours after preparation, and those extensively ripened (5-7 days) showing the already mentioned height reduction are the most significant. For this reason both samples are continuously contrasted along the article.

The AFM microscope is a Nanotec “Cervantes” with a $10\ \mu m \times 10\ \mu m$ scanner and connected to a “Dulcinea” electronics. A rectangular Olympus RC800PSA lever with $k = 0.1\ N/m$ was employed. For distance calibration we used a NT-MDT TGT01 silicon grating ($2.12\ \mu m$ pitch) for the X and Y directions, and a Nanosensor H8 certified grating with 7.0 nm step height for the Z direction. Images were processed and analyzed using the WSxM software.¹² AFM images were acquired using the so called “jumping mode” in air at 20-25 °C and 45-55% RH. In this mode, a full approach-retract cycle is completed at every point of the matrix defining an image. Feedback enabling at the contact force set point provides the topographic data while pull-off forces define the adhesion map. Standard contact mode AFM has been unsuitable for

the study of non-ripened ODA/mica SAMs, in particular when the scanning size and speed are reduced. ODA/mica SAMS islands do need some time, typically several hours, to gain cohesion and resist the mechanical erosion and compression from the tip working in permanent contact. With jumping mode, dragging forces associated to contact and tip displacement in the (X,Y) plane are avoided because rastering is done out of contact.¹³ To further prevent mechanical damage, the set point (i.e. the vertical load exerted by the tip on the SAMs islands when re-establishing contact) was kept as low as possible. With this type of lever the force applied to the islands when reestablishing contact is calculated to be around 4.5 nN. 256 lines are acquired in every image at 1 line/s rate. A more detailed description of the AFM acquisition conditions is given elsewhere.¹⁴ Stable and reproducible approach/retract cycling is considered as a reference for the absence of material picking by the probe.

ATR-FTIR spectra have been collected using a PIKE MIRacleTM ATR accessory (ZnSe crystal plate) attached to a Jasco FT/IR 6200 spectrometer equipped with a MCT detector operating at 4 cm⁻¹ resolution. 250 scans have been accumulated in each run using non-polarized radiation. To prevent interferences arising from mica support, small pieces were repetitively cleaved to the minimum thickness to allow handling and deposition of n-octadecylamine by dipping.¹⁵

XPS spectra were obtained with a Physical Electronics PHI 5700 spectrometer using non-monochromatic Mg K α radiation (300 W, 15 kV, 1253.6 eV) and a multi-channel detector. Spectra were recorded in the constant pass energy mode at 29.35 eV with a 720 μ m diameter analysis area. Binding energy (B.E.) values were referred to the methylene C_{1s} peak at 285 eV. C_{1s}, O_{1s}, K_{2p} and N_{1s} regions have been collected. Particularly, the N_{1s} signal has been analyzed in detail and experimental data have been fitted to Gauss–Lorentz curves with fixed 1.8 eV FWHM using the resident software

(PHI Multipack v.8.2B). This band width is extracted from the XPS of bulk ODA containing only the ($-\text{NH}_2$) contribution. The relative concentration of N species is calculated from the area of the fitting components. In some cases and to improve the fitting, virtual weak contributions were added to account for some asymmetry on the low and high B.E. sides of the N_{1s} peak.

EXPERIMENTAL RESULTS

Topographic characterization of ODA/mica SAMs

In our experimental conditions, ODA forms rounded, 500-750 nm in diameter and one monolayer thick islands on mica. In such islands ODA molecules are attached to the surface of mica by the amino group and expose the terminal methyl group, as deduced from friction and adhesion maps.^{9,14} When freshly prepared (i.e. ≈ 2 hours old) isolated ODA/mica SAM islands with relatively sharp edges are detected, Figure 1a. Ripening in air causes their progressive contour rounding and aggregation, Figure 1b. However the most striking observation is the spontaneous island height reduction from an initial $17\text{\AA}$ value to about $13\text{\AA}$ after exposition to the atmosphere for about a week. No such height reduction is observed at periods of aging below 5-7 days. Island flattening is a sudden event and only in very rare occasions both heights can be observed in the same analysis area (see Figure S1 in supporting information). In both cases height values are well below the full molecular length ($24.6\text{\AA}$) and, therefore, a configuration in which the alkyl axis is tilted from the surface normal direction is proposed (theoretically 46° and 58° , respectively).

Structural and chemical characterization of ODA/mica SAMs

1
2
3 Use of contact mode AFM has been unsuccessful to obtain molecular resolution
4 images of ODA/mica SAMs.⁹ The pressure and dragging exerted by the scanning probe
5 is too high to prevent the displacement of the weakly bonded ODA molecules. This
6 disadvantage has hindered the structural resolution of ODA/mica SAMs packing. We
7 also lack direct structural information of ODA/mica SAMs from diffraction techniques.
8 Consequently, we have to rely on indirect structural data obtained from ATR-FTIR
9 spectroscopy, mostly from the analysis of vibrational modes of methylene ($-\text{CH}_2-$)
10 groups.
11
12

13 The frequencies of methylene C-H stretching bands of ODA/mica SAMs (ν_a
14 2917 cm^{-1} and ν_s 2850 cm^{-1}), Figure 2a, are much closer to those reported for crystalline
15 than to the ones corresponding to liquid n-alkanes.¹⁶ The peak positions are also very
16 similar to those of solid octadecylamine and well-packed alkyl monolayers.^{17,18} Another
17 indication of an ordered, crystal-like structure of ODA/mica SAMs is the splitting of the
18 ($-\text{CH}_2-$) scissoring deflection around 1470 cm^{-1} , Figure 2b.¹⁹ The magnitude of the
19 experimental splitting (6 cm^{-1}) is also consistent with a tilted configuration of the alkyl
20 molecules within the crystalline subcell.¹⁸ Finally the series of methylene twisting-
21 rocking (T) and /or wagging (W) progression bands in the $1350\text{-}1250\text{ cm}^{-1}$, Figure 2b
22 are an additional indication of a high degree of chain ordering within the ODA/mica
23 SAMs structure.^{20,21}
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47

48 The methylene C-H stretching region displays very slight modifications upon
49 ripening and tilting (i to ii in Figure 2a). No ν_a and ν_s frequency modification is
50 observed, however a mild peak sharpening (FWHM from 20 to 16 cm^{-1} for ν_a and 12 to
51 10 cm^{-1} for ν_s) upon aging can be detected. The bandwidth has been related to the
52 molecule mobility within the packed layer²² and therefore, a slight improvement of the
53 conformational ordering in the ODA/mica SAMs can be deduced. The same conclusion
54
55
56
57
58
59
60

can be obtained from the enhancement of the methylene twisting-rocking+wagging (T+W) peaks in the 1300-1350 cm^{-1} range, Figure 2b.

The ATR-FTIR spectra of ODA/mica SAMs also contain an intense peak at 1569 cm^{-1} . It is assigned to the deformation and vibration of the ($-\text{NH}-\text{COO}^-$) group of in alkylammonium alkylcarbamates.^{23,24,25,26} The presence of such carbamate in ODA/mica SAMs is unexpected but it is confirmed by other peaks at 1645 cm^{-1} , 1391 cm^{-1} and by the symmetric deformation of the ($-\text{NH}_3^+$) counterion at 1486 cm^{-1} .^{27,28} The origin of such octadecylammonium octadecylcarbamate is the fast reaction between ODA molecules and the CO_2 dissolved in the water adlayer formed on mica surface after cleaving in air.²⁹

The N_{1s} XPS spectra of ODA/mica SAMs clearly show the presence of both protonated and non-protonated amino groups, Figure 3, but there is no direct indication of the carbamate phase. However the detection of this species is so irrefutable from infrared data that a contribution at 400.2 eV ($-\text{NH}-\text{COO}^-$) has to be added to those at 399.4 and 401.3 eV, respectively assigned to amino ($-\text{NH}_2$) and ammonium ($-\text{NH}_3^+$) species.^{18,26,30,31,32,33,34} The N_{1s} peaks have been fitted using these components and a progressive increment of the $-\text{NH}_3^+/-\text{NH}_2$ ratio is observed along the ripening process (see Table S1 and Figure S2 in supporting information). Furthermore, carbamation seems to be constant along the ODA/mica SAM exposition to air, as indicated by the evolution of the 400.2 eV component in Figure 3. However, the presence of protonated amino groups ($-\text{NH}_3^+$) is higher than expected from the mere formation of the carbamate (nominal 1:1 $-\text{NH}_3^+:-\text{NH}-\text{COO}^-$ ratio). Consequently, it can be concluded that an important fraction ($\approx 20\%$) of ($-\text{NH}_3^+$) is produced by direct amino protonation by the water adlayer at the mica surface at the moment of ODA/mica SAMs preparation. After ripening for a week, the concentration of protonated amino groups increases up to about

28% by reaction with extra adsorbed water molecules from moisture. This is corroborated by the increment of the 1486 cm^{-1} peak in the ATR-FTIR spectrum, Figure 2b. The process has been described as the proton transference from water molecules at the edges of islands towards the inside. Steric effects prevent an analogous penetration mechanism for the CO_2 molecule.²⁹

Cohesive and electrostatic energy balance in ODA/mica SAMs

The theoretical packing model proposed by Salmeron et al.^{6,8} defines the molecular tilt by the components along the NN (θ_x) and NNN (θ_y) directions of a hexagonal arrangement according to the conditions:

$$\tan \theta_x = \frac{na}{s_x} \quad (1)$$

$$\tan \theta_y = \frac{ma}{s_y} \quad (2)$$

where (a) is the distance ($2.5\text{ \AA}$) between alternating C atoms projected along the molecular axis and (s_x and s_y) the separations, in the perpendicular direction to their alkyl axis, between molecules in the NN ($s_x = 4.7\text{ \AA}$) and NNN ($s_y = 3^{1/2}s_x$) directions respectively. When fully interlocked, (n) and (m) are numbers adopting the values:

$$n = 0, \frac{1}{2}, 1, 1\frac{1}{2}, 2, 2\frac{1}{2}, \dots \quad (3)$$

$$m = 0, 1, 2, 3, \dots \quad (4)$$

The combination of nearest and next nearest neighbor tilting yields a series of island relative heights (h/L , L = full molecular length) values defining an effective tilting angle (θ). Values for $n \leq 4$ and $m \leq 3$ are compiled in Table 1.

Molecular tilt has a direct effect in the cohesion of the monolayer because end methylene units from both sides of the alkyl chains loose half of their matching

counterparts, Figure 4. To evaluate the cohesive energy dependence upon tilting we have defined an overlapping factor (F) defined as:

$$F = 1 - \frac{s \tan \theta}{L} \quad (5)$$

Where (s) is the chain to chain separation in the packed structure (4.7 Å) and (L) the full *n*-octadecylamine molecular length (24.6 Å). We have considered the cohesive energy to be proportional to the effective overlapping between alkyl chains (F), being $E_{\text{coh}} = 129.5$ kJ/mol when fully vertical ($F = 1$). This energy value has been obtained from C_{18} alkane sublimation energy.³⁵ Considering the discrete tilting angles of Table 1 and the corresponding overlapping factors (F), we have constructed a curve predicting the evolution of the cohesive energy (E_{coh}) with tilting, Figure 5a. In this case, inclination is represented by the head to head distance (d) along a direction parallel to the plane support ($d = s/\cos \theta$). As observed, a continuous decrease of cohesive energy vs (d) is postulated.

To estimate the electrostatic repulsion energy we have represented the protonation of ODA molecules in the SAM as the association of hydroxyl groups and NH_3^+ cations. Such ion pair would define a dipole. Because of the superimposed SAM packing symmetry, all dipoles are considered to be parallel. Besides, and due to the dynamic character of molecules in this weakly adsorbed system, we postulate that dipoles should be uniformly distributed to minimize electrostatic repulsions. XPS reveals that the percentage of amino groups protonated by water is about 20% when freshly prepared and $\approx 28\%$ after ripening for a week. In our model, these protonation states are represented by two homogeneous distributions considering protonated molecules along the NN ($\Theta = 1/4$) and NNN ($\Theta = 1/3$) directions, Figure 6. This would yield a theoretical 25% and 33% amine protonation, respectively, very similar to the experimental values indicated.

The interaction energy between two parallel dipoles can be expressed as:

$$U = \frac{p^2}{4\pi\epsilon_r\epsilon_o} \frac{1}{D^3} \quad (6)$$

Where (p) is the dipole moment, (ϵ_o) and (ϵ_r) the vacuum and the relative dielectric permittivities, respectively, and (D) the distance between dipoles. Expanding the interaction to every shell containing (N_i) dipoles located at distances (D_i) and expressing (D) as a function of the effective radius (R) of the packed dipoles (Figure 6):

$$U = \frac{1}{4\pi\epsilon_o} \left(\frac{p^2}{\epsilon_r} \right) \frac{C}{R^3} \quad (7)$$

Where (C) is a constant obtained by convergence of the additive series ($C = 1.3764641$) (see supporting info). If we express the energy values in kJ/mol and dividing by a factor of 2 to avoid counting the same interaction twice, the repulsion interaction between dipoles in a close packed hexagonal arrangement with a dipole fraction (Θ) can be written as:

$$U(kJ \text{ mol}^{-1}) = 415 \left(\frac{p^2}{\epsilon_r} \right) \frac{\Theta}{R^3} \quad (8)$$

Where (R) is indicated in angstroms and (p) in Debyes ($1D = 3.33564 \times 10^{-30} \text{ C m}$). To compare with cohesive energy values, (U) will be expressed as a function of (d), the head to head distance. For the $\Theta = 1/4$ arrangement, $R = d$ and for the $\Theta = 1/3$, $R = d \cdot 3^{1/2}/2$, Figure 6, thus:

$$U(\Theta = 1/4) = 103.75 \left(\frac{p^2}{\epsilon_r} \right) \frac{1}{d^3} \quad (9)$$

And

$$U(\Theta = 1/3) = 212.98 \left(\frac{p^2}{\epsilon_r} \right) \frac{1}{d^3} \quad (10)$$

Separation between ($-\text{NH}_3^+$) cations and an hydroxyl anions (OH^-) is set as $3\text{\AA}$, the sum of ionic radii of ammonium ($1.50\text{\AA}$) and hydroxyl ions ($1.54\text{\AA}$). This would yield (p) values of about 14.4 D. Assuming a dielectric constant ($\epsilon_r = 3.5$)³⁶ and the set of head to head separation (d) values corresponding to the tilted states indicated in Table 1, electrostatic repulsion energy (E_{rep}) vs (d) curves has been constructed, Figure 5a. The energy balance between cohesion and electrostatic repulsion ($E_{\text{coh}} + E_{\text{rep}}$) for both $\Theta = 1/4$ and $\Theta = 1/3$ are also indicated, Figure 5b. As observed, energy minima develop for both configurations and equilibrium head to head distances of about $7\text{\AA}$ and $9\text{\AA}$ are obtained for $\Theta = 1/4$ and $\Theta = 1/3$ respectively. Such distances corresponds to relative height values (h/L) of 0.67 and 0.52 in quite good agreement with the 0.69 ($h = 17\text{\AA}$) and 0.53 ($h = 13\text{\AA}$) experimental data for the freshly prepared and the ripened ODA SAMs, respectively, Figure 1.

DISCUSSION

AFM topographic data indicates that ODA/mica SAMs forms a highly packed and ordered molecular structure with the alkyl skeleton tilted with respect to the surface normal. ATR-FTIR provides additional experimental evidence supporting this finding via the methylene stretching and deflection peaks. Molecular tilt derived from experimental height values, Figure 1, do match the $n = 2$ and $n = 3$ tilting states (47° and 58° from the surface normal respectively) defined by the close packing model reported by Salmeron et al.⁶⁻⁸ Such inclination is much higher than the ones observed for similar SAMs of alkyl-silanes and thiols,^{6,8} which is intriguing because island cohesive energy is lost upon tilting. To address this issue we have revised the literature on octadecylamine specific surface areas obtained from Langmuir-Blodgett isotherms. Didymus et al.³⁷ have reported values of $20\text{-}22\text{\AA}^2/\text{molec}$. Taking into account the

surface packing density factor ($\pi/\sqrt{12}$), the amino to amino separation (d) in a closed hexagonal packing calculated from such specific surface areas is 4.8-5.0 Å. This is slightly above the predicted 4.7 Å for the fully vertical $n = 0$ state, so it can be deduced then that mere steric repulsions between unprotonated $-\text{NH}_2$ head groups already prevents the formation of such ($n = 0$) phase. At low subphase pH (pH = 3), at which full $-\text{NH}_2$ protonation is expected, the specific area increases up to 30-35 Å²/molec.³⁷ This means a higher head group separation (about 5.9-6.4 Å) arising from the electrostatic repulsions between protonated amino groups ($-\text{NH}_3^+$). The nominal (d) value for the next tilted state $n = 1$ is 5.3 Å. Though amino group protonation is only partial in ODA/mica SAMs, it is assumable that the 5.3 Å value is too close to the limiting 4.8-5.0 Å separation to make the $n = 1$ to be a stable configuration when an electrostatic repulsion component develops. These qualitative considerations seem to explain why the way tilted $n = 2$ state ($d = 6.9$ Å, $\theta \approx 47^\circ$) is systematically observed upon ODA/mica SAMs preparation. Our work introduces a more quantitative argument based on the balance between cohesive and electrostatic repulsion energy. Thus, at short periods of contact with air ($\Theta = 1/4$), the model predicts a stable configuration at separation values (d) around 7 Å, Figure 5b, which is in good agreement with our experimental topographic AFM data.

Apart from island rounding, displacement and coalescence into bigger ones, the ODA/mica SAMs height reduction and the increment of protonation percentage are the only experimental observations caused by extended ripening. Consequently we have related both phenomena. Amine protonation in solution is an exothermic reaction with reported enthalpy values of about 60 kJ/mol³⁸ and can be considered then as the driving force for the process. The progressive incorporation of water molecules to the $-\text{NH}_2$ /mica interface would displace the equilibrium towards protonation. The resulting

increment of charge density in the confined structure of the ODA/mica SAM is accompanied by an increase of the electrostatic repulsions and, to accommodate the charge increment, the system reacts by separating them and reaching the $\Theta = 1/3$ state, Figure 6. Separation is achieved by a step-wise alkyl chain to chain sliding and the transition to the next allowed tilted configuration ($n = 2$ to $n = 3$). In these conditions, the new cohesive-repulsive energy balance is represented by the $\Theta = 1/3$ curve in Figure 5b and predicts a head to head separation (d) of $\approx 9\text{\AA}$, in good agreement with the one calculated from experimental AFM data.

From the curves in Figure 5b, the $n = 2$ to $n = 3$ transition needs $\Delta E \approx 12$ kJ on going from a protonation percentage of 25% to 33.3%. This would require a process supplying about 140 kJ/mol, which is a higher value but in the order of magnitude of the amine protonation enthalpy reported. In addition to this, it should take into account that mica surfaces carries a negative charge and the incorporation of positively charged groups provides an additional electrostatic energy that may contribute to the $n = 2$ to $n = 3$ transition.

CONCLUSIONS

Extended contact with air (ripening) is an important parameter influencing the topography of weakly adsorbed self-assembled monolayers of *n*-octadecylamine on mica. The spontaneous protonation of weak basic amino groups induced by atmospheric water introduces significant electrostatic repulsions between molecules in such a confined structure. Starting from a well established model describing the close packing of alkyl chains in SAMs, the contribution of the electrostatic repulsions have been evaluated using dipole to dipole interactions. The balance between cohesive and repulsion energy as a function of the head to head separation in ODA/mica SAMs show

1
2
3 a series of minima that can be assigned to experimentally observed tilted configurations.
4
5 Tilting, and the consequent head to head separation, is the response of the packed
6
7 system to relax such electrostatic repulsions. The model proposed predicts an energy
8
9 gap for the transition between tilted configurations in the order of magnitude of the
10
11 driving process: the amine protonation by water.
12
13
14
15
16

17 ACKNOWLEDGMENT

18
19 Funding is provided by the Spanish Ministerio de Ciencia e Innovación under
20
21 project CTQ2008-00188.
22
23
24
25
26

27 SUPPORTING INFORMATION

28
29 Supporting information contains AFM data showing the coexistence of the $h \approx$
30
31 $17\text{\AA}$ and the $h \approx 13\text{\AA}$ phases in a *n*-octadecylamine self-assembled monolayer on mica;
32
33 XPS data on the progressive protonation of ODA molecules along ripening; the
34
35 algorithm to calculate the convergence constant (*C*) in the electrostatic repulsion energy
36
37 calculation. This information is available free of charge via the internet at
38
39
40
41
42 <http://pubs.acs.org>.
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

TABLES

Table 1 Molecular Tilting Angle from the Surface normal (θ) Predicted from the Structural Model Proposed by Salmeron et al.

n	$\cos \theta$			
	$m = 0$	$m = 1$	$m = 2$	$m = 3$
0	1	0.956	0.852	0.735
$\frac{1}{2}$	0.966	0.923	0.823	0.710
1	0.883	0.844	0.752	0.649
$1 \frac{1}{2}$	0.782	0.748	0.666	0.575
2	0.685	0.655	0.584	0.503
$2 \frac{1}{2}$	0.601	0.575	0.512	0.442
3	0.531	0.508	0.452	0.390
$3 \frac{1}{2}$	0.475	0.454	0.405	0.349
4	0.425	0.406	0.362	0.312

REFERENCES

-
- ¹ Ulman, A. *Chem. Rev.* **1996**, *96*, 1533-1554.
- ² Whitesides, G. M.; Grzybowski, B. *Science* **2002**, *295*, 2418-2421.
- ³ Widrig, C. A.; Alves, C.; Porter, M. D. *J. Am. Chem. Soc.* **1991**, *113*, 2805-2810.
- ⁴ Alves, C. A.; Smith, E. L.; Porter, M. D. *J. Am. Chem. Soc.* **1992**, *114*, 1222-1227.
- ⁵ Liu, G.-y.; Fenter, P.; Chidsey, C. E. D.; Ogletree, D. F.; Eisenberger, P.; Salmeron, M. *J. Chem. Phys.* **1994**, *101*, 4301-4306.
- ⁶ Barrena, E.; Kopta, S.; Ogletree, D. F.; Charych, D. H.; Salmeron, M. *Phys. Rev. Lett.* **1999**, *82*, 2880-2883.
- ⁷ Würger, A. *Phys. Rev. Lett.* **1999**, *83*, 1696.
- ⁸ Barrena, E.; Ocal, C.; Salmeron, M. *J. Chem. Phys.* **2000**, *113*, 2413-2418.
- ⁹ Benítez, J. J.; Kopta, S.; Ogletree, D. F.; Salmeron, M. *Langmuir* **2002**, *18*, 6096-6100.
- ¹⁰ Benítez, J. J.; Kopta, S.; Díez-Pérez, I.; Sanz, F.; Ogletree, D. F.; Salmeron, M. *Langmuir* **2003**, *19*, 762-765.
- ¹¹ Benítez, J. J.; Salmeron, M. *J. Chem. Phys.* **2006**, *125*, 044708.
- ¹² Horcas, I.; Fernandez, R.; Gomez-Rodriguez, J. M.; Colchero, J.; Gomez-Herrero, J.; Baro, A. *Rev. Sci. Instrum.* **2007**, *78*, 013705.
- ¹³ de Pablo, P. J.; Colchero, J.; Gómez-Herrero, J.; Baró, A. M. *Appl. Phys. Lett.* **1998**, *73*, 3300-3302.
- ¹⁴ Benítez, J. J.; Heredia-Guerrero, J. A.; Salmeron, M. *J. Phys. Chem. C* **2010**, *114*, 12630-12634.
- ¹⁵ Guzonas, D. A.; Hair, M. L.; Tripp, C. P. *Appl. Spectrosc.* **1990**, *44*, 290-293.
- ¹⁶ Snyder, R. G.; Strauss, H. L.; Elliger, C. A. *J. Phys. Chem.* **1982**, *86*, 5145-5150.
- ¹⁷ Hostetler, M. J.; Stokes, J. J.; Murray, R. W. *Langmuir* **1996**, *12*, 3604-3612.

-
- ¹⁸ Chernyshova, I. V.; Hanumantha Rao, K.; Vidyadhar, A.; Shchukarev, A. V. *Langmuir* **2000**, *16*, 8071-8084.
- ¹⁹ Snyder, R. G. *J. Mol. Spectrosc.* **1961**, *7*, 116-144.
- ²⁰ Smith, E. L.; Porter, M. D. *J. Phys. Chem.* **1993**, *97*, 8032-8038.
- ²¹ Snyder, R. G. *J. Chem. Phys.* **1967**, *47*, 1316-1360.
- ²² Katayama, N.; Enomoto, S.; Sato, T.; Ozaki, Y. *J. Phys. Chem.* **1993**, *97*, 6880-6884.
- ²³ Gaines, G. L. *Nature* **1982**, *298*, 544-545.
- ²⁴ Aresta, M.; Quaranta, E. *Tetrahedron* **1992**, *48*, 1515-1530.
- ²⁵ Holas, T.; Zbytovska, J.; Vavrova, K.; Berka, P.; Madlova, M.; Klimentova, J.; Hrabalek, A. *Thermochimica Acta* **2006**, *441*, 116-123.
- ²⁶ Luo, B.; Rossini, J. E.; Gladfelter, W. L. *Langmuir* **2009**, *25*, 13133-13141.
- ²⁷ Pohle, W.; Gauger, D. R. *J. Mol. Struct.* **2009**, *924-926*, 144-147.
- ²⁸ Nakanishi, K.; Goto, T.; Ohashi, M. *Bull. Chem. Soc. Jpn.* **1957**, *30*, 403-408.
- ²⁹ Benítez, J. J.; San-Miguel, M. A.; Domínguez-Meister, S.; Heredia-Guerrero, J. A.; Salmeron, M. *J. Phys. Chem. C* **2011**, *115*, 19716-19723.
- ³⁰ Himmel, H. J.; Kaschke, M.; Harder, P.; Wöll, Ch. *Thin Solid Films* **1996**, *284-285*, 275-280.
- ³¹ Nora, G.; Yegen, E.; Gross, T.; Lippitz, A.; Weigel, W.; Krakert, S.; Terfort, A.; Unger, W. E. S. *Surf. Sci.* **2009**, *603*, 2849-2860.
- ³² Kumar, A.; Mandal, S.; Selvakannan, P. R.; Pasricha, R.; Mandale, A. B.; Sastry, M. *Langmuir* **2003**, *19*, 6277-6282.
- ³³ Matsuo, Y.; Miyabe, T.; Fukutsuka, T.; Sugie, Y. *Carbon* **2007**, *45*, 1005-1012.
- ³⁴ Chmielewska, E.; Tylus, W. In *Combined and Hybrid Adsorbents*; Loureiro, J. M.; Kartel, M. T., Eds.; Springer, 2006; pp 63-70.

³⁵ Israelachvili, J. *Intermolecular and Surface Forces*; Academic Press: New York, 1991; p 89.

³⁶ Wohlfarth, C. In *Handbook of Chemistry and Physics* 87th Edition; Lide, D. R., Ed.; CRC Press: Boca Raton FL, 2006; secc. 6, pp 132-153.

³⁷ Didymus, J. M.; Mann, S.; Benton, W. B.; Collins, I. R. *Langmuir* **1995**, *11*, 3130-3136.

³⁸ Paoletti, P.; Barbucci, R.; Vacca, A. *J. Chem. Soc. Dalton Trans.* **1972**, *18*, 2010-2013.

TABLE OF CONTENT

Figure 1

Figure 1. Topographic AFM images of ODA/mica SAMs islands prepared from a 15 mM chloroform solution: (a) imaged 2 hours after preparation, (b) after 7 days in contact with air. Height histograms (right) show an island height reduction from 17Å to 13Å after such ripening time.
138x175mm (300 x 300 DPI)

Figure 2

Figure 2. ATR-FTIR spectra of ODA/mica SAMs: (i) 2 hours after preparation and (ii) after 7 days ripening in air in (a) the 3000-2800 cm^{-1} and (b) the 1700-1200 cm^{-1} regions. Spectroscopic features indicate a closed packing of alkyl molecules and a slight improvement of ordering with ripening time. In addition to this, the presence of a fraction of octadecylammonium octadecylcarbamate ($-\text{NH}-\text{COO}^-$) and additional protonated amino groups ($-\text{NH}_3^+$) are detected.

125x111mm (600 x 600 DPI)

Figure 3

Figure 3. N_{1s} XPS spectra of ODA/mica SAMs exposed to air for (i) 2 hours and (ii) 7 days. Contributions of $-NH_3^+$ (401.7 eV), $-NH-COO^-$ (400.4 eV) and $-NH_2$ (399.2 eV) have been extracted. Extended contact with air causes further amino groups protonation but no additional carbamation.
137x193mm (600 x 600 DPI)

Figure 4

Figure 4. Schematic drawing illustrating the reduction of lateral molecule to molecule interactions in a self-assembled monolayer upon tilting (θ). Asterisk indicates the methylene ($-\text{CH}_2-$) groups having no counterparts on one side.
113x94mm (300 x 300 DPI)

Figure 5

Figure 5. (a) Electrostatic repulsion (E_{rep}) and cohesive (E_{coh}) energy dependence with the molecular head to head separation (d) and protonation fraction (Θ) derived from the models proposed for ODA/mica SAMs. (b) Cohesive-repulsion energy balance for the $\Theta = 1/4$ and $\Theta = 1/3$ configurations, energy minima at $d \approx 7\text{\AA}$ and $d \approx 9\text{\AA}$ are detected respectively.

Figure 6

Figure 6. Hexagonal molecular packing models (at the support plane) proposed for the uniform distributions of protonated ODA molecules within the SAM. Theoretic protonation fraction (Θ) are selected according to XPS results for freshly prepared ($\Theta = 1/4$) and ripened ($\Theta = 1/3$) ODA/mica SAMs.

169x259mm (300 x 300 DPI)

Table of content
36x49mm (300 x 300 DPI)